

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION

# ISO RECOMMENDATION R 745

SODIUM CARBONATE FOR INDUSTRIAL USE

DETERMINATION OF LOSS OF MASS

AND OF NON-VOLATILE MATTER AT 250 °C

1st EDITION May 1968

#### COPYRIGHT RESERVED

The copyright of ISO Recommendations and ISO Standards belongs to ISO Member Bodies. Reproduction of these documents, in any country, may be authorized therefore only by the national standards organization of that country, being a member of ISO.

For each individual country the only valid standard is the national standard of that country.

Printed in Switzerland

Also issued in French and Russian. Copies to be obtained through the national standards organizations.

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO/R 745:1968</u>

https://standards.iteh.ai/catalog/standards/sist/0a168796-677d-47f5-a323-079325f6cd36/iso-r-745-1968

### BRIEF HISTORY

The ISO Recommendation R 745, Sodium carbonate for industrial use – Determination of loss of mass and of non-volatile matter at 250 °C, was drawn up by Technical Committee ISO/TC 47, Chemistry, the Secretariat of which is held by the Ente Nazionale Italiano di Unificazione (UNI).

Work on this question by the Technical Committee began in 1951 and led, in 1956, to the adoption of a Draft ISO Recommendation.

In June 1966, this Draft ISO Recommendation (No. 1011) was circulated to all the ISO Member Bodies for enquiry. It was approved, subject to a few modifications of an editorial nature, by the following Member Bodies :

Argentina	Italy	Switzerland
Austria	Japan	Turkey
Belgium	Korea, Rep. of	U.A.R.
Brazil	Netherlands	United Kingdom
Chile	New Zealand	U.S.A.
Czechoslovakia	Poland	U.S.S.R.
France	Portugal	Yugoslavia
Germany	Romania	
Hungary	South Africa,	
India	Rep. of	
Israel	Spain	

No Member Body opposed the approval of the Draft.

The Draft ISO Recommendation was then submitted by correspondence to the Council, which decided, in May 1968, to accept it as an ISO RECOMMENDATION.

- 3 -

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO/R 745:1968</u>

https://standards.iteh.ai/catalog/standards/sist/0a168796-677d-47f5-a323-079325f6cd36/iso-r-745-1968

## SODIUM CARBONATE FOR INDUSTRIAL USE

# DETERMINATION OF LOSS OF MASS AND OF NON-VOLATILE MATTER AT 250 °C

#### I. SCOPE

This ISO Recommendation describes a method for the determination of loss of mass and of non-volatile matter at a temperature of 250 °C.

### 2. FIELD OF APPLICATION

The method is applicable to the determination of the loss of mass and of non-volatile matter at 250 °C in anhydrous sodium carbonate for industrial use.

2.1 Special case

Sodium carbonate decahydrate.

### 3. PRINCIPLE

Heating of thin layers of a test portion to constant mass at a temperature of 250 °C.

The loss of mass represents water in its various forms plus half the carbon dioxide content of the hydrogen carbonate present.

The residue constitutes the non-volatile matter at 250 °C.

### 4. APPARATUS

Ordinary laboratory apparatus and

- 4.1 *Weighing bottle*.approximately 100 ml capacity and 75 mm in diameter, with ground glass stopper.
- 4.2 *Electric oven*, capable of reaching a temperature of at least 250 °C, regulated so as not to exceed a temperature of 270 °C.

### 5. PROCEDURE

### 5.1 Test portion

Weigh to the nearest 0.1 mg,  $5 \pm 0.1$  g of the test sample.\*

-- 5 ---

<sup>\*</sup> See clause 2.2 of ISO Recommendation R 739, Sodium carbonate for industrial use - Preparation and storage of test samples,

#### 5.2 Determination

Spread thin layers of the test portion (5.1) in the weighing bottle (4.1) previously dried for 30 minutes in the oven (4.2) controlled at a temperature of 250 °C and allowed to cool to room temperature in a desiccator and weighed.

Place in the oven (4.2) with the ground glass stopper of the weighing bottle (4.1) placed slantwise. Gradually heat in the oven (4.2) from the starting temperature (which should not exceed 100 °C) to at least 250 °C and maintain this temperature for 3 hours. Do not exceed a temperature of 270 °C.

Remove the weighing bottle, place it in a desiccator to cool, and after cooling to room temperature, weigh it again with stopper in position.

#### 6. EXPRESSION OF RESULTS

Loss of mass at 250 °C is expressed as a percentage by mass, by the following formula :

$$\frac{(M_1 - M_2) \times 100}{E}$$

Non-volatile matter at  $250 \, ^\circ C$  is expressed as a percentage by mass, by the following formula :

$$100 - \frac{(M_1 - M_2) \times 100}{E}$$

where

- $M_1$  is the mass, in grammes, of the test portion and weighing bottle before heating,
- $M_{\rm 2}$   $\,$  is the mass, in grammes, of the test portion and weighing bottle after heating,
- E is the mass, in grammes, of the test portion.

#### 7. SPECIAL CASE

### 7.1 Principle

When sodium carbonate decahydrate (soda crystals) is being analysed, the temperature should be raised slowly in order to avoid loss through sputtering.

#### 7.2 Apparatus

(See section 4).

#### 7.3 Procedure

7.3.1 Test portion (see clause 5.1).

- 6 ---

7.3.2 *Determination*. Place the weighing bottle (4.1) containing the test portion (5.1), covered with a perforated watch glass in the cold oven (4.2).

Gradually raise the temperature to approximately 95  $^{\circ}$ C and maintain this temperature until the product is apparently dry. Then gradually increase the temperature to at least 250  $^{\circ}$ C but do not allow it to exceed 270  $^{\circ}$ C and maintain this temperature for 3 hours. Then proceed as indicated in clause 5.2.

### 7.4 Expression of results

(See section 6).

#### 8. TEST REPORT

Give the following particulars:

- (a) the reference to the method used,
- (b) the results and the method of expression used,
- (c) any unusual features noted during the determination,
- (d) any operation not laid down in this ISO Recommendation or regarded as optional.