



Designation: C 1384 – 02

Standard Specification for Admixtures for Masonry Mortars¹

This standard is issued under the fixed designation C 1384; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope *

1.1 This specification pertains to admixtures for masonry mortars. Admixtures are substances other than Specification C 270 prescribed materials of water, aggregate, and cementitious materials that are used to improve one or more of the recognized desirable properties of conventional masonry mortar.

1.2 This specification does not cover coloring pigments.

NOTE 1—Information on coloring pigments can be found in Specification C 979.

1.3 This specification does not cover additives that are added to the cementitious materials during the manufacture of the cementitious materials.

1.4 Acceptance of an admixture is based on its performance in an admixed mortar. Acceptance of the admixed masonry mortar is based on attainment of performance either equivalent to that required for conventional mortar or improved performance of one or more indicated properties, while maintaining required performance levels for other properties.

1.5 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

NOTE 2—The testing laboratory performing the test methods referenced in this specification should be evaluated in accordance with Practice C 1093.

2. Referenced Documents

2.1 *ASTM Standards:*

C 91 Specification for Masonry Cement²

C 144 Specification for Aggregate for Masonry Mortar³

C 150 Specification for Portland Cement²

C 207 Specification for Hydrated Lime for Masonry Purposes²

C 270 Specification for Mortar for Unit Masonry³

C 305 Practice for Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency²

C 403 Test Method for Time of Setting of Concrete Mix-

tures by Penetration Resistance⁴

C 595 Specification for Blended Hydraulic Cements²

C 723 Practice for Chemical-Resistant Resin Grouts for Brick or Tile³

C 778 Specification for Standard Sand²

C 780 Test Method for Preconstruction and Construction Evaluation of Mortars for Plain and Reinforced Unit Masonry³

C 979 Specification for Pigments for Integrally Colored Concrete⁴

C 1093 Practice for Accreditation of Testing Agencies for Unit Masonry³

C 1152 Test Method for Acid-Soluble Chloride in Mortar and Concrete⁴

C 1157 Performance Specification for Hydraulic Cement²

C 1218 Test Method for Water-Soluble Chloride in Mortar and Concrete⁴

C 1329 Specification for Mortar Cement²

C 1357 Test Method for Evaluating Masonry Bond Strength³

C 1403 Test Method for Rate of Water Absorption of Masonry Mortars³

C 1437 Test Method for Flow of Hydraulic Cement Mortar²

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *admixed mortar, n*—masonry mortar that deviates from those combinations of materials recognized by Specification C 270 in that it also contains an admixture.

3.1.2 *admixture, n*—substance other than the Specification C 270 prescribed materials of water, aggregate, and cementitious materials that is added to a masonry mortar as an ingredient to improve one or more chemical or physical properties of the conventional masonry mortar.

3.1.3 *bond enhancer, n*—admixture incorporated into a masonry mortar to increase the bond strength between the mortar and the masonry unit.

3.1.4 *reference mortar, n*—mortar of the same composition as an admixed mortar except that the reference mortar does not include the admixture and may contain a different amount of water to obtain an equivalent flow or penetration as the admixed mortar.

¹ This specification is under the jurisdiction of ASTM Committee C12 on Mortars and Grouts for Unit Masonry and is the direct responsibility of Subcommittee C12.09 on Modified Mortars.

Current edition approved Feb. 10, 2002. Published May 2002. Originally published as C 1384–98. Last previous edition C 1384–01.

² *Annual Book of ASTM Standards*, Vol 04.01.

³ *Annual Book of ASTM Standards*, Vol 04.05.

⁴ *Annual Book of ASTM Standards*, Vol 04.02.

*A Summary of Changes section appears at the end of this standard.

3.1.5 *set accelerator, n*—admixture incorporated into a masonry mortar to shorten the time of setting of a mortar.

3.1.6 *set retarder, n*—admixture incorporated into a masonry mortar to lengthen the time of setting of a mortar.

3.1.7 *water repellent, n*—admixture incorporated into a masonry mortar to decrease the rate of water absorption of the hardened mortar.

3.1.8 *workability enhancer, n*—admixture incorporated into a masonry mortar to increase the ease of being worked and used. A workability enhancer will increase the board life and maintain the water retention of a mortar.

4. Classification

4.1 Admixtures are classified by their effect on the performance characteristics of conventional masonry mortars. Admixed mortars are classified by their modified properties, as compared to a reference mortar. The following classifications are recognized:

4.1.1 Bond Enhancer.

4.1.2 Workability Enhancer.

4.1.3 Set Accelerator.

4.1.4 Set Retarder.

4.1.5 Water Repellent.

5. Materials

5.1 *Cements*—The cement used in the evaluation of the admixture shall conform to applicable requirements specified in 5.1.1-5.1.5.

5.1.1 *Cement, Portland*—When the admixture is evaluated in a mortar containing portland cement, the portland cement shall conform to the requirements for Type I, IA, II, IIA, III, or IIIA of Specification C 150.

5.1.2 *Cement, Blended Hydraulic*—When the admixture is evaluated in a mortar containing blended hydraulic cement, the blended hydraulic cement shall conform to the requirements for Type IS, IS-A, IP, IP-A, I(PM) or I(PM)-A of Specification C 595.

5.1.3 *Cement, Hydraulic*—When the admixture is evaluated in a mortar containing a hydraulic cement, the hydraulic cement shall conform to the requirements for Type GU, HE, MS, HS, MH, or LH of Specification C 1157.

5.1.4 *Cement, Masonry*—When the admixture is evaluated in a mortar containing a masonry cement, the masonry cement shall conform to the requirements of Specification C 91.

5.1.5 *Cement, Mortar*—When the admixture is evaluated in a mortar containing a mortar cement, the mortar cement shall conform to the requirements of Specification C 1329.

5.2 *Lime*—When the admixture is evaluated in a cement-lime mortar, the hydrated lime shall conform to Specification C 207.

5.3 *Sand*—The fine aggregate used in the tests will vary dependent on the test procedure.

5.3.1 Sands used for flexural bond strength and rate of water absorption tests shall be a blend of equal parts by weight of graded standard sand and standard 20-30 sand conforming with Specification C 778.

5.3.2 Sands used for soluble chloride, compressive strength, water retention, determination of air content of plastic mortar, board life, and time of setting tests shall conform to the

requirements of Specification C 144.

6. Chemical Composition

6.1 The admixture shall not react adversely with embedded or attached materials common to masonry.

NOTE 3—Currently, there is no standard test method for determining the corrosion potential of masonry mortars toward embedded and attached materials. Nonetheless, the admixture shall not be offered for sale if the manufacturer has evidence that the admixture does react adversely with embedded or attached materials common to masonry.

6.2 At the maximum recommended dosage, the mortar admixture shall add not more than 65 ppm (0.0065 %) water-soluble chloride, or 90 ppm (0.0090 %) acid-soluble chloride to the mortar's overall chloride content as determined by testing of the reference and admixed mortars in accordance with 9.1.1.

7. Physical Properties

7.1 All modified masonry mortars shall comply with the property specification requirements of Specification C 270. In addition, the admixed mortars shall conform to all of the specific classification requirements in Table 1 for which the admixture is obtaining qualification. Unless more specimens are required by a specific test method, a minimum of three specimens shall be tested and the results averaged. These result averages shall meet the requirements of this section.

7.2 Admixture compliance tests shall be the responsibility of the manufacturer of the admixture. These compliance tests shall be completed within the past five (5) years and prior to any admixture composition change.

8. Mortar Types and Proportions

8.1 Design the reference mortar to be a specific type of cement/lime, mortar cement, or masonry cement mortar in conformance with the proportion specification of Specification C 270 except that the aggregate ratio shall be fixed at three times the sum of the separate volumes of cementitious materials. In addition, the aggregate shall meet the requirements in 5.3.

8.2 The corresponding admixed mortars shall have the same composition as the reference mortars but also shall include the admixture, and the water content shall be adjusted to yield the flow or penetration appropriate for each test method. The admixture dosage rate, time of addition, and mixing sequence shall follow the manufacturer's recommendations.

8.3 A complete set of tests shall be run for all applicable cement/lime, mortar cement, and masonry cement types for which the admixture is to be qualified.

9. Test Methods

9.1 For all required tests, test both the reference mortar and the admixed mortar in accordance with the following test methods:

9.1.1 *Soluble Chloride Content*—Prepare six mortar cubes in accordance with the specimen preparation section of Test Method C 1403 including the drying procedure, except that mortar proportions shall be as specified in Section 8 and aggregates shall be as specified in 5.3. After 28 days of age, determine the water-soluble chloride content of three cubes, as