International Standard



Rubber compounding ingredients – Carbon black – Standard reference blacks

Ingrédients de mélange du caoutchouc - Noir de carbone - Noirs de référence

First edition – 1984-04-15 Teh STANDARD PREVIEW

(standards.iteh.ai)

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION+MEXCHAPOCHAR OPPAHUSALUUR IIO CTAHCAPTUSALUUHOORGANISATION INTERNATIONALE DE NORMALISATION

ISO 6809:1984 https://standards.iteh.ai/catalog/standards/sist/90d131ad-e131-439a-85bd-12ef70c541fe/iso-6809-1984

UDC 678.046.2:53.089.68

Descriptors : rubber, carbon black, ingredients, tests, properties.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been authorized has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 6809 was developed by Technical Committee SO/TC 45, V K V Rubber and rubber products, and was circulated to the member bodies in June 1982, Standards.iten.al

It has been approved by the member bodies of the following countries :

		<u>ISO 6809:1984</u>				
Australia	httHungarylards.iteh.ai/catalog/sSpain/ds/sist/90d131ad-e131-439a-85bd-					
Austria		0c5 Srift/anka 809-1984				
Belgium	Indonesia	Sweden				
Brazil	Italy	Thailand				
Canada	Korea, Rep. of	Turkey				
China	Netherlands	United Kingdom				
Czechoslovakia	New Zealand	USA				
Egypt, Arab Rep. of	Poland	USSR				
France	Romania					
Germany, F. R.	South Africa, Rep. of					

No member body expressed disapproval of the document.

© International Organization for Standardization, 1984

Printed in Switzerland

INTERNATIONAL STANDARD

Rubber compounding ingredients — Carbon black — Standard reference blacks

Scope and field of application 1

This International Standard specifies the agreed values for the properties of standard reference blacks to be used in conjunction with methods of test for carbon black.

2 References

ISO 1304, Carbon black for use in the rubber industry - Determination of iodine adsorption number.

ISO 4652, Rubber compounding ingredients - Carbon black - Determination of specific surface area - Nitrogen adsorption methods.

ISO 4656/2, Rubber compounding ingredients - Carbon black - Determination of dibuty/phthalate absorption number -Part 2 : Method using plastograph or plasticorder.

ISO 5435, Rubber compounding ingredients - Carbon black - Determination of tinting strength.

ISO 6810, Rubber compounding ingredients - Carbon black - Determination of specific surface area - Surfactant adsorption methods.¹⁾

ISO 6894, Rubber compounding ingredients - Carbon black - Determination of dibutylphthalate absorption number of a compressed sample.¹⁾

3 Agreed values

ISO 4656/1, Carbon black for use in the rubber industry Determination of dibutylphthalate absorption number 210 Part 1 : Method using absorptometer.

The agreed values for the properties of standard reference blacks are given in the table.

ISO 6809:1984

12ef70c541fe/iso-6809-1984										
Property	Unit	A-3*	B-3*	C-3*	D-3*	ITRB**	IRB No. 5***	Method of test		
lodine adsorption number	mg/g	23,2 ± 1	80,5 ± 1	112,7 ± 1	33,4 ± 1		80,5 ± 1	ISO 1304		
C.T.A.B. surface area	m²/g	24,2 ± 1	79,9 ± 1	113 ± 1	40,6 ± 1	83	-	ISO 6810		
Nitrogen surface area	m²/g	23,6 ± 1	79,5 ± 1	119,8 ± 1	37,9 ± 1	`	76,5†	ISO 4652		
Dibutylphthalate absorption of compressed sample	cm ³ /100 g	58,9 ± 1	89,2 ± 1	102,0 ± 1	89,0 ± 1		89,6 ± 1	ISO 6894		
Dibutylphthalate absorption	cm ³ /100 g	67,0 ± 1	101,2 ± 1	119,8 ± 1	129,8 ± 1 **		102,1 ± 1	ISO 4656/1 or		
– mass used	g	25	20	20	20		20	ISO 4656/2		
Tinting strength	% ITRB	42,4 ± 1,5	101,2 ± 1,5	116,0 ± 1,5	53,3 ± 1,5	100	101,5 ± 1,5	ISO 5435		
Туре		N 762	N 330	N 234	N 683		N 330			

Table - Agreed values for properties of standard reference blacks dried at 125 °C

Samples of A-3, B-3, C-3 and D-3 are available from Forcoven Products Inc., PO Box 1556, Humble, Texas 77338, USA

ITRB is available from Ashland Chemical Co., Columbus, Ohio 43216, USA

Standard reference black IRB No. 5 is available from Columbian Chemicals Co., 3200 W Market Street, Akron, Ohio 44313, USA

Results obtained by classical B.E.T. method. t

This value may be difficult to obtain.

1) At present at the stage of draft.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 6809:1984 https://standards.iteh.ai/catalog/standards/sist/90d131ad-e131-439a-85bd-12ef70c541fe/iso-6809-1984