



SLOVENSKI STANDARD
SIST EN ISO 7539-2:1999

01-oktober-1999

**Korozija kovin in zlitin - Ugotavljanje pokanja zaradi napetostne korozije - 2. del:
Priprava in uporaba upogibnih preskušancev (ISO 7539-2:1989)**

Corrosion of metals and alloys - Stress corrosion testing - Part 2: Preparation and use of bent-beam specimen (ISO 7539-2:1989)

Korrosion der Metalle und Legierungen - Prüfung der Spannungsrißkorrosion - Teil 2:
Vorbereitung und Anwendung von Biegeproben (ISO 7539-2:1989)

Corrosion des métaux et alliages - Essais de corrosion sous contrainte - Partie 2:
Préparation et utilisation des éprouvettes pour essais en flexion (ISO 7539-2:1989)

[https://standards.iteh.ai/catalog/standards/sist/cc916a60-1d84-47c4-afd1-](https://standards.iteh.ai/catalog/standards/sist/cc916a60-1d84-47c4-afd1-d50e7f9600e3/sist-en-iso-7539-2-1999)

Ta slovenski standard je istoveten z: EN ISO 7539-2:1995

ICS:

77.060

Korozija kovin

Corrosion of metals

SIST EN ISO 7539-2:1999

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 7539-2:1999](#)

<https://standards.iteh.ai/catalog/standards/sist/cc916a60-1d84-47c4-afd1-d50e7f9600e3/sist-en-iso-7539-2-1999>

EUROPEAN STANDARD

EN ISO 7539-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 1995

ICS 77.060

Descriptors: metals, alloys, tests, corrosion tests, stress corrosion tests, test specimens

English version

Corrosion of metals and alloys - Stress corrosion testing - Part 2: Preparation and use of bent-beam specimen (ISO 7539-2:1989)

Corrosion des métaux et alliages - Essais de corrosion sous contrainte - Partie 2: Préparation et utilisation des éprouvettes pour essais en flexion (ISO 7539-2:1989)

Korrosion der Metalle und Legierungen - Prüfung der Spannungsrißkorrosion - Teil 2: Vorbereitung und Anwendung von Biegeproben (ISO 7539-2:1989)

STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/cc916a60-1d84-47c4-afd1-d50e7f9600e3/sist-en-iso-7539-2-1999>

This European Standard was approved by CEN on 1995-04-08. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

© 1995

All rights of reproduction and communication in any form and by any means reserved in all countries to CEN and its members.

Ref. No. EN ISO 7539-2:1995 E

Page 2
EN ISO 7539-2:1995

Foreword

This European Standard has been taken over by the Technical Committee CEN/TC 262 "Protection of metallic materials against corrosion" from the work of ISO/TC 156 "Corrosion of metals and alloys" of the International Organization for Standardization (ISO).

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1995, and conflicting national standards shall be withdrawn at the latest by November 1995.

According to the CEN/CENELEC Internal Regulations, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, United Kingdom.

Endorsement notice

The text of the International Standard ISO 7539-2:1989 was approved by CEN as a European Standard without any modification.

(standards.iteh.ai)

[SIST EN ISO 7539-2:1999](https://standards.iteh.ai/catalog/standards/sist/cc916a60-1d84-47c4-afd1-d50e7f9600e3/sist-en-iso-7539-2-1999)

<https://standards.iteh.ai/catalog/standards/sist/cc916a60-1d84-47c4-afd1-d50e7f9600e3/sist-en-iso-7539-2-1999>



INTERNATIONAL STANDARD

ISO 7539-2

First edition
1989-12-15

Corrosion of metals and alloys — Stress corrosion testing —

Part 2:

Preparation and use of bent-beam specimens

iTeh STANDARD PREVIEW

(standards.iteh.ai)

Corrosion des métaux et alliages — Essais de corrosion sous contrainte —

Partie 2: Préparation et utilisation des éprouvettes pour essais en flexion

SIST EN ISO 7539-2:1999

<https://standards.iteh.ai/catalog/standards/sist/cc916a60-1d84-47c4-afd1-d50e7f9600e3/sist-en-iso-7539-2-1999>



Reference number
ISO 7539-2 : 1989 (E)

ISO 7539-2 : 1989 (E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 7539-2 was prepared by Technical Committee ISO/TC 156, *Corrosion of metals and alloys*.

SIST EN ISO 7539-2:1999

<https://standards.iteh.ai/catalog/standards/sist/cc916a60-1d84-47c4-afd1-45071b000c3/sist-en-iso-7539-2-1999>

ISO 7539 consists of the following parts, under the general title *Corrosion of metals and alloys – Stress corrosion testing*:

- *Part 1: General guidance on testing procedures*
- *Part 2: Preparation and use of bent-beam specimens*
- *Part 3: Preparation and use of U-bend specimens*
- *Part 4: Preparation and use of uniaxially loaded tension specimens*
- *Part 5: Preparation and use of C-ring specimens*
- *Part 6: Preparation and use of pre-cracked specimens*
- *Part 7: Slow strain rate testing*
- *Part 8: Preparation and use of welded specimens*

© ISO 1989

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Introduction

This part of ISO 7539 is one of a series giving procedures for designing, preparing and using various forms of test specimen to carry out tests to establish a metals resistance to stress corrosion.

Each of the standards in the series needs to be read in association with ISO 7539-1. This helps in the choice of an appropriate test procedure to suit particular circumstances as well as giving guidance towards assessing the significance of the results of the tests.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 7539-2:1999](https://standards.iteh.ai/catalog/standards/sist/cc916a60-1d84-47c4-afd1-d50e7f9600e3/sist-en-iso-7539-2-1999)

<https://standards.iteh.ai/catalog/standards/sist/cc916a60-1d84-47c4-afd1-d50e7f9600e3/sist-en-iso-7539-2-1999>

iTeh STANDARD PREVIEW

(standards.iteh.ai)
This page intentionally left blank

SIST EN ISO 7539-2:1999

<https://standards.iteh.ai/catalog/standards/sist/cc916a60-1d84-47c4-afd1-d50e7f9600e3/sist-en-iso-7539-2-1999>

Corrosion of metals and alloys — Stress corrosion testing —

Part 2: Preparation and use of bent-beam specimens

WARNING — Bent-beam specimens made from high strength materials may fracture rapidly; pieces may fly off at high velocity and can be dangerous. Personnel installing and examining specimens must be made aware of this possibility and be protected against injury.

1 Scope

1.1 This part of ISO 7539 covers procedures for designing, preparing and using bent-beam test specimens for investigating the susceptibility of a metal to stress corrosion.

The term "metal" as used in this part of ISO 7539 includes alloys.

1.2 Bent-beam specimens may be used to test a variety of product forms. They are used principally for sheet, plate or flat extruded material, which conveniently provides flat specimens of rectangular cross-section, but may also be employed for cast material, wire or rod, or for machined specimens of circular cross-section. They can also be used for parts joined by welding.

1.3 Since the preparation of the specimens and the apparatus used for stressing them are both simple and inexpensive, bent-beam specimens are especially suitable for multiple testing and for atmospheric stress corrosion tests.

1.4 Bent-beam specimens are usually tested under nominally constant strain conditions but nominally constant load conditions may be employed. In either case local change of curvature in the specimen when cracking occurs results in changing conditions during crack propagation. The "test stress" is taken as the highest surface tensile stress existing at the start of the test.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 7539. At the time of publication, the editions indicated

iTeh STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/cc916a60-1d84-47c4-afd1-450c7b006c3/sist-en-iso-7539-2:1999>

were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 7539 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 7539-1 : 1987, *Corrosion of metals and alloys — Stress corrosion testing — Part 1: General guidance on testing procedures.*

ISO 7539-4 : 1989, *Corrosion of metals and alloys — Stress corrosion testing — Part 4: Preparation and use of uniaxially loaded tension specimens.*

3 Definitions

For the purposes of this part of ISO 7539, the definitions given in ISO 7539-1 are applicable.

4 Principle

4.1 The test consists of applying a bending stress to a beam specimen of rectangular or circular section and exposing the stressed specimen to a specified test environment.

4.2 The magnitude of the resultant applied tensile stress in the outer fibres of the bent-beam specimen is calculated from the dimensions and modulus of elasticity of the specimen and the bending deflection, as described in 5.4.

4.3 Bent-beam specimens are used only for testing at stress levels below the elastic limit since the formulae used for calculating stress in bent beams apply only within the elastic range.