



# SLOVENSKI STANDARD SIST EN ISO 2177:1999

01-oktober-1999

Metallische Überzüge - Schichtdickenmessung - Coulometrisches Verfahren durch anodisches Ablösen (ISO 2177:1985)

Metallic coatings - Measurement of coating thickness - Coulometric method by anodic dissolution (ISO 2177:1985)

Revetements métalliques - Mesurage de l'épaisseur - Méthode coulométrique par dissolution anodique (ISO 2177:1985)

Ta slovenski standard je istoveten z: EN ISO 2177:1994

<https://standards.iteh.ai/catalog/standards/sist/ac528bd6-bb7b-4793-b831-f520df07120e/sist-en-iso-2177-1999>

## ICS:

17.040.20	Lastnosti površin	Properties of surfaces
25.220.40	Kovinske prevleke	Metallic coatings

SIST EN ISO 2177:1999

en

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 2177:1999

<https://standards.iteh.ai/catalog/standards/sist/ac528bd6-bb7b-4793-b831-f520df07120e/sist-en-iso-2177-1999>

EUROPEAN STANDARD

EN ISO 2177

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 1994

ICS 25.220.40

Descriptors: coatings, metal coatings, tests, determination, thickness, coulometric methods

English version

**Metallic coatings - Measurement of coating  
thickness - Coulometric method by anodic  
dissolution (ISO 2177:1985)**

Revêtements métalliques - Mesurage de l'épaisseur - Méthode coulométrique par dissolution anodique (ISO 2177:1985) (standards.iteh.ai) Metallische Überzüge - Schichtdickenmessung - Coulometrisches Verfahren durch anodisches Ablösen (ISO 2177:1985)

SIST EN ISO 2177:1999

<https://standards.iteh.ai/catalog/standards/sist/ac528bd6-bb7b-4793-b831-f520df07120e/sist-en-iso-2177-1999>

This European Standard was approved by CEN on 1994-10-26. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

## CEN

European Committee for Standardization  
Comité Européen de Normalisation  
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

## Foreword

This European Standard was taken over by the Technical Committee CEN/TC 262 "Protection of metallic materials against corrosion" from the work of ISO/TC 107 "Metallic and other inorganic coatings" of the International Standards Organization (ISO).

CEN/TC 262 had decided to submit the final draft for Formal Vote. The result was positive.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 1995, and conflicting national standards shall be withdrawn at the latest by April 1995.

According to the CEN/CENELEC Internal Regulations, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, United Kingdom.

**ITeH STANDARD PREVIEW**  
**(standards.iteh.ai)**

## Endorsement notice

The text of the International Standard ISO 2177:1985 has been approved by CEN as a European Standard without any modification.

NOTE: Normative references to international publications are listed in annex ZA (normative).



**Annex ZA (normative)****Normative references to international publications  
with their relevant European publications**

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
ISO 2064		Metallic and other non-organic coatings - Definitions and conventions concerning the measurement of thickness	EN ISO 2064	

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 2177:1999](https://standards.iteh.ai/catalog/standards/sist/ac528bd6-bb7b-4793-b831-f520df07120e/sist-en-iso-2177-1999)

<https://standards.iteh.ai/catalog/standards/sist/ac528bd6-bb7b-4793-b831-f520df07120e/sist-en-iso-2177-1999>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 2177:1999

<https://standards.iteh.ai/catalog/standards/sist/ac528bd6-bb7b-4793-b831-f520df07120e/sist-en-iso-2177-1999>

---

# International Standard



# 2177

---

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

---

## Metallic coatings — Measurement of coating thickness — Coulometric method by anodic dissolution

*Revêtements métalliques — Mesurage de l'épaisseur — Méthode coulométrique par dissolution anodique*

Second edition — 1985-05-15  
Corrected and reprinted — 1986-03-01

**ITh STANDARD PREVIEW**  
(standards.iteh.ai)

SIST EN ISO 2177:1999

<https://standards.iteh.ai/catalog/standards/sist/ac528bd6-bb7b-4793-b831-f520df07120e/sist-en-iso-2177-1999>

---

UDC 621.793 : 531.717 : 621.317.39

Ref. No. ISO 2177-1985 (E)

**Descriptors:** coatings, metal coatings, tests, determination, thickness, coulometric methods.

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 2177 was prepared by Technical Committee ISO/TC 107, *Metallic and other non-organic coatings*.

This second edition cancels and replaces the first edition (ISO 2177-1972), of which it constitutes a technical revision.

Users should note that all International Standards undergo revision from time to time and that any reference made herein to any other International Standard implies its latest edition, unless otherwise stated.



# Metallic coatings — Measurement of coating thickness — Coulometric method by anodic dissolution

## 1 Scope and field of application

This International Standard specifies a coulometric method by anodic dissolution for measuring the thickness of metallic coatings.

Typical combinations of coatings and substrates that can be tested by this method are given in table 1. Other combinations may be tested with electrolytes in current use (see annex B), or new electrolytes may be developed for them, but, in both cases, it is necessary to verify the suitability of the complete system.

The method is also applicable to multi-layer systems, for example Cu/Ni/Cr (see also 8.6).

This method may be used to measure the thickness of coatings applied by various means, if due account is taken of special features, such as the presence of an alloy layer. In some cases, the presence and thickness of diffusion layers can also be measured. It can also be used to measure the thickness of coatings on cylindrical specimens and wires (see 8.8).

## 2 Reference

ISO 2064, *Metallic and other non-organic coatings — Definitions and conventions concerning the measurement of thickness*.

## 3 Definitions

For the purpose of this International Standard, the definitions of ISO 2064, and the following, apply.

**measuring area:** The area of the significant surface over which a single measurement is made.

The measuring area for this method is the area enclosed by the sealing ring of the cell.

## 4 Principle

Anodic dissolution of a well-defined area of the coating using a suitable electrolyte. Detection of the virtually complete dissolution of the coating by a rapid change in cell voltage. Calculation

of the coating thickness from the quantity of electricity (in coulombs) used, which may in turn be calculated from

- a) the time interval between the start and the end of the test, if it is conducted at constant current density;
- b) the integrated quantity of electricity used in dissolving the coatings.

## 5 Instrumentation

**5.1** Suitable instruments may be constructed from readily available components but proprietary instruments are usually used (see annex A).

**5.2** Proprietary direct reading instruments are available for use with electrolytes recommended by the manufacturer. Other instruments record the quantity of electricity, in coulombs, used in dissolving the coating from the measuring area (see clause 3), usually in arbitrary units, from which the thickness is calculated using factors or tables.

With direct reading instruments, the calculation of thickness from current density is made electronically.

**5.3** The performance of the instrument shall be checked using specimens of known coating thickness. If the instrument readings agree to  $\pm 5\%$  of the known thicknesses of the specimens, the instrument may be used without further adjustment. Otherwise, the cause of the discrepancy shall be removed. Proprietary instruments shall always, however, be calibrated in accordance with the manufacturer's instructions.

Suitable specimens of known coating thickness shall consist of the same type of coating and substrate as the specimen to be measured, and they shall have an accuracy of 5 % or better. If measuring alloy coatings, the use of correct specimens is of particular importance.

## 6 Electrolyte

The electrolyte shall have a known, adequate shelf-life and shall be such that:

- a) there is no reaction with the coating metal in the absence of an impressed flow of current;
- b) the coating dissolves anodically at an efficiency as close to 100 % as possible;