



Edition 1.0 2005-06

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Low-frequency caples with polyolefin insulation and moisture barrier polyolefin insulation and moisture barrier polyolefin sheath (standards.iteh.ai)

Câbles pour basses fréquences à isolation polyoléfine et gaine polyoléfine à barrière d'étanchéité 9dd6af7c57e1/iec-60708-2005





THIS PUBLICATION IS COPYRIGHT PROTECTED Copyright © 2005 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office	Tel.: +41 22 919 02 11
3, rue de Varembé	Fax: +41 22 919 03 00
CH-1211 Geneva 20	info@iec.ch
Switzerland	www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on TEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by (a)70 variety of criteria (reference number, text, technica) committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in 14 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

70 More than 55 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries icchave been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Catalogue IEC - webstore.iec.ch/catalogue

Application autonome pour consulter tous les renseignements bibliographiques sur les Normes internationales, Spécifications techniques, Rapports techniques et autres documents de l'IEC. Disponible pour PC, Mac OS, tablettes Android et iPad.

Recherche de publications IEC - www.iec.ch/searchpub

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - www.electropedia.org

Le premier dictionnaire en ligne de termes électroniques et électriques. Il contient plus de 30 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans 14 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Glossaire IEC - std.iec.ch/glossary

Plus de 55 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: csc@iec.ch.





Edition 1.0 2005-06

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Low-frequency cables with polyolefin insulation and moisture barrier polyolefin insulation and moisture barrier polyolefin sheath (standards.iteh.ai)

Câbles pour basses fréquences à <u>iscolation</u> polyoléfine et gaine polyoléfine à barrière d'étanchéité andards.iteh.ai/catalog/standards/sist/3d40308e-2f44-408d-b19c-9dd6af7c57e1/iec-60708-2005

INTERNATIONAL ELECTROTECHNICAL COMMISSION

COMMISSION ELECTROTECHNIQUE INTERNATIONALE

PRICE CODE CODE PRIX



ICS 29.060.20

ISBN 978-2-8322-1510-4

Warning! Make sure that you obtained this publication from an authorized distributor. Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

 Registered trademark of the International Electrotechnical Commission Marque déposée de la Commission Electrotechnique Internationale

CONTENTS

FO	REWC)RD		.4
1	Scop	e		.6
2	Norm	ative re	ferences	.6
3	Quali	tv assui	rance	.7
4			uction	
•	4.1		ctor	
	7.1	4.1.1	Conductor material	
		4.1.2	Type of conductor	
		4.1.3	Conductor-finish	
		4.1.4	Continuity of conductor	
	4.2		ion	
	7.2	4.2.1	Insulation material	
		4.2.2	Insulation thickness	
		4.2.3	Colour of insulated conductor	
	4.3	-	g element	
	4.4	•	ing	
	4.5		code	
		4.5.1		
		4.5.2	General Sub-units, units and cables up to and including 100 pairs or	0
		4.5.3	100 quads	۳. ۵
	4.6			.9 10
	4.7	Filling	pairs or quads	10
	4.8	Core n	rotection	10
	4.9	•		
	1.0	4.9.1	General	
		4.9.2	Sheath material	
		4.9.3	Application of the sheath	
	4 10		protection	
			d cable	
				11
		4.11.2	Sheath marking	11
			Sealing of ends	
	4.12		y	
5			equirements	
	5.1		ctor	
		ion		
	5.3	Sheath	· · · · · · · · · · · · · · · · · · ·	12
		5.3.1	Tensile strength and elongation	
		5.3.2	Adhesion of aluminium tape to the polyethylene	
		5.3.3	Adhesion of aluminium tape at the overlap	
	5.4		d cable	
		5.4.1	Sheath integrity	
		5.4.2	Resistance to water penetration	
		5.4.3	Cable drip	

6	Therr	nal stab	ility and environmental requirements	13
	6.1		on	
		6.1.1	Thermal oxidative stability (OIT-test)	
		6.1.2	Shrinkage	
		6.1.3	Wrapping test of insulation after thermal aging	14
		6.1.4	Bending test at low temperature	
	6.2	Sheath		14
		6.2.1	Elongation at break after ageing	14
		6.2.2	Resistance to weathering	14
		6.2.3	Resistance to environmental stress cracking	14
7	Elect	rical req	uirements	14
	7.1	Genera	۱	14
	7.2	Electric	al resistance of conductor	14
	7.3	Electric	al resistance unbalance	15
	7.4	Dielect	ric strength	15
	7.5	Insulati	on resistance	15
	7.6	Mutual	capacitance	15
	7.7	Capaci	tance unbalance	16
	7.8	Transm	nission characteristics (when used for digital communication)	17
		7.8.1	Attenuation	17
		7.8.2	Attenuation	17
		7.8.3	Equal Level Far-end Crosstalk (ELFEXT)	17
		7.8.4	Power sum (PS) of crosstalk loss	17
		7.8.5	Characteristic impedance: 60708:2005	17
		7.8.6	Velocity of a propagation g/standards/sist/3d40308e-2f44-408d-b19c	17
			9dd6af7c57e1/iec-60708-2005	
Anr	nex A	(normat	ive) Colour code: 10 pair or 5 quad count	19
			ive) Colour code: sub-unit identification for 50 pair (25 quad) and d) cables or units, using 10 pair or 5 quad count	20
	•	· ·	ive) Colour code: 25 pair count	
Anr	nex D	(normat	ive) Colour code: unit identification for 50 pair or quad and 100 pair r units, using 25 pair or quad count	
		•	ive) Colour code: 25 quad count	23
			ve) Colour code: unit identification for cables with more than r count	24
	•	•	ive) Colour code: unit identification for cables with more than	27
			uads, using 10 pair or 5 quad count or 25 quad count	26

INTERNATIONAL ELECTROTECHNICAL COMMISSION

LOW-FREQUENCY CABLES WITH POLYOLEFIN INSULATION AND MOISTURE BARRIER POLYOLEFIN SHEATH

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any enduser.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an EC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60708 has been prepared by subcommittee 46C: Wires and symmetric cables, of IEC technical committee 46: Cables, wires, waveguides, r.f. connectors, r.f. and microwave passive components and accessories.

This bilingual version (2014-04) corresponds to the English version, published in 2005-06.

IEC 60708 cancels and replaces IEC 60708-1 published in 1981 and amendment 3(1988). This edition constitutes a technical revision.

IEC 60708 has been completely revised technically and structurally. IEC 60708 now comprises only one single standard dealing with general design details and requirements. The old IEC 60708-2(1981), IEC 60708-3(1981) and IEC 60708-4(1983) have already been withdrawn because they are not used anymore. Although IEC 60708 addresses low frequency cables, these cables are often used for digital communications up to 2 Mbit/s or 1 MHz. Therefore a Subclause 7.8 has been added, which provides transmission characteristics for the cable when used for digital communication. Furthermore, Annex H of IEC 60708-1(1981) was deleted: The requirements for filling compounds are not needed anymore since they are covered by the cable performance requirements.

The text of this standard is based on the following documents:

FDIS	Report on voting
46C/713/FDIS	46C/728/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above Table.

The French version has not been voted upon.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

The contents of the corrigendum of August 2016 have been included in this copy.

iTeh STANDARD PREVIEW (standards.iteh.ai)

IEC 60708:2005 https://standards.iteh.ai/catalog/standards/sist/3d40308e-2f44-408d-b19c-9dd6af7c57e1/iec-60708-2005

LOW-FREQUENCY CABLES WITH POLYOLEFIN INSULATION AND MOISTURE BARRIER POLYOLEFIN SHEATH

1 Scope

This standard is intended to define polyolefin-insulated cables for insertion into local outdoor networks.

This standard is applicable to polyolefin insulated and moisture barrier polyolefin sheathed telephone cables, filled or unfilled with copper conductors, and used as:

- a) Cables suitable for installation in ducts.
- b) Cables suitable for direct burial in the ground.
- c) Cables with integral suspension strand for aerial installations.

This standard is in accordance with ITU-T Recommendations.

This standard includes general design details and requirements for dimensions and other constructional details as well as mechanical, electrical and environmental characteristics for all types of low-frequency cables with polyolefin insulation (solid or cellular), filled or unfilled, and moisture barrier polyolefin sheath (with integral suspension strand).

2 Normative references

(standards.iteh.ai)

IEC 60708:2005

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60028, International Standard of Resistance for Copper

IEC 60189-1, Low-frequency cables and wires with PVC Insulation and PVC sheath – Part 1: General test and measuring methods

IEC 60304, Standard colours for insulation for low-frequency cables and wires

IEC 60794-1-2, Optical fibre cables – Part 1-2: Generic specification – Basic optical cable test procedures

IEC 60811-1-1, Common test methods for insulating and sheathing materials of electric cables – Part 1: Methods for general application – Section 1: Measurement of thickness and overall dimensions – Tests for determining the mechanical properties

IEC 60811-1-2, Common test methods for insulating and sheathing materials of electric cables – Part 1: Methods for general application – Section Two: Thermal ageing methods

IEC 60811-1-3, Insulating and sheathing materials of electric cables – Part 1: General application – Section 3: Methods for determining the density – Water absorption tests – Shrinkage test

IEC 60811-1-4, Common test methods for insulating and sheathing materials of electric cables – Part 1: Methods for general application – Section Four – Test at low temperature

IEC 60708:2005 © IEC 2005

IEC 60811-4-1, Insulating and sheathing materials of electric and optical cables – Common test methods – Part 4-1: Methods specific to polyethylene and polypropylene compounds – Resistance to environmental stress cracking – Measurement of the melt flow index – Carbon black and/or mineral filler content measurement in polyethylene by direct combustion – Measurement of carbon black content by thermogravimetric analysis (TGA) – Assessment of carbon black dispersion in polyethylene using a microscope

IEC 60811-4-2, Insulating and sheathing materials of electric and optical cables – Common test methods – Part 4-2: Methods specific to polyethylene and polypropylene compounds – Tensile strength and elongation at break after conditioning at elevated temperature – Wrapping test after conditioning at elevated temperature – Wrapping test after conditioning at elevated temperature – Tensile strength of mass increase – Long-term stability test – Test method for copper-catalyzed oxidative degradation

IEC 60811-5-1, Common test methods for insulating and sheathing materials of electric cables – Part 5-1: Methods specific to filling compounds – Drop point – Separation of oil – Lower temperature brittleness – Total acid number – Absence of corrosive components – Permittivity at 23 °C – DC resistivity at 23 °C and 100 °C

IEC 61156-1, Multicore and symmetrical pair/quad cables for digital communications – Part 1: Generic specification

ITU-T L.3, Armouring of cables

Quality assurance

(standards.iteh.ai)

It is the responsibility of the manufacturer to establish quality assurance by quality control procedures which will ensure that the product will meet the requirements of this standard.

https://standards.iteh.ai/catalog/standards/sist/3d40308e-2f44-408d-b19c-

It is not intended that a complete **testing** programme shall be carried out on every length of conductor and cable. When the purchaser wishes to specify acceptance tests or other quality procedures, it is essential that agreement be reached between the purchaser and the manufacturer by the time of ordering.

4 Cable construction

4.1 Conductor

3

4.1.1 Conductor material

The conductor shall consist of annealed copper, uniform in quality and free from defects. The properties of the copper shall be in accordance with IEC 60028.

4.1.2 Type of conductor

The conductor shall consist of a single strand circular in section. The nominal diameter shall be at least 0,4 mm.

4.1.3 Conductor-finish

The conductor shall be plain.

4.1.4 Continuity of conductor

Joints in the conductor are permitted provided that the tensile strength of a joint is not less than 90 % of the tensile strength of the unjointed conductor.

4.2 Insulation

4.2.1 Insulation material

The conductor shall be covered with solid or cellular polyolefin insulation or any combination thereof.

For cellular insulation, the cells produced by the expanding process shall be uniformly distributed circumferentially and should be substantially non-intercommunicating.

The material for the insulation shall be a virgin thermoplastic compound suitably stabilized. Examples of suitable materials are:

- Polyethylene.
- Polypropylene.

4.2.2 Insulation thickness

The insulation shall be continuous and shall have a thickness such that the completed cable will meet the electrical requirements specified.

4.2.3 Colour of insulated conductor

The insulated conductors shall be coloured. Colours shall be readily identifiable and shall correspond reasonably with the standard colours shown in IEC 60304.

4.3 Cabling element (standards.iteh.ai)

A cabling element (Figure 1) shall be: IEC 60708:2005

- a pair of two insulated conductors twisted together and designated wire a and b respectively,

or

- a quad of four insulated conductors twisted together and designated wire a, wire c, wire b, and wire d respectively.

The maximum length of lay in the finished cable shall not exceed 150 mm.

NOTE Forming the element with a variable lay can lead to the infrequent but acceptable occurrence of the maximum lay being longer than specified.

4.4 Stranding

The cable elements shall be formed into a number of sub-units or units which can be stranded into a regular make up to produce the required number of pairs.

4.5 Colour code

4.5.1 General

Three different colour schemes for identifying pair or quad counts are defined. One with 10 pair or 5 quad sub-units, one for 25 pair colour groups and a third for 25 quad colour groups.

4.5.2 Sub-units, units and cables up to and including 100 pairs or 100 quads

4.5.2.1 10 pair or 5 quad count

The pairs or quads shall be identified by each insulated conductor having a single colour in accordance with the colour scheme given in Annex A.

Sub-units of 10 pairs or 5 quads shall be identified by coloured bindings of tape or threads according to the colour scheme given in Annex B for assembly into units of 50 pairs (25 quads) or 100 pairs (50 quads).

4.5.2.2 25 pair count

The pairs shall be identified by each insulated conductor having a single colour in accordance with the colour scheme given in Annex C.

Sub-units shall be identified by coloured bindings of tape or threads. Each group of sub-units making up a 25 pair count shall be identified by a common colour of bindings. For 50 and 100 pair cables the colours of the bindings are given in Annex D.

4.5.2.3 25 quad count

The quads shall be identified by each insulated conductor having a single colour in accordance with the colour scheme given in Annex E.

iTeh STANDARD PREVIEW

Sub-units shall be identified by coloured bindings of tape or threads. Each group of sub-units making up a 25 quad count shall be identified by a common colour of bindings. For 50 quad (100 pair) and 100 quad (200 pair) cables the colours of the bindings are given in Annex D.

4.5.3 Cables of more than 100 pairs or 100 guads 40308e-244-408d-b19e-

Cables shall be assembled in concentric layers of units. The units shall be identified by coloured bindings of tape or threads.

4.5.3.1 Marker / reference identification system

In each layer, the marker unit shall be identified by red coloured bindings, the reference unit shall be identified by green coloured bindings and the other units shall be identified by bindings of a contrasting or natural colour.

The marker and reference units shall be adjacent and the counting of units in each layer of the cable shall be in the same direction.

4.5.3.2 Marker identification system

In each layer, the marker unit shall be identified by red coloured bindings and the other units shall be identified by bindings of a contrasting or natural colour.

4.5.3.3 Full colour code system for 25 pair count

Each 25 pair count group shall be identified by bindings coloured in accordance with Annex F.

4.5.3.4 Full colour code system for 10 pair or 5 quad count or 25 quad count

Each group of sub-units making up a 100 pair (50 quad) count group shall be identified by a common colour of bindings in accordance with Annex G.

4.6 Spare pairs or quads

Spare pairs or quads may be provided individually or as a spare pair unit and shall be placed in the interstices of the cable core.

4.7 Filling

For filled cables, the interstices of the cable core shall be filled continuously with a compound suitable to prevent water penetration within the cable.

The filling compound shall be compatible with the other relevant cable elements. The suitability shall be tested by the use of the following test methods:

- the amount of oil separation from the filling compound shall meet the requirements of Clause 5 of IEC 60811-5-1.
- The drop point shall be higher than 70 °C. The determination of the drop point shall be in accordance with Clause 4 of IEC 60811-5-1.
- The filling compound shall be tested for the presence of corrosive components in accordance with Clause 8 of IEC 60811-5-1.

4.8 Core protection

The core of the cable may have a protective layer (e.g. a helical or longitudinal lapping of one or more tapes). **iTeh STANDARD PREVIEW**

4.9 Sheath

(standards.iteh.ai)

4.9.1 General

IEC 60708:2005

A moisture barrier aluminium laminated polyethylene sheath construction is specified for both underground and aerial cables. This type of sheath will also provide screening.

For aerial cables a figure "8" construction is specified.

Circular sheath cables can also be used as aerial cables.

4.9.2 Sheath material

4.9.2.1 Polyethylene

The polyethylene shall have a minimum carbon black content of 2,0 %.

4.9.2.2 Aluminium tape

The aluminium tape shall be coated on at least one side with a polymer film. The aluminium tape without the polymer layer shall have a nominal thickness of at least 0,15 mm.

4.9.3 Application of the sheath

4.9.3.1 Sheath

The aluminium tape shall be applied longitudinally with a minimum overlap of not less than 6 mm or 20 % of the circumference of the core protection, whichever is the smaller.

The polyethylene part of the sheath shall adhere to the polymer coating of the aluminium tape and the sheath shall be applied to fit closely to the protected core of the cable.

4.9.3.2 Sheath with an integral suspension strand

The polyethylene part of the sheath, complying with 4.9.3.1, shall cover the suspension strand and cable core to form a figure "8" construction in which the suspension strand is parallel with but separate from the cable core.

NOTE The web dimensions should be compatible with the clamping hardware.

The minimum tensile strength of strand is specified in Table 1.

Maximum overall diameter of the sheathed cable core <i>D</i> _{max} mm	Minimum tensile strength of strand kN
D _{max} <10	6,0
$10 \leq D_{max}$ <20	12,5
$20 \leq D_{max}$ <30	16,0
$30 \leq D_{max}$ <40	22,5

Table 1 – Tensile strength of strand

4.10 Cable protection

According to ITU-T Recommendation L3, armouring can be applied over the sheath to improve the strength of the cable against mechanical damage, rodents and insect attack and/or to improve the screening efficiency against electromagnetic interference and lightning discharges. The armouring may be made by metallic tape (or tapes) or wires with a protective laver.

4.11 Finished cable 9dd6af7c57e1/iec-60708-2005

4.11.1 Overall diameter

To obtain nominal values, the user may ask the supplier to quote his values.

The overall diameter of the cable shall be measured in accordance with the method specified in 2.2.2 of IEC 60189-1.

4.11.2 Sheath marking

The sheath may be marked. Common methods of marking are embossing, sintering, imprinting, hot foil and surface printing.

Marking may be provided as a single or double line of marking. A single line of marking shall be provided by marking longitudinally along the length of the cable. A double line of marking shall be provided with the two lines diametrically opposite each other, longitudinally along the length of the cable.

The abrasion resistance of the sheath markings shall be demonstrated in accordance with IEC 60794-1-2, method E2B.

For a double line of marking, the abrasion resistance test needs only be carried out on one line of marking.

4.11.3 Sealing of ends

The ends of the finished cable shall be adequately sealed to prevent the ingress of moisture.

4.12 Delivery

Delivery shall be made on drums with suitable protection.

Mechanical requirements 5

5.1 Conductor

Elongation at break of the bare conductor shall be not less than:

10 % for conductor of 0,4 mm diameter;

15 % for conductor over 0,4 mm diameter.

Compliance shall be checked by measuring the elongation at break in accordance with the method specified in 3.3 of IEC 60189-1.

5.2 Insulation

The elongation at break shall be measured on tubular samples in accordance with the method specified in 9.1 of IEC 60811-1STANDARD PREVIEW

The measured values of elongation at break shall be not less than 300 %.

5.3 Sheath

IEC 60708:2005

eh.ai/catalog/standards/sist/3d40308e-2f44-408d-b19c-

Tensile strength and elongation Strength 2005 Tensile strength and elongation 5.3.1

Compliance shall be checked on samples of sheath after removing the aluminium tape by measuring the tensile strength and elongation at break in accordance with the method specified in 9.2 of IEC 60811-1-1.

The measured values of tensile strength shall be not less than:

- 10 MPa for low or medium density polyethylene;
- 16,5 MPa for high density polyethylene.

The median of the measured values of elongation at break shall be not less than 300 %.

5.3.2 Adhesion of aluminium tape to the polyethylene

The force required to peel the aluminium tape from the polyethylene shall be not less than 0,8 N per millimetre width when tested as follows:

Rectangular test pieces about 150 mm long and 15 mm wide shall be cut longitudinally from the cable sheath in one operation using a sharp punch. The test piece shall not include the overlap of the aluminium tape.

About 50 mm of the aluminium tape shall be separated from one end of the test piece. The aluminium tape shall be inserted in the upper grip of a suitable tensile testing machine and the separated end of sheath of the test piece in the lower grip.

The grips of the tensile machine shall be separated at a rate of 100 ± 50 mm/min and the average force required to separate the aluminium tape and the polyethylene sheath shall be noted.

The mean of three determinations shall be recorded as the force required to peel the aluminium tape from the cable sheath.

5.3.3 Adhesion of aluminium tape at the overlap

The force required to peel the aluminium tape at the overlap shall be not less than 0,8 N per millimeter.

5.4 Finished cable

5.4.1 Sheath integrity

5.4.1.1 The sheath shall withstand a spark test voltage of at least 8 kV r.m.s. or 12 kV d.c.

5.4.1.2 For unfilled cables, the sheath shall withstand without leakage an internal gas pressure of 50 kPa to 100 kPa for 2 h after equalization of pressure throughout the cable length.

NOTE It is not necessary to carry out this test if the sheath is tested in accordance with 5.4.1.1.

5.4.2 Resistance to water penetration ARD PREVIEW

For filled cables, the interstices of the cable core shall be filled continuously with compound to prevent the water penetration within the cable.

Compliance shall be checked on samples of filled cable according to IEC 60794-1-2, method F5B. 9dd6af7c57e1/iec-60708-2005

5.4.3 Cable drip

The cable shall pass the compound flow test of IEC 60794-1-2, method E14. The test temperature shall be 70 $^\circ\text{C}.$

6 Thermal stability and environmental requirements

6.1 Insulation

6.1.1 Thermal oxidative stability (OIT-test)

A 30 cm length of cable, with its ends sealed, shall be conditioned in an oven for 14 days at 70 °C. At the end of the conditioning period, one sample of each colour of insulation shall be removed from the cable, any filling compound present removed by wiping with a dry towel, and the measurement of OIT of the insulation carried out at 200 °C in accordance with Annex B of IEC 60811-4-2.

The insulation shall be removed from the conductor prior to testing.

The minimum oxidative induction time of any pair/quad in the finished cable shall not be less than 40 min for solid insulation and 60 min for cellular insulation.