



**SLOVENSKI STANDARD**  
**SIST EN 12501-2:2003**

**01-december-2003**

---

Dfch]\_cfcn]`g\_UnUý ]HJ\_cj ]bg\_] \ `a UHf]Ucj `!`&`XY.`A Uc`Y[ ]fUb] ]b`bYfY[ ]fUb]  
ÿYncj ]`a UHf]U]

Protection of metallic materials against corrosion - Corrosion likelihood in soil - Part 2:  
Low alloyed and non alloyed ferrous materials

Korrosionsschutz metallischer Werkstoffe - Korrosionswahrscheinlichkeit in Böden - Teil  
2: Niedrig- und unlegierte Eisenwerkstoffe

Protection des matériaux métalliques contre la corrosion - Risque de corrosion dans les  
sols - Partie 2 : Matériaux ferreux faiblement ou non alliés

<https://standards.iteh.ai/catalog/standards/sist/3b2c0ce-8991-4e01-9d3b-35b3584037e2/sist-en-12501-2-2003>

**Ta slovenski standard je istoveten z: EN 12501-2:2003**

---

**ICS:**

77.060

Korozija kovin

Corrosion of metals

**SIST EN 12501-2:2003**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 12501-2:2003

<https://standards.iteh.ai/catalog/standards/sist/3bf2c0ce-8991-4e01-9d3b-35b3584037e2/sist-en-12501-2-2003>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN 12501-2**

April 2003

ICS 77.060

English version

**Protection of metallic materials against corrosion - Corrosion likelihood in soil - Part 2: Low alloyed and non alloyed ferrous materials**

Protection des matériaux métalliques contre la corrosion -  
Risque de corrosion dans les sols - Partie 2: Matériaux  
ferreux peu ou non alliés

Korrosionsschutz metallischer Werkstoffe -  
Korrosionswahrscheinlichkeit in Böden - Teil 2: Niedrig- und  
unlegierte Eisenwerkstoffe

This European Standard was approved by CEN on 21 February 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/3b2c0ce-8991-4e01-9d3b-35b3584037e2/sist-en-12501-2-2003>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

## Contents

	page
Foreword.....	3
Introduction .....	4
1 Scope .....	4
2 Normative references .....	4
3 Terms and definitions.....	4
4 Assessment of the corrosion load in soil for a new structure to be buried .....	4
4.1 Method .....	4
4.2 Criteria.....	5
4.2.1 Soil conditions .....	5
4.2.2 Preliminary Inquiry .....	5
4.2.3 Site survey .....	5
4.2.4 Soil sampling.....	6
4.2.5 Backfill materials .....	7
5 Complementary information for an existing structure.....	7
5.1 General.....	7
5.2 Investigations and analysis .....	8
Annex A (informative) Procedure for assessing the corrosion load in soil in the case of a new structure.....	9
Annex B (informative) General principles of soil studies.....	10

## Foreword

This document (EN 12501-2:2003) has been prepared by Technical Committee CEN/TC 262 "Metallic and other inorganic coatings", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2003, and conflicting national standards shall be withdrawn at the latest by October 2003.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 12501-2:2003

<https://standards.iteh.ai/catalog/standards/sist/3bf2c0ce-8991-4e01-9d3b-35b3584037e2/sist-en-12501-2-2003>

**EN 12501-2:2003 (E)****Introduction**

This European Standard should be used in conjunction with EN 12501-1, *Protection of metallic materials against corrosion — Corrosion likelihood in soil — Part 1: General*, which describes general principles of the assessment of the corrosion load.

The method of assessing the corrosion load in the case of a new structure to be installed takes into account the adverse parameters of the soil and environment with regard to corrosion. They have been chosen to avoid underestimation of the risks of corrosion damage. The assessment is performed considering a bare structure in direct contact with the soil without taking into account any protective system that will be present in service.

The complexity of corrosion in soil demands that the measurements and their interpretation are carried out by experienced personnel. The described method should be adapted in relation to the expected service life of the structure and to possible future changes of its environment.

**1 Scope**

This part of this European Standard deals with the assessment of the corrosion load in soil for low-alloyed and non-alloyed ferrous materials in direct contact with soil. Corrosion protection systems and their performance are not covered by this standard but by specific products standards.

This part of this European Standard deals with the case of new structures to be buried and gives information for existing structures.

<https://standards.iteh.ai/catalog/standards/sist/3b2c0ce-8991-4e01-9d3b-35b3584037e2/sist-en-12501-2-2003>

**2 Normative references**

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 12501-1:2003, *Protection of metallic materials against corrosion — Corrosion likelihood in soil — Part 1: General*.

**3 Terms and definitions**

For the purposes of this European Standard, the terms and definitions given in EN 12501-1:2003 apply.

**4 Assessment of the corrosion load in soil for a new structure to be buried****4.1 Method**

The method to be applied is based on:

- general concepts and factors influencing the corrosion load given in EN 12501-1;
- criteria defined in the present standard.

The corrosion load is accepted high if no investigation is done for any reason.

## 4.2 Criteria

### 4.2.1 Soil conditions

Table 1 summarises different soil conditions to be examined during either the preliminary inquiry or the site survey and which indicate a location of high corrosion load, in the absence of further investigation.

**Table 1 — soil conditions that can lead to a high corrosion load**

Characteristics	Circumstances	Examples of criteria
Type of soil	Natural soil	Presence of peat, lignite, coal .. in the soils Areas such as marsh, fen, .. Tidal zone Presence of brackish or sea water table Anaerobic soils (Possible Microbially Induced Corrosion)
	Artificial soil	Soils containing ashes, slag, industrial by-products, residues of household refuse, ... Areas backfilled by industrial by-products (any type) Uncontrolled recycled materials
Electrical influence	Device using DC	Close vicinity of DC railways, tramways, underground, ... Proximity of a cathodically protected structure, or anodes, ...
	Device using AC	Proximity of AC power lines, AC railways Proximity to AC earthing electrodes
Pollution	Contaminated soils	Contamination by de-icing salts, manure, fertilisers, leaking sewer, industrial pollution
Others	Topography Hydrography	Presence on the pipe route of a low point, a creek or river crossing, ...
	Toponymy	Indications from the village names of special characters of the nature of soil
	Three phase boundary	Fluctuating water table

### 4.2.2 Preliminary Inquiry

A preliminary inquiry generally consists of a topographical study, a geological study and an investigation for specific information. It enables to identify areas which should be studied with particular attention during the site survey.

Annex B gives more detailed information on the way to collect data during the preliminary inquiry.

In the absence of further investigation, such as site survey or soil sampling, and if one or more criteria as given in table 1 are met corrosion load is accepted high.

### 4.2.3 Site survey

A site survey consists in collecting additional information (see Table 1) by observations and measurements on the construction site; soil resistivity measurements have to be performed and, when appropriate, potential gradient measurements.

Annex B gives additional information on the way to carry out a site survey.

The following criteria allow to assess the corrosion load, based on visual inspection of soil and resistivity measurements from the surface during the site survey:

## EN 12501-2:2003 (E)

- resistivity values below 30  $\Omega\cdot\text{m}$  and/or soil conditions as given in Table 1 indicate locations of high corrosion load;
- if resistivity values are above 30  $\Omega\cdot\text{m}$ , additional investigation such as soil sampling shall be done. However, if the three following conditions are fulfilled together, they indicate locations of low corrosion load and no other investigation is necessary:
  - soil is sand or gravel,
  - resistivity values are above 100  $\Omega\cdot\text{m}$ , for site survey conditions representative of the average soil moisture content and temperature values,
  - soil conditions as given in Table 1 are absent.

In addition, in case of a possible electrical influence, whatever its origin, measurements should be taken on site in order to assess more precisely its effects on the estimation of the corrosion load. If no measurement is performed the corrosion load is accepted high.

#### 4.2.4 Soil sampling

Soil samples are taken at various locations on site taking into account the nature, the heterogeneity and the wetness of the soil; the resistivity and pH values of the soil samples are then measured in the laboratory.

Annex B gives additional information on the procedure and measurement methods used for soil sampling.

The minimum resistivity value  $\rho^*$  and the pH value measured on a soil sample after addition of deionized water allow to assess the corrosion load using Table 2; the evaluation of soils on the border between two fields of corrosion load requires expert knowledge.

<https://standards.iteh.ai/catalog/standards/sist/3b2c0ce-8991-4e01-9d3b-11b581937c2d/sist-en-12501-2-2003>

In addition, a medium corrosion load should be changed to high when heterogeneous soil conditions occur at the level of the structure, such as:

- presence of a water table (partly submerged structure);
- wide range of  $\rho^*$  values of samples ( $\rho^*_{\text{max}} / \rho^*_{\text{min}} > 3$ );
- wide range of pH values of samples ( $\text{pH}_{\text{max}} - \text{pH}_{\text{min}} > 1,5$ ).

**Table 2 — Corrosion load (free corrosion without concentration cell)**

pH	> 9,5				
	6 – 9,5				
	4,5 - 6				
	< 4,5				
		10	30	50	100
		$\rho^*$ = Minimum resistivity value after adding deionized water ( $\Omega\cdot\text{m}$ )			



#### 4.2.5 Backfill materials

The corrosion of a buried structure will depend upon the corrosion load of the native soil, but also upon the backfilling procedure, the backfill materials (especially if they are different from the native soil) and the possible leaching conditions. An assessment of the corrosion load of imported backfill materials should therefore be carried out as it may either increase or reduce the effective corrosion load on the structure.

Table 3 indicates criteria to be met by the backfill materials in order to lead to a low corrosion load.

**Table 3 — Criteria for backfill materials**

Parameters	Low corrosion load
Resistivity	$\rho^* > 100 \Omega \cdot m$
pH <sup>a</sup>	$6 < \text{pH} < 9$
Sulfide	$< 10 \text{ mg/kg}$
Carbon	No visual detection of coal, coke, graphite, carboniferous residues
<sup>a</sup> Materials outside this pH range, but with low acidity or alkalinity amount, could be considered as leading to a low corrosion load.	

**iTeh STANDARD PREVIEW**  
(standards.itih.ai)

When industrial by-products are considered as backfill materials, the presence and amount of metallic salts should also be considered in order to avoid possible galvanic corrosion.

The use of selected backfill materials as shown in Table 3 can reduce the corrosion load (from high to medium or from medium to low), but only when the following conditions are fulfilled:

- no water table or leaching conditions that could cause contamination from the surrounding native soil;
- no mixed soils (native and imported) in contact with the structure.

## 5 Complementary information for an existing structure

### 5.1 General

In the case of an existing structure, the corrosion load in soil is assessed either to perform a diagnosis in order to evaluate the remaining life time of the structure or to establish the reasons of corrosion damages and/or failures on the structure.

As the structure actually lays in the soil, more information can be collected than in the case of a new structure (see EN 12501-1:2003; annex B). This covers:

- the information on the structure itself (such as corrosion effects, operating conditions);
- the characteristics of the soil directly in contact with the walls of the structure;
- the effect of the environment (mainly electrical influences);
- the system of protection (type of coating, cathodic protection, ...).

The three steps of the procedure for a new structure can be used for the assessment of the corrosion load; but the investigation conducted during preliminary inquiry, site survey and soil sampling will be more complete than for a