



Designation: D 6261 – 98

Standard Specification for Extruded and Compression Molded Basic Shapes Made from Thermoplastic Polyester (TPES)¹

This standard is issued under the fixed designation D 6261; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

This specification is intended to be a means of calling out mechanical grade plastic product used in the fabrication of end items or parts.

1. Scope

1.1 This specification covers requirements and test methods for the material, dimensions, and workmanship, and the properties of extruded and compression molded plate, rod and tubular bar manufactured from thermoplastic polyester.

1.2 The properties included in this specification are those required for the compositions covered. Requirements necessary to identify particular characteristics important to specialized applications may be described by using the classification system given in Section 4.

1.3 This specification allows the use of recycled plastics² (see Section 4).

1.4 The values are stated in inch-pound units and are regarded as the standard in all property and dimensional tables. For reference purposes, SI units are also included in Table 1 and Table S-TPES only.

1.5 The following precautionary caveat pertains only to the test method portions sections of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no similar or equivalent ISO Standard.

2. Referenced Documents

2.1 ASTM Standards:

D 256 Test Method for Determining the Pendulum Impact Resistance of Notched Specimens of Plastics³

D 618 Practice for Conditioning Plastics and Electrical

Insulating Materials³

D 638 Test Method for Tensile Properties of Plastics³

D 790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Materials³

D 883 Terminology Relating to Plastics³

D 3892 Practice for Packaging/Packing of Plastics⁴

D 4507 Specification for Thermoplastic Polyester (TPES) Unfilled and Reinforced Material⁴

D 4000 Classification System for Specifying Plastics Materials⁴

D 5033 Guide for the Development of Standards Relating to the Proper Use of Recycled Plastics⁵

D 5927 Specification for Thermoplastic Polyester (TPES) Injection and Extrusion Materials Based on ISO Test Methods⁴

2.2 ANSI Standard:

Z1.4-1993 Sampling Procedures and Tables for Inspection by Attributes⁶

3. Terminology

3.1 Definitions:

3.1.1 For definitions of other technical terms pertaining to plastics used in this specification, see Terminology D 883 or Guide D 5033.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *plate, n*—flat stock 1/4 in. (6.4 mm) or greater.

3.2.2 *recycled-plastic shape, n*—a product made from up to 100 % recycled plastic.

3.2.3 *rod, n*—an extruded solid cylindrical shape with a minimum diameter of 1/8 in. (3.2 mm).

3.2.4 *tubular bar, n*—an extruded annular shape with minimum inside diameter of 3/8 in. (9.6 mm) and minimum wall

¹ This specification is under the jurisdiction of ASTM Committee D-20 on Plastics and is the direct responsibility of Subcommittee D20.20 on Plastic Products (Section D20.20.02).

Current edition approved May 10, 1998. Published February 1999.

² As defined in Guide D 5033.

³ *Annual Book of ASTM Standards*, Vol 08.01.

⁴ *Annual Book of ASTM Standards*, Vol 08.02.

⁵ *Annual Book of ASTM Standards*, Vol 08.03.

⁶ Available from American National Standards Institute, 11 W. 42nd St., 13th Floor, New York, NY 10036.



thickness of 1/16 in. (1.6 mm).

4. Classification and Material

4.1 Product shape and size as defined in the applicable purchase order.

4.2 This specification covers product extruded and compression molded as listed in Table S-TPES. Products included in the designations reference Specification D 4507 or Specification D 5927 callouts where applicable.

4.2.1 The type of thermoplastic polyester shape product may be categorized by type, grade and class depending on resin and filler compositions as defined in Table S-TPES.

4.2.2 Each type of thermoplastic polyester shape may be categorized into one of several grades as follows:

4.2.2.1 *Grade 1—General Purpose*—Extruded or compression molded product made using only 100 % virgin thermoplastic polyester resin.

4.2.2.2 *Grade 2—Recycled*—Extruded or compression molded product made using any amount up to 100 % recycled thermoplastic polyester plastics.

4.3 The type, class and grade is further differentiated based on dimensional stability (elevated temperature excursion test), Table S-TPES, and dimensional requirements, Tables A and B.

4.4 Property Tables:

4.4.1 Table S-TPES may be used to describe both extruded or compression molded products.

4.4.2 Table 1 may also be used to describe extruded or compression molded products not included in Table S-TPES via a cell callout that includes the applicable Table S-TPES thermoplastic polyester type and specific properties (Designations 1 through 7).

4.4.3 To facilitate the incorporation of future or special materials not covered by the Table S-TPES, the “as specified” category (00) for type, class and grade is shown in the table with the basic properties to be obtained from Table 1, as they apply.

4.4.4 *Reinforcements and Additive Materials*—A symbol (single-letter) will be used for the major reinforcement or combination, or both, along with two numbers that indicate the percentage of addition by mass with the tolerances as tabulated below. This must be included in all Table 1 callouts.

Symbol	Material	Tolerance (Based on the Total Mass)
C	Carbon and graphite fiber reinforced	± 2 %
G	Glass-reinforced < 15 % glass content > 15 % glass content	± 2 % ± 3 %
L	Lubricants (for example, PTFE, graphite and silicone)	by agreement between the supplier and the user
M	Mineral	± 2 %
R	Combinations of reinforcements or fillers, or both	± 3 % for the total reinforcement

4.5 *Callout Designation*—A one-line system shall be used to specify thermoplastic polyester materials covered by this specification. The system uses pre-defined cells to refer to specific aspects of this specification as illustrated below:

4.5.1 Examples:

4.5.1.1 *Example 1*—Product made from general purpose PBT

CELL CALLOUT: S-TPES0111

S-TPES01 = Product made from PBT in accordance with Table S-TPES

1 = Unfilled class

1 = General purpose grade product

4.5.1.2 *Example 2*—Product made from general purpose PET

CELL CALLOUT: S-TPES0211

S-TPES02 = Product made from PET in accordance with Table S-TPES

1 = Unfilled class

1 = General purpose grade product

4.5.2 These two examples illustrate how a one-line, alphanumeric sequence can identify the product composition, commercial parameters and physical characteristics of extruded or compression molded product. A space must be used as a separator between the specification number and the type designation. No separators are needed between type, class and grade. When special notes are to be included, such information should be preceded by a comma. Special tolerances must be noted at time of order and are inserted after the grade in parentheses and preceded by a comma.

5. Ordering Information

5.1 All shapes covered by this specification shall be ordered using the proper callout designation (see 4.5).

6. Physical Property Requirements

6.1 The physical property values listed within this specification's tables are to be considered minimum specification values. Any requirement for specific test data for a given production lot should be specified at the time of order. Physical properties for products not yet included in Table S-TPES may be specified using Table 1 for extruded or compression molded products.

7. Dimensional Requirements

7.1 The type, class and grade is differentiated based on dimensional stability (elevated temperature excursion test), as indicated in Table S-TPES.

7.2 Products shall be produced within commercial tolerances and with the lowest stress levels for machined parts as delineated in Tables A and B.

7.3 Tubular bar dimensions shall be supplied in the unfinished condition, unless otherwise specified at time of order, sufficient to finish to the nominal dimension ordered.

7.4 The maximum allowable camber or bow or both, shall be within the limits referenced in Tables A and B.

8. Workmanship, Finish and Appearance

8.1 *Appearance*—The resin material color is white to off-white. The product color shall be as published by the shapes manufacturer. They shall be uniform in color throughout the thickness. Specific colors and color matching only as agreed to by order. Physical properties may be affected by other colors.

8.2 *Finish*—All products shall be free of blisters, wrinkles, cracks, gouges and defects that restrict commercial use of the