



Designation: D 6297 – 01

Standard Specification for Asphaltic Plug Joints for Bridges¹

This standard is issued under the fixed designation D 6297; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This specification covers the material, testing and application requirements for a field molded asphaltic plug joint (APJ) used in expansion joint sealing on asphalt concrete overlay and portland cement concrete decks. The scope of this specification is limited to field molded APJ. This molded element can consist of multilayer, or single layer, or both, application systems depending upon individual manufacturing requirements. The details of this specification are limited to the materials used in the application of APJ. It is recommended that a practical means of testing the watertightness aspects of the individual systems, either in the field or at the testing laboratory, be developed. When used on highway bridges, limits on maximum joint movements shall be specifically identified for each type of APJ. APJs should not be used for movement applications exceeding ± 25 mm from the installation width.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are provided for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- A 36/A 36M Specification for Carbon Structural Steel²
- B 209 Specification for Aluminum and Aluminum-Alloy Sheet and Plate³
- D 5 Test Method for Penetration of Bituminous Materials⁴
- D 36 Test Method for Softening Point of Bitumen (Ring-and-Ball Apparatus)⁵

¹ This specification is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.32 on Bridges and Structures.

Current edition approved Dec. 10, 2001. Published February 2002. Originally published as D 6297–98. Last previous edition D 6297–98.

² *Annual Book of ASTM Standards*, Vol 01.04.

³ *Annual Book of ASTM Standards*, Vol 02.02.

⁴ *Annual Book of ASTM Standards*, Vol 04.03.

⁵ *Annual Book of ASTM Standards*, Vol 04.04.

- D 113 Test Method for Ductility of Bituminous Materials⁴
- D 217 Test Methods for Cone Penetration of Lubricating Grease⁶
- D 3405 Specification for Joint Sealants, Hot-Applied, for Concrete and Asphalt Pavements⁴
- D 3407 Test Methods for Joint Sealants, Hot-Poured, for Concrete and Asphalt Pavements⁴
- D 5167 Practice for Melting of Hot-Applied Joint and Crack Sealant and Filler for Evaluation⁴
- D 5249 Specification for Backer Material for Use with Cold and Hot-Applied Joint Sealants in Portland Cement Concrete and Asphalt Joints⁴
- D 5329 Test Methods for Sealants and Fillers, Hot-Applied, for Joints and Cracks in Asphalt and Portland Cement Concrete Pavements⁴

3. Terminology

3.1 Acronyms:

- 3.1.1 *APJ*—Asphaltic Plug Joint.
- 3.1.2 *AB*—Asphaltic Binder.

4. Material

4.1 The AB shall be a thermoplastic polymeric-modified asphalt conforming to the physical properties in Table 1.

4.2 The specified aggregate shall be crushed, washed, and dried. Specific size and gradations of aggregate shall be agreed upon by the purchaser and APJ manufacturer. The aggregate shall be preweighed and packaged to avoid confusion on the jobsite. It shall be noted that specific sizes of aggregate may be proprietary to certain manufacturers.

4.3 The closed cell foam expansion joint filler shall be nongassing and capable of withstanding the elevated installation temperature (199 °C) of the AB and meet Specification D 5249.

4.4 The steel bridging plate shall conform to Specification A 36/A 36M for mild steel or Specification B 209 for aluminum.

5. Physical Properties

5.1 The thermoplastic polymeric modified asphalt shall conform to the physical properties prescribed in Table 1.

⁶ *Annual Book of ASTM Standards*, Vol 05.01.