



# Standard Test Methods for Thin Thermally Conductive Solid Materials for Electrical Insulation and Dielectric Applications<sup>1</sup>

This standard is issued under the fixed designation D 6343; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This standard is a compilation of test methods for evaluating properties of thermally conductive electrical insulation sheet materials to be used for dielectric applications.

1.2 Such materials are thin, compliant sheets, typically produced by mixing thermally conductive particulate fillers with organic or silicone binders. For added physical strength these materials are often reinforced with a woven or nonwoven fabric or a dielectric film.

1.3 These test methods apply to thermally conductive sheet material ranging from about 0.02 to 6-mm thickness.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* See also 18.1.2 and 19.1.2.

1.5 The values stated in SI units are to be regarded as standard.

NOTE 1—There is no IEC publication or ISO standard equivalent to this standard.

## 2. Referenced Documents

### 2.1 ASTM Standards:

D 149 Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies<sup>2</sup>

D 150 Test Methods for AC Loss Characteristics and Permittivity (Dielectric Constant) of Solid Electrical Insulating Materials<sup>2</sup>

D 257 Test Methods for DC Resistance or Conductance of Insulating Materials<sup>2</sup>

D 374M Test Methods for Thickness of Solid Electrical Insulation [Metric]<sup>2</sup>

D 412 Test Methods for Vulcanized Rubber and Thermoplastic Rubbers and Thermoplastic Elastomers—Tension<sup>3</sup>

D 624 Test Method for Tear Strength of Conventional Vulcanized Rubber and Thermoplastic Elastomers<sup>3</sup>

D 792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement<sup>4</sup>

D 883 Terminology Relating to Plastics<sup>4</sup>

D 1000 Test Methods for Pressure-Sensitive Adhesive-Coated Tapes Used for Electrical and Electronic Applications<sup>2</sup>

D 1458 Test Methods for Fully Cured Silicone Rubber-Coated Glass Fabric and Tapes for Electrical Insulation<sup>2</sup>

D 1711 Terminology Relating to Electrical Insulation<sup>2</sup>

D 2240 Test Method for Rubber Property—Durometer Hardness<sup>3</sup>

D 5470 Test Method for Thermal Transmission Properties of Thin Thermally Conductive Solid Electrical Insulation Materials<sup>5</sup>

D 6054 Practice for Conditioning Electrical Insulating Materials for Testing<sup>5</sup>

## 3. Terminology

### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *apparent thermal conductivity,  $n$* —the time rate of heat flow, under steady conditions, through unit area, per unit temperature gradient in the direction perpendicular to the area, for a nonhomogeneous material.

3.1.1.1 See 16.1 for a discussion of the terms *thermal conductivity* and *apparent thermal conductivity*. To avoid confusion, these test methods use *apparent thermal conductivity* for measurements of homogeneous and nonhomogeneous materials.

<sup>1</sup> These test methods are under the jurisdiction of ASTM Committee D-9 on Electrical and Electronic Insulating Materials and are the direct responsibility of Subcommittee D09.19 on Dielectric Sheet and Roll Products.

Current edition approved March 10, 1999. Published June 1999. Originally published as D 6343 – 98. Last previous edition D 6343 – 98.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 10.01.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 09.01.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 08.01.

<sup>5</sup> *Annual Book of ASTM Standards*, Vol 10.02.

3.1.2 See Terminologies D 1711 and D 883 for definitions of other terms used in these test methods.

#### 4. Significance and Use

4.1 These test methods are useful to determine compliance of thermally conductive sheet electrical insulation with specification requirements established jointly by a producer and a user.

4.2 These test methods have been found useful for quality assessment. Results of the test methods can be useful in apparatus design.

#### 5. Specimen Preparation

5.1 From a sample of sufficient size, prepare test specimens of the dimensions and of the quantity to meet the requirements for each test procedure.

#### 6. Conditioning

6.1 Unless otherwise specified, condition specimens in accordance with Procedure A of Practice D 6054. Perform all tests on specimens that are in equilibrium with the conditions of Procedure A of Practice D 6054. Make the tests in a chamber maintained at  $23 \pm 2^\circ\text{C}$  and  $50 \pm 5\%$  relative humidity.

6.2 When required by a test procedure, condition specimens in accordance with Procedure D of Practice D 6054 except that either distilled or deionized water may be used. In such cases, remove the specimens from the water into air maintained at  $23 \pm 2^\circ\text{C}$  and  $50 \pm 5\%$  relative humidity, remove surface water with a paper towel, and begin testing within 30 s.

#### 7. Precision and Bias

7.1 No evaluation of precision or bias has been established for the test methods herein as they relate to these thin thermally conductive materials. For general guidance only, reference may be made to Precision and Bias statements in the referenced test methods as listed in Section 2.

#### 8. Thickness

8.1 *Significance and Use*—The accurate determination of thickness is essential for design purposes for both thermal conduction and electrical insulation. Thickness enters into the calculation of thermal, electrical, and tensile properties.

##### 8.2 Procedure:

8.2.1 Make thickness measurements on specimens in accordance with Test Methods D 374M, Method H. This test method uses a micrometer which applies a pressure of  $26 \pm 4$  kPa on the specimen, using a 6.25-mm diameter presser foot.

8.2.2 Clean the surfaces where the measurements are to be made. Take five randomly spaced measurements to cover the length and width of the specimen. Take measurements at least 6 mm from the edges of the specimen.

NOTE 2—At the compressive loads of this test method, some materials will undergo compression or compression deflection. The buyer and the seller may wish to agree on other conditions of pressure, anvil and presser foot geometry, and the dwell time to be used.

8.3 *Report*—Report the thickness in millimetres as the average of the five measurements.

#### 9. Adhesion Strength

9.1 *Significance and Use*—Materials covered by this test method are optionally coated with a pressure sensitive adhesive on one or both sides. In some cases performance in a particular application can be affected by the adhesion strength.

9.2 *Procedure*—Test three specimens of 25-mm width in accordance with Test Methods D 1000 except, clean the steel panel with isopropyl alcohol.

9.3 *Calculation*—From the 3 specimens, calculate the average adhesion strength.

9.4 *Report*—Report the average adhesion strength in newtons per metre of width.

#### 10. Breaking Strength

10.1 *Significance and Use*—Breaking strength can be a significant limitation on methods of applying tapes. Hence it may be important to measure the tensile force they can withstand.

##### 10.2 Procedure:

10.2.1 Prepare three specimens at least 500 mm long and 25 mm wide. If the material contains reinforcing fibers, cut the test specimen such that the machine direction reinforcing fibers are parallel to the long axis of the specimen. In the case of materials narrower than 25 mm, test the full width as received.

10.2.2 Test the breaking strength in accordance with Test Methods D 1458.

10.3 *Calculation*—From the test measurements on the 3 specimens, calculate the average breaking strength.

10.4 *Report*—Report the average breaking strength in newtons per metre of width.

#### 11. Tensile Strength and Elongation

11.1 *Significance and Use*—Tensile test results with these materials will vary with specimen geometry and conditions of testing. Hence, these tensile measurements are not always reliable indicators of usefulness in a particular application. Tensile properties of glass-fiber-reinforced materials vary with the ratio of the glass-fiber thickness to the total thickness. Measurements of tensile properties vary with the direction of the glass fibers with respect to the direction in which the specimen is cut.

##### 11.2 Procedure:

11.2.1 Prepare three specimens in accordance with Test Methods D 412 using Die C.

11.2.2 If the material contains reinforcing fibers, cut the test specimen such that any reinforcing fibers are at  $45 \pm 10^\circ$  to the long axis of the specimen.

11.2.3 In accordance with Test Methods D 412, measure the tensile breaking strength and tensile elongation at a jaw separation rate of 500 mm/min (20 in./min).

##### 11.3 Calculation:

11.3.1 Calculate the tensile strength in kilopascals using the initial thickness and width for each specimen. Calculate the average tensile strength from the three test measurements.

11.3.2 Similarly, calculate each elongation at break as a percentage of the initial jaw separation. Calculate the average from the three test measurements.

11.4 *Report*—Report the average tensile strength in kilopascals and the average elongation in percent.