## International Standard



INTERNATIONAL ORGANIZATION FOR STANDARDIZATION•МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ•ORGANISATION INTERNATIONALE DE NORMALISATION

# Caprolactam for industrial use — Determination of absorbance at a wavelength of 290 nm

Caprolactame à usage industriel — Détermination de l'absorbance à la longueur d'onde de 290 nm

First edition – 1982-12-01 Teh STANDARD PREVIEW (standards.iteh.ai)

ISO 7059:1982 https://standards.iteh.ai/catalog/standards/sist/aafce6cc-7f44-4de6-bbe2-cbd42cf78df4/iso-7059-1982



UDC 661.733:543.422

Ref. No. ISO 7059-1982 (E)

Descriptors: industrial products, caprolactams, tests, determination, absorbance, spectrophotometry,

#### **Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 7059 was developed by Technical Committee ISO/TC 47, Chemistry, and was circulated to the member bodies in July 1981. ds. iteh.ai)

It has been approved by the member bodies of the following countries:

Hungary India characteristics of the hard standards of the hard st Austria

Belgium

Brazil Italy Romania

China Korea, Dem. P. Rep. of South Africa, Rep. of Czechoslovakia Korea, Rep. of Switzerland

Egypt, Arab Rep. of Mexico Thailand France Netherlands United Kingdom

New Zealand Germany, F.R. USSR

No member body expressed disapproval of the document.

This International Standard has also been approved by the International Union of Pure and Applied Chemisty (IUPAC).

### Caprolactam for industrial use — Determination of absorbance at a wavelength of 290 nm

#### Scope and field of application

This International Standard specifies a spectrometric method for the determination of the absorbance at a wavelength of 290 nm of caprolactam for industrial use.

#### **Principle**

Spectrometric measurement of the absorbance of a 50 % caprolactam water solution at a wavelength of 290 nm.

Carry out the spectrometric measurements, using the spectrometer (4.1) set at a wavelength of 290 nm, after having adjusted the instrument to zero absorbance against water.

#### 5.2.2 Check for absorbance of cells

Fill the two cells used for the measurements (5.2.1) with water and measure the absorbance of each cell at a wavelength of 290 nm.

One of the cells will read "zero" since it has been used to adjust the instrument to zero absorbance.

iTeh STANDAR

NOTE — The difference between the measured absorbances should not exceed 0,003. (standards.iten.al

#### Reagents

During the analysis, use only distilled water or water of equivalent purity.

**Expression of results** 

https://standards.iteh.ai/catalog/standards/ The absorbance at a wavelength of 290 nm, expressed in relacbd42cf78df4/iso-7 tion to an optical path length of 1 cm, is given by the formula

#### **Apparatus**

Ordinary laboratory apparatus and

- 4.1 Ultraviolet molecular absorption spectrometer, fitted with a hydrogen or deuterium lamp.
- 4.2 Two quartz cells, of optical path length 1 cm, as minimum.

#### **Procedure**

#### 5.1 Test portion and preparation of the test solution

Weigh to the nearest 0,1 g, 50 g of the test sample, dissolve it in 50 ml of water, and mix.

#### 5.2 Determination

#### 5.2.1 Spectrometric measurements

Fill one of the cells (4.2) with the test solution (5.1) and fill the other cell with water.

$$\frac{(A_1-A_0)}{l}$$

where

- $A_0$  is the correction for the difference in absorbances of the cells (see 5.2.2);
- $A_1$  is the absorbance (5.2.1) of the test solution (5.1);
- l is the optical path length, in centimetres, of the cell.

#### Test report

The test report shall include the following information:

- a) an identification of the sample;
- the reference of the method used;
- the results and the method of expression used;
- any unusual features noted during the determination;
- e) any operation not included in this International Standard or regarded as optional.

## iTeh STANDARD PREVIEW

This page intentionally left blank

ISO 7059:1982 https://standards.iteh.ai/catalog/standards/sist/aafce6cc-7f44-4de6-bbe2-cbd42cf78df4/iso-7059-1982