

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Magnetic materials –
Part 8-7: Specifications for individual materials – Cold-rolled grain-oriented
electrical steel strip and sheet delivered in the fully-processed state**

**Matériaux magnétiques –
Partie 8-7: Spécifications pour matériaux particuliers – Bandes et tôles
magnétiques en acier à grains orientés, laminées à froid et livrées à l'état fini**

<https://standards.iteh.ai/standards/iec/94245427-7d7d-487c-b5ca-79d791bae242/iec-60404-8-7-2008>



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2008 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch

Tel.: +41 22 919 02 11

Fax: +41 22 919 03 00

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

- Catalogue des publications de la CEI: www.iec.ch/searchpub/cur_fut-f.htm

Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,...). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.

- Just Published CEI: www.iec.ch/online_news/justpub

Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.

- Electropedia: www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International en ligne.

- Service Clients: www.iec.ch/webstore/custserv/custserv_entry-f.htm

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:

Email: csc@iec.ch

Tél.: +41 22 919 02 11

Fax: +41 22 919 03 00

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Magnetic materials –
Part 8-7: Specifications for individual materials – Cold-rolled grain-oriented
electrical steel strip and sheet delivered in the fully-processed state**

**Matériaux magnétiques –
Partie 8-7: Spécifications pour matériaux particuliers – Bandes et tôles
magnétiques en acier à grains orientés, laminées à froid et livrées à l'état fini**

<https://standards.iteh.ai/catalog/standards/iec/94245427-7d7d-487c-b5ca-79d791bae242/iec-60404-8-7-2008>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

R

CONTENTS

FOREWORD.....	4
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	7
4 Classification.....	7
5 Designation	7
6 General requirements	8
6.1 Production process.....	8
6.2 Form of supply	8
6.3 Delivery condition.....	9
6.4 Surface condition	9
6.5 Suitability for cutting.....	9
7 Technical requirements	9
7.1 Magnetic properties.....	9
7.1.1 General	9
7.1.2 Magnetic polarization.....	9
7.1.3 Specific total loss	11
7.2 Geometric characteristics and tolerances	11
7.2.1 Thickness	11
7.2.2 Width.....	12
7.2.3 Length	12
7.2.4 Edge camber.....	13
7.2.5 Flatness (wave factor)	13
7.2.6 Residual curvature	13
7.2.7 Burr height	13
7.3 Technological characteristics	13
7.3.1 Density	13
7.3.2 Stacking factor	13
7.3.3 Number of bends	13
7.3.4 Internal stresses	13
7.3.5 Insulation coating resistance	13
8 Inspection and testing	14
8.1 General	14
8.2 Selection of samples	14
8.3 Preparation of test specimens	14
8.3.1 Magnetic properties	14
8.3.2 Geometrical characteristics and tolerances.....	15
8.3.3 Technological characteristics.....	15
8.4 Test methods	16
8.4.1 General	16
8.4.2 Magnetic properties	16
8.4.3 Geometrical characteristics and tolerances.....	16
8.4.4 Technological characteristics.....	17
8.5 Retests.....	17
9 Marking, labelling and packaging.....	17
10 Complaints	17

11 Information to be supplied by the purchaser	18
Annex A (informative) European steel designation	19

Table 1 – Technological and magnetic properties of the conventional grades of grain-oriented material.....	10
Table 2 – Technological and magnetic properties of the high permeability grades of grain-oriented material.....	11
Table 3 – Tolerances on nominal width	12
Table A.1 – European steel designation.....	19

Withheld

iTech Standards
(<https://standards.itih.ai>)
Document Preview

<https://standards.itih.ai/catalog/standards/iec/94245427-7d7d-487c-b5ca-79d791bae242/iec-60404-8-7-2008>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

MAGNETIC MATERIALS –

**Part 8-7: Specifications for individual materials –
Cold-rolled grain-oriented electrical steel strip and sheet
delivered in the fully-processed state**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60404-8-7 has been prepared by IEC technical committee 68: Magnetic alloys and steels.

This third edition cancels and replaces the second edition published in 1998 of which it constitutes a technical revision. This revision extends the range of electrical steels to include the improved grades.

The text of this standard is based on the following documents:

FDIS	Report on voting
68/367/FDIS	68/370/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60404 series, under the general title *Magnetic materials*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

Withdrawing

iTech Standards
(<https://standards.itih.ai>)
Document Preview

<https://standards.itih.ai/Catalogue/standards/iec/94245427-7d7d-487c-b5ca-79d791bae242/iec-60404-8-7-2008>

MAGNETIC MATERIALS –

Part 8-7: Specifications for individual materials – Cold-rolled grain-oriented electrical steel strip and sheet delivered in the fully-processed state

1 Scope

This part of IEC 60404 defines the grades of cold-rolled grain-oriented electrical steel strip and sheet in nominal thicknesses of 0,23 mm, 0,27 mm, 0,30 mm and 0,35 mm. In particular, it gives general requirements, magnetic properties, geometric characteristics, tolerances and technological characteristics, as well as inspection procedures.

This standard applies to Goss textured grain-oriented electrical steel strip and sheet supplied in the final annealed condition in sheets or coils, and intended for the construction of magnetic circuits.

The grades are grouped into two classes:

- conventional grades;
- high permeability grades.

They correspond to Class C.22 of IEC 60404-1.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-121, *International Electrotechnical Vocabulary – Part 121: Electromagnetism*

IEC 60050-221, *International Electrotechnical Vocabulary – Part 221: Magnetic materials and components*

IEC 60404-1, *Magnetic materials – Part 1: Classification*

IEC 60404-1-1, *Magnetic materials – Part 1-1: Classification - Surface insulations of electrical steel sheet, strip and laminations*

IEC 60404-2, *Magnetic materials – Part 2: Methods of measurement of the magnetic properties of electrical steel sheet and strip by means of an Epstein frame*

IEC 60404-3, *Magnetic materials – Part 3: Methods of measurement of the magnetic properties of magnetic sheet and strip by means of a single sheet tester*

IEC 60404-9, *Magnetic materials – Part 9: Methods of determination of the geometrical characteristics of magnetic steel sheet and strip*

IEC 60404-11, *Magnetic materials – Part 11: Method of test for the determination of surface insulation resistance of magnetic sheet and strip*

IEC 60404-13, *Magnetic materials – Part 13: Methods of measurement of density, resistivity and stacking factor of electrical steel sheet and strip*

ISO 404, *Steel and steel products – General technical delivery requirements*

ISO 7799, *Metallic materials – Sheet and strip 3 mm thick or less – Reverse bend test*

ISO 10474, *Steel and steel products – Inspection documents*

3 Terms and definitions

For the purposes of this document, the definitions of the principal terms relating to magnetic properties given in IEC 60050-121 and IEC 60050-221 apply, as well as the following definitions:

3.1

edge camber

greatest distance between a longitudinal edge of the sheet and the line joining the two extremities of the measured length of this edge

NOTE See IEC 60404-9.

3.2

flatness (wave factor)

the property of a sheet or of a length of strip which is characterized by the wave factor, i.e. by the relation of the height of the wave to its length

NOTE See IEC 60404-9.

3.3

number of bends

number of alternate bends possible before the appearance of the first crack in the base metal visible to the naked eye

NOTE It constitutes an indication of the ductility of the material.

3.4

internal stresses

stresses which are characterized by a deviation in relation to the line of cutting

4 Classification

The grades covered by this standard are classified according to the value of maximum specific total loss in watts per kilogram and according to the nominal thickness of the material¹⁾ (0,23 mm, 0,27 mm, 0,30 mm and 0,35 mm).

5 Designation

The steel name comprises the following in the order given:

- 1) the letter M for electrical steel;
- 2) one hundred times the specified value of maximum specific total loss at 1,7 T and 50 Hz, in watts per kilogram and corresponding to the nominal product thickness;

1) In the rest of the document, the word "material" is used to mean "sheet and strip".

- 3) one hundred times the nominal thickness of the material, in millimetres;
- 4) the characteristic letter
 - S for conventional grades;
 - P for high permeability grades;
- 5) one tenth of the frequency 50 Hz, i.e. 5.

EXAMPLE M140-30S5 for cold-rolled grain-oriented electrical steel sheet or strip of conventional grade with a maximum specific total loss at 1,7 T of 1,40 W/kg at 50 Hz and a nominal thickness of 0,30 mm, supplied in the fully-processed state.

NOTE The corresponding steel numbers used in the relevant European Standard are given in Annex A.

6 General requirements

6.1 Production process

The production process of the steel and its chemical composition are left to the discretion of the manufacturer.

6.2 Form of supply

The material is supplied in bundles in the case of sheets and in coils in the case of strip.

The mass of the bundles of sheets or coils shall be agreed at the time of ordering.

The recommended value for the internal diameter of coils is approximately 508 mm.

Sheets which make up each bundle shall be stacked so that the side faces are substantially flat and approximately perpendicular to the top face.

Strip shall be of constant width and wound in such a manner that the edges are superimposed in a regular manner and the side faces of the coil are substantially flat.

Coils shall be sufficiently tightly wound in order that they do not collapse under their own weight.

Strip may exhibit welds or interleaves resulting from the removal of defective zones if agreed at the time of enquiry and order. If necessary, the marking of welds or interleaves may be agreed at the time of enquiry and order.

For coils containing repair welds or interleaves, each part of the strip shall be of the same grade.

The edges of parts welded together shall not be so much out of alignment as to affect the further processing of the material.

6.3 Delivery condition

Cold-rolled grain-oriented steel material is usually supplied with an insulating coating on both sides. This coating generally consists of an EC-5-G coating on an EC-2 coating in accordance with IEC 60404-1-1²⁾.

6.4 Surface condition

The surfaces shall be smooth and clean, free from grease and rust³⁾. Dispersed defects such as scratches, blisters, cracks, etc. are permitted if they are within the limits of the tolerances on thickness and if they are not detrimental to the correct use of the supplied material.

The insulation coating present on the surface of the material shall be sufficiently adherent so that it does not become detached during cutting operations or heat treatment under conditions specified by the supplier.

NOTE If the product is to be immersed in a fluid, an agreement, initiated by the purchaser, should be reached to ensure compatibility between the fluid and the coating.

6.5 Suitability for cutting

The material shall be suitable for cutting accurately into the usual shapes at any point when appropriate cutting tools are used.

7 Technical requirements

7.1 Magnetic properties

7.1.1 General

The properties defined in 7.1.2 and 7.1.3 shall apply to materials in the delivery condition defined in 6.3 and to the aged condition defined in 8.3.1.

The Epstein strips shall receive a stress relief heat treatment after cutting under conditions specified by the manufacturer.

The single sheet test specimens shall not be heat treated.

7.1.2 Magnetic polarization

The specified minimum values of peak magnetic polarization for the peak magnetic field strength of 800 A/m at 50 Hz or 60 Hz shall be as given in Tables 1 and 2.

2) Other types of coating exist which are used only when particularly specified.

3) Not to be confused with some coloration of the insulating coating inherent to the manufacturing process.

Table 1 – Technological and magnetic properties of the conventional grades of grain-oriented material

Steel name	Nominal thickness mm	Maximum specific total loss at 1,5 T		Maximum specific total loss at 1,7 T		Minimum magnetic polarization for $H = 800 \text{ A/m}^a$ T	Minimum stacking factor
		W/kg		W/kg			
		50 Hz	60 Hz	50 Hz	60 Hz		
M110-23S5	0,23	0,73	0,96	1,10	1,45	1,78	0,945
M120-23S5	0,23	0,77	1,01	1,20	1,57	1,78	0,945
M120-27S5	0,27	0,80	1,07	1,20	1,58	1,78	0,950
M130-27S5	0,27	0,85	1,12	1,30	1,68	1,78	0,950
M130-30S5	0,30	0,85	1,15	1,30	1,71	1,78	0,955
M140-30S5	0,30	0,92	1,21	1,40	1,83	1,78	0,955
M145-35S5	0,35	1,03	1,36	1,45	1,91	1,78	0,960
M155-35S5	0,35	1,07	1,41	1,55	2,04	1,78	0,960

^a It has been common practice for many years to give values of magnetic flux density. In fact the Epstein frame is used to determine magnetic polarization (intrinsic flux density) which is defined as

$$J = B - \mu_0 H$$

where

J is the magnetic polarization;

B is the magnetic flux density;

μ_0 is the magnetic constant: $4 \pi \times 10^{-7} \text{ H}\cdot\text{m}^{-1}$;

H is the magnetic field strength.

NOTE The difference between B and J at 800 A/m is equal to 0,001 T.