



Designation: E1980 – 01

Standard Practice for Calculating Solar Reflectance Index of Horizontal and Low-Sloped Opaque Surfaces¹

This standard is issued under the fixed designation E1980; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

The steady-state surface temperature (T_s) under the sun is strongly correlated to solar reflectivity and thermal emissivity of the surface. For equivalent conditions, the T_s of dark surfaces (with low solar reflectance) is higher than light-colored surfaces (with high solar reflectance); and surfaces with low thermal emissivity have higher T_s 's than surfaces with high thermal emissivity. The procedure recommended in this standard will allow a direct comparison of T_s of surfaces under the sun. The procedure defines a Solar Reflectance Index (SRI) that measures the relative T_s of a surface with respect to the standard white (SRI = 100) and standard black (SRI = 0) under the standard solar and ambient conditions.

1. Scope

1.1 This practice covers the calculation of the Solar Reflectance Index (SRI) of horizontal and low-sloped opaque surfaces at standard conditions. The method is intended to calculate SRI for surfaces with emissivity greater than 0.1.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E408 [Test Methods for Total Normal Emittance of Surfaces Using Inspection-Meter Techniques](#)

E772 [Terminology Relating to Solar Energy Conversion](#)

E891 [Tables for Terrestrial Direct Normal Solar Irradiance for Air Mass 1.5](#)³

E903 [Test Method for Solar Absorptance, Reflectance, and Transmittance of Materials Using Integrating Spheres](#)⁴

¹ This test method is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.18 on Nonbituminous Organic Roof Coverings.

Current edition approved April 10, 2001. Published April 2001. Originally published as E1980–98. Last previous edition E1980–98¹. DOI: 10.1520/E1980-01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Withdrawn.

⁴ Withdrawn. The last approved version of this historical standard is referenced on www.astm.org.

[E1918 Test Method for Measuring Solar Reflectance of Horizontal and Low-Sloped Surfaces in the Field](#)

3. Terminology

3.1 *Definitions:*

3.1.1 *convective coefficient (h_c)*—the rate of heat transfer from the surface to air induced by the air movement, expressed in watts per square metre per degree Kelvin, $W \cdot m^{-2} \cdot K^{-1}$.

3.1.2 *low-sloped surfaces*—surfaces with a slope smaller than 9.5° from the horizontal.

3.1.3 *reference black surface temperature (T_b)*—is the steady-state temperature of a black surface with solar reflectance of 0.05 and thermal emissivity of 0.9, under the standard solar and ambient conditions.

3.1.4 *reference white surface temperature (T_w)*—is the steady-state temperature of a white surface with solar reflectance of 0.80 and thermal emissivity of 0.9, under the standard solar and ambient conditions.

3.1.5 *sky temperature (T_{sky})*—is the temperature of a black body that would radiate the same power toward the earth as does the sky.

3.1.6 *solar absorptance (α)*—the fraction of solar flux absorbed by a surface. For an opaque surface $\alpha = 1 - a$.

3.1.7 *solar flux (I)*—is the direct and diffuse radiant power from the sun received at ground level over the solar spectrum, expressed in watts per square metre, $W \cdot m^{-2}$.

3.1.8 *solar reflectance (a)*—the fraction of solar flux reflected by a surface.