



Designation: D 6437 – 99

## Standard Test Method for Polyurethane Raw Materials: Alkalinity in Low-Alkalinity Polyols (Determination of CPR Values of Polyols)<sup>1</sup>

This standard is issued under the fixed designation D 6437; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method covers measuring alkalinity in low-alkalinity ( $<0.002$  meq/g basicity) polyols. This alkalinity is often expressed as CPR (controlled polymerization rate) of polyether polyols. This test method is not applicable to amine-based polyols.

1.2 The values stated in SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no similar or equivalent ISO standard.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D 883 Terminology Relating to Plastics<sup>2</sup>

E 180 Practice for Determining the Precision of ASTM Methods for Analysis and Testing of Industrial Chemicals<sup>3</sup>

E 691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method<sup>4</sup>

### 3. Terminology

#### 3.1 Definitions:

3.1.1 The terminology in this test method is in accordance with the standard terminology defined in Terminology D 883.

#### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *CPR*—controlled polymerization rate is expressed as basicity in milliequivalents per 30 kg of sample (meq/30 kg).

### 4. Summary of Test Method

4.1 This test method is a potentiometric titration for sample basicity in methanol solvent. This test method uses a relatively large sample and titration with dilute acid solution to determine trace quantities of basicity.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D-20 on Plastics and is the direct responsibility of Subcommittee D20.22 on Cellular Materials—Plastics and Elastomers.

Current edition approved July 10, 1999. Published September 1999.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 08.01.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 15.05.

<sup>4</sup> *Annual Book of ASTM Standards*, Vols 06.03, 08.03, and 14.02.

### 5. Significance and Use

5.1 This test method is suitable for quality control, as a specification test and for research. The urethane reaction between polyols and isocyanates to form polyurethane polymers is known to be sensitive to the presence of basic substances. This is particularly important in the preparation of polyurethane prepolymers which contain isocyanate groups that are known to react in the presence of trace amounts of basic substances. Since many polyether polyols are often made with strongly basic catalysts, it is important to have an analytical method capable of detecting small quantities of residual basic substances. This test method is capable of detecting ppm levels of base (as KOH).<sup>5</sup>

### 6. Apparatus

6.1 *Potentiometric Automatic Titrator*, capable of detecting multiple titration end points.

6.2 *Autotitrator Buret*, 5 mL (See Note 2) .

6.3 *Buret or Dosing Device*, capable of dosing 50 mL.

6.4 *pH Glass Electrode and Reference Electrode or a Combination Glass Electrode*.

6.5 *Analytical Balance*, capable of weighing to the nearest 0.01 g.

NOTE 2—A 1-mL titrator buret may be used if available. Due to the low volumes of titrant typically required (0 to 0.5 mL), larger burets will give less precise results.

### 7. Reagents and Materials

7.1 *HCl Aqueous*, 0.01 N—Standardize to detect changes of 0.0001 N.

7.2 *Methanol*, reagent grade

### 8. Procedure

8.1 Set up the autotitrator to find multiple end points with a maximum volume of 5 mL.

8.2 Place  $50 \pm 0.1$  mL of methanol solvent in a 100-mL titration cup and titrate a blank using 0.01 N aqueous HCl.

8.3 Weigh  $30 \pm 1.00$  g of sample into a titration cup. Add  $50 \pm 0.1$  mL of reagent grade methanol, stir to mix well, and

<sup>5</sup> H.G. Scholten, J.G. Schuhman, R.E. TenHoor, *Journal of Chemical Engineering Data*, 5, 1960, p. 396.