# INTERNATIONAL STANDARD



Second edition 1994-10-01

# Methods for the petrographic analysis of bituminous coal and anthracite —

## Part 1: iTeh SVocabularRD PREVIEW (standards.iteh.ai)

Méthod<u>es d'analyse pétrographique des charbons bitumineux et de</u> https://standards.it/ant/van/estandards/sist/7c9fae99-af61-41b7-aeda-Partie (198/66/abulair/e4-1-1994



## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting VIEW a vote.

International Standard ISO 7404-1 was prepared by Technical Committee ISO/TC 27, *Solid mineral fuels*.

ISO 7404-1:1994

This second edition canbels://standirdsrieplacesalogthendafitstist/7edition-af61-41b7-aeda-(ISO 7404-1:1984), which has been technically:revised.5ffe/iso-7404-1-1994

ISO 7404 consists of the following parts, under the general title *Methods* for the petrographic analysis of bituminous coal and anthracite:

- Part 1: Vocabulary
- Part 2: Method of preparing coal samples
- Part 3: Method of determining maceral group composition
- Part 4: Method of determining microlithotype, carbominerite and minerite composition
- Part 5: Method of determining microscopically the reflectance of vitrinite

Annex A of this part of ISO 7404 is for information only.

Printed in Switzerland

<sup>©</sup> ISO 1994

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization

Case Postale 56 • CH-1211 Genève 20 • Switzerland

## Introduction

Petrographic analyses have been recognized internationally as important in the context of the genesis, vertical and lateral variation, continuity, metamorphism and usage of coal. The International Committee for Coal and Organic Petrology (ICCP) has made recommendations concerning nomenclature and analytical methods and has published an extensive handbook describing in detail the characteristics of a wide range of coals. The text of this part of ISO 7404 agrees substantially with the text of the handbook and incorporates many useful comments made by members of the ICCP and by member bodies of ISO/TC 27, *Solid mineral fuels.* 

Petrographic analyses of a single coal provide information about the rank, the maceral and microlithotype compositions and the distribution of minerals in the coal. The reflectance of vitrinite is a useful measure of coal rank and the distribution of the reflectance of vitrinite in a coal blend, together with a maceral group analysis, can provide information about some important chemical and technological properties of the blend.

ISO 7404 is concerned with the methods of petrographic analysis currently employed in characterizing bituminous coal and anthracite in the https://standards.it.contextlof.their technological use.-Itlestablishes a system for petrographic analysis and comprises five parts, as follows:

Part 1: Vocabulary.

Part 2: Method of preparing coal samples.

Part 3: Method of determining maceral group composition.

Part 4: Method of determining microlithotype, carbominerite and minerite composition.

Part 5: Method of determining microscopically the reflectance of vitrinite.

For information on the nomenclature and analysis of brown coals and lignites, reference should be made to the *International Handbook of Coal Petrography*<sup>[1]</sup> published by the ICCP.

The complexity of coals mined throughout the world, coupled with the many applications of coal petrology in all branches of coal utilization, makes the compilation of a fully comprehensive glossary of terms a very difficult task.

This difficulty is compounded because some of the terms requiring definition have different meanings in different national nomenclatures. As a consequence, several general terms, such as bituminous coal, anthracite, brown coal and lignite, and sub-bituminous coal have had to be defined very loosely in this part of ISO 7404 pending international agreement on a new rationalized system of coal nomenclature. The definitions given are intended for use solely in connection with the generally accepted international methods of petrographic analysis of bituminous coal and anthracite described in the other parts of ISO 7404.

The petrographic terms listed are those most widely used internationally. They do not include terms such as pseudovitrinite, semi-vitrinite and semi-inertinite which refer to types of maceral with particular properties but which are difficult to define. Such terms may be considered important for specific applications in certain countries but their wider use is not recommended.

# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 7404-1:1994 https://standards.iteh.ai/catalog/standards/sist/7c9fae99-af61-41b7-aedac2810d865ffe/iso-7404-1-1994

# Methods for the petrographic analysis of bituminous coal and anthracite —

Part 1: Vocabulary

#### Scope 1

This part of ISO 7404 defines terms that are used in connection both with maceral and microlithotype an- R alyses carried out in white light and with the determination of the reflectance of vitrinite. It applies to the S. terms used in the examination of bituminous coal and anthracite only and is not concerned with the analysis, of brown coal, sub-bituminous coal or lignite atalog/standards/sis

This part of ISO 7404 is not intended to be a comprehensive glossary of coal petrographic terminology, nor does it attempt to provide sufficient information to allow recognition of all the coal components described. Further information may be obtained from the International Handbook of Coal Petrography (see the fourth paragraph of the introduction).

#### 2 Definitions

For the purposes of this part of ISO 7404, the following definitions apply.

#### 2.1 General terms

2.1.1 coal: Combustible sedimentary rock formed from altered plant remains consolidated under superimposed strata.

The characteristics of different coals are due to NOTE 1 differences in source plant material, in the conditions and the degree of change that the material has undergone in its geological history, and in the range of impurities present. Coals can be characterized microscopically by their maceral and microlithotype compositions.

2.1.2 coalification: Process by which sedimented compacted plant remains are transformed into coal.

NOTE 2 This process is characterized by an increase in the carbon content in the plant remains and a decrease in the yield of volatile matter from the plant remains. As coalification proceeds, the reflectances of the macerals increase. Vitrinite is used as a reference material for the de--10 dermination of the rank of coal because its reflectance increases uniformly with the extent of coalification.

2.1.3 rank: Position of a coal in the coalification series from brown coal (low rank) to anthracite (high rank), indicating maturity in terms of chemical and physical properties.

2.1.4 brown coal and lignite: Coals of low rank which, in their natural state, are characterized by high inherent moisture content, high volatile matter content and low calorific value, and are nonagglommerating.

NOTE 3 In some countries, the terms are used to describe all low rank coals up to bituminous coals. In other countries, the coals at the higher end of this range are referred to as sub-bituminous coals.

2.1.5 sub-bituminous coal: Coal of rank immediately below that of bituminous coal.

2.1.6 bituminous coal: A general descriptive term for coal between anthracite and brown coal/lignite.

The vitrinites in all coals in the bituminous range NOTE 4 melt and form a coke when the coal is heated above 400 °C.

2.1.7 anthracite: Coal of high rank, with a low volatile matter content and a semi-metallic lustre, and which does not soften or swell when heated.

#### 2.2 Optical microscopy terms

2.2.1 reflectance: Percentage of the near-normal incident light reflected from a polished surface.

For the purpose of this part of ISO 7404, NOTE 5 reflectance refers to measurements made on coal under oil immersion.

2.2.2 maximum reflectance: Highest value of reflectance obtained when any polished section of a particle or lump of coal is rotated in its own plane in linearly polarized light.

2.2.3 random reflectance: Reflectance of any polished section of a particle or a lump of coal when determined in unpolarized light without rotation of the specimen.

NOTE 6 The term "random reflectance" has replaced the terms "mean reflectance" and "average reflectance" to avoid any possible confusion arising from the meaning of DA specific rank. (See also 3.1.) the words "mean" and "average" in the mathematical sense.

(standards.iteh.ai) 2.3.4 microlithotype: Naturally occurring maceral 2.2.4 parasitic reflection: Percentage of the incior association of macerals with a minimum bandwidth dent light reaching the photomultiplier from lens SO 74 of 50 µm. (See also 3.2.) -aedaboundary faces and other reflecting surfaces in chalog/standar c2810d865ffe/iso-7404-1-1994 microscope.

2.2.5 reflectance standard: Polished surface of a material of known reflectance which is used for calibrating reflectance-measuring equipment.

2.2.6 zero standard: Non-reflecting standard used for calibrating reflectance-measuring equipment.

2.2.7 particulate block: Solid block consisting of particles of crushed coal representative of the sample, bound in resin, cast in a mould and with one face ground and polished.

2.2.8 lump section: Piece of coal of size suitable for polishing and examination under the microscope.

NOTE 7 One face of the lump section, usually that perpendicular to the bedding plane, is ground and polished.

**2.2.9 point:** The area overlain by the intersection of the cross-wires in the eyepiece graticule during microscopical analysis.

#### 2.3 Petrographic terms

**2.3.1 maceral:** Microscopically recognizable organic constituents of coal analogous to the minerals of inorganic rocks, but differing from them in that macerals have no characteristic crystal form and are not constant in chemical composition.

The macerals are distinguished from one an-NOTE 8 other microscopically on the basis of their differences in such properties as reflectance, colour, fluorescence, morphology, size and hardness. They originate from the remains of different tissues of plants and their physical and chemical properties change as coalification proceeds.

2.3.2 submaceral: Subdivision of a maceral based on slight morphological and physical differences.

NOTE 9 Information on the description and properties of the macerals and submacerals may be obtained by reference to the International Handbook of Coal Petrography<sup>[1]</sup>.

2.3.3 maceral group: Collective term for macerals having broadly similar properties in a single coal of

2.3.5 minerals: Natural inorganic constituents of coal observed during microscopical examination.

NOTE 10 Minerals are determined on a volume basis as part of a maceral analysis.

2.3.6 mineral matter: The inorganic material, except moisture, in a coal.

NOTE 11 Mineral matter is calculated on a mass basis either from a direct determination at low temperature or from the ash yield at high temperature.

2.3.7 carbominerite: Collective term for intergrowths of minerals and macerals. (See also 3.3.)

2.3.8 minerite: Collective term for intergrowths of minerals with different macerals in which the proportion of minerals is more than 60 % by volume, or in which more than 20 % by volume of sulfide minerals is present.

groups and at least 5 % by volume of each. A

trimaceral microlithotype contains at least 95 % by

volume, on a mineral-free basis, of the three principal maceral groups and at least 5 % by volume of each.

Microlithotypes may contain not more than 5 % by volume of sulfide minerals or 20 % by volume of clay

The classification of the main microlithotypes and their maceral group compositions is given in table 2.

minerals as impurities.

# 3 Classification of macerals, microlithotypes and carbominerites

#### 3.1 Macerals

Three maceral groups are recognized: vitrinite, liptinite<sup>1)</sup> and inertinite. Maceral groups and their subdivisions are shown in table 1.

Maceral group	Maceral	Submaceral	Table 2 — Classification of the main microlithotypes		
Vitrinite	Telinite Collinite	Telinite 1 Telinite 2 Telocollinite		Microlithotype	Maceral-group composition (Total ≥ 95 % by volume, mineral-free basis)
	Vitrodetrinite	Celocollinite Desmocollinite Corpocollinite		<b>Monomaceral</b> Vitrite Liptite Inertite	Vitrinite Liptinite Inertinite
Liptinite	Sporinite Cutinite Resinite Suberinite <sup>1)</sup> Alginite Liptodetrinite Bituminite	h STANDA (standar	RD ds.i	Bimaceral Clarite Durite Vitrinertite Trimaceral Trimacerite	Vitrinite + Liptinite Inertinite + Liptinite Vitrinite + Inertinite Vitrinite + Liptinite + Inertinite
Inertinite	Micrinite Macrinite Semifusinite Fusinite Sclerotinite Inertodetrinite	<u>ISO 74</u> dards ich ai/catalog/stan Pyrofusinite Degradofusinite	<u>04-1:19</u> dards/sis so-740	<b>3.3 Carbominerit</b> st/7c9fae99-af61-41b7-ae The19Various types of table 3.	<b>es</b> da- of carbominerite are given in
1) Occurs in	post-carboniferous bi	tuminous coals		Table 3 — Ty	pes and compositions of

Tahlo	1	 Macoral	aroune and	thoir	subdivisions
Ianic		 waterar	groups and	uleii	SUDUIVISIONS

### 3.2 Microlithotypes

Microlithotypes are classified in one of three categories, namely monomaceral, bimaceral and trimaceral microlithotypes, according to whether they contain significant proportions of macerals of one, two or three maceral groups. A monomaceral microlithotype contains at least 95 % by volume, on a mineral-free basis, of the principal maceral group. A bimaceral microlithotype contains at least 95 % by volume, on a mineral-free basis, of the two principal maceral

# Table 3 — Types and compositions of carbominerite

Туре	Volume percentage of minerals			
Carbargilite Carbopyrite Carbankerite Carbosilicite Carbopolyminerite <sup>1)</sup>	20 to 60, clay minerals 5 to 20, sulfides 20 to 60, carbonates 20 to 60, quartz 20 to 60, various minerals			
<ol> <li>The term is also used for carbopolyminerite con- taining a maximum of 5 % minerals, provided sulfides form a substantial part of the mineral matter.</li> </ol>				

<sup>1)</sup> This maceral group has also been referred to as "exinite" but the use of this term is now deprecated.

### Annex A

(informative)

## **Bibliography**

[1] *International Handbook of Coal Petrography,* published by the International Committee for Coal and Organic Petrology (ICCP).

NOTE 12 The second edition (1963), together with the first supplement (1971, corrected and revised in 1985),

second supplement (1975) and third supplement (1993) may be obtained from Professor D.G. Murchison, Fossil Fuels and Environmental Geochemistry, Drummond Building, University of Newcastle, Newcastle-upon-Tyne, NE1 7RU, United Kingdom.

# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 7404-1:1994 https://standards.iteh.ai/catalog/standards/sist/7c9fae99-af61-41b7-aedac2810d865ffe/iso-7404-1-1994

## iTeh STANDARD PREVIEW This page intentionally left blank (standards.iteh.ai)

ISO 7404-1:1994 https://standards.iteh.ai/catalog/standards/sist/7c9fae99-af61-41b7-aedac2810d865ffe/iso-7404-1-1994