

---

**Predmeti, ki pridejo v stik s človeškim tkivom - Primerjalna metoda določitve koncentracije niklja s plamensko atomsko absorpcijsko spektrometrijo**

Body-piercing post assemblies - Reference test method for determination of nickel content by flame atomic absorption spectrometry

Stecker, die durch Teile des Körpers gestochen werden - Referenzprüfverfahren zur Bestimmung des Nickelgehalts durch Atomabsorptionsspektrometrie

Ensemble de perçage de parties du corps - Méthode d'essai de référence pour la détermination de la teneur en nickel par spectrométrie d'absorption atomique de flamme

<https://standards.iteh.ai/catalog/standards/sist/591460fd-8550-40dc-bed6-5e90d3469696/sist-en-1810-1998>

**Ta slovenski standard je istoveten z: EN 1810:1998**

---

**ICS:**

39.060

Nakit

Jewellery

**SIST EN 1810:1998**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 1810:1998

<https://standards.iteh.ai/catalog/standards/sist/591460fd-8550-40dc-bed6-5e90d3469696/sist-en-1810-1998>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

EN 1810

May 1998

ICS 39.060

Descriptors: precious metals, alloys, aluminium alloys, silver alloys, gold alloys, titanium alloys, copper alloys, steels, tests, determination, determination of content, nickel, atomic absorption spectrometry

English version

Body-piercing post assemblies - Reference test method for  
determination of nickel content by flame atomic absorption  
spectrometry

Ensembles de perçage de parties du corps - Méthode  
d'essai de référence pour la détermination de la teneur en  
nickel par spectrométrie d'absorption atomique de flamme

Stecker, die durch Teile des Körpers gestochen werden -  
Referenzprüfverfahren zur Bestimmung des Nickelgehalts  
durch Atomabsorptionsspektrometrie

This European Standard was approved by CEN on 10 April 1998.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

SIST EN 1810:1998

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

## Foreword

This European Standard has been prepared by Technical Committee CEN/TC 283 "Precious metals - Applications in jewellery and associated products", the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1998, and conflicting national standards shall be withdrawn at the latest by November 1998.

Annex A is informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 1810:1998

<https://standards.iteh.ai/catalog/standards/sist/591460fd-8550-40dc-bed6-5e90d3469696/sist-en-1810-1998>

## Introduction

This method is used to determine whether the nickel content in post assemblies which are inserted into pierced ears and other pierced parts of the human body during epithelization of the wound caused by piercing, whether subsequently removed or not, is equal to or less than 0,05 % (m/m).

## 1 Scope

This European Standard specifies a method for the determination of nickel in aluminium, titanium, copper, silver, gold and their alloys and in steels by flame atomic absorption spectrophotometry. The method is primarily suitable when the nickel content of a sample lies between 0,03 % and 0,07 % (m/m).

## 2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to, or revisions of, any of these publications apply to this standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

prEN 1811 Precious metals - Reference test method for release of nickel from products intended to come into direct and prolonged contact with the skin.

<https://standards.iteh.ai/catalog/standards/sist/591460fd-8550-40dc-bed6-5e90d3469696/sist-en-1810-1998>

## 3 Principle

A test portion is dissolved in an acid medium. The resulting solution is atomized into an air-acetylene flame of the atomic absorption spectrophotometer and the absorption of the resonance energy of nickel (232,0 nm) is compared with that of calibration solutions.

## 4 Reagents

All reagents shall be of recognized pro analysis, p.a., grade or better and shall be free of nickel.

NOTE: Only those reagents appropriate to the matrices under examination are required.

**WARNING: Concentrated acids are hazardous. Wear safety glasses or goggles and carry out dissolution of metals in a well-ventilated fume cupboard.**

**4.1 Deionized water**, specific conductivity, maximum 1  $\mu\text{S}/\text{cm}$ .

**4.2 Hydrochloric acid**, 38 % (m/m),  $\rho = 1,19 \text{ g/ml}$ .

**4.3 Dilute hydrochloric acid**, 20 % (m/m),  $\rho = 1,10 \text{ g/ml}$ .

Carefully add 125 ml of hydrochloric acid (see 4.2) to approximately 110 ml deionized water in a 500-ml beaker. Stir and cool to room temperature. Transfer the solution into a 250-ml volumetric flask and make up to volume with deionized water.

**4.4 Hydrogen peroxide solution, 30 % (m/m).**

**4.5 Hydrofluoric acid, 40 % (m/m),  $\rho = 1,13$  g/ml.**

**4.6 Nitric acid, 65 % (m/m),  $\rho = 1,40$  g/ml:**

**4.7 Dilute nitric acid, 33 % (m/m),  $\rho = 1,20$  g/ml.**

Carefully add 44 ml of nitric acid (see 4.6) to approximately 40 ml deionized water in a 250-ml beaker. Stir and cool to room temperature. Transfer the solution into a 100-ml volumetric flask and make up to volume with deionized water.

**4.8 Perchloric acid, 60 % (m/m),  $\rho = 1,54$  g/ml.**

**4.9 Aqua regia**

Cautiously mix 120 ml of hydrochloric acid (see 4.2) and 40 ml of nitric acid (see 4.6). This mixture shall be prepared immediately before use.

**4.10 Solution of hydrochloric acid and nitric acid**

Cautiously add 50 ml hydrochloric acid (see 4.2) to 40 ml of deionized water with stirring. Add 20 ml nitric acid (see 4.6) and mix well. Prepare this solution immediately before use.

**4.11 Solution of nitric acid and perchloric acid**

Cautiously mix 5 ml of nitric acid (see 4.6) and 40 ml of perchloric acid (see 4.8). Transfer the solution into a 50-ml volumetric flask and make up to volume with deionized water.

**4.12 Nickel stock solution,  $(1,0000 \pm 0,0002)$  g/l.**

Prepare nickel stock solution, for example, by using a certified standard solution ampoule.

**4.13 Aluminium matrix, 10 g/l stock solution.**

Weigh, to the nearest 0,001 g, 2,000 g of aluminium (containing less than 0,0005% nickel) and transfer to a 125-ml conical flask. Add, in small portions, 60 ml of dilute hydrochloric acid (see 4.3) and warm gently until complete dissolution. Add a few drops of hydrogen peroxide (see 4.4) and heat for about 2 min to remove excess hydrogen peroxide. Cool to room temperature, transfer the solution into a 200-ml volumetric flask and make up to volume with deionized water.

**4.14 Titanium matrix, 10 g/l stock solution.**

Weigh, to the nearest 0,001 g, 2,000 g of titanium (containing less than 0,000 5 % nickel) and transfer to a 125-ml conical flask. Add, in small portions, 60 ml of hydrofluoric acid (see 4.5) and warm gently until complete dissolution. Cool to room temperature, transfer the solution into a 200-ml volumetric flask and make up to volume with deionized water. Use laboratory apparatus appropriate for hydrofluoric acid, eg. polytetrafluoroethylene (PTFE).

**4.15 Copper matrix, 10 g/l stock solution.**

Weigh, to the nearest 0,001 g, 2,000 g of copper (containing less than 0,0005 % nickel) and transfer to a 125-ml conical flask. Add, in small portions, 40 ml of dilute hydrochloric acid (see 4.3) and 10 ml of hydrogen peroxide (see 4.4). Cool until the violent reaction has ceased. When completely dissolved, heat the solution to boiling and continue boiling for approximately 1 min to remove excess hydrogen peroxide, then cool to room temperature. Transfer the solution into a 200-ml volumetric flask and make up to volume with deionized water.

**4.16 Silver matrix, 10 g/l stock solution.**

Weigh, to the nearest 0,001 g, 2,000 g of silver (containing less than 0,0005 % nickel) and transfer to a 125-ml conical flask. Add 60 ml of dilute nitric acid (see 4.7) and warm gently until

complete dissolution. Heat, without boiling, until evolution of nitrogen oxide fumes ceases. Cool to room temperature, transfer the solution into a 200-ml volumetric flask and make up to volume with deionized water.

#### 4.17 Gold matrix, 10 g/l stock solution.

Weigh, to the nearest 0,001 g, 2,000 g of gold (containing less than 0,0005 % nickel) and transfer to a 125-ml conical flask. Add 80 ml aqua regia (see 4.9) and warm. Add aqua regia, as required, until complete dissolution. Note the amount of aqua regia used. Cool to room temperature, transfer the solution into a 200-ml volumetric flask and make up to volume with deionized water.

#### 4.18 Iron matrix, 10 g/l stock solution.

Weigh, to the nearest 0,001 g, 2,000 g of iron (containing less than 0,0005 % nickel) and transfer to a 125-ml conical flask. Add 50 ml of the hydrochloric acid - nitric acid solution (see 4.10) and warm until complete dissolution. Cool to room temperature and filter if necessary. Transfer the solution into a 200-ml volumetric flask and make up to volume with deionized water.

### 5 Apparatus

Normal laboratory equipment and:

#### 5.1 Balance, capable of weighing in grams to four decimal places.

**5.2 An atomic absorption spectrophotometer**, a nickel hollow-cathode lamp and supplies of air and acetylene (free from water, oil and nickel), sufficiently pure to give a steady clear flame. The apparatus shall, after optimization according to 6.5, meet the performance criteria given in 5.2.1 to 5.2.3. Additionally, it is recommended that the apparatus conforms to the performance criteria given in 5.2.4.

##### 5.2.1 Minimum precision

The standard deviation of 10 measurements of the absorbance of the most concentrated calibration solution (see 6.4) shall not exceed 1,0 % of the mean absorbance of the most concentrated calibration solution.

The standard deviation of 10 measurements of the absorbance of the least concentrated calibration solution (excluding the zero calibration solution) (see 6.4) shall not exceed 0,5 % of the mean absorbance of the most concentrated calibration solution.

##### 5.2.2 Characteristic concentration

The characteristic concentration for nickel in a matrix similar to the final test solution shall be no greater than 0,10 mg/l of nickel at 232,0 nm.

##### 5.2.3 Limit of detection

The limit of detection shall be considered as twice the standard deviation of 10 measurements of the absorbance of a solution containing nickel at a concentration level selected to give an absorbance just above that of the zero calibration solution.

The limit of detection of nickel in a matrix similar to the final test solution shall be better than 0,15 mg/l at 232,0 nm.

#### 5.2.4 Graph linearity

The slope of the calibration graph covering the top 20 % of the concentration range (expressed as a change in absorbance) should be not less than 0,7 times the value of the slope for the bottom 20 % of the concentration range.

In this standard the calibration graph is drawn at the lower part of the optimum working range, normally defined as 20 to 125 times the characteristic concentration.

NOTE: The performance criteria given in 5.2.1 to 5.2.4 are based on provisions given in ISO/CD 13204.

### 6. Procedure

#### 6.1 Detection of surface layers

Samples shall be subjected to the nickel release test according to prEN 1811 to detect nickel contamination on the surface, and abraded with an abrasive material to check visually for the presence of coatings. When checking for the presence of nickel on the surface, samples shall not be degreased prior to analysis.

NOTE: If coatings are suspected, X-ray analysis may assist recognition.

#### 6.2 Composition of sample

Identify the approximate composition of the sample by any appropriate means, for example, by X-ray fluorescence spectrometry (XRF) or other semi-quantitative method. This is necessary in order to classify the sample as an aluminium, titanium, copper, silver, gold or steel alloy.

#### 6.3 Sample preparation

SIST EN 1810:1998

<https://standards.iteh.ai/catalog/standards/sist/591460fd-8550-40dc-bed6-5e90d3469696/sist-en-1810-1998>

##### 6.3.1 Aluminium

Weigh, to the nearest 0,001 g, 0,125 g of the test sample and transfer to a 25-ml beaker. Add 5 ml of dilute hydrochloric acid (see 4.3) and warm gently until complete dissolution. Add two drops of hydrogen peroxide solution (see 4.4) and heat for about 2 min to remove excess hydrogen peroxide. Filter if necessary. Cool, transfer the solution to a 25-ml volumetric flask and make up to volume with deionized water.

##### 6.3.2 Titanium

Weigh, to the nearest 0,001 g, 0,125 g of the test sample and transfer to a 25-ml beaker. Add, in small portions, 5 ml of hydrofluoric acid (see 4.5) and warm gently until complete dissolution. Cool to room temperature, transfer the solution to a 25-ml volumetric flask and make up to volume with deionized water. Use laboratory apparatus appropriate for hydrofluoric acid, e.g. polytetrafluoroethylene (PTFE).

##### 6.3.3 Copper

Weigh, to the nearest 0,001 g, 0,125 g of the test sample and transfer to a 25-ml beaker. Add 3 ml of dilute hydrochloric acid (see 4.3) and 1 ml of hydrogen peroxide solution (see 4.4). Cool until the violent reaction has ceased. When the test portion is completely dissolved, heat the solution to boiling and continue boiling for approximately 1 min to remove excess hydrogen peroxide. Cool to room temperature, transfer the solution to a 25-ml volumetric flask and make up to volume with deionized water.

##### 6.3.4 Silver

Weigh, to the nearest 0,001 g, 0,125 g of the test sample and transfer to a 25-ml beaker. Add 5 ml of dilute nitric acid (see 4.7) and warm gently until complete dissolution. Heat, without



boiling, until evolution of nitrogen oxide fumes ceases. Cool to room temperature, transfer the solution to a 25-ml volumetric flask and make up to volume with deionized water.

### 6.3.5 Gold

Weigh, to the nearest 0,001 g, 0,125 g of the test sample and transfer to a 25-ml beaker. Add 5 ml aqua regia (see 4.9) and warm until complete dissolution. If more acid was used in order to prepare the gold matrix solution then add an appropriate proportion of the excess here. Cool to room temperature, transfer the solution to a 25-ml volumetric flask and make up to volume with deionized water.

### 6.3.6 Steels

Weigh, to the nearest 0,001 g, 0,125 g of the test sample and transfer to a 25-ml beaker. Add 3 ml of the hydrochloric acid-nitric acid solution (see 4.10) and warm until complete dissolution. If complete dissolution is not achieved, add 2 ml of the nitric acid-perchloric acid solution (see 4.11) and evaporate until dense white fumes of perchloric acid appear. Continue fuming for approximately 1 min at such a temperature as to maintain a steady reflux of white perchloric acid fumes on the walls of the beaker. Allow to cool, add 5 ml of water and heat gently to dissolve salts. Cool and filter if necessary. Transfer the solution to a 25-ml volumetric flask and make up to volume with deionized water.

## 6.4 Preparation of the calibration solutions

To a series of six 50-ml volumetric flasks transfer 0 µl (the zero calibration solution), 75 µl, 100 µl, 125 µl, 150 µl and 175 µl of the nickel stock solution (see 4.12) using a micro-pipette having an accuracy of  $\pm 1$  %. Then add to each flask a volume,  $V_r$ , of one or more of the matrix solutions (see 4.13 to 4.18), corresponding to the nature and proportion of the main element(s) of the test sample, given by the equation:

$$V_r = \frac{25 \times W}{100}$$

SIST EN 1810:1998  
<https://standards.iteh.ai/catalog/standards/sist/591460fd-8550-40dc-bed6-5e90d3469696/sist-en-1810-1998>

where:

$V_r$  is the volume of matrix solution, in millilitres;

$W$  is the approximate content of an element in the sample (see 6.2), expressed as a percentage by mass.

Make each flask up to volume with deionized water and mix.

The calibration solutions thus obtained contain 0, 1,5, 2,0, 2,5, 3,0 and 3,5 micrograms of nickel per millilitre (µg/ml).

NOTE: By extending the range of the calibration solutions to include those with nickel concentrations of 0,5 µg/ml and 1,0 µg/ml (obtained by diluting 25 µl and 50 µl of the nickel stock solution to 50 ml) this method can be used to determine nickel contents down to 0,01 % (m/m).

## 6.5 Optimization of the atomic absorption spectrometer settings

Follow the manufacturer's instructions for preparing the instrument for use.

Set the lamp current, the wavelength and gas flows. Light the burner and spray deionized water until the absorbance has stabilized.

Adjust the flame characteristics and the burner height for nickel determination according to the manufacturer's instructions, taking into account the actual matrix. Spraying alternately the calibration solution of highest concentration and the zero calibration solution, adjust the gas flow and burner position (horizontally, vertically and rotationally) until the difference in absorbance between the calibration solutions is at a maximum.

Check that the spectrometer is set accurately to the required wavelength, 232,0 nm.