

INTERNATIONAL STANDARD

**Optical fibre cables –
Part 2-50: Indoor cables – Family specification for simplex and duplex cables
for use in terminated cable assemblies**

Withhold

IEC 60794-2-50:2008

<https://standards.iteh.ai/standards/iec/388/3d4e-996c-430d-90bd-fd81862bd98c/iec-60794-2-50-2008>





THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2008 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch

Tel.: +41 22 919 02 11

Fax: +41 22 919 03 00

IEC 60794-2-50:2008

<https://standards.iec.org/standards/iec/382/384e-996c-430d-90bd-fd81862bd98c/iec-60794-2-50-2008>

INTERNATIONAL STANDARD

**Optical fibre cables –
Part 2-50: Indoor cables – Family specification for simplex and duplex cables
for use in terminated cable assemblies**

<https://standards.iteh.ai/standards/iec/38813d4e-996c-430d-90bd-fd81862bd98c/iec-60794-2-50-2008>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE



CONTENTS

FOREWORD.....	4
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	7
4 Construction.....	7
4.1 General.....	7
4.2 Optical fibres and primary coating	7
4.3 Buffer.....	7
4.4 Tube.....	8
4.5 Strength and anti-buckling members	8
4.6 Sheath	8
4.7 Sheath marking	8
4.8 Examples of cable constructions	8
5 Tests.....	8
5.1 Dimensions	9
5.2 Mechanical requirements.....	9
5.2.1 Tensile performance.....	9
5.2.2 Crush	9
5.2.3 Impact.....	10
5.2.4 Repeated bending.....	10
5.2.5 Bend.....	10
5.2.6 Torsion.....	11
5.2.7 Bend at low temperature.....	11
5.2.8 Kink.....	11
5.2.9 Sheath pull-off force.....	11
5.2.10 Buffered fibre movement in compression	12
5.3 Environmental requirements.....	12
5.3.1 Temperature cycling.....	12
5.3.2 Sheath shrinkage.....	12
5.4 Transmission requirements	13
5.5 Fire performance.....	13
Annex A (informative) Examples of some types of cable construction	14
Annex B (normative) METHOD E21 – Sheath pull-off force for optical fibre cable for use in patch cords	17
Annex C (normative) METHOD F11 – Sheath shrinkage for optical fibre cable for use in patchcords	22
Annex D (normative) METHOD E22 – Buffered fibre movement under compression in optical fibre cables for use in patchcords	24
Annex E (normative) METHOD F12 – Temperature cycling for optical fibre cable for use in patchcords	26
Annex F (normative) – Guidance on the selection of tests applicable to optical fibre cables for use in patchcords	28
Bibliography.....	31
Figure A.1 – Simplex loose non-buffered fibre cable	14
Figure A.2 – Simplex ruggedized fibre cable	14

Figure A.3 – Duplex loose non-buffered fibre cable.....	14
Figure A.4 – Duplex ruggedized fibre cable.....	15
Figure A.5 – Duplex ruggedized fibre zip cord.....	15
Figure A.6 – Duplex ruggedized flat cable.....	15
Figure A.7 – Duplex ruggedized round cable.....	16
Figure B.1 – Schematic of test arrangement	19
Figure B.2 – Example of pulling jig.....	20
Figure B.3 – Cable sample preparation	21
Figure D.1 – Test set up for fibre movement under compression.....	25
Table 1 – Dimensions of buffered fibres.....	8
Table 2 – Temperature cycling severities.....	12
Table F.1 – Cable test method summary.....	28
Table F.2 – Cable testing agreement	30

iTech Standards
(<https://standards.iteh.ai>)
Document Preview

IEC 60794-2-50:2008

<https://standards.iteh.ai/catalog/standards/iec/388d3d4e-996c-430d-90bd-fd81862bd98c/iec-60794-2-50-2008>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRE CABLES –

Part 2-50: Indoor cables – Family specification for simplex and duplex cables for use in terminated cable assemblies

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60794-2-50 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This standard cancels and replaces IEC/PAS 60794-2-50 published in 2004. This first edition constitutes a technical revision.

This standard is to be used in conjunction with IEC 60794-1-1, IEC 60794-1-2 and IEC 60794-2.

The text of this standard is based on the following documents:

FDIS	Report on voting
86A/1204/FDIS	86A/1223/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of IEC 60794 series, under the general title *Optical fibre cables*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication will be issued at a later date.

(<https://standards.iteh.ai>)
Document Preview

IEC 60794-2-50:2008

<https://standards.iteh.ai/cou/standards/iec/388d3d4e-996c-430d-90bd-fd81862bd98c/iec-60794-2-50-2008>

OPTICAL FIBRE CABLES –

Part 2-50: Indoor cables – Family specification for simplex and duplex cables for use in terminated cable assemblies

1 Scope

This part of IEC 60794 is a family specification that covers requirements for simplex and duplex optical fibre cables for use in terminated cable assemblies or for termination with optical fibre passive components.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

They complete the normative references already listed in the generic specification (IEC 60794-1-1 and IEC 60794-1-2) or in the sectional specification (IEC 60794-2 series).

IEC 60068-2-14, *Environmental testing – Part 2: Tests. Test N: Change of temperature*

IEC 60189-1, *Low-frequency cables and wires with PVC insulation and PVC sheath – Part 1: General test and measuring methods*

IEC 60793-1-1, *Optical fibres – Part 1-1: Measurement methods and test procedures – General and guidance*

IEC 60793-1-20, *Optical fibres – Part 1-20: Measurement methods and test procedures – Fibre geometry*

IEC 60793-1-21, *Optical fibres – Part 1-21: Measurement methods and test procedures – Coating geometry*

IEC 60793-1-40, *Optical fibres – Part 1-40: Measurement methods and test procedures – Attenuation*

IEC 60793-1-46, *Optical fibres – Part 1-46: Measurement methods and test procedures – Monitoring of changes in optical transmittance*

IEC 60793-2-10, *Optical fibres – Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres*

IEC 60793-2-50, *Optical fibres – Part 2-50: Product specifications – Sectional specification for class B single-mode fibres*

IEC 60794-1-1, *Optical fibre cables – Part 1-1: Generic specification – General*

IEC 60794-1-2, *Optical fibre cables – Part 1-2: Generic specification – Basic optical cable test procedures*

IEC 60794-2, *Optical fibre cables – Part 2: Indoor cables – Sectional specification*

IEC 60811-1-3, *Common test methods for insulating and sheathing materials of electric and optical cables – Part 1-3: General application – Methods for determining the density – Water absorption tests – Shrinkage test*

IEC 60811-1-4, *Common test methods for insulating and sheathing materials of electric cables – Part 1: Methods for general application – Section Four: Tests at low temperature*

ISO/IEC 11801, *Information technology – Generic cabling for customer premises*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

terminated cable assembly

short length of cable provisioned with a connector at both ends

NOTE Examples from ISO/IEC 11801 are:

Patchcords are used to establish connections on a patch panel. Typical length of the patchcord 1m to 10 m.

Work area cords are used to connect outlet to the terminal equipment. Typical length of the work area cords according to this specification is between 1m and 35 m.

Equipment cords should fulfill the requirements of patchcords or work area cords depending on their application.

4 Construction

4.1 General

In addition to the constructional requirements in IEC 60794-2, the following considerations apply to simplex and duplex indoor cables for use in terminated cable assemblies.

It is not the intention of this standard to specify the finished terminated cable assembly complete with terminations.

The cable shall be designed and manufactured for an expected operating lifetime of 15 years. The materials in the cable shall not present a health hazard within its intended use.

There shall be no fibre splice in a delivery length. It shall be possible to identify each individual fibre throughout the length of the cable.

4.2 Optical fibres and primary coating

Multimode or single-mode optical fibres meeting the requirements of IEC 60793-2-10, type A1a and A1b, and IEC 60793-2-50, type B, shall be used.

4.3 Buffer

If a tight or semi-tight (loosely applied) buffer is required, it shall consist of one or more layers of inert material. Semi-tight tubes may be filled. Unless otherwise specified, the buffer shall be removable in one operation over a length of 15 mm.

Buffer dimensions are shown in Table 1.

Table 1 – Dimensions of buffered fibres

Nominal diameter (mm)	0,3 – 1,3
Tolerances (mm)	± 0,05

4.4 Tube

One or two primary coated or buffered fibres are packaged (loosely or not) in a tube construction which may be filled. The tube may be reinforced with a composite wall.

If required the suitability of the tube shall be determined by an evaluation of its kink resistance in accordance with IEC 60794-1-2, Method G7.

4.5 Strength and anti-buckling members

The cable shall be designed with sufficient strength members to meet the requirements of this standard.

The strength and/or anti-buckling member may be either metallic or non-metallic and may be located in the cable core and/or under the sheath and/or in the sheath.

4.6 Sheath

The cable shall have a uniform overall protective sheath. The cable diameter shall be specified in the relevant detail specification (or product specification). Sheath removal is an important feature of these cables. This is tested by the method E21 described in Annex B of this standard.

4.7 Sheath marking

If required, the cable shall be marked as agreed between the customer and supplier. The marking shall be resistant to abrasion.

4.8 Examples of cable constructions

Examples of some main types of cable construction are shown in Figures A.1 to A.7.

Other configurations are not excluded if they meet the mechanical, environmental, transmission and termination requirements given in this standard.

5 Tests

Compliance with the specification requirements shall be verified by carrying out tests selected from the following subclauses. It is not intended that all tests be carried out in all cases, and Annex F provides guidance on the selection of tests. The tests to be applied and the frequency of testing shall be agreed between the customer and supplier.

Some of the following tests can be performed on a short sample length of cable which is still an integral part of a longer length, thus making it possible to detect permanent changes in attenuation.

Single-mode cables shall be measured at 1 550 nm and 1 625 nm and multimode¹ cables shall be measured at 1 300 nm unless otherwise agreed. Measurements shall be carried out according to IEC 60793-1-40.

If loops are used within a test to fix the ends of a cable, the diameter shall not be so small as to cause excessive mode filtering in multimode fibre.

Unless otherwise specified, all tests shall be carried out at ambient temperature, as described in IEC 60793-1-1, Clause 5.

5.1 Dimensions

The fibre dimensions and tolerances shall be checked in accordance with test method of IEC 60793-1-20 or IEC 60793-1-21. The diameter of the buffer and of the cable, as well as the thickness of the sheath, shall be measured in accordance with the methods of IEC 60189-1.

5.2 Mechanical requirements

5.2.1 Tensile performance

Method: IEC 60794-1-2-E1A.

Diameter of chuck drums and transfer devices: not less than the minimum dynamic bending diameter specified for the cable, at least 250 mm diameter.

Rate of transfer device: either 100 mm/min or 100 N/min.

Load: 100 N applied for 5 min for simplex cables, 200 N for 5 min for duplex cables.

Length of sample: sufficient to achieve the desired accuracy of measurement of attenuation change and shall be agreed between the customer and the supplier.

Requirements: the maximum increase in attenuation during the test shall be specified in the product specification, there shall be no change in attenuation after the test, and there shall be no damage to the cable elements.

5.2.2 Crush

Method: IEC 60794-1-2-E3.

Force: 500 N.

Duration: 1 min.

Length between test locations: 500 mm.

Requirements: the maximum increase in attenuation during the test shall be specified in the product specification, there shall be no change in attenuation after the test, and there shall be no damage to the cable elements.

NOTE For cables having a non-circular cross section, the force should be applied in the direction of the minor axis (perpendicular to the major axis).

¹ OM3 multimode cables should be tested at 850 nm and may be tested at 1300 nm in addition, all other multimode cables should be tested at 1300 nm.