



Standard Test Method for Photopic Luminance of Photoluminescent (Phosphorescent) Markings¹

This standard is issued under the fixed designation E 2073; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a procedure for determining the photopic luminance of photoluminescent (phosphorescent) markings. It does not cover scotopic or mesopic measurements.

1.2 When reference is made regarding photoluminescence in the text of this test method, it implies phosphorescence.

1.3 The values stated in SI units are the standard. The values given in parentheses are provided for information purposes only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

E 284 Terminology of Appearance²

E 1316 Terminology for Non-Destructive Examinations³

E 2072 Specification for Photoluminescent (Phosphorescent) Safety Markings²

2.2 Other Standards:

Publication CIE No. 69 (1987)⁴

3. Terminology

3.1 Definitions of terms in Terminology E 284 and Terminology E 1316 are applicable to this specification.

4. Significance and Use

4.1 To assess how photoluminescent markings perform under identical test conditions, the luminance shall be measured in accordance with this test method (see Specification E 2072).

5. Apparatus

5.1 *Illuminance Meter*—To measure the illumination of the activating light source on the surface of the photoluminescent

marking, use an illuminance meter calibrated to measure illuminance in lux (fc), with the following features: spectral error, f_1' , $\leq 5\%$; UV response, u , $\leq 0.5\%$; resolution 1.0 lux; and linearity error, f_3 , $\leq 0.5\%$ (see Public. CIE No. 69).

5.2 *Luminance Meter*—To measure the photopic luminance of photoluminescent markings, use a luminance meter with the following minimum features (see Publication CIE No. 69): spectral error, f_1' , $\leq 5\%$; UV response, u , $\leq 0.5\%$; resolution at least 0.1 mcd/m²; linearity error, f_3 , $\leq 0.5\%$; signal-to-noise-ratio: at least 10:1 for all measurements. The instrument shall have been calibrated within the preceding 12 months using photometric standards traceable to a national standards institute.

6. Sampling, Test Specimens and Test Units

6.1 *Method of Sampling*—Take a minimum of three samples. Each sample shall be of a minimum size of at least 45 mm (1¾ in.) in diameter. Select samples at random. If a manufacturer, samples shall be representative of the production lot, coded and identified to correspond to production batch codes, and shall be numbered consecutively. Paints shall be applied in compliance with the manufacturer's application instructions.

7. Conditioning

7.1 Precondition all test specimens by placing them in complete darkness for 48 h and remove them immediately before performing the tests. No ambient or stray light shall be present.

8. Procedure

8.1 *Ambient Conditions*—The ambient temperature during darkness preconditioning of specimens, activation and luminance testing shall be $25 \pm 3^\circ\text{C}$ ($77 \pm 5^\circ\text{F}$). The relative humidity shall not exceed 60%. All luminance testing shall be performed in a room whose ambient light level is such that the luminance of a white diffuse reflectance standard is at least one decade lower than the lowest test specimen luminance measurement to be recorded.

8.2 *Preparation of Apparatus*—The luminance meter shall be zeroed prior to every measurement, then checked immediately after the measurement and the measurement shall be rejected if the zero drifted by more than 5% of the measured value. The distance between the luminance meter and the

¹ This test method is under the jurisdiction of ASTM Committee E 12 on Color and Appearance, and is the direct responsibility of Subcommittee E12.13 on Photoluminescent Safety Markings.

Current edition approved Feb. 10, 2000. Published April 2000.

² *Annual Book of ASTM Standards*, Vol 06.01.

³ *Annual Book of ASTM Standards*, Vol 03.03.

⁴ Available from the CIE-USNC Publications Office, c/o TLA Lighting Consultants, 7 Pond St., Salem, MA 01970.

ASTM-E2073

ADOPTION NOTICE

ASTM-E2073, "Test Method For Photopic Luminance of Photoluminescent (Phosphorescent) Markings", was adopted on 16-OCT-00 for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Commander, Defense Supply Center Philadelphia, ATTN: DSCP-IFA, 700 Robbins Avenue, Philadelphia, PA 19111-5096. Copies of this document may be purchased from the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959. <http://www.astm.org/>

ASTM-E2073 should be used instead of MIL-L-3891B, which was cancelled on October 16, 2000.

Custodians:

Army - AV
Navy - OS
Air Force - 99
DLA - IS

Adopting Activities:

DLA - IS
(Project 9390-0003)

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ASTM E2073-00](#)

<https://standards.iteh.ai/catalog/standards/sist/4fd5e02-80b4-44fb-818a-8932d5e0233f/astm-e2073-00>

FSC 9390

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.