



SLOVENSKI STANDARD

SIST ISO 7530-1:1996

01-avgust-1996

Nikljeve zlitine - Plamenska atomska absorpcijska spektrometrična analiza - 1. del: Splošne zahteve in raztapljanje vzorca

Nickel alloys -- Flame atomic absorption spectrometric analysis -- Part 1: General requirements and sample dissolution

iTeh STANDARD PREVIEW

Alliages de nickel -- Analyse par spectrométrie d'absorption atomique dans la flamme --
Partie 1: Caractéristiques générales et mise en solution de l'échantillon

[SIST ISO 7530-1:1996](https://standards.iteh.ai/catalog/standards/sist/c4ac837a-7304-4e3b-b12e-20120ccc6665/sist-iso-7530-1-1996)

Ta slovenski standard je istoveten z: **ISO 7530-1:1990**

ICS:

| | | |
|-----------|-------------------------------|-----------------------------------|
| 77.120.40 | Nikelj, krom in njune zlitine | Nickel, chromium and their alloys |
|-----------|-------------------------------|-----------------------------------|

SIST ISO 7530-1:1996

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 7530-1:1996](#)

<https://standards.iteh.ai/catalog/standards/sist/c4ac837a-7304-4e3b-b12e-26f20cebe665/sist-iso-7530-1-1996>

INTERNATIONAL STANDARD

ISO
7530-1

First edition
1990-12-15

Corrected and reprinted
1992-02-15

Nickel alloys — Flame atomic absorption spectrometric analysis —

Part 1:

**General requirements and sample dissolution
(standards.iteh.ai)**

*Alliages de nickel — Analyse par spectrométrie d'absorption atomique
dans la flamme —
Partie 1: Caractéristiques générales et mise en solution de l'échantillon*



Reference number
ISO 7530-1:1990(E)

ISO 7530-1:1990(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 7530-1 was prepared by Technical Committee ISO/TC 155, *Nickel and nickel alloys*, Sub-Committee SC 4, *Analysis of nickel alloys*.

ISO 7530 consists of the following parts, under the general title *Nickel alloys — Flame atomic absorption spectrometric analysis*:

- Part 1: *General requirements and sample dissolution*
- Part 2: *Determination of cobalt content*
- Part 3: *Determination of chromium content*
- Part 4: *Determination of copper content*
- Part 5: *Determination of iron content*
- Part 6: *Determination of manganese content*
- Part 7: *Determination of aluminium content*
- Part 8: *Determination of silicon content*
- Part 9: *Determination of vanadium content*

Annex A forms an integral part of this part of ISO 7530. Annex B is for information only.

© ISO 1990

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Introduction

This part of ISO 7530 is to be used in conjunction with the other parts which specify methods for the determination of individual elements in nickel alloys by flame atomic absorption spectrometry.

Although the analytical methods are specified in independent International Standards, it is possible to determine more than one element on a single test solution by adjustment of the sample weight and initial and subsequent dilutions.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 7530-1:1996](https://standards.iteh.ai/catalog/standards/sist/c4ac837a-7304-4e3b-b12e-26f20cebe665/sist-iso-7530-1-1996)

<https://standards.iteh.ai/catalog/standards/sist/c4ac837a-7304-4e3b-b12e-26f20cebe665/sist-iso-7530-1-1996>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

This page intentionally left blank

[SIST ISO 7530-1:1996](#)

<https://standards.iteh.ai/catalog/standards/sist/c4ac837a-7304-4e3b-b12e-26f20cebe665/sist-iso-7530-1-1996>

Nickel alloys — Flame atomic absorption spectrometric analysis —

Part 1:

General requirements and sample dissolution

WARNING — The manufacturer's recommendations should be closely followed and particular attention is drawn to the following safety points:

- a) the explosive nature of acetylene, and regulations concerning its use,
- b) the need to shield the eyes of the operator from ultraviolet radiation by means of tinted glass,
- c) the need to keep the burner head clear of deposits because a badly clogged burner may cause a flashback,
- d) the need to ensure that the liquid trap is filled with water,
- e) always spray distilled water between the test solutions, blank solution and/or calibration solutions.

1 Scope

1.1 ISO 7530 specifies flame atomic absorption methods for the determination of up to 4 % (*m/m*) of cobalt, chromium, copper, iron, manganese and aluminium, up to 2 % (*m/m*) of silicon and from 0,05 % (*m/m*) to 1 % (*m/m*) of vanadium in nickel alloys. Other elements may be added in subsequent parts of ISO 7530. Typical compositions of some nickel alloys are given in annex B.

1.2 This part of ISO 7530 specifies the general requirements for analysis by flame atomic absorption, preparation and dissolution of the test sample, method of calculation and the procedures used for

the evaluation of the repeatability and reproducibility of the individual methods specified in the other parts of ISO 7530.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 7530. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 7530 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 7530-1:1990(E)

ISO 385-1:1984, *Laboratory glassware — Burettes — Part 1: General requirements.*

ISO 648:1977, *Laboratory glassware — One-mark pipettes.*

ISO 1042:1983, *Laboratory glassware — One-mark volumetric flasks.*

ISO 5725:1986, *Precision of test methods — Determination of repeatability and reproducibility for a standard test method by inter-laboratory tests.*

3 Principle

Dissolution of a test portion in acid, evaporation of excess acid and redissolution of the salts.

Addition of an ionization suppressant, if necessary, and dilution of the solution to a known volume.

Aspiration of the test solution, after a secondary dilution, if necessary, into the air-acetylene or nitrous oxide-acetylene flame of an atomic absorption spectrometer.

Measurement of the absorption of the resonance line energy from the spectrum of the element being determined and comparison with that of calibration solutions of the same element.

4 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

4.1 High purity metals, 99,9 % (*m/m*) minimum, as specified in the relevant part of ISO 7530.

4.2 Nitric acid, (HNO_3), $\rho_{20} = 1,41$ g/ml.

4.3 Nitric acid, (HNO_3), $\rho_{20} = 1,41$ g/ml diluted (1 + 1).

4.4 Hydrochloric acid, (HCl), $\rho_{20} = 1,18$ g/ml.

4.5 Hydrochloric acid, (HCl), $\rho_{20} = 1,18$ g/ml diluted (1 + 1).

4.6 Nitric acid-hydrochloric acid mixture.

CAUTION — This acid mixture is highly corrosive and unstable. Noxious gas (chlorine) is liberated on standing. It shall be prepared and used in a fume cupboard and shall not be kept in a closed container.

Carefully mix 1 part of nitric acid (4.2) and 3 parts of hydrochloric acid (4.4). This mixture is not stable and should be prepared only as needed.

4.7 Standard reference solutions, 1,000 g/l of metal.

Prepare separately for each metal as specified in the appropriate part of ISO 7530.

5 Apparatus

Ordinary laboratory apparatus, and

5.1 Atomic absorption spectrometer

5.1.1 The atomic absorption spectrometer used in this method shall meet the instrument performance parameters given in annex A.

5.1.2 The instrument shall be equipped with burner heads suitable for both an air-acetylene and a nitrous oxide-acetylene flame.

5.1.3 The instrument should be capable of using single element hollow cathode or electrodeless discharge lamps operated at currents recommended by the manufacturer.

5.2 Volumetric glassware

5.2.1 Burettes, of capacity 50 ml, graduated in divisions of 0,1 ml in accordance with ISO 385-1, class A.

5.2.2 Pipettes, in accordance with ISO 648, class A.

5.2.3 Volumetric flasks, in accordance with ISO 1042, class A.

6 Sampling and sample preparation

6.1 Sampling and preparation of the laboratory sample shall be carried out by normal agreed procedures or, in case of dispute, by the relevant International Standard.

6.2 The laboratory sample normally is in the form of millings or drillings and no further preparation of the sample is necessary.

6.3 If it is suspected that the laboratory sample is contaminated with oil or grease from the milling or drilling process, it shall be cleaned by washing with high purity acetone and drying in air.

6.4 If the laboratory sample contains particles or pieces of widely varying sizes, the test sample should be obtained by riffing.

7 Procedure

7.1 Preparation of test solution — General method

7.1.1 Weigh, to the nearest 0,001 g, 1,00 g of the laboratory sample and transfer to a clean unetched 600 ml beaker. Add 20 ml of the nitric acid-hydrochloric acid mixture (4.6). Apply sufficient heat to initiate and maintain the reaction until dissolution is complete. If the alloy resists dissolution, some adjustment of the acid mixture may be required. Add hydrochloric acid (4.4) in 1 ml increments and continue heating to dissolve the sample.

7.1.2 Using a low heat, evaporate the solution just to dryness. Do not bake. Cool to about 50 °C, add 25 ml of hydrochloric acid (4.4) and again evaporate just to dryness. Add a further 25 ml of hydrochloric acid and repeat the evaporation.

7.1.3 Cool to about 50 °C, add 5 ml of hydrochloric acid (4.4) and 20 ml of water and heat to dissolve the salts.

7.1.4 Proceed as directed in the relevant part of ISO 7530.

NOTES

1 Some alloys having a high copper content may be dissolved in nitric acid diluted 1 + 1. For some alloys an acid mixture containing 30 ml hydrochloric acid and 2 ml of nitric acid is more effective.

2 The general method of dissolution may be modified as specified in other parts of ISO 7530.

3 If sample inhomogeneity is suspected, a larger mass of sample (10 g to 50 g) may be taken for analysis. However, an aliquot portion corresponding to a 1 g sample shall be taken from such a solution and processed in accordance with the procedure given.

7.2 Blank test

Carry out a blank test in parallel with the determination, following the same procedure and using the same quantities of all the reagents.

7.3 Preparation of calibration solutions

Proceed as directed in the relevant part of ISO 7530.

7.4 Calibration and determination

7.4.1 Atomic absorption measurements

7.4.1.1 The spectral lines for each element to be used in the analysis are specified in the relevant part of ISO 7530.

7.4.1.2 Set the required instrument parameters according to the manufacturer's recommendations. Light the burner and aspirate water until thermal equilibrium is reached. The flame conditions will vary according to the element being determined. Zero the instrument.

7.4.1.3 Ensure that the instrument meets the performance requirements given in annex A. Optimum settings for the operating parameters vary from instrument to instrument. Scale expansion may have to be used to obtain the required readability.

7.4.1.4 Ensure that the calibration solutions and the test solution(s) are within 1 °C of the same temperature.

7.4.1.5 Aspirate water and zero the instrument.

7.4.1.6 Aspirate the calibration solutions and the test solution(s) and note the reading to determine the approximate concentration of the test solutions.

7.4.1.7 Aspirate water until the initial reading is obtained. Zero the instrument if necessary.

7.4.1.8 Aspirate the calibration solutions and the test solution(s) in the order of increasing instrument response, starting with the zero member solution. When a stable response is obtained, record the reading. Flush the system by aspirating water between each test or calibration solution.

7.4.1.9 Repeat the measurement of the full set of the calibration and test solutions twice more and record the data.

7.4.2 Preparation of calibration graphs

Plot the average instrument reading against the concentration of the analyte in the calibration solutions for each set of measurements. Proceed with the calculations as directed in clause 8.

NOTE 4 Some instruments may be adjusted to give a read-out directly in concentration of the analyte. A graph of instrument response versus concentration should be plotted to check the validity of the readings.

7.5 Number of determinations

Carry out the determination at least in duplicate.

8 Expression of results

8.1 Calculation

8.1.1 Determine the concentration of the analyte in the test solution from the corresponding calibration graphs for each of the three sets of instrument readings recorded.