INTERNATIONAL STANDARD NORME INTERNATIONALE

IEC CEI 61138

Third edition Troisième édition 2007-07

Cables for portable earthing and short-circuiting equipment

Câbles d'équipements portables de mise à la terre et de court-circuit

<u>IEC 61138:2007</u> https://standards.iteh.ai/catalog/standards/sist/84e6f4a7-c8e5-4cca-b9a5dc11986a5199/iec-61138-2007



Reference number Numéro de référence IEC/CEI 61138:2007



THIS PUBLICATION IS COPYRIGHT PROTECTED Copyright © 2007 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office 3, rue de Varembé CH-1211 Geneva 20 Switzerland Email: inmail@iec.ch Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publicationisTeh STANDARD PREVIEW

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

IEC Just Published: www.ec.ch/ohine_ice/statlog/standards/sist/84e6f4a7-c8e5-4cca-b9a5-

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch Tel.: +41 22 919 02 11 Fax: +41 22 919 03 00

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Catalogue des publications de la CEI: www.iec.ch/searchpub/cur_fut-f.htm

Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,...). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.

Just Published CEI: www.iec.ch/online_news/justpub

Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.

Service Clients: www.iec.ch/webstore/custserv/custserv_entry-f.htm

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:

Email: csc@iec.ch Tél.: +41 22 919 02 11 Fax: +41 22 919 03 00

INTERNATIONAL STANDARD NORME INTERNATIONALE

IEC CEI 61138

Third edition Troisième édition 2007-07

Cables for portable earthing and short-circuiting equipment

Câbles d'équipements portables de mise à la terre et de court-circuit

<u>IEC 61138:2007</u> https://standards.iteh.ai/catalog/standards/sist/84e6f4a7-c8e5-4cca-b9a5dc11986a5199/iec-61138-2007



Commission Electrotechnique Internationale International Electrotechnical Commission Международная Электротехническая Комиссия



For price, see current catalogue Pour prix, voir catalogue en vigueur

Т

CONTENTS

FO	REWO	ORD		4	
1	Scop	e		6	
2	Normative references				
3	Terms and definitions			7	
4	Gene	General requirements for the construction of cables			
•	1 1				
	4.1		Material	۰۵ و	
		4.1.1		۰۵ و	
		4.1.2	Check of construction	۰ و	
		4.1.5	Electrical resistance	۰۵ و	
	1 2	4.1.4 Sonar	Electrical resistance	0	
	4.2				
	4.5	1 2 1	Matorial	0	
		4.3.1	Material	0	
		4.3.2	Application to the conductor	9 Q	
		4.3.3		9	
		4.3.4	Machine Information before bedieflanding U.D.V.	9	
	1 1	4.3.5 Markin		9 0	
	4.4		Indication of distandards itch.ai)	9 0	
		4.4.1	Indication of odd designation and cross sectional area of the	9	
		4.4.2	conductor	9	
		4.4.3	Coministry or state as a constant of the second state of the secon	10	
		4.4.4	dc11986a5199/iec-61138-2007	10	
		4.4.5	Legibility	10	
5	Tests on completed cables				
	51	Electri	cal properties	10	
	0.1	5 1 1	General	10	
		512	Voltage test	10	
		513	Spark test	10	
	52	Overal	l diameter	10	
	5.3	Flexibi	lity test	11	
	0.0	531	General	11	
		532	Test for cables with conner conductors	11	
		533	Test for cables with aluminium conductors	12	
	54	Ontion	al clashing test	13	
6	Parti	cular sn	pecifications	13	
Ũ					
	6.2 Code designation		al	13	
	6.3 Rated voltage				
	0.J	Construction			
	0.4		Conductors	13 12	
		0.4.1 6 4 2		10	
		0.4.Z	Averall diameter	13	
	6 5	U.4.3 Tooto		14 1 /	
7	Guid	e to the	use of the cables	14 1/	
	Juiu				

61138 © IEC:2007 – 3	-
Annex A (normative) Clashing test	
Figure 1 – Flexing apparatus	
Figure A.1 – Impact test apparatus (vertical imp	act)24
Table 1 – Requirement for test voltages	11
Table 2 – Requirements for the static flexibility	est12
Table 3 – General data for Types 61138 IEC 60	110, 60150, 60155, 6016515
Table 4 – General data for Types 61138 IEC 60	210, 60250, 60255 and 6026515
Table 5 – Tests for Types 61138 IEC 60110 and	60210 (EPR insulation)16
Table 6 – Tests for Types 61138 IEC 60150, 60 insulation)	155, 60250 and 60255 (PVC
Table 7 – Requirements for the non-electrical te	sts for PVC/ST 11 insulation18
Table 8 – Tests for types 61138 IEC 60165 and	60265 (SiR insulation)20
Table 9 – Requirements for the non-electrical te	sts for SiR insulation21
Table A.1 – Height of fall	

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>IEC 61138:2007</u> https://standards.iteh.ai/catalog/standards/sist/84e6f4a7-c8e5-4cca-b9a5dc11986a5199/iec-61138-2007

INTERNATIONAL ELECTROTECHNICAL COMMISSION

CABLES FOR PORTABLE EARTHING AND SHORT-CIRCUITING EQUIPMENT

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication est-4cca-b9a5-
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61138 has been prepared by IEC technical committee 20: Electric cables.

This third edition cancels and replaces the second edition published in 1994 and constitutes a technical revision.

The significant technical changes with respect to the previous edition are as follows:

- extension of the scope to cover silicone rubber as an insulation material;
- introduction of a new normative annex for clashing test.

The text of this standard is based on the following documents:

FDIS	Report on voting
20/881/FDIS	20/898/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>IEC 61138:2007</u> https://standards.iteh.ai/catalog/standards/sist/84e6f4a7-c8e5-4cca-b9a5dc11986a5199/iec-61138-2007

CABLES FOR PORTABLE EARTHING AND SHORT-CIRCUITING EQUIPMENT

1 Scope

This International Standard applies to flexible cables with insulation based on ethylene propylene rubber (EPR), polyvinyl chloride (PVC) or silicone rubber (SiR) for portable earthing and short-circuiting equipment.

For this type of cable no rated voltage is given as such cables are exclusively intended for earthing and short-circuiting equipment.

The particular types of cable and their code designations are specified in Clause 6 of this standard.

The test methods specified in this standard are given in IEC 60227-2, IEC 60245-2, IEC 60811 and IEC 62230.

NOTE In addition to the requirements given in this standard, mechanical requirements and requirements for the marking for the complete equipment should be taken into account. These requirements can be found in IEC 61230.

2 Normative references (standards.iteh.ai)

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE One or more references to the standard below are in respect of a specific subdivision of that standard, for instance a clause, a table, a class or a type. Cross-references to these standards are undated and, at all times, the latest version should be applied.

IEC 60227-1, Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V – Part 1: General requirements

IEC 60227-2, Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V – Part 2: Test methods

IEC 60228, Conductors of insulated cables

IEC 60245-2, Rubber insulated cables of rated voltages up to and including 450/750 V - Part 2: Test methods

IEC 60502-1, Extruded solid dielectric insulated power cables for rated voltages from 1 kV up to 30 kV

IEC 60811-1-1, Common test methods for insulating and sheathing materials of electric and optical cables – Part 1-1: Methods for general application – Measurement of thickness and overall dimensions – Tests for determining the mechanical properties

IEC 60811-1-2, Common test methods for insulating and sheathing materials of electric and optical cables – Part 1-2: Methods for general application – Thermal ageing methods

IEC 60811-1-3, Common test methods for insulating and sheathing materials of electric and

61138 © IEC:2007

optical cables – Part 1-3: Methods for general application – Methods for determining the density – Water absorption tests – Shrinkage test

IEC 60811-1-4, Common test methods for insulating and sheathing materials of electric and optical cables – Part 1-4: Methods for general application – Tests at low temperature

IEC 60811-2-1, Common test methods for insulating and sheathing materials of electric and optical cables – Part 2-1: Methods specific to elastomeric compounds – Ozone resistance, hot set and mineral oil immersion tests

IEC 60811-3-1, Common test methods for insulating and sheathing materials of electric and optical cables – Part 3-1: Methods specific to PVC compounds – Pressure test at high temperature – Tests for resistance to cracking

IEC 60811-3-2, Common test methods for insulating and sheathing materials of electric and optical cables – Part 3-2: Methods specific to PVC compounds – Loss of mass test – Thermal stability test

IEC 61230, Live working – Portable equipment for earthing or earthing and short-circuiting

IEC 62230, Electrical cables – Spark-test method

Terms and definitions STANDARD PREVIEW 3

For the purposes of this document, the following definitions apply.

3.1

IEC 61138:2007 type tests https://standards.iteh.ai/catalog/standards/sist/84e6f4a7-c8e5-4cca-b9a5symbol T

tests required to be made before supplying a type of cable covered by this standard on a general commercial basis in order to demonstrate satisfactory performance characteristics to meet the intended application

NOTE These tests are of such a nature that, after they have been made, they need not be repeated unless changes are made in the cable materials, design or type of manufacturing process which might change the performance characteristics.

3.2 sample tests symbol S

tests made on samples of completed cable, or components taken from a completed cable, adequate to verify that the finished product meets the design specifications

3.3 routine tests symbol R tests made on all production cable lengths to demonstrate their integrity

4 General requirements for the construction of cables

4.1 Conductors

4.1.1 Material

The conductor shall consist of annealed copper, aluminium or aluminium alloy in accordance with IEC 60228. The wires of copper conductors may be plain or tinned. Tinned wires shall be covered with an effective layer of tin.

4.1.2 Construction

The maximum diameter of the conductor wires is specified in Table 3 and Table 4.

4.1.3 Check of construction

Compliance with the requirements of 4.1.1 and 4.1.2 shall be checked by visual inspection and by measurement.

4.1.4 Electrical resistance

The d.c. resistance of copper conductors at 20 °C is specified in IEC 60228 Class 6.

The d.c. resistance of aluminium conductors at 20 °C is specified in Table 4 of this standard.

The test shall be carried out in accordance with IEC 60228, Annex A.

The current density shall not exceed 1 A/mm² to₈ayoid any significant increase of temperature during the test. https://standards.iteh.ai/catalog/standards/sist/84e6f4a7-c8e5-4cca-b9a5-

dc11986a5199/iec-61138-2007

4.2 Separator between conductor and insulation

A separating tape made of suitable material may be placed between the conductor and the insulation.

4.3 Insulation

4.3.1 Material

The insulation shall be one of the following types specified for each type of cable in Clause 6:

- an elastomeric insulation compound based on a cross-linked ethylene propylene rubber (EPR) or similar (EPM or EPDM);
- a general purpose thermoplastic insulation compound based on polyvinylchloride (PVC);
- a cold-resistant thermoplastic insulation compound based on polyvinylchloride (PVC);
- a cross-linked silicone rubber insulation compound (SiR).

For the requirements of these compounds, see 4.3.5.

The temperature limits for cables insulated by the above compounds are given in Clause 7.

4.3.2 Colour of insulation

There is no preferred colour for the insulation. The colour of the insulation shall be achieved by the use of coloured compounds or other suitable method.

The insulation, whether coloured or not, may be transparent.

4.3.3 Application to the conductor

The insulation shall be closely applied to the conductor or separator. It shall be possible to remove the insulation without damage to the insulation itself, to the conductor, or to the tin coating if any. Compliance shall be checked by inspection and by manual test.

4.3.4 Thickness

The mean value of the thickness of the insulation shall be not less than the specified value in Table 3 and Table 4.

However, the thickness at any place may be less than the specified value, provided that the difference does not exceed 0,1 mm + 15 % of the specified value. Compliance shall be checked by the test given in 1.9 of IEC 60227-2 or IEC 60245-2.

4.3.5 Mechanical properties before and after ageing

The insulation shall have adequate mechanical strength and elasticity within the temperature limits to which it may be exposed in normal use (standards.iteh.ai)

Compliance shall be checked by carrying out the tests specified for each type of insulation in: IEC 61138:2007

- IEC 60502-1, Table/<u>15</u> for ERR on similar; din addition, cables covered by this type of compound shall be subjected to a pold bending on elongation test at -50 °C;
- IEC 60227-1, Table 2 (PVC/ST 5) as a general purpose compound;
- Table 7 of this standard for PVC/ST 11 as a cold-resistant compound;
- Table 9 of this standard for cross-linked silicone rubber compound.

The applicable test methods and the results to be obtained for each type of insulation are also specified in the above-mentioned tables.

4.4 Marking

4.4.1 Indication of origin

Cables shall be provided with an indication of origin consisting of either

- the manufacturer's identification thread; or
- the continuous marking of the manufacturer's name or trade mark, by printing, or by indenting or embossing on the insulation.

4.4.2 Indication of code designation and cross-sectional area of the conductor

Cables shall be provided with an indication of the code designation according to 6.2 and the cross-sectional area of the conductor ".... mm^{2} ". (See Table 3 and Table 4).

This shall be made by printing or by indenting or embossing on the insulation.

4.4.3 Continuity of marks

The distance between the end of one complete set of marks and the beginning of the next shall not exceed 550 mm.

- 10 -

4.4.4 Durability

Printed markings shall be durable. Compliance with this requirement shall be checked by the test given in 1.8 of IEC 60227-2 or IEC 60245-2.

4.4.5 Legibility

All marking shall be legible.

The colours of the identification threads shall be easy to recognize or easily made recognizable if necessary, by cleaning with petrol or other solvent.

5 Tests on completed cables

5.1 Electrical properties

5.1.1 General

The cables shall have adequate dielectric strength. PREVIEW

Compliance shall be checked by carrying out the following tests.

5.1.2 Voltage test <u>IEC 61138:2007</u>

A sample of cable shall be immersed in water and the voltage specified below shall be applied between the conductor and the water, with the following test conditions:

-	minimum length of sample:	10 m
-	minimum period of immersion in water:	1 h
_	temperature of water:	20 °C ± 5 °C
_	voltage applied (a.c.):	1 000 V
_	duration of application of voltage, minimum:	5 min
_	result to be obtained:	during test no breakdown shall occur

5.1.3 Spark test

The integrity of the insulation shall be verified by compliance with IEC 62230.

Tabulated radial thickness of layer under test mm		Test voltage k∨			
from	up to	a.c.	d.c.	h.f.	pulse
1,01	1,25	9	13	10 ^a	13
1,26	1,50	10	15	11 ^a	15
1,51	1,75	12	17	13 ª	17
1,76	2,00	13	20	14 ^a	20
2,01	2,25	14	22	15 ª	-
2,26	2,50	16	24	17 ^a	-
2,51	2,75	17	26	18 ^a	-
2,76	3,00	19	28	20 ª	-
h.f. Voltage tes	sting for layer thickne	ess greater than 1,	0 mm should be limi	ted to frequencies I	between 500 Hz

Table 1 – Requirement for test voltages

The insulation shall exhibit no fault when tested with the above mentioned test method.

5.2 Overall diameter

The mean overall diameter of the cables shall be within the limits specified in Table 3 and 4.

The difference between any two values of the overall diameter of the cables at the same cross-section (ovality) shall not exceed 15 % of the upper limit specified for the mean overall diameter.

IEC 61138:2007

https://standards.iteh.ai/catalog/standards/sist/84e6f4a7-c8e5-4cca-b9a5-Compliance shall be checked by the test given in 1113.0f IEC 60227-2 or IEC 60245-2.

5.3 Flexibility test

5.3.1 General

The cables shall be sufficiently flexible in normal use.

5.3.2 Test for cables with copper conductors

Compliance shall be checked by carrying out the test specified in 3.2 of IEC 60245-2.

Before the test, the samples shall be conditioned at 20 °C \pm 5 °C for 24 h in a vertical position, after which the test shall be carried out within the same temperature limits.

The mean of the two values of /' (see Figure 2 in IEC 60245-2) shall not exceed the values specified in Table 2.

Nominal cross-sectional area of conductor mm²	Max distance /' EPR, PVC and SiR insulation m
16	0,45
25	0,45
35	0,50
50	0,50
70	0,55
95	0,60
120	0,65
150	0,65

Table 2 – Requirements for the static flexibility test

5.3.3 Test for cables with aluminium conductors

The test shall be carried out by means of an apparatus shown in Figure 1. This apparatus has a carrier C supporting two pulleys A and B arranged so that the cable is horizontal between the pulleys. The carriers make backward and forward movements over a distance of 1 m, at an approximately constant speed of 0,33 m/s (see also IEC 60227-2 or IEC 60245-2).

A sample of flexible cable about 5 m long shall be stretched over the pulleys, as shown in Figure 1, each end being loaded with a weight having a mass of 10 kg. The diameter of the pulleys A and B shall be 120 mm. IEC 61138:2007

https://standards.iteh.ai/catalog/standards/sist/84e6f4a7-c8e5-4cca-b9a5-The pulleys have a semi-circular shaped groovec the diameter of which is 30 mm. An electrical current of 5 A shall be applied to the sample; the voltage shall be about 230 V, the frequency of which shall be between 48 Hz and 62 Hz.

A total of 2 000 movements (1 000 in each direction) shall be made.



61138 © IEC:2007

At the conclusion of the flexing movements no crack shall appear on the insulation. Furthermore, the value of the electrical resistance at the end of the test shall not vary by more than 10 % from the electrical resistance at the beginning of the test.

5.4 Optional clashing test

This test is optional and limited only on PVC insulated cables and carried out according to special national rules or customers requirement.

Cable satisfying the clashing test shall be identified by the manufacturer by printing of the words "Clashing test" on the insulation.

Test shall be carried as described in Annex A.

6 Particular specifications

6.1 General

Each cable shall comply with the appropriate requirements given in Clauses 4 and 5 and the particular requirements of this Clause 6.

6.2 Code designation

TAL OT AND AT	
Type of insulation and of conductor	Code designation
EPR – Copper (standard	s.iteh.@1 138 IEC 60110
EPR – Aluminium	61138 IEC 60210
PVC/ST 5 – Copper IEC 6113	61138 IEC 60150
PVC/ST 5 - Aluminium	Is/sist/84e614a/-c8e0-4cca-b9a0- -61138-2007
PVC/ST 11 – Copper	61138 IEC 60155
PVC/ST 11 – Aluminium	61138 IEC 60255
SiR – Copper	61138 IEC 60165
SiR – Aluminium	61138 IEC 60265

6.3 Rated voltage

Not specified, see Clause 1.

6.4 Construction

6.4.1 Conductors

Number of conductors: 1.

The conductor shall comply with the requirements given in Table 3 and 4, column 2.

6.4.2 Insulation

Conductor and separator if any shall be protected by an insulation as specified in 4.3.

The thickness of insulation shall comply with the specified value given in Table 3 and 4, column 3.