

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V –

Part 1: General requirements

Conducteurs et câbles isolés au polychlorure de vinyle, de tension nominale au plus égale à 450/750 V –

Partie 1: Exigences générales

ITU STANDARD PREVIEW
(standards.iteh.ai)

IEC 60227-1:2007
<https://standards.iteh.ai/catalog/standards/sist/1dccb6d5-4ca5-4171-a71e-b7022a1c68c0/iec-60227-1-2007>



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2007 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch
Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

- Catalogue des publications de la CEI: www.iec.ch/searchpub/cur_fut-f.htm

Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,...). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.

- Just Published CEI: www.iec.ch/online_news/justpub

Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.

- Electropedia: www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International en ligne.

- Service Clients: www.iec.ch/webstore/custserv/custserv_entry-f.htm

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:

Email: csc@iec.ch
Tél.: +41 22 919 02 11
Fax: +41 22 919 03 00



IEC 60227-1

Edition 3.0 2007-10

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Polyvinyl chloride insulated cables of rated voltages up to and including
450/750 V –
Part 1: General requirements

Conducteurs et câbles isolés au polychlorure de vinyle, de tension nominale au
plus égale à 450/750 V –
Partie 1: Exigences générales

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

S

CONTENTS

FOREWORD.....	4
1 General	6
1.1 Scope.....	6
1.2 Normative references	6
2 Definitions	7
2.1 Definitions relating to insulating and sheathing materials.....	7
2.1.1 Polyvinyl chloride compound (PVC).....	7
2.1.2 Type of compound	7
2.2 Definitions relating to the tests.....	7
2.2.1 Type tests (symbol T)	7
2.2.2 Sample tests (symbol S).....	7
2.3 Rated voltage	7
3 Marking	8
3.1 Indication of origin and cable identification.....	8
3.1.1 Continuity of marks	8
3.2 Durability	8
3.3 Legibility.....	8
4 Core identification.....	9
4.1 Core identification by colours.....	9
4.1.1 General requirements	9
4.1.2 Colour scheme	9
4.1.3 Colour combination green and yellow.....	9
4.2 Core identification by numbers.....	9
4.2.1 General requirements	9
4.2.2 Preferred arrangement of marking.....	10
4.2.3 Durability	10
5 General requirements for the construction of cables.....	10
5.1 Conductors.....	10
5.1.1 Material	10
5.1.2 Construction	10
5.1.3 Check on construction	11
5.1.4 Electrical resistance.....	11
5.2 Insulation.....	11
5.2.1 Material	11
5.2.2 Application to the conductor	11
5.2.3 Thickness	11
5.2.4 Mechanical properties before and after ageing	11
5.3 Filler.....	13
5.3.1 Material	13
5.3.2 Application.....	14
5.4 Extruded inner covering	14
5.4.1 Material	14
5.4.2 Application.....	14
5.4.3 Thickness	14
5.5 Sheath.....	14
5.5.1 Material	14

5.5.2	Application.....	14
5.5.3	Thickness	15
5.5.4	Mechanical properties before and after ageing	15
5.6	Tests on completed cables	17
5.6.1	Electrical properties	17
5.6.2	Overall dimensions	18
5.6.3	Mechanical strength of flexible cables	19
5.6.4	Flame retardance.....	19
6	Guide to use of the cables	19
Annex A (normative) Code designation		20
Table 1 – Requirements for the non-electrical tests for polyvinyl chloride (PVC) insulation		12
Table 2 – Requirements for the non-electrical test for polyvinyl chloride (PVC) sheaths.....		16
Table 3 – Requirements for electrical tests for PVC insulated cables		18

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[IEC 60227-1:2007](https://standards.iteh.ai/catalog/standards/sist/fdceb8d5-49a5-4f71-a71e-b7022a1c68c0/iec-60227-1-2007)

<https://standards.iteh.ai/catalog/standards/sist/fdceb8d5-49a5-4f71-a71e-b7022a1c68c0/iec-60227-1-2007>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**POLYVINYL CHLORIDE INSULATED CABLES
OF RATED VOLTAGES UP TO AND
INCLUDING 450/750 V –****Part 1: General requirements**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60227-1 has been prepared by IEC technical committee 20: Electric cables.

This third edition of IEC 60227-1 cancels and replaces the second edition, published in 1993, amendment 1 (1995) and amendment 2 (1997) The document 20/903/FDIS, circulated to the National Committees as amendment 3, led to the publication of this new edition.

The text of this standard is based on the second edition, its amendments 1 and 2, and the following documents:

FDIS	Report on voting
20/903/FDIS	20/910/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[IEC 60227-1:2007](#)

<https://standards.iteh.ai/catalog/standards/sist/fdceb8d5-49a5-4f71-a71e-b7022a1c68c0/iec-60227-1-2007>

POLYVINYL CHLORIDE INSULATED CABLES OF RATED VOLTAGES UP TO AND INCLUDING 450/750 V –

Part 1: General requirements

1 General

1.1 Scope

This part of International Standard IEC 60227 applies to rigid and flexible cables with insulation, and sheath if any, based on polyvinyl chloride, of rated voltages U_0/U up to and including 450/750 V used in power installations of nominal voltage not exceeding 450/750 V a.c.

NOTE For some types of flexible cables the term cord is used.

The particular types of cables are specified in IEC 60227-3, IEC 60227-4, etc. The code designations of these types of cables are given in Annex A.

The test methods specified in Parts 1, 3, 4, etc. are given in IEC 60227-2, IEC 60332-1-2 and in the relevant parts of IEC 60811.

1.2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60173, *Colours of the cores of flexible cables and cords*

IEC 60227-2, *Polyvinyl chloride insulated cables of rated voltage up to and including 450/750 V – Part 2: Test methods*

IEC 60227-3, *Polyvinyl chloride insulated cables of rated voltage up to and including 450/750 V – Part 3: Non-sheathed cables for fixed wiring*

IEC 60227-4, *Polyvinyl chloride insulated cables of rated voltage up to and including 450/750 V – Part 4: Sheathed cables for fixed wiring*

IEC 60227-5, *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V – Part 5: Flexible cables (cords)*

IEC 60228, *Conductors of insulated cables*

IEC 60332-1-2, *Tests on electric and optical fibre cables under fire conditions – Part 1-2: Test for vertical flame propagation for a single insulated wire or cable – Procedure for 1 kW pre-mixed flame*

IEC 60811-1-1, *Common test methods for insulating and sheathing materials of electric cables and optical cables – Part 1: Methods for general application – Measuring of thickness and overall dimensions – Tests for determining the mechanical properties*

IEC 60811-1-2, *Common test methods for insulating and sheathing materials of electric cables – Part 1: Methods for general application – Section Two: Thermal ageing methods*

IEC 60811-1-4, *Common test methods for insulating and sheathing materials of electric cables – Part 1: Methods for general application – Section Four: Tests at low temperature*

IEC 60811-3-1, *Common test methods for insulating and sheathing materials of electric cables – Part 3: Methods specific to PVC compounds – Section One: Pressure test at high temperature – Tests for resistance to cracking*

IEC 60811-3-2, *Common test methods for insulating and sheathing materials of electric cables – Part 3: Methods specific to PVC compounds – Section Two: Loss of mass test – Thermal stability tests*

IEC 62440, *Electric cables – Guide to use for cables with a rated voltage not exceeding 450/750V¹*

2 Definitions

For the purpose of this standard the following definitions shall apply.

2.1 Definitions relating to insulating and sheathing materials

2.1.1 Polyvinyl chloride compound (PVC)

Combination of materials suitably selected, proportioned and treated, of which the characteristic constituent is the plastomer polyvinyl chloride or one of its copolymers. The same term also designates compounds containing both polyvinyl chloride and certain of its polymers.

<https://standards.iteh.ai/catalog/standards/sist/fdceb8d5-49a5-4f71-a71e-b7022a1c68c0/iec-60227-1-2007>

2.1.2 Type of compound

The category in which a compound is placed according to its properties, as determined by specific tests. The type designation is not directly related to the composition of the compound.

2.2 Definitions relating to the tests

2.2.1 Type tests (symbol T)

Tests required to be made before supplying a type of cable covered by this standard on a general commercial basis in order to demonstrate satisfactory performance characteristics to meet the intended application. These tests are of such a nature that, after they have been made, they need not be repeated unless changes are made in the cable materials or design which might change the performance characteristics.

2.2.2 Sample tests (symbol S)

Tests made on samples of completed cable or components taken from a completed cable, adequate to verify that the finished product meets the design specifications.

2.3 Rated voltage

The rated voltage of a cable is the reference voltage for which the cable is designed and which serves to define the electrical tests.

¹ In preparation.

The rated voltage is expressed by the combination of two values U_0/U , expressed in volts:

U_0 being the r.m.s. value between any insulated conductor and "earth" (metal covering of the cable or the surrounding medium);

U being the r.m.s. value between any two-phase conductors of a multicore cable or of a system of single-core cables.

In an alternating current system, the rated voltage of a cable shall be at least equal to the nominal voltage of the system for which it is intended.

This condition applies both to the value U_0 and to the value U .

In a direct current system, the nominal voltage of the system shall be not higher than 1,5 times the rated voltage of the cable.

NOTE The operating voltage of a system may permanently exceed the nominal voltage of such a system by 10 %. A cable can be used at a 10 % higher operating voltage than its rated voltage if the latter is at least equal to the nominal voltage of the system.

3 Marking

3.1 Indication of origin and cable identification

Cables shall be provided with an indication of the manufacturer, which shall be either an identification thread or a repetitive marking of the manufacturer's name or trade-mark.

Cables for use at a conductor temperature exceeding 70 °C shall also be marked either with the code designation or with the maximum conductor temperature.

Marking may be by printing or by reproduction in relief on or in the insulation or sheath.

3.1.1 Continuity of marks

Each specified mark shall be regarded as continuous if the distance between the end of the mark and the beginning of the next identical mark does not exceed

- 550 mm if the marking is on the outer sheath of the cable;
- 275 mm if the marking is
 - a) on the insulation of an unsheathed cable;
 - b) on the insulation of a sheathed cable;
 - c) on a tape within a sheathed cable.

3.2 Durability

Printed markings shall be durable. Compliance with this requirement shall be checked by the test given in 1.8 of IEC 60227-2.

3.3 Legibility

All markings shall be legible.

The colours of the identification threads shall be easy to recognize or easily made recognizable, if necessary, by cleaning with petrol or other suitable solvent.

4 Core identification

Each core shall be identified as follows:

- in cables having up to and including five cores by colour, see 4.1;
- in cables having more than five cores by number, see 4.2.

NOTE The colour scheme, and in particular the scheme for rigid multicore cables, is under consideration.

4.1 Core identification by colours

4.1.1 General requirements

Identification of the cores of a cable shall be achieved by the use of coloured insulation or other suitable method.

Each core of a cable shall have only one colour, except the core identified by a combination of the colours green-and-yellow.

The colours green and yellow, when not in combination, shall not be used for any multicore cable.

NOTE The colours red and white should preferably be avoided.

4.1.2 Colour scheme

The preferred colour scheme for flexible cables and single-core cables is:

- single-core cable: no preferred colour scheme;
- two-core cable: no preferred colour scheme;
- three-core cable: either green-and-yellow, blue, brown, or, brown, black, grey
- four-core cable: either green-and-yellow, brown, black, grey, or blue, brown, black, grey
- five-core cable: either green-and-yellow, blue, brown, black, grey, or blue, brown, black, grey, black.

The colours shall be clearly identifiable and durable. Durability shall be checked by the test given in 1.8 of IEC 60227-2.

4.1.3 Colour combination green-and-yellow

The distribution of the colours for the core coloured green-and-yellow shall comply with the following condition (which is in accordance with IEC 60173): for every 15 mm length of core, one of these colours shall cover at least 30 % and not more than 70 % of the surface of the core, the other colour covering the remainder.

NOTE Information on the use of the colours green-and-yellow and blue.

It is understood that the colours green and yellow, when they are combined as specified above, are recognized exclusively as a means of identification of the core intended for use as earth connection or similar protection, and that the colour blue is intended for the identification of the core intended to be connected to neutral. If, however, there is no neutral, blue can be used to identify any core except the earthing or protective conductor.

4.2 Core identification by numbers

4.2.1 General requirements

The insulation of the cores shall be of the same colour and numbered sequentially, except for the core coloured green-and-yellow, if one is included.

The green-and-yellow core, if any, shall comply with the requirement of 4.1.3 and shall be in the outer layer.

The numbering shall start by number 1 in the inner layer.


The numbers shall be printed in arabic numerals on the outer surfaces of the cores. All the numbers shall be of the same colour, which shall contrast with the colour of the insulation. The numerals shall be legible.

4.2.2 Preferred arrangement of marking

The numbers shall be repeated, at regular intervals along the core, consecutive numbers being inverted in relation to each other.

When the number is a single numeral, a dash shall be placed underneath it. If the number consists of two numerals, these shall be disposed one below the other and a dash placed below the lower numeral. The spacing d between consecutive numbers shall not exceed 50 mm.

The arrangement of the marks is shown in the figure below.



<https://standards.iteh.ai/catalog/standards/sist/fdceb8d5-49a5-4f71-a71e-b7022a1c68c0/iec-60227-1-2007>

4.2.3 Durability

Printed numerals shall be durable. Compliance with this requirement shall be checked by the test given in 1.8 of IEC 60227-2.

5 General requirements for the construction of cables

5.1 Conductors

5.1.1 Material

The conductors shall consist of annealed copper, except for the wires of tinsel cords, for which a copper alloy may be used. The wires may be plain or tinned.

5.1.2 Construction

The maximum diameters of the wires of flexible conductors – other than the conductors of tinsel cords – and the minimum number of the wires of rigid conductors shall be in accordance with IEC 60228.

The classes of the conductors relevant to the various types of cables are given in the particular specifications (see IEC 60227-3, IEC 60227-4, etc.).

Conductors of cables for fixed installations shall be circular solid, circular stranded or compacted circular stranded conductors.

For tinsel cords each conductor shall comprise a number of strands or groups of strands, twisted together, each strand being composed of one or more flattened wires of copper or copper alloy, helically wound on a thread of cotton, polyamide or similar material.

5.1.3 Check on construction

Compliance with the requirements of 5.1.1 and 5.1.2, including the requirements of IEC 60228, shall be checked by inspection and by measurement.

5.1.4 Electrical resistance

For cables – other than tinsel cords – the resistance of each conductor at 20 °C shall be in accordance with the requirements of IEC 60228 for the given class of the conductor.

Compliance shall be checked by the test given in 2.1 of IEC 60227-2.

5.2 Insulation

5.2.1 Material

The insulation shall be polyvinyl chloride compound of the type specified for each type of cable in the particular specifications (see IEC 60227-3, IEC 60227-4, etc.).

Type PVC/C in the case of cables for fixed installation.

Type PVC/D in the case of flexible cables.

Type PVC/E in the case of heat-resistant cables for internal wiring.

The test requirements for these compounds are specified in Table 1.

The maximum operating temperatures for cables insulated with any of the above types of compound and covered by the particular specifications (see IEC 60227-3, IEC 60227-4, etc.) are given in those publications.

5.2.2 Application to the conductor

The insulation shall be so applied that it fits closely on the conductor, but for cables other than tinsel cords, it shall be possible to remove it without damage to the insulation itself, to the conductor or to the tin coating if any. Compliance shall be checked by inspection and by manual test.

5.2.3 Thickness

The mean value of the thickness of insulation shall be not less than the specified value for each type and size of cable shown in the tables of the particular specifications (IEC 60227-3, IEC 60227-4, etc.).

However, the thickness at any place may be less than the specified value provided that the difference does not exceed 0,1 mm + 10 % of the specified value.

Compliance shall be checked by the test given in 1.9 of IEC 60227-2.

5.2.4 Mechanical properties before and after ageing

The insulation shall have adequate mechanical strength and elasticity within the temperature limits to which it may be exposed in normal use.

Compliance shall be checked by carrying out the tests specified in Table 1.

The applicable test methods and the results to be obtained are specified in Table 1.