International Standard



7627/5

Hardmetals – Chemical analysis by flame atomic absorption spectrometry – Part 5: Determination of cobalt, iron, manganese, molybdenum, nickel, titanium and vanadium in contents from 0,5 to 2 % (m/m) ANDARD PREVIEW (standards.iteh.ai)

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION MEX DY HAPODHAR OPPAHUSALUR TO CTAHDAPTUSALUNOORGANISATION INTERNATIONALE DE NORMALISATION

Métaux-durs — Analyse chimique par spectrométrie d'absorption atomique dans la flamme — Partie 5: Dosage du cobalt, du fer, du manganèse, du molybdène, du nickel, du titane et du vanadium à des teneurs comprises entre 0,5 et 2 % (m/m) ISO 7627-5:1983

First edition – **1983-10-15** *Taae*7002e454/iso-7627-5-1983

UDC 669.018.25 : 643.422

Ref. No. ISO 7627/5-1983 (E)

Descriptors : hardmetals, chemical analysis, determination of content, cobalt, iron, manganese, molybdenum, nickel, titanium, vanadium, atomic absorption spectrometry.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been authorized has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 7627/5 was developed by Technical Committee ISO/TC 119, *Powder metallurgy*, and was circulated to the member bodies in August 1982.

It has been approved by the member bodies of the following countries: 1983

https://standards.iteh.ai/catalog/standards/sist/807a445d-e816-4351-8152-

| Austria | |
|---------------------|---|
| Brazil | |
| Bulgaria | |
| China | |
| Czechoslovakia | |
| Egypt, Arab Rep. of | F |
| France | |

Germany, F.R. 7aa Italy Korea, Rep. of Norway Romania South Africa, Rep. of Spain

7aae700 Sweden)-7627-5-1983 Switzerland United Kingdom USA USSR

No member body expressed disapproval of the document.

© International Organization for Standardization, 1983 •

Printed in Switzerland

Hardmetals — Chemical analysis by flame atomic absorption spectrometry —

Part 5: Determination of cobalt, iron, manganese, molybdenum, nickel, titanium and vanadium in contents from 0,5 to 2 % (m/m)

1 Scope and field of application

This part of ISO 7627 specifies the method to be used for the determination of cobalt, iron, manganese, molybdenum, nickel, titanium and vanadium contents of hardmetals within the range 0,5 to 2 % (m/m) by flame atomic absorption spectrometry.

General requirements concerning the field of application, prints ciple, interfering elements, apparatus, sampling and test report are given in ISO 7627/1. ISO 7627-5

https://standards.iteh.ai/catalog/standards/sia NOTE — Determination of element contents in high concentration by the atomic absorption spectrophotometry method yields a wider scattering of results than are obtainable by other methods, i.e. ISO 3909, 4501, 4503 and 4883. See also clause 4.2.

2 Reference

ISO 7627/1, Hardmetals – Chemical analysis by flame atomic absorption spectrometry – Part 1: General requirements.

3 Reagents

- **3.1** Hydrofluoric acid, ϱ 1,12 g/ml.
- **3.2** Nitric acid, *ρ* 1,42 g/ml.
- 3.3 Ammonium fluoride, 0,1 g/ml solution.

3.4 Caesium chloride, 0,01 g/ml solution.

3.5 High-purity stock solutions, for calibration purposes for each element to be determined, containing 1,000 g of the element per litre.

NOTE — This value is understood to establish a maximum limit of 1,000 5 g and a minimum limit of 0,999 5 g.

4 Procedure

teh.ail

4.1 Test portion

Weigh, to the nearest 0,001 g, approximately 1 g of the test sample. Transfer it to a 100 ml polytetrafluorethylene beaker or a beaker of other suitable material. Cover the beaker.

4.2 Dissolution of the test portion

Add 10 ml of water, 5 ml of the hydrofluoric acid (3.1). and then 5 ml of the nitric acid (3.2), drop by drop, to the beaker containing the test portion (4.1) and heat gently until the test portion is completely dissolved. Add 10 ml of the caesium chloride solution (3.4) and 10 ml of the ammonium fluoride solution (3.3). Then transfer the solution totally to a 100 ml polypropylene one-mark volumetric flask and dilute to the mark.

4.3 Dilution volume

Prepare the relevant dilution volume for the analysis according to table 1 in the following way.

4.3.1 Dilution volume 100 ml: use the solution in 4.2.

4.3.2 The concentration of the solution may be reduced by a factor of 10 for instruments of higher sensitivity by transferring 10 ml of the solution in 4.2 to a 100 ml polypropylene one-mark volumetric flask. Add 10 ml of the caesium chloride solution (3.4). Add 10 ml of the ammonium fluoride solution (3.3) and dilute to the mark.

4.4 Preparation of calibration and blank solutions

4.4.1 Prepare at least six solutions according to 4.2 with a matrix composition as similar as possible to the test portion to be analysed, but without making up to volume. Then add increasing volumes of properly diluted stock solutions of the elements to be determined according to the concentration ranges to be covered. Make up to 100 ml and mix.

| Element | Dilution volume (V) for 1 g test portion ¹⁾ ml | Oxidant | Wavelength nm | Reciprocal sensitivity, for 1 % absorption ¹⁾ μg/ml | Linear range ¹⁾ % | Notes |
|---------|---|------------------|------------------|--|---------------------------------|---------|
| Со | 100 | N ₂ O | 352,7 | 20 | 0,1 to 15 | |
| Fe | 1 000 | N ₂ O | 248,3 | 0,3 | 0,03 to 2,0 | |
| Mn | 1 000 | N ₂ 0 | 279,8 | 0,1 | 0,01 to 2,0 | 1 |
| Mo | 100 | N ₂ 0 | 313,3 | 6 | 0,06 to 10,0 | 2 |
| Ni | 1 000 | N ₂ 0 | 232,0 | 0,3 | 0,05 to 5,0 | 3 and 4 |
| ТіІ | 100 | N ₂ O | 364,3 | 30 | 0,2 to 10 | 2 |
| v | 1 000 | N ₂ O | 318,4 | 1,0 | 0,1 to 5,0 | 1 |

Table 1 — Instrumental parameters and characteristics of calibration functions

Guidelines for information only. 1)

NOTES

1 Use of the triplet.

2 Use a fuel-rich flame. Adjust the burner head at right angles to the light beam or dilute the solution appropriately.

Sensitivity is greatly dependent on matrix composition. 3

4 Use of a narrow-spectral band pass and a single-element hollow-cathode lamp is mandatory.

4.4.2 Also prepare calibration solutions with a diluted matrix **Expression of results** 5 in accordance with 4.3 for dilution volumes of 1 000 ml, if necessary. iTeh STANDA51DCalculation/IEW

4.4.3 Prepare one or more blank solutions (see 4.4.1) without an The element content, expressed as a percentage by mass, is the addition of the relevant element to be determined. given by the formula

<u>ISO 7627-5:1088</u> V

4.5 Adjustment of the atomic absorption https://standards.iteh.ai/catalog/standards/104/82/7m445d-e816-4351-8152spectrometer

7aae7002e454/iso-7627-5-1983

SAFETY PRECAUTION : Follow the manufacturer's recommendation on igniting and extinguishing the flame.

Optimize the response of the instrument at the wavelength given for the element being determined. See table 1.

Preheat the burner for about 5 min and then adjust the fuel and correct the burner to obtain maximum absorption while aspirating a calibration solution. Make sure that the absorbance reading is not drifting. Aspirate water and set the initial reading to zero absorbance.

4.6 Atomic absorbance measurements

4.6.1 Aspirate first the blank solution and then the calibration and test solutions consecutively and record the readings. Aspirate water between each solution. Make at least two measurements for each solution. Solids which build up on the burner slit must be removed, otherwise they will cause a decrease of sensitivity.

4.6.2 Prepare a calibration curve by plotting the obtained absorbance values of the calibration solutions corrected for the blank against the concentration, in milligrams per litre, of the element.

4.6.3 Convert the absorbance values of the test solutions corrected for the blank to milligrams of the element per litre by means of the calibration curve.

where

c is the concentration, in milligrams per litre, of the element in the test solution;

- is the dilution volume, in millilitres; V
- *m* is the mass, in grams, of the test portion.

5.2 Permissible tolerances

The deviations between three independent determinations shall not exceed 0,1 times the element content in per cent (absolute value).

5.3 Final result

Report the arithmetical mean of acceptable determinations rounded to the nearest value as shown in table 2.

Table 2 - Rounding of results

| Content | Round to the nearest |
|------------------|---------------------------|
| % (<i>m/m</i>) | % (<i>m</i> / <i>m</i>) |
| from 0,5 to 1 | 0,02 |
| over 1 to 2 | 0,05 |

If the element content is below 0,5 % (m/m), use the relevant part of this standard. If the element is greater than 2 % (m/m), report it as greater than 2 % (m/m).

2