IEC/TS 60695-1-20

Edition 1.0 2008-02

TECHNICAL SPECIFICATION

SPÉCIFICATION TECHNIQUE

BASIC SAFETY PUBLICATION

PUBLICATION FONDAMENTALE DE SÉCURITÉ

Fire hazard testing –
Part 1-20: Guidance for assessing the fire hazard of electrotechnical products – Ignitability – General guidance

Essais relatifs aux risques du feu –
Partie 1-20: Lignes directrices pour l'évaluation des risques du feu des produits électrotechniques – Allumabilité – Lignes directrices générales

IEC Central Office
3, rue de Varembé
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub
The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,…). It also gives information on projects, withdrawn and replaced publications.
- IEC Just Published: www.iec.ch/online_news/justpub
Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.
- Electropedia: www.electropedia.org
The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.
- Customer Service Centre: www.iec.ch/webstore/custserv
If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:
Email: csc@iec.ch
Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

- Catalogue des publications de la CEI: www.iec.ch/searchpub/cur_fut-f.htm
Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,…). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.
- Just Published CEI: www.iec.ch/online_news/justpub
Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.
- Electropedia: www.electropedia.org
Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International en ligne.
- Service Clients: www.iec.ch/webstore/custserv/custserv_entry-f.htm
Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:
Email: csc@iec.ch
Tél.: +41 22 919 02 11
Fax: +41 22 919 03 00

IEC/TS 60695-1-20

Edition 1.0 2008-02

TECHNICAL SPECIFICATION

SPÉCIFICATION TECHNIQUE

BASIC SAFETY PUBLICATION

PUBLICATION FONDAMENTALE DE SÉCURITÉ

Fire hazard testing – Part 1-20: Guidance for assessing the fire hazard of electrotechnical products – Ignitability – General guidance

Essais relatifs aux risques du feu – Partie 1-20: Lignes directrices pour l'évaluation des risques du feu des produits électrotechniques – Allumabilité – Lignes directrices générales

INTERNATIONAL ELECTROTECHNICAL COMMISSION

COMMISSION ELECTROTECHNIQUE INTERNATIONALE

PRICE CODE
CODE PRIX R

ICS 13.220.40; 29.020

ISBN 2-8318-9602-9

CONTENTS

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FIRE HAZARD TESTING –

Part 1-20: Guidance for assessing the fire hazard of electrotechnical products – Ignitability – General guidance

FOREWORD

1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
6) All users should ensure that they have the latest edition of this publication.
7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. In exceptional circumstances, a technical committee may propose the publication of a technical specification when

- the required support cannot be obtained for the publication of an International Standard, despite repeated efforts, or
- the subject is still under technical development or where, for any other reason, there is the future but no immediate possibility of an agreement on an International Standard.

Technical specifications are subject to review within three years of publication to decide whether they can be transformed into International Standards.

IEC 60695-1-20, which is a technical specification, has been prepared by IEC technical committee 89: Fire hazard testing.

It has the status of a basic safety publication in accordance with IEC Guide 104 and ISO/IEC Guide 51.

The text of this technical specification is based on the following documents:

Enquiry draft	Report on voting
89/807/DTS	89/827/RVC

Full information on the voting for the approval of this technical specification can be found in the report on voting indicated in the above table.

This technical specification is to be used in conjunction with IEC 60695-1-21 .

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60695 series, under the general title *Fire hazard testing*, can be found on the IEC website.

Part 1 consists of the following parts:

Part 1-10[1]: Guidance for assessing the fire hazard of electrotechnical products – General guidelines

Part 1-11[1]: Guidance for assessing the fire hazard of electrotechnical products – Fire hazard assessment

Part 1-20: Guidance for assessing the fire hazard of electrotechnical products – Ignitability – General guidance

Part 1-21: Guidance for assessing the fire hazard of electrotechnical products – Ignitability – Summary and relevance of test methods

Part 1-30: Guidance for assessing the fire hazard of electrotechnical products – Preselection testing procedures – General guidelines

Part 1-40: Guidance for assessing the fire hazard of electrotechnical products – Insulating liquids

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- transformed into an International standard,
- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

[1] Under consideration.

INTRODUCTION

Fires are responsible for creating hazards to life and property as a result of the generation of heat (thermal hazard), and also as a result of the production of toxic effluent, corrosive effluent and smoke (non-thermal hazard). Fires start with ignition and then can grow, leading in some cases to flash-over and a fully developed fire. Ignition resistance is therefore one of the most important parameters of a material to be considered in the assessment of fire hazard. If there is no ignition there is no fire.

For most materials (other than metals and other elements), ignition occurs in the gas phase. Ignition occurs when combustible vapour, mixed with air, reaches a high enough temperature for exothermic oxidation reactions to rapidly propagate. The ease of ignition is a function of the chemical nature of the vapour, the fuel/air ratio and the temperature.

In the case of liquids, the combustible vapour is produced by vaporization of the liquid, and the vaporization process is dependent on the temperature and chemical composition of the liquid.

In the case of solids, the combustible vapour is produced by pyrolysis when the temperature of the solid is sufficiently high. The vaporization process is dependent on the temperature and chemical composition of the solid, and also on the thickness, density, specific heat, and thermal conductivity of the solid.

The ease of ignition of a test specimen depends on many variables. Factors that need to be considered for the assessment of ignitability are:

a) the geometry of the test specimen, including thickness and the presence of edges, corners or joints;

b) the surface orientation;

c) the rate and direction of air flow;

d) the nature and position of the ignition source;

e) the magnitude and position of any external heat flux; and

f) whether the combustible material is a solid or a liquid.

In the design of any electrotechnical product, the risk of fire and the potential hazards associated with fire need to be considered. In this respect the objective of component, circuit and equipment design as well as the choice of materials is to reduce to acceptable levels the potential risks of fire even in the event of foreseeable abnormal use, malfunction or failure. IEC 60695-1-10[2], together with its companion, IEC 60695-1-11[2], provide guidance on how this is to be accomplished.

The primary aims are to prevent ignition caused by an electrically energized component part, and in the event of ignition, to confine any resulting fire within the bounds of the enclosure of the electrotechnical product.

Secondary aims include the minimization of any flame spread beyond the product's enclosure and the minimization of harmful effects of fire effluents including heat, smoke, and toxic or corrosive combustion products.

Fires involving electrotechnical products can also be initiated from external non-electrical sources. Considerations of this nature are dealt with in the overall risk assessment.

This technical specification gives an overview of ignitability and its relevance to the fire hazard of electrotechnical products.

---

2 Under consideration.

FIRE HAZARD TESTING –

Part 1-20: Guidance for assessing the fire hazard of electrotechnical products – Ignitability – General guidance

1 Scope

IEC 60695-1-20, which is a technical specification provides guidance on the ignitability of electrotechnical products and the materials from which they are formed. It gives guidance on;

a) the principles of ignitability,

b) the selection of appropriate test methods, and

c) the use and interpretation of results.

This technical specification is intended for use by technical committees in preparation of standards in accordance with the principles laid down IEC Guide 104 and ISO/IEC Guide 51.

One of the responsibilities of a technical committee is, wherever applicable, to make use of basic safety publications in the preparation of its publications. The requirements, test methods or test conditions of this basic publication will not apply unless specifically referred to or included in the relevant publications.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60695-1-10, *Fire hazard testing – Part 1-10:Guidance for assessing the fire hazard of electrotechnical products – General guidelines*[3]

IEC 60695-1-11, *Fire hazard testing – Part 1-11: Guidance for assessing the fire hazard of electrotechnical products – Fire hazard assessment*[3]

IEC 60695-1-21, *Fire hazard testing – Part 1-21: Guidance for assessing the fire hazard of electrotechnical products – Ignitability – Summary and relevance of test methods*

IEC 60695-2-11, *Fire hazard testing – Part 2-11: Glowing/hot-wire based test methods – Glow-wire flammability test method for end-products*

IEC 60695-2-12, *Fire hazard testing – Part 2-12: Glowing/hot-wire based test methods – Glow-wire flammability test method for materials*

IEC 60695-2-13, *Fire hazard testing – Part 2-13: Glowing/hot-wire based test methods – Glow-wire ignitability test method for materials*

IEC 60695-4:2005, *Fire hazard testing – Part 4: Terminology concerning fire tests in electrotechnical equipment*

IEC 60695-8-3, *Fire hazard testing – Part 8-3: Heat release – Heat release of insulating liquids used in electrotechnical products*[4]

---

3 Under consideration.

4 To be published.

IEC 60695-11-5, *Fire hazard testing – Part 11-5: Test flames – Needle-flame test method – Apparatus, confirmatory test arrangement and guidance*

IEC 60695-11-10, *Fire hazard testing – Part 11-10: Test flames – 50 W horizontal and vertical flame test methods*

IEC 60695-11-11 , *Fire hazard testing – Part 11-11: Test flames – Determination of the ignition characteristic heat flux from a flame source*[5]

IEC 60695-11-20, *Fire hazard testing – Part 11-20: Test flames – 500 W flame test methods*

IEC Guide 104:1997, *The preparation of safety publications and the use of basic safety publications and group safety publications*

EN 14522, *Determination of the auto ignition temperature of gases and vapours*

ISO/IEC Guide 51:1999, *Safety aspects – Guidelines for their inclusion in standards*

ISO/IEC 13943:2000, *Fire safety – Vocabulary*

ISO 871, *Plastics – Determination of ignition temperature using a hot-air furnace*

ISO 2592, *Determination of flash and fire points. Cleveland open cup method*

ISO 2719, *Petroleum products and lubricants - Determination of flash point – Pensky-Martens closed cup method*

ISO 5657, *Reaction to fire tests – Ignitability of building products using a radiant heat source*

ISO 10840, *Plastics – Guidance for the use of standard fire tests*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1
auto ignition temperature
lowest temperature (of a hot surface) at which under specified test conditions an ignition of a flammable gas or flammable vapour in mixture with air or air/inert gas occurs

[EN 14522, definition 3.1]

3.2
combustion
exothermic reaction of a substance with an oxidizer

NOTE Combustion generally emits effluent accompanied by flames and/or visible light.

[ISO/IEC 13943:2000, definition 23]

3.3
fire
a) a process of combustion characterized by the emission of heat and effluent accompanied by smoke, and/or flame, and/or glowing;

b) rapid combustion spreading uncontrolled in time and space

[IEC 60695-4:2005, definition 3.19]

5 Under consideration.

3.4
fire hazard
⟨cause of fire⟩ physical object or condition with a potential for an undesirable consequence from fire

3.5
fire point
minimum temperature at which a material ignites and continues to burn for a specified time after a standardized small flame has been applied to its surface under specified conditions

NOTE 1 It is expressed in degrees Celsius.

NOTE 2 In some countries the term "fire point" has an additional meaning: a location where fire fighting equipment is sited, which may also comprise a fire-alarm call point and fire instruction notices.

[ISO/IEC 13943:2000, definition 53]

3.6
fire retardant (noun)
a substance added or a treatment applied to a material in order to suppress, reduce or delay the combustion of the material

[IEC 60695-4:2005, definition 3.31]

3.7
fire scenario
a detailed description of conditions, including environmental, of one or more of the stages from before ignition to the completion of combustion in an actual fire at a specific location, or in a full-scale simulation

[IEC 60695-4:2005, definition 3.32]

3.8
flame (noun)
zone of combustion in the gaseous phase, usually with emission of light

[ISO/IEC 13943:2000, definition 60]

3.9
flame retardant (noun)
substance added, or a treatment applied, to a material in order to suppress or delay the appearance of a flame and/or reduce its propagation (spread) rate

NOTE The use of flame retardants does not necessarily suppress fire.

[ISO/IEC 13943:2000, definition 65]

3.10
flaming combustion
combustion in gaseous phase, usually with emission of light

[ISO/IEC 13943:2000, definition 72]

3.11
flash-ignition temperature (FIT)
the minimum temperature at which, under specified test conditions, sufficient flammable gases are emitted to ignite momentarily on application of a pilot flame

[ISO 871, definition 3.1]

3.12
flash-over
the rapid transition to a state of total surface involvement in a fire of combustible materials within an enclosure

[IEC 60695-4:2005, definition 3.42]

3.13
flash point
the minimum temperature to which a product must be heated for the vapours emitted to ignite momentarily in the presence of flame, under specified test conditions

NOTE Expressed in °C.

[IEC 60695-4:2005, definition 3.43]

3.14
fully developed fire
state of total involvement of combustible materials in a fire

[ISO/IEC 13943:2000, definition 80]

3.15
glowing combustion
combustion of a material in the solid phase without flame but with the emission of light from the combustion zone

[ISO/IEC 13943:2000, definition 84]

3.16
ignitability
measure of the ease with which an item can be ignited, under specified conditions

[ISO/IEC 13943:2000, definition 91]

3.17
ignition
initiation of combustion

NOTE The term "ignition" in French has a very different meaning [state of body combustion].

[ISO/IEC 13943:2000, definition 96]

3.18
ignition source
source of energy that initiates combustion

[ISO/IEC 13943:2000, definition 97]

3.19
ignition temperature (minimum)
the (minimum) temperature of a material or of an ignition source at which sustained combustion can be initiated under specified test conditions, as defined in the test method

NOTE Ignition requires a sufficient volume of flammable gas and oxidant (air). Sustained combustion requires a sufficient rate of production of flammable gas. The minimum ignition temperature implies thermal stressing to infinite time. For practical purposes, the standard should define the minimum ignition temperature appropriately.

[IEC 60695-4:2005, definition 3.51]

3.20
lower flammability limit (LFL)
lowest concentration of a flammable substance in air within which a self-propagating flame can occur

3.21
spontaneous-ignition temperature (SIT)
minimum temperature at which ignition is obtained by heating, under specified test conditions, in the absence of any additional flame ignition source

[ISO 871, definition 3.2]

3.22
thermal inertia
product of thermal conductivity, density and specific heat capacity

NOTE 1 When a material is exposed to a heat flux, the rate of increase in surface temperature depends strongly on the value of the thermal inertia of the material. The surface temperature of a material with a low thermal inertia rises relatively quickly when it is heated, and vice versa.

NOTE 2 The typical units are $J^2 \cdot s^{-1} \cdot m^{-4} \cdot K^{-2}$.

3.23
upper flammability limit (UFL)
highest concentration of a flammable substance in air within which a self-propagating flame can occur

4 Principles of ignitability

4.1 Gases

Ignition of a gas depends on how the gas is mixed with air. If the gas is mixed with air before ignition, the subsequent reaction is known as premixed combustion. In a burner the combustion is controlled, but if a large volume of a gas/air mixture is ignited a gas explosion results.

In most fires ignition results in the development of diffusion flames where combustible gas comes in contact with air without being previously mixed.

Gas mixtures can be ignited in two basic ways:

a) auto-ignition – where the temperature of all the gas mixture is raised, and

b) piloted ignition – where a local source of heat is introduced, e.g. a flame or an electrical spark.

Some fires are the result of the ignition of a material which is already in the gaseous state, but combustible gases can also be produced by the vaporization of liquids (see 4.2) or by the pyrolysis of solids (see 4.3).

4.1.1 Flammability limits

Flame propagation cannot occur in a fuel/air gas mixture if the fuel concentration is too low or too high. The limiting concentration values are known as the lower flammability limit (LFL) and the upper flammability limit (UFL). These limits arise because flames need a minimum temperature to exist. Too much air or fuel prevents the temperature being maintained at a sufficiently high level. Flammability limits are normally expressed as the percentage of fuel, by volume, in the fuel/air mixture.

4.1.2 Arc fires

Faults in some electrical equipment such as junction boxes and power transformers can result in disruptive electrical discharges (electric arcs) which can pyrolyse insulation materials to produce high temperature combustible gases. Such gases expand rapidly and in contact with air can result in an explosion (see 5.3.3.4).

4.2 Liquids

4.2.1 Introduction

With the exception of some unstable or reactive substances, liquids do not generally ignite. Normally it is combustible vapour which ignites. The combustible vapour is produced by vaporization of the liquid, and the vaporization process is dependent on the temperature and chemical composition of the liquid.

4.2.2 Ignition parameters

Temperature is normally used to define the ignitability of a liquid. Three different temperatures are used. These are the auto ignition temperature (see 3.1), the fire point (see 3.5) and the flash point (see 3.13). Auto ignition refers to ignition in the absence of a localized heat