



SLOVENSKI STANDARD

SIST EN ISO 787-11:1997

01-december-1997

Splošne metode preskušanja pigmentov in polnil - 11. del: Določanje navideznega nasipnega volumna in navidezne nasipne gostote po steptanju (ISO 787-11:1981)

General methods of test for pigments and extenders - Part 11: Determination of tamped volume and apparent density after tamping (ISO 787-11:1981)

Allgemeine Prüfverfahren für Pigmente und Füllstoffe - Teil 11: Bestimmung des Stampfvolumens und der Stampfdichte (ISO 787-11:1981)

Méthodes générales d'essai des pigments et matières de charge - Partie 11: Détermination de la masse volumique apparente et de la masse apparente apres tassement (ISO 787-11:1981)

ITEH STANDARD PREVIEW
(standards.iteh.ai)
SIST EN ISO 787-11:1997
<https://standards.iteh.ai/catalog/standards/sist/672cb145-2e03-4129-a2f8-fb24d1701d81/sist-en-iso-787-11-1997>

Ta slovenski standard je istoveten z: EN ISO 787-11:1995

ICS:

87.060.10 Pigmenti in polnila Pigments and extenders

SIST EN ISO 787-11:1997 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 787-11:1997](#)

<https://standards.iteh.ai/catalog/standards/sist/672cb145-2e03-4129-a2f8-fb24d1701d81/sist-en-iso-787-11-1997>

EUROPEAN STANDARD

EN ISO 787-11

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 1995

ICS 87.060.10; 87.060.30

Descriptors: paints, pigments, tests, chemical analysis, determination, density measurement, volume, volumeters

English version

**General methods of test for pigments and
extenders - Part 11: Determination of tamped
volume and apparent density after tamping
(ISO 787-11:1981)**

Méthodes générales d'essai des pigments et
matières de charge - Partie 11: Détermination
du masse volumique apparent et de la masse
apparente après tassement (ISO 787-11:1981)

Allgemeine Prüfverfahren für Pigmente und
Füllstoffe - Teil 11: Bestimmung des
Stampfvolumens und der Stampfdichte
(ISO 787-11:1981)

(standards.iteh.ai)

SIST EN ISO 787-11:1997

<https://standards.iteh.ai/catalog/standards/sist/672cb145-2e03-4129-a2f8-fb24d1701d81/sist-en-iso-787-11-1997>

This European Standard was approved by CEN on 1995-03-23. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

© 1995

All rights of reproduction and communication in any form and by any means reserved in all countries to CEN and its members.

Ref. No. EN ISO 787-11:1995 E

Page 2
EN ISO 787-11:1995

Foreword

The text of the International Standard from ISO/TC 35 "Paints and varnishes" of the International Organization for Standardization (ISO) has been taken over as a European Standard by the Technical Committee CEN/TC 298 "Pigments and extenders".

This European Standard shall be given the status of a National Standard, either by publication of an identical text or by endorsement, at the latest by February 1996, and conflicting national standards shall be withdrawn at the latest by February 1996.

According to CEN/CENELEC Internal Regulations, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 787-11:1981 has been approved by CEN as a European Standard without any modification.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 787-11:1997](https://standards.iteh.ai/catalog/standards/sist/672cb145-2e03-4129-a2f8-fb24d1701d81/sist-en-iso-787-11-1997)

<https://standards.iteh.ai/catalog/standards/sist/672cb145-2e03-4129-a2f8-fb24d1701d81/sist-en-iso-787-11-1997>

International Standard



787/11

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

General methods of test for pigments and extenders — Part 11 : Determination of tamped volume and apparent density after tamping

Méthodes générales d'essai des pigments et matières de charge — Partie 11 : Détermination du volume massique apparent et de la masse volumique apparente après tassement

First edition — 1981-10-01

ITeH STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 787-11:1997](https://standards.iteh.ai/catalog/standards/sist/672cb145-2e03-4129-a2f8-fb24d1701d81/sist-en-iso-787-11-1997)

<https://standards.iteh.ai/catalog/standards/sist/672cb145-2e03-4129-a2f8-fb24d1701d81/sist-en-iso-787-11-1997>

UDC 667.622 : 531.755

Ref. No. ISO 787/11-1981 (E)

Descriptors : paints, pigments, tests, chemical analysis, determination, density measurement, volume, voltmeters.

Price based on 3 pages

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 787/11 was developed by Technical Committee ISO/TC 35, *Paints and varnishes*, and was circulated to the member bodies in January 1980.

iTeH STANDARD PREVIEW
(standards.iteh.ai)

It has been approved by the member bodies of the following countries:

| | | |
|---------------------|----------------|-----------------------|
| Australia | Ireland | Romania |
| Austria | Israel | South Africa, Rep. of |
| Brazil | Italy | Spain |
| China | Kenya | Sweden |
| Egypt, Arab Rep. of | Korea, Rep. of | Switzerland |
| France | Netherlands | United Kingdom |
| Germany, F. R. | New Zealand | USSR |
| Hungary | Norway | |
| India | Poland | |

No member body expressed disapproval of the document.

This International Standard cancels and replaces ISO Recommendation R 787/11-1970, of which it constitutes a technical revision.

The purpose of this International Standard is to establish a series of general test methods for pigments and extenders which are suitable for all or many of the individual pigments and extenders for which specifications might be required. In such cases, a cross-reference to the general method should be included in the International Standard relating to that pigment or extender, with a note of any detailed modifications which might be needed in view of the special properties of the product in question.

Technical Committee ISO/TC 35, *Paints and varnishes*, decided that all the general methods should be published as they become available, as parts of a single International Standard, in order to emphasize the relationship of each to the whole series.

The Technical Committee also decided that, where two or more procedures were widely used for determining the same or a similar characteristic of a pigment or extender, there would be no objection to including more than one of them in the ISO series. In such cases it will, however, be essential to state clearly in a specification which method is to be used and, in the test report, which method has been used.

Parts of the series already published are as follows :

<https://standards.iteh.ai/catalog/standards/sist/672cb145-2e03-4129-a2f8-fb2701d80000/iso-787-11-1997>

- Part 1 : Comparison of colour of pigments
- Part 2 : Determination of matter volatile at 105 °C
- Part 3 : Determination of matter soluble in water — Hot extraction method
- Part 4 : Determination of acidity or alkalinity of the aqueous extract
- Part 5 : Determination of oil absorption value
- Part 6 : Determination of residue on sieve — Oil method
- Part 7 : Determination of residue on sieve — Water method — Manual procedure
- Part 8 : Determination of matter soluble in water — Cold extraction method
- Part 9 : Determination of pH value of an aqueous suspension
- Part 10 : Determination of density — Pyknometer method
- Part 11 : Determination of tamped volume and apparent density after tamping
- Part 13 : Determination of water-soluble sulphates, chlorides and nitrates
- Part 14 : Determination of resistivity of aqueous extract
- Part 15 : Comparison of resistance of coloured pigments of similar types to light from a specified light source
- Part 16 : Comparison of relative tinting strength (or equivalent colouring value) and colour on reduction in linseed stand oil using the automatic muller
- Part 17 : Comparison of lightening power of white pigments
- Part 18 : Determination of residue on sieve — Water method — Mechanical flushing procedure
- Part 19 : Determination of water-soluble nitrates — Salicylic acid method
- Part 20 : Comparison of ease of dispersion — Oscillatory shaking method
- Part 21 : Comparison of heat stability of pigments using a stoving medium
- Part 22 : Comparison of resistance to bleeding of pigments
- Part 23 : Determination of density (using a centrifuge to remove entrained air)
- Part 24 : Determination of relative tinting strength of coloured pigments and relative scattering power of white pigments — Photometric method

iTeh STANDARD PREVIEW
This page intentionally left blank
(standards.iteh.ai)

[SIST EN ISO 787-11:1997](https://standards.iteh.ai/catalog/standards/sist/672cb145-2e03-4129-a2f8-fb24d1701d81/sist-en-iso-787-11-1997)

<https://standards.iteh.ai/catalog/standards/sist/672cb145-2e03-4129-a2f8-fb24d1701d81/sist-en-iso-787-11-1997>

General methods of test for pigments and extenders — Part 11 : Determination of tamped volume and apparent density after tamping

0 Introduction

This document is a part of ISO 787, *General methods of test for pigments and extenders*.

1 Scope and field of application

This part of ISO 787 specifies a general method of test for determining the tamped volume and the apparent density after tamping of a sample of pigment or extender.

NOTE — When this general method is applicable to a given pigment or extender, only a cross-reference to it should be included in the International Standard relating to that pigment or extender, with a note of any detailed modification which may be needed in view of the special properties of the material in question. Only when this general method is not applicable to a particular material should a special method for determination of tamped volume and apparent density after tamping be specified.

2 References

ISO 565, *Test sieves — Woven metal wire cloth and perforated plate — Nominal sizes of apertures*.

ISO 842, *Raw materials for paints and varnishes — Sampling*.

ISO 4788, *Laboratory glassware — Graduated measuring cylinders*.

3 Apparatus

Ordinary laboratory apparatus and

3.1 Sieve, of diameter 100 or 200 mm, with a nominal mesh aperture of 500 μm , complying with the requirements of ISO 565.

NOTE — If necessary or specified, it is permissible to use sieves with other nominal mesh apertures or diameters. It is, however, recommended that the nominal mesh aperture chosen should correspond to one of the principal sizes given in ISO 565.

3.2 Tamping volumeter (see the figure), composed of the following items.

3.2.1 Measuring cylinder of capacity 250 ml, complying with the requirements of ISO 4788, fitted with a suitable stopper, and with graduation marks at 2 ml intervals.

3.2.2 Holder for the measuring cylinder (3.2.1), with shaft. The total mass of the cylinder, stopper and shaft shall be 670 ± 45 g.

3.2.3 Cam, which lifts the shaft with the measuring cylinder once per revolution and which has a rotational frequency of 250 ± 15 r/min.

3.2.4 Anvil, so placed that the raised shaft falls from a height of $3 \pm 0,1$ mm over the anvil.

3.2.5 Revolution counter, to count the number of revolutions of the cam.

3.2.6 Sleeve, to guide the shaft, constructed of a suitable material to give minimum friction.

NOTE — The apparatus should be so constructed that, without undue free play, the friction between the shaft and the sleeve is as low as possible without the use of a lubricant.

3.3 Oven, capable of being maintained at 105 ± 2 °C.

3.4 Balance, accurate to 0,5 g or better.

3.5 Desiccator, containing an efficient desiccant.

4 Sampling

Take a representative sample of the material to be tested as described in ISO 842.