



# SLOVENSKI STANDARD SIST EN ISO 787-23:1997

01-december-1997

---

## Splošne metode preskušanja pigmentov in polnil - 23. del: Določanje gostote (uporaba centrifuge za odstranitev ujetega zraka) (ISO 787-23:1979)

General method of tests for pigments and extenders - Part 23: Determination of density (using a centrifuge to remove entrained air) (ISO 787-23:1979)

Allgemeine Prüfverfahren für Pigmente und Füllstoffe - Teil 23: Bestimmung der Dichte (unter Verwendung einer Zentrifuge zum Entfernen eingeschlossener Luft) (ISO 787-23:1979)

(standards.iteh.ai)

Méthodes générales d'essai des pigments et matières de charge - Partie 23: Détermination de la masse volumique (en utilisant une centrifugeuse pour chasser l'air entrainé) (ISO 787-23:1979)

**Ta slovenski standard je istoveten z: EN ISO 787-23:1995**

---

### **ICS:**

87.060.10      Pigmenti in polnila                      Pigments and extenders

**SIST EN ISO 787-23:1997**                      **en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 787-23:1997](https://standards.iteh.ai/catalog/standards/sist/67667672-63e7-4f4e-879d-505c380a5ad9/sist-en-iso-787-23-1997)

<https://standards.iteh.ai/catalog/standards/sist/67667672-63e7-4f4e-879d-505c380a5ad9/sist-en-iso-787-23-1997>

EUROPEAN STANDARD

EN ISO 787-23

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 1995

ICS 87.060.10; 87.060.30

Descriptors: paints, pigments, tests, density measurement

English version

**General methods of tests for pigments and  
extenders - Part 23: Determination of density  
(using a centrifuge to remove entrained air)  
(ISO 787-23:1979)**

Méthodes générales d'essai des pigments et  
matières de charge - Partie 23: Détermination  
de la masse volumique (en utilisant une  
centrifugeuse pour chasser l'air entraîné)  
(ISO 787-23:1979)

Allgemeine Prüfverfahren für Pigmente und  
Füllstoffe - Teil 23: Bestimmung der Dichte  
(unter Verwendung einer Zentrifuge zum  
Entfernen eingeschlossener Luft)  
(ISO 787-23:1979)

<https://standards.iteh.ai/catalog/standards/sist/67667672-63e7-4f4e-879d-505c380a5ad9/sist-en-iso-787-23-1997>

This European Standard was approved by CEN on 1995-03-23. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

## CEN

European Committee for Standardization  
Comité Européen de Normalisation  
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

© 1995

All rights of reproduction and communication in any form and by any means reserved in all countries to CEN and its members.

Ref. No. EN ISO 787-23:1995 E

## Foreword

The text of the International Standard from ISO/TC 35 "Paints and varnishes" of the International Organization for Standardization (ISO) has been taken over as a European Standard by the Technical Committee CEN/TC 298 "Pigments and extenders".

This European Standard shall be given the status of a National Standard, either by publication of an identical text or by endorsement, at the latest by February 1996, and conflicting national standards shall be withdrawn at the latest by February 1996.

According to CEN/CENELEC Internal Regulations, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

## Endorsement notice

The text of the International Standard ISO 787-23:1979 has been approved by CEN as a European Standard without any modification.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 787-23:1997](https://standards.iteh.ai/catalog/standards/sist/67667672-63e7-4f4e-879d-505c380a5ad9/sist-en-iso-787-23-1997)

<https://standards.iteh.ai/catalog/standards/sist/67667672-63e7-4f4e-879d-505c380a5ad9/sist-en-iso-787-23-1997>

---

# International Standard



# 787/23

---

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

---

## General methods of test for pigments and extenders — Part 23 : Determination of density (using a centrifuge to remove entrained air)

*Méthodes générales d'essai des pigments et matières de charge —  
Partie 23 : Détermination de la masse volumique (en utilisant une centrifugeuse pour chasser l'air entrainé)*

First edition — 1979-12-27

(standards.iteh.ai)

[SIST EN ISO 787-23:1997](https://standards.iteh.ai/catalog/standards/sist/67667672-63e7-4f4e-879d-505c380a5ad9/sist-en-iso-787-23-1997)

<https://standards.iteh.ai/catalog/standards/sist/67667672-63e7-4f4e-879d-505c380a5ad9/sist-en-iso-787-23-1997>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 787/23 was developed by Technical Committee ISO/TC 35, *Paints and varnishes*, and was circulated to the member bodies in March 1978.

It has been approved by the member bodies of the following countries:

Austria	Ireland	Poland
Bulgaria	Israel	Romania
Canada	Italy	South Africa, Rep. of
Egypt, Arab Rep. of	Kenya	Sweden
France	Korea, Rep. of	Switzerland
Germany, F. R.	Netherlands	Turkey
India	New Zealand	United Kingdom
Iran	Norway	Yugoslavia

No member body expressed disapproval of the document.

The purpose of this International Standard is to establish a series of general test methods for pigments and extenders which are suitable for all or many of the individual pigments and extenders for which specifications might be required. In such cases, a cross-reference to the general method should be included in the International Standard relating to that pigment or extender, with a note of any detailed modifications which might be needed in view of the special properties of the product in question.

Technical Committee ISO/TC 35 decided that all the general methods should be published as they become available, as parts of a single International Standard, in order to emphasize the relationship of each to the whole series.

The Technical Committee also decided that, where two or more procedures were widely used for determining the same or a similar characteristic of a pigment or extender, there would be no objection to including more than one of them in the ISO series. In such cases it will, however, be essential to state clearly in a specification which method is to be used and, in the test report, which method has been used.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

Parts of the series already published are as follows :

- Part 1 : Comparison of colour
- Part 2 : Determination of matter volatile at 105 °C
- Part 3 : Determination of matter soluble in water — Hot extraction method
- Part 4 : Determination of acidity or alkalinity of the aqueous extract
- Part 5 : Determination of oil absorption value
- Part 6 : Determination of residue on sieve — Oil method
- Part 7 : Determination of residue on sieve — Water method
- Part 8 : Determination of matter soluble in water — Cold extraction method
- Part 9 : Determination of pH value of an aqueous suspension
- Part 10 : Determination of density — Pyknometer method
- Part 11 : Determination of tamped volume and apparent density after tamping
- Part 12 : Visual comparison of hue of powdered white pigment (Hollow cone method)<sup>1)</sup>
- Part 13 : Determination of water-soluble sulphates, chlorides and nitrates
- Part 14 : Determination of resistivity of aqueous extract
- Part 15 : Comparison of resistance of coloured pigments of similar types to light from a specified light source
- Part 16 : Comparison of relative tinting strength (or equivalent colouring value) and colour on reduction in linseed stand oil using the automatic muller
- Part 17 : Comparison of lightening power of white pigments
- Part 18 : Determination of residue on sieve by a mechanical flushing procedure
- Part 19 : Determination of water-soluble nitrates — Salicylic acid method
- Part 20 : Comparison of ease of dispersion — Oscillatory shaking method
- Part 21 : Comparison of heat stability of pigments using a stoving medium
- Part 22 : Comparison of resistance to bleeding of pigments
- Part 23 : Determination of density (using a centrifuge to remove entrained air)

1) This part will be withdrawn as the specified method is no longer in use.

**iTeh STANDARD PREVIEW**  
This page intentionally left blank  
**(standards.iteh.ai)**

[SIST EN ISO 787-23:1997](#)

<https://standards.iteh.ai/catalog/standards/sist/67667672-63e7-4f4e-879d-505c380a5ad9/sist-en-iso-787-23-1997>



# General methods of test for pigments and extenders — Part 23 : Determination of density (using a centrifuge to remove entrained air)

## 0 Introduction

This document is a part of ISO 787, *General methods of test for pigments and extenders*.

## 1 Scope and field of application

**1.1** Part 23 of this International Standard specifies a general method of test for determining the density of a sample of pigment or extender, using a centrifuge to remove entrained air.

NOTE — When this general method is applicable to a given pigment or extender, only a cross-reference to it should be included in the International Standard relating to that pigment or extender, with a note of any detailed modification which may be needed in view of the special properties of the material in question. Only when this general method is not applicable to a particular material should a special method for determination of density using a centrifuge be specified.

**1.2** Part 10 of this International Standard specifies a general method of test for determining the density of a sample of pigment or extender, using a pycnometer.

## 2 References

ISO 787, *General methods for pigments and extenders — Part 10 : Determination of density — Pycnometer method*.<sup>1)</sup>

ISO 842, *Raw materials for paints and varnishes — Sampling*.

## 3 Preliminary considerations

### 3.1 Displacement liquids of known density

A liquid should be selected in which the material to be tested is insoluble, and which has good wetting properties and a low evaporation rate under vacuum. High-boiling aromatic or aliphatic hydrocarbon solvents with a boiling point over 170 °C are suitable.

Particular care, however, may be necessary in the selection of the liquid if carbon black or organic dyestuffs are to be examined.

### 3.2 Temperature of the determination

The temperature  $t$  at which the determination is carried out will significantly affect the density of the displacement liquid used, but not that of the material tested. When using this method, therefore, it is most important that each weighing should be made at a constant temperature. It is desirable that a constant temperature room or enclosure should be used but if these are not available the temperature at which each weighing is made should be noted and corrections made to the density of the displacement liquid.

## 4 Apparatus

**4.1 Centrifuge tube** of glass or other suitable material such as polypropylene or stainless steel.

**4.2 Cradle and loop** of fine platinum or nickel-chromium wire not more than 0,12 mm diameter to suspend the tube from the balance.

**4.3 Glass stirring rod**, slightly longer than the tube (4.1).

**4.4 Centrifuge**, laboratory type.

**4.5 Sieve**, with nominal mesh aperture of 500  $\mu\text{m}$ .

**4.6 Balance**, accurate to 1 mg or better.

## 5 Sampling

Take a representative sample of the material to be tested as described in ISO 842.

1) At present at the stage of draft. (Revision of ISO/R 787/10-1970.)