



SLOVENSKI STANDARD

SIST ISO 2470:2002

01-maj-2002

Papir, karton in lepenka - Merjenje faktorja razpršene odsevnosti v modrem (belina po ISO)

Paper, board and pulps -- Measurement of diffuse blue reflectance factor (ISO brightness)

iTeh STANDARD PREVIEW

Papier, carton et pâtes -- Mesurage du facteur de réflectance diffuse dans le bleu (degré de blancheur ISO)

[SIST ISO 2470:2002](https://standards.iteh.ai/catalog/standards/sist/7467947d-de7e-4080-b5bc-d10c1f672fc/sist-iso-2470-2002)

Ta slovenski standard je istoveten z: **ISO 2470:1999**

ICS:

85.040	Vlaknine	Pulps
85.060	Papir, karton in lepenka	Paper and board

SIST ISO 2470:2002 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 2470:2002

<https://standards.iteh.ai/catalog/standards/sist/7467947d-de7e-4080-b5bc-d1f6e1f672fc/sist-iso-2470-2002>

INTERNATIONAL
STANDARD

ISO
2470

Third edition
1999-10-15

**Paper, board and pulps — Measurement
of diffuse blue reflectance factor
(ISO brightness)**

*Papier, carton et pâtes — Mesurage du facteur de réflectance diffuse dans
le bleu (degré de blancheur ISO)*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 2470:2002](https://standards.iteh.ai/catalog/standards/sist/7467947d-de7e-4080-b5bc-d1f6e1f672fc/sist-iso-2470-2002)

[https://standards.iteh.ai/catalog/standards/sist/7467947d-de7e-4080-b5bc-
d1f6e1f672fc/sist-iso-2470-2002](https://standards.iteh.ai/catalog/standards/sist/7467947d-de7e-4080-b5bc-d1f6e1f672fc/sist-iso-2470-2002)



Reference number
ISO 2470:1999E)

ISO 2470:1999(E)**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 2470 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Working Group WG 3, *Optical properties*.

This third edition cancels and replaces the second edition (ISO 2470:1977). This edition differs from the 1977 edition in that it describes the use of abridged spectrophotometers and also prescribes a routine for adjusting the relative UV-content of the illumination in this type of instrument to a defined level when materials containing fluorescent whitening agents are to be measured.

Annexes A and B form a normative part of this International Standard.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 2470:2002

<https://standards.iteh.ai/catalog/standards/sist/7467947d-de7e-4080-b5bc-d1f6e1f672fc/sist-iso-2470-2002>

© ISO 1999

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet iso@iso.ch

Printed in Switzerland

Introduction

The reflectance factor depends on the conditions of measurement, particularly the spectral and geometric characteristics of the instrument used. This International Standard should therefore be read in conjunction with ISO 2469 which defines the geometric characteristics of the instrument and the calibration procedure. This edition of ISO 2470 differs from the 1977 edition in that it describes the use of abridged spectrophotometers and also prescribes a routine for adjusting the relative UV-content of the illumination in this type of instrument to a defined level when materials containing fluorescent whitening agents are to be measured.

The definition of ISO brightness is historically linked to the Zeiss Elrepho instrument having as a light source an incandescent lamp which excites fluorescence to only a limited extent. It is specified here that, in instruments of the abridged spectrophotometer type, the UV-content of the illumination be adjusted using a suitable filter to conform to the CIE illuminant C as defined by a fluorescent reference standard having an assigned value of ISO brightness as described in annex B. Only if this is done may the property measured on a fluorescent material be called ISO brightness.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 2470:2002](https://standards.iteh.ai/catalog/standards/sist/7467947d-de7e-4080-b5bc-d1f6e1f672fc/sist-iso-2470-2002)

<https://standards.iteh.ai/catalog/standards/sist/7467947d-de7e-4080-b5bc-d1f6e1f672fc/sist-iso-2470-2002>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 2470:2002

<https://standards.iteh.ai/catalog/standards/sist/7467947d-de7e-4080-b5bc-d1f6e1f672fc/sist-iso-2470-2002>

Paper, board and pulps — Measurement of diffuse blue reflectance factor (ISO brightness)

1 Scope

This International Standard specifies a method for measuring the diffuse blue reflectance factor (ISO brightness) of pulps, papers and boards.

This International Standard is limited in its scope to white and near-white pulps, papers and boards. Materials exhibiting fluorescence which promotes the appearance of whiteness may be measured but the ultraviolet energy level of the illumination must be adjusted using a fluorescent calibration standard if standardization and agreement between instruments is to be achieved.

NOTE A brightness value associated with an instrument setting adjusted to conform to the CIE standard illuminant D65 (cf. ISO 11475^[1]), which has a much higher UV-content than the CIE illuminant C specified in this International Standard, is outside the scope of this International Standard and consequently is not "ISO brightness". Such a property may be called "D65 brightness".

iTeh STANDARD PREVIEW
(standards.iteh.ai)

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 186, *Paper and board — Sampling to determine average quality.*

ISO 2469, *Paper, board and pulps — Measurement of diffuse reflectance factor.*

ISO 3688, *Pulps — Preparation of laboratory sheets for the measurement of diffuse blue reflectance factor (ISO brightness).*

ISO 4094, *Paper, board and pulps — International calibration of testing apparatus — Nomination and acceptance of standardizing and authorized laboratories.*

ISO 7213, *Pulps — Sampling for testing.*

3 Terms and definitions

For the purposes of this International Standard, the following terms and definitions apply.

3.1 reflectance factor

R
ratio, expressed as a percentage, of the radiation reflected by a body to that reflected by the perfect reflecting diffuser under the same conditions

3.2

intrinsic reflectance factor

R_{∞}

reflectance factor of a layer or pad of material thick enough to be opaque, i.e. such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured reflectance factor

3.3

diffuse blue reflectance factor

ISO brightness

R_{457}

intrinsic reflectance factor measured with a reflectometer having the characteristics described in ISO 2469, equipped with a filter or corresponding function having an effective wavelength of 457 nm and a width at half-height of 44 nm, and adjusted so that the UV-content of the illumination incident upon the test piece corresponds to that of the CIE illuminant C

NOTE 1 In the 1994 edition of ISO 2469 the reflectometer characteristics are described in annex A. When ISO 2469 is revised, the numbering may change; users of editions subsequent to 1994 should therefore determine which elements of text specify these characteristics.

NOTE 2 The filter function is described more fully by the weighting function factors given in annex A and Table A.1.

4 Principle

A test piece is illuminated diffusely in a standard instrument and the light reflected normal to the surface is either allowed to pass through a defined glass filter and then measured by a photocell or measured by an array of diodes, where each diode responds to a different effective wavelength. The brightness is then determined directly from the output from the photocell, or by calculation from the diode outputs using the appropriate weighting function.

5 Apparatus

SIST ISO 2470:2002

[https://standards.iteh.ai/catalog/standards/sist/7467947d-de7e-4080-b5bc-](https://standards.iteh.ai/catalog/standards/sist/7467947d-de7e-4080-b5bc-418c18726/sist-iso-2470-2002)

5.1 Reflectometer, having the geometric, spectral and photometric characteristics described in ISO 2469 and calibrated in accordance with the provisions of ISO 2469, and equipped for the measurement of blue reflectance factor.

NOTE In the 1994 edition of ISO 2469 the reflectometer characteristics are described in annex A and the calibration service is described in annex B. When ISO 2469 is revised, the numbering may change; users of editions subsequent to 1994 should therefore determine which elements of text specify these characteristics and this service.

5.1.1 In the case of a filter reflectometer, the radiation falling upon the test piece shall have a UV-content corresponding to that of the CIE illuminant C.

5.1.2 In the case of an abridged spectrophotometer, the instrument shall have an adjustable filter with a cut-off wavelength of 395 nm, and this filter shall be adjusted with the help of the fluorescent reference standard (5.2.2), so that the UV-content of the illumination falling upon the sample corresponds to that of the CIE illuminant C. For this purpose, a reference standard with an assigned ISO-brightness value provided by an ISO/TC 6 authorized laboratory is required.

5.2 Reference standards for calibration of the instrument and the working standards

Use reference standards sufficiently frequently to ensure satisfactory calibration and UV-adjustment.

5.2.1 Non-fluorescent reference standard, for photometric calibration, issued by an ISO/TC 6 authorized laboratory in accordance with the provisions of ISO 2469.

5.2.2 Fluorescent reference standard, for use in adjusting the UV-content of the radiation incident upon the sample, having an ISO-brightness value assigned as prescribed in annex B.

5.3 Working standards

5.3.1 Two plates of flat opal glass or ceramic material, cleaned and calibrated as described in ISO 2469.

NOTE In some instruments, the function of the primary working standard may be taken over by a built-in internal standard.

5.3.2 A stable plastic or other tablet, incorporating a fluorescent whitening agent.

5.4 Black cavity, having a reflectance factor which does not differ from its nominal value by more than 0,2 %, at all wavelengths. The black cavity should be stored upside down in a dust-free environment or with a protective cover.

NOTE The condition of the black cavity can be checked by reference to the instrument maker.

6 Sampling

If the tests are being made to evaluate a lot of paper or board, the sample shall be selected in accordance with ISO 186. If the tests are being made to evaluate a lot of pulp, the sample shall be selected in accordance with ISO 7213. If the tests are made on another type of sample, make sure that the test pieces taken are representative of the sample received.

7 Preparation of test pieces

7.1 Pulp

Prepare sheets in accordance with ISO 3688. Remove the protective filter papers and assemble the test sheets in a pad, with the top side uppermost. Laboratory sheets of sufficient size may be cut into several test pieces.

[SIST ISO 2470:2002](https://standards.iteh.ai/catalog/standards/sist/7467947d-de7e-4080-b5bc-d1f6e1f672fc/sist-iso-2470-2002)

7.2 Paper or board <https://standards.iteh.ai/catalog/standards/sist/7467947d-de7e-4080-b5bc-d1f6e1f672fc/sist-iso-2470-2002>

Avoiding watermarks, dirt and obvious defects, cut rectangular test pieces of approximately 75 mm × 150 mm. Assemble at least ten of the test pieces in a pad with their top sides uppermost; the number should be such that doubling the number of test pieces does not alter the reflectance factor. Protect the pad by placing an additional sheet on both the top and bottom of the pad. Avoid contamination and unnecessary exposure to light or heat.

Mark the top test piece in one corner to identify the sample and its top side.

If the top side can be distinguished from the wire side, it shall be uppermost; if not, as may be the case for papers manufactured on twin-wire machines, ensure that the same side of the sheet is uppermost.

8 Procedure

8.1 Calibrate the instrument according to the instrument maker's instructions, using a non-fluorescent ISO reference standard of level 3 (IR 3) (5.2.1) or a working standard calibrated in relation to an IR 3 (5.3.1). If the instrument is of the abridged spectrophotometer type, and if the material to be measured contains or is suspected to contain a fluorescent component, adjust the UV-content of the illumination using the fluorescent (5.2.2) and non-fluorescent (5.2.1) ISO level 3 standards in an iterative procedure according to the instrument maker's instructions.

8.2 Remove the protective sheets from the test piece pad. Without touching the test area, use the procedure appropriate to the instrument, and the working standard, to measure the intrinsic blue reflectance factor of the top side of the test piece pad. Read and record the value to the nearest 0,05 % reflectance factor.

8.3 Move the measured test piece to the bottom of the pad and determine the intrinsic blue reflectance factor for the next and similarly for the following test pieces, until a total of not less than ten test pieces has been measured or, in the case of pulp, until all the test sheets have been measured.