INTERNATIONAL STANDARD



INTERNATIONAL ORGANIZATION FOR STANDARDIZATION ORGANISATION INTERNATIONALE DE NORMALISATION MEЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ

Sterile hypodermic needles for single use

Aiguilles hypodermiques stériles, non réutilisables

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 7864:1988</u> https://standards.iteh.ai/catalog/standards/sist/57df2045-7898-4f0d-86f4-96ee055076ec/iso-7864-1988

> Reference number ISO 7864:1988 (E)

84

ISO

7864

Second edition 1988-08-15

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting A DARD PREVIE

International Standard ISO 7864 was prepared by Technical Committee ISO/TC 84, Syringes for medical use and needles for injections.

<u>SO 7864:1988</u>

This second edition cancels and replaces the first edition (ISO 7864 ; 1984), of which it 8-410d-8674constitutes a minor revision (re-designation of the needle length, addition of new tolerances on the needle length, and correction of error in B.1.2 as regards the International Standard referenced for aspiration testing).

Users should note that all International Standards undergo revision from time to time and that any reference made herein to any other International Standard implies its latest edition, unless otherwise stated.

© International Organization for Standardization, 1988

Printed in Switzerland

Dag

Contents

		ige
0	Introduction	1
an di san ang ang ang ang ang ang ang ang ang a	Scope and field of application	1
2	References	1
3	Nomenclature	1
4	Materials	2
5	Manufacture	2
iTeh STA	Freedom from pyrogenic materials	2
(sta	Test for abnormal toxicity	2
8	Freedom from extraneous matter	2
https://standards.iteh.a%	aLingistor extractable matter-7898-4004-86f4-	2
96 10	ce055076cc/iso-7864-1988 Lubrication of hypodermic needles	3
11	Size designation	3
12	Range of sizes	3
13	Needle hub	3
14	Sheath	3
15	Needle tube	3
16	Test requirements for needle assembly	4
17	Packaging	5
18	Sterility	5
19	Marking of containers	5
An	nexes	
А	Preparation of extracts	6
B	Testing of conical fitting for integrity of needle assembly on aspiration	6
С	Resistance to corrosion	7
D	Test for resistance of needle tubes to breakage	7

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 7864:1988</u> https://standards.iteh.ai/catalog/standards/sist/57df2045-7898-4f0d-86f4-96ee055076ec/iso-7864-1988

Sterile hypodermic needles for single use

0 Introduction

This International Standard deals with products primarily in **PD** tended for use with humans and provides performance requirements, but permits some variation of design and of the methods of packaging and sterilization by individual manufacturers.

Materials to be used for the construction of hubs for sterileds/sist/hypode needles for single use are not specified in detail as their selector -7864-1988 tion will depend to some extent upon the design, process of manufacture and method of sterilization employed by individual manufacturers. The materials should be compatible with injection fluids included in relevant pharmacopoeias.

The majority of injections are in aqueous media. Such media are not known to give problems. It is usual for non-aqueous injections to be formulated in either ester type solvent or the active ingredient itself may be fluid.

Tests for freedom from pyrogenic material, abnormal toxicity and certain chemical tests for extractable material are included in clauses 6, 7 and 9 respectively.

Annexes A, B, C and D form an integral part of this International Standard.

In some countries national pharmacopoeias or other government regulations are legally binding and their requirements may take precedence over this International Standard.

Hypodermic needles specified in this International Standard are intended for use with hypodermic syringes specified in

1) ISO 595, Reusable all-glass or metal-and-glass syringes for medical use – Part 1 : Dimensions.

Part 2 : Design, performance requirements and tests.

2) At present at the stage of draft. (Revision, in part, of ISO/R 594 : 1967.)

ISO 595¹⁾ and ISO 7886. The 6 % taper conical fitting (Luer) specified is in conformity with ISO 594.

Scope and field of application

ISO 7864:1988 This International Standard specifies requirements for sterile Materials to be used for the construction of hubs for sterile s/sist/hypodermic needles for single use.

2 References

ISO 594, Conical fitting with a 6 % (Luer) taper for syringes, needles and certain other medical equipment –

Part 1 : General requirements.

Part 2 : Lock fittings.²⁾

ISO 6009, Hypodermic needles for single use — Colour coding for identification.

ISO 7886, Sterile hypodermic syringes for single use.

3 Nomenclature

The nomenclature of components of hypodermic needles for single use is illustrated in the figure.

1



NOTE - The drawing is intended to illustrate the nomenclature of a typical hypodermic needle, but does not otherwise form part of the specification.

Figure — Typical hypodermic needle for single use

standar

iTeh STANDARD PREVIEW 7 Test for abnormal toxicity

4 Materials

4.1 Materials used in the manufacture of hypodermic needles shall be suitable for their intended use and the process to be used for sterilization.

Hypodermic needles shall be capable of satisfying the test for abnormal toxicity specified in the relevant national pharmaconogia

https://standards.iteh.ai/catalog/standards/sist/57df2045-7898-4f0d-86f4-

4.2 Materials used in the manufacture of hypodermic needles shall not cause them to be detrimentally affected, physically or chemically, by the normal use of injectable preparations.

4.3 Materials used in the manufacture of hypodermic needles shall not cause them to yield, under conditions of normal use, significant amounts of toxic substances and shall permit them to satisfy the requirements for freedom from pyrogenic materials (see clause 6), abnormal toxicity (see clause 7) and tests for extractable matter (see clause 9).

5 Manufacture

Hypodermic needles shall be manufactured in accordance with recognized national or international codes of good manufacturing practice and shall be substantially free from defects affecting appearance, safety and serviceability for the intended use.

6 Freedom from pyrogenic materials

Hypodermic needles shall be capable of satisfying the test for freedom from pyrogenic materials in accordance with the relevant national pharmacopoeia.

The extract to be used in the test shall be prepared as described in clause A.2.

macopoeia. /sist/57df2045-7898-4f0d-86f4-

The extract to be used in the test shall be prepared as described in clause A.2.

8 Freedom from extraneous matter

The surface of the hypodermic needle shall be clean and free from extraneous matter when viewed by normal or corrected vision without magnification.

9 Limits for extractable matter

9.1 General

Hypodermic needles shall be capable of satisfying the chemical tests for extractable matter in accordance with the relevant national pharmacopoeia.

9.2 Limits for acidity or alkalinity

The pH-value of the needle extract, prepared as described in clause A.3, shall be determined with a laboratory potentiometric pH-meter and using a general purpose electrode, and shall be within one unit of pH of that of the control fluid.

9.3 Limits for extractable metals

An extract, prepared as described in clause A.3, shall contain not more than a combined total of 5mg/kg of lead, tin, zinc and

iron when tested in accordance with a recognized microanalytical method, e.g. an atomic absorption method. The cadmium content of the extract shall be less than 0,1 mg/kg.

10 Lubrication of hypodermic needles

10.1 If the external surface of the hypodermic needle tube is lubricated, the lubricant shall not adversely affect compliance with the requirements of clause 4.

10.2 The quantity of lubricant used shall be minimal and shall not be visible as drops of fluid on the exterior surface of the hypodermic needle tube or in the bore.

11 Size designation

The size of hypodermic needle shall be designated by the following :

a) nominal external diameter of needle tube, expressed in millimetres;

b) nominal length of needle, expressed in millimetres.

The size shall be expressed, in millimetres, in accordance with the following example :

0,8 × 40

NOTE - If the needle is made of thin-walled Subing this may be s.iteh.ai) stated.

13 Needle hub

13.1 Conical fitting

The conical socket of the hypodermic needle hub shall comply with the requirements of ISO 594.

When mated with a reference steel male conical fitting in accordance with ISO 594-1, the socket shall make a leakproof union when subjected to the test described in annex B.

13.2 Colour of hub

The hub shall be made either of pigmented or of unpigmented material. If pigmented, the colour shall be in accordance with clause 12.

13.3 Finish

The surface of the hub shall be free from functional defects and substantially free from visual defects.

When examined under X2,5 magnification with adequate illumination, the hub socket shall be free from particles and other extraneous matter.

ISO 7864:1988 14 Sheath

12 Range of sizes https://standards.iteh.ai/catalog/standards/sist

96ce055076cc/iso The diameter of hypodermic needles shall be in accordance with table 1,

The preferred range of nominal lengths of hypodermic needles shall be in accordance with table 1.

The nominal diameter of hypodermic needles shall be identified by colour coding in accordance with ISO 6009 and as shown in table 1, applied to the unit container and/or part of the needle assembly such as the needle hub or the sheath.



Nominal external	Colour coding in accordance with ISO 6009	Preferred nominal length of needle tube					
diameter		12	16	25	30	40	50
0,45	Brown	x			[
0,5	Orange	x	x	Į	l	1	
0,6	Deep blue	1:		×	x	1.1	ľ,
0,7	Black	ł	}	×) x	x .	
0,8	Deep green	ł	·	x	ł	x	X
0,9	Yellow			x		x	
1,1	Cream	1		x	x	x	x
1,1 (thin- walled)	Cream				ļ	×	
1,2	Pink	1		1	1.	x	

If a separate needle sheath is provided, it shall be made of either pigmented or unpigmented material. If pigmented, the colour shall be in accordance with clause 12.

15 Needle tube

15.1 Material

The needle tube shall be made from austenitic stainless steel having properties capable of satisfying the tests for mechanical strength and corrosion resistance in 15.5, 15.6 and 15.7.

NOTE — Suitable needle tubing may be manufactured from steel the composition of which is in accordance with ISO $683-13^{11}$, types 10, 11, 16, 20, 21 and 23.

15.2 Dimensions of needle tube

The external diameter and minimum bore of the needle tube shall be as given in table 2.

The length, *l*, of the needle tube shall be as given in table 3.

1) ISO 683-13, Heat-treatable steels, alloy steels and free-cutting steels - Part 13 : Wrought stainless steels.

3

Nominal	External diameter		Bore of needle
diameter	min.	max.	min.
0.45	0.44	0,47	0,24
0,40	0.5	0,53	0,24
0,5	0.62	0.65	0,32
0,6	0.7	0 73	0,39
0,7	0.8	0.83	0,49
0,8	0,0	0.92	0,56
0,9	1.03	11	0,65
1,1	1,03	1	0.79
1,1 (thin-walled) 1,2	1,03	1,3	0,79

Table 3 — Length of needle tube

Nominal length

12

16

25

30

40

50

15

ho

Dimensions in millimetres

Length /

+1 12

-2

+1 16

-2

+1.525

2,5

+15

2.5

+1.5

- 2,5

+ (,5

30

50

Table 2 — Diameter of needle tube **Dimensions in millimetres**

Table 4 - Stiffness test

Nominal external diameter mm	Span mm	Load N	Maximum deflection mm		
0,45 0,5 0,6 0,7 0,8 0,9 1,1 1,1 (thin-walled) 1,2	10 10 12,5 15 15 17,5 25 25 25 25	6 7 15 15 15 15 20 10 20	0,56 0,38 0,59 0,61 0,41 0,48 0,84 0,84 0,65 0,45		

Resistance to breakage 15.7

When tested in accordance with the method given in annex D, the needle tube shall withstand 20 complete cycles of reversal of force without breaking.

Test requirements for needle assembly 16

Bond between hub and needle tube 16.1

The union of the hub and needle tube shall not be broken by a force of the magnitude given in table 5 applied as push or pull in the direction of the axis of the needle.

ards.itable 52 Bond between hub and needle tube

-2,0	
	Nominal external diameter Force 4:1988 mm N
https://standards.iteh.ai/catalog/standar 15.3 Needle point 96ee055076ec/is	ds/sist/570,45)45-7898-4f0d-86f4 22 0-7864-0,588 34 0,6 40
The needle point shall be sharp, free from feather edges, burrs, hooks and other defects.	0,7 0,8 0,9 1,1 0,7 44 54 69 60
NOTE — The needle point, as illustrated by the angle shown in the figure, usually has a bevel with an angle of $12^{\circ} \pm 2^{\circ}$. Alternatively a "short" bevel with an angle of $18^{\circ} \pm 2^{\circ}$ or other nominal angle subject	1,1 (thin-walled) 1,2 69

Freedom from defects 15.4

to a tolerance of $\pm 2^{\circ}$ may be supplied.

The needle tube shall be straight, of regular cross-section and wall thickness and free from manufacturing defects. The external surface of the tube shall be smooth.

Resistance to corrosion 15.5

The needle tube shall not show corrosion when tested in accordance with the procedure given in annex C.

15.6 Stiffness

The needle tube, after removal of the hub if necessary, shall not show a deflection greater than that given for the appropriate nominal diameter when loaded centrally between two supports under the conditions defined in table 4.

16.2 Patency of lumen

A stainless steel stylet of the appropriate diameter selected from table 6 shall pass through the needle.

Alternatively, the lumen shall satisfy a water flow rate test in which the flow rate shall be not less than 80 % of that of a needle of equivalent diameter and length with a minimum bore in accordance with table 2. The water pressure during the test shall not exceed 1 \times 10⁵ Pa (\approx 1 atm).

Table 6 -	Size of	stylet to tes	t patency of lumen
			Dimensions in millimetres

Nominal external diameter	Diameter of stylet
0,45	0,18
0,5	0,18
0,6	0,25
0,7	0,3
0,8	0,4
0,9	0,48
1,1	0,58
1,1 (thin-walled)	0,7
1,2	0,7

17 Packaging

17.1 Unit container

Each hypodermic needle shall be sealed in a unit container. The material and design of this container shall be such as to ensure

a) visible colour coding to denote nominal external diameter of the needle tube in accordance with the requirements of table 1;

b) maintenance of sterility of the contents under dry, clean and adequately ventilated storage conditions;

c) minimum risk of contamination of the contents during removal from the container;

d) adequate protection of the contents during normal handling, transit and storage.

17.2 Outer container

A convenient number of unit containers shall be packaged in an outer container which shall be sufficiently robust to protect the contents during handling, transit and storage.

18 Sterility

iTeh STANDARD PRE Use of the term "disposable" is not acceptable.

(standards.iteh.al) warning to check the integrity of each unit container;

The contents of the unit container (see 17.1) shall be sterile.

d) identification reference to the batch [to accord with 19.1d]] and date (month and year) of sterilization;

NOTE – National regulatory authorities in many countries may require (sist/57df2045-7898-4f0d-86f4) conformance with pharmacopoeia tests or national regulations. (b) the manufacturer's or supplier's name and address.

ISO 7864<u>:1988</u>

19 Marking of containers

19.1 Unit container

The unit container shall be marked to include the following :

a) description of contents, including the size designated in accordance with clause 11;

b) the word "STERILE";

c) the name and/or trade-mark of the manufacturer or supplier;

d) an identification reference to the batch or the date of manufacture.

19.2 Outer container

Outer containers shall be marked to include the following :

 a) description of contents, including the size designated in accordance with clause 11, the type or angle of bevel (see 15.3) and the word "STERILE";

b) the words "FOR SINGLE USE" or equivalent;