

**Materiali za izoliranje, oplaščenje in prevleke nizkonapetostnih energetskih kablov - 5. del: Omrežene mase za izoliranje brez halogenov**

Insulating, sheathing and covering materials for low voltage energy cables - Part 5:  
Halogen-free, cross-linked insulating compounds

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 50363-5:2006

[https://standards.iteh.ai/catalog/standards/sist/e506067e-c7c9-46ad-8adb-  
32efecfe4e26/sist-en-50363-5-2006](https://standards.iteh.ai/catalog/standards/sist/e506067e-c7c9-46ad-8adb-32efecfe4e26/sist-en-50363-5-2006)

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 50363-5:2006

<https://standards.iteh.ai/catalog/standards/sist/e506067e-c7c9-46ad-8adb-32efecfe4e26/sist-en-50363-5-2006>

EUROPEAN STANDARD

**EN 50363-5**

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2005

ICS 29.035.20

English version

**Insulating, sheathing and covering materials  
for low voltage energy cables**

**Part 5: Halogen-free, cross-linked insulating compounds**

Matériaux pour enveloppe isolante,  
gainage et revêtement pour les câbles  
d'énergie basse tension

Partie 5: Mélanges réticulés sans  
halogène pour enveloppe isolante

Isolier-, Mantel- und  
Umhüllungswerkstoffe für  
Niederspannungskabel und -leitungen  
Teil 5: Halogenfreie, vernetzte  
Isolermischungen

**iTeh STANDARD PREVIEW  
(standards.iteh.ai)**

This European Standard was approved by CENELEC on 2005-11-01. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

**CENELEC**

European Committee for Electrotechnical Standardization  
Comité Européen de Normalisation Electrotechnique  
Europäisches Komitee für Elektrotechnische Normung

**Central Secretariat: rue de Stassart 35, B - 1050 Brussels**

## Foreword

This European Standard was prepared by the Technical Committee CENELEC TC 20, Electric cables.

The text of the draft was submitted to the formal vote and was approved by CENELEC as EN 50363-5 on 2005-11-01.

EN 50363 (in all its parts) supersedes the equivalent information at present in HD 21.1 S4, HD 21.14 S1, HD 22.1 S4, HD 22.10 S1, HD 22.14 S2 and prHD 21.15 S1. The existing information in these HDs will be deleted at the next maintenance review.

EN 50363-5 should be read in conjunction with EN 50363-0.

The following dates were fixed:

- latest date by which the EN has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2006-11-01
- latest date by which the national standards conflicting with the EN have to be withdrawn (dow) 2007-11-01

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 50363-5:2006

<https://standards.iteh.ai/catalog/standards/sist/e506067e-c7c9-46ad-8adb-32efecfe4e26/sist-en-50363-5-2006>

## Contents

1 Scope .....	4
2 Normative references .....	4
3 Definitions .....	4
4 Properties .....	4
Table 1 – Types of halogen-free cross-linked insulating compound .....	4
Table 2 – Requirements for the tests for halogen-free crosslinked insulating compounds .....	5

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 50363-5:2006

<https://standards.iteh.ai/catalog/standards/sist/e506067e-c7c9-46ad-8adb-32efecfe4e26/sist-en-50363-5-2006>

## 1 Scope

This part of EN 50363 specifies the requirements for the physical properties of the harmonised halogen-free, cross-linked insulating compounds given in Table 1. The relevant test methods are given in EN 60811 series, EN 50267-2 (series), EN 60684-2 and EN 50396.

NOTE 1 Requirements for smoke emission, which are based on tests on cables and not individual materials, are given in the relevant cable standard.

NOTE 2 This part of EN 50363 is to be read in conjunction with EN 50363-0.

**Table 1 – Types of halogen-free cross-linked insulating compound**

Type	Maximum material operating temperature °C	General application
EI 5	90	Ordinary duty
EI 8	70	Ordinary duty for flexible cables

## 2 Normative references

# The STANDARD PREVIEW

For the purposes of this part of EN 50363, the requirements of EN 50363-0, Clause 2, apply with regard to normative references.

[SIST EN 50363-5:2006](#)

**3 Definitions** <https://standards.iteh.ai/catalog/standards/sist/e506067e-c7c9-46ad-8adb-32efecfe4e26/sist-en-50363-5-2006>

For the purposes of this part of EN 50363, the definitions given in EN 50363-0, Clause 3, apply.

## 4 Properties

Each compound shall meet the particular requirements listed in Table 2, when using the test methods referenced in columns 4 and 5.

NOTE For cross-references to the latest editions of the test method standards see Table 2 of EN 50363-0.

**Table 2 – Requirements for the tests for halogen-free crosslinked insulating compounds**

1	2	3	4	5	6	7
Ref No	Test <sup>a</sup>	Unit	Test method described in EN 60811 <sup>b</sup>		Type of compound	
			Section	Clause	EI 5	EI 8
<b>1</b>	<b>Mechanical properties</b>					
1.1	Properties before ageing		1-1	9.1		
1.1.1	Values to be obtained for the tensile strength: - median, min.	N/mm <sup>2</sup>			10,0	5,0
1.1.2	Values to be obtained for the elongation at break: - median, min.	%			125	125
1.2	Properties after ageing in air oven		1-2	8.1.3.1		
1.2.1	Ageing conditions: - temperature	°C			135 ± 2	110 ± 2
	- duration of treatment	h			7 x 24	7 x 24
1.2.2	Value to be obtained for the tensile strength: - median, min.	N/mm <sup>2</sup>			-	-
	- variation, max.	%			± 30	- 30 <sup>c</sup>
1.2.3	Values to be obtained for the elongation at break: - median, min.	%			-	125
	- variation, max.	%			± 30	± 30
<b>2</b>	<b>Hot set test</b>		2-1	9		
2.1	Conditions of treatment: - temperature	°C			200 ± 3	200 ± 3
	- time under load	min			15	15
	- mechanical stress	N/cm <sup>2</sup>			20	20
2.2	Test requirements: - max. elongation under load	%			100	100
	- max. elongation after unloading	%			25	25

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN 50363-5:2006

[www.iteh.ai/catalog/standards/sist/e506067e-c7c9-46ad-8adb-32efccfe4e26/sist-en-50363-5-2006](http://www.iteh.ai/catalog/standards/sist/e506067e-c7c9-46ad-8adb-32efccfe4e26/sist-en-50363-5-2006)

**Table 2 – Requirements for the tests for halogen-free crosslinked insulating compounds**  
*(continued)*

1	2	3	4	5	6	7
Ref No	Test <sup>a</sup>	Unit	Test method described in EN 60811 <sup>b</sup>		Type of compound	
			Section	Clause	EI 5	EI 8
3	<b>Pressure test at high temperature</b>		3-1	8.1		
3.1	Test conditions: - force exerted by the blade <sup>d</sup> - duration of heating under load - temperature	N h °C	3-1	8.1.4 8.1.5	e e 100 ± 2	- - -
3.2	Result to be obtained: - median of the depth of indentation, max.	%			50	-
4	<b>Bending test at low temperature</b>		1-4	8.1		
4.1	Test conditions: - temperature - period of application of low temperature	°C h	1-4	8.1.4	- 15 ± 2 e	- 15 ± 2 e
4.2	Result to be obtained		SIST EN 50363-5:2006		f	f
5	<b>Elongation test at low temperature</b>		1-4	8.3		
5.1	Test conditions: - temperature - period of application of low temperature	°C h	1-4	8.3.4	- 15 ± 2 e	- 15 ± 2 e
5.2	Result to be obtained: - elongation without break, min.	%			30	30
6	<b>Ozone resistance test</b>					
6.1	Method A - test temperature - test duration - ozone concentration (by volume)	°C h %	2-1	8	25 ± 2 24 (250 to 300) × 10 <sup>-4</sup>	25 ± 2 24 (250 to 300) × 10 <sup>-4</sup>
6.2	Method B - test temperature - test duration - ozone concentration (by volume)	°C h %	EN 50396	8.1.3	40 ± 2 72 (200 ± 50) × 10 <sup>-6</sup>	40 ± 2 72 (200 ± 50) × 10 <sup>-6</sup>
6.3	Result to be obtained				f	f