
Materiali za izoliranje, oplaščenje in prevleke nizkonapetostnih energetskih kablov - 9-1. del: Razne mase za izoliranje - Omreženi polivinilklorid (XLPVC)

Insulating, sheathing and covering materials for low voltage energy cables - Part 9-1: Miscellaneous insulating compounds - Cross-linked polyvinyl chloride (XLPVC)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 50363-9-1:2006](https://standards.iteh.ai/catalog/standards/sist/438293b2-221e-46a0-840b-e4062a920f53/sist-en-50363-9-1-2006)

<https://standards.iteh.ai/catalog/standards/sist/438293b2-221e-46a0-840b-e4062a920f53/sist-en-50363-9-1-2006>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 50363-9-1:2006

<https://standards.iteh.ai/catalog/standards/sist/438293b2-221e-46a0-840b-e4062a920f53/sist-en-50363-9-1-2006>

EUROPEAN STANDARD

EN 50363-9-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2005

ICS 29.035.20

English version

**Insulating, sheathing and covering materials
for low voltage energy cables
Part 9-1: Miscellaneous insulating compounds –
Cross-linked polyvinyl chloride (XLPVC)**

Matériaux pour enveloppe isolante,
gainage et revêtement pour les câbles
d'énergie basse tension
Partie 9-1: Mélanges divers pour
enveloppe isolante –
Polychlorure de vinyle réticulé (XLPVC)

Isolier-, Mantel- und
Umhüllungswerkstoffe für
Niederspannungskabel und -leitungen
Teil 9-1: Diverse Isoliermischungen -
Vernetztes Polyvinylchlorid (XLPVC)

ITeh STANDARD PREVIEW
(standards.iteh.ai)

This European Standard was approved by CENELEC on 2005-11-01. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, B - 1050 Brussels

Foreword

This European Standard was prepared by the Technical Committee CENELEC TC 20, Electric cables.

The text of the draft was submitted to the formal vote and was approved by CENELEC as EN 50363-9-1 on 2005-11-01.

EN 50363 (in all its parts) supersedes the equivalent information at present in HD 21.1 S4, HD 21.14 S1, HD 22.1 S4, HD 22.10 S1, HD 22.14 S2 and prHD 21.15 S1. The existing information in these HDs will be deleted at the next maintenance review.

EN 50363-9-1 should be read in conjunction with EN 50363-0.

The following dates were fixed:

- latest date by which the EN has to be implemented
at national level by publication of an identical
national standard or by endorsement (dop) 2006-11-01
- latest date by which the national standards conflicting
with the EN have to be withdrawn (dow) 2007-11-01

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 50363-9-1:2006

<https://standards.iteh.ai/catalog/standards/sist/438293b2-221e-46a0-840b-e4062a920f53/sist-en-50363-9-1-2006>

Contents

1	Scope	4
2	Normative references	4
3	Definitions.....	4
4	Properties	4
	Table 1 – Types of XLPVC insulating compound.....	4
	Table 2 – Requirements for the tests for XLPVC insulating compounds	5

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

SIST EN 50363-9-1:2006

<https://standards.iteh.ai/catalog/standards/sist/438293b2-221e-46a0-840b-e4062a920f53/sist-en-50363-9-1-2006>

1 Scope

This part of EN 50363 specifies the test requirements for the physical properties of the harmonised cross-linked PVC insulating compound given in Table 1. The relevant test methods are given in EN 60811 series.

NOTE This part of EN 50363 is to be read in conjunction with EN 50363-0.

Table 1 - Types of XLPVC insulating compound

Type	Maximum cable operating temperature °C	General application
XI 1	70	Cords requiring high flexibility, for example iron cords

2 Normative references

For the purposes of this part of EN 50363, the requirements of EN 50363-0, Clause 2, apply with regard to normative references.

3 Definitions

For the purposes of this part of EN 50363, the definitions given in EN 50363-0, Clause 3, apply.

4 Properties

Each compound shall meet the particular requirements listed in Table 2, when using the test methods referenced in columns 4 and 5.

NOTE For cross-references to the latest editions of the test method standards see Table 2 of EN 50363-0.

Table 2 – Requirements for the tests for XLPVC insulating compounds

1	2	3	4	5	6
Ref No	Test ^a	Unit	Test method described in EN 60811 ^b		Type of compound
			Section	Clause	XI 1
1	Mechanical properties				
1.1	Properties before ageing		1-1	9.1	
1.1.1	Values to be obtained for the tensile strength: - median, min.	N/mm ²			10,0
1.1.2	Values to be obtained for the elongation at break: - median, min.	%			150
1.2	Properties after ageing in air oven		1-2	8.1.3.1	
1.2.1	Ageing conditions: - temperature - duration of treatment	°C h			100 ± 2 7 x 24
1.2.2	Value to be obtained for the tensile strength: - median, min. - variation, max.	N/mm ² %			10,0 ± 25
1.2.3	Values to be obtained for the elongation at break: - median, min. - variation, max.	% %			150 ± 20
2	Loss of mass test		3-2	8.1	
2.1	Ageing conditions: - temperature - duration of treatment	°C h			100 ± 2 7 x 24
2.2	Values to be obtained for the loss of mass, max.	mg/cm ²			2,0
3	Heat shock test		3-1	9.1	
3.1	Test conditions: - temperature - duration of treatment	°C h			150 ± 2 1,0
3.2	Result to be obtained				^c
4	Pressure test at high temperature		3-1	8.1	
4.1	Test conditions: - force exerted by the blade (k value) ^d - duration of heating under load - temperature	 h °C	3-1 3-1	8.1.4 8.1.5	 ^e ^e 90 ± 2

STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 50363-9-1:2006

<https://standards.iteh.ai/catalog/standards/sist/438293b2-221e-46a0-840b-e4062a920f53/sist-en-50363-9-1-2006>

Table 2 – Requirements for the tests for XLPVC insulating compounds
(continued)

1	2	3	4	5	6
Ref No	Test ^a	Unit	Test method described in EN 60811 ^b		Type of compound
			Section	Clause	XI 1
4.2	Result to be obtained: - median of the depth of indentation, max.	%			50
5	Bending test at low temperature		1-4	8.1	
5.1	Test conditions: - temperature - period of application of low temperature	°C h	1-4	8.1.4	- 15 ± 2 ^e
5.2	Result to be obtained				^c
6	Thermal stability		3-2	9	
6.1	Test condition: - temperature	°C			200 ± 0,5
6.2	Value to be obtained, min.	min			60
7	Hot set test		2-1	9	
7.1	Conditions of treatment: - temperature - time under load - mechanical stress	°C min. N/cm ²			200 ± 3 15 10
7.2	Test requirements: - max. elongation under load - max. elongation after unloading	% %			100 25
^a	Information on other tests is given in EN 50363-0, Clause 5.				
^b	Unless stated otherwise.				
^c	No cracks.				
^d	The standard shows how to convert the given k value into a force in Newtons.				
^e	See test method referred to in columns 4 and 5.				