



**SLOVENSKI STANDARD**  
**SIST EN 12770:2000**

**01-december-2000**

---

**Footwear - Test methods for outsoles - Abrasion resistance**

Footwear - Test methods for outsoles - Abrasion resistance

Schuhe - Prüfverfahren für Laufsohlen - Abriebwiderstand

Chaussures - Méthodes d'essai applicables aux semelles d'usure - Résistance à l'abrasion

**(standards.iteh.ai)**

**Ta slovenski standard je istoveten z: EN 12770:1999**

<https://standards.iteh.ai/catalog/standards/sist/3a2ead30-7ca4-4b50-9c89-c1f408c9679f/sist-en-12770-2000>

**ICS:**

61.060

Obuvala

Footwear

**SIST EN 12770:2000**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 12770:2000

<https://standards.iteh.ai/catalog/standards/sist/3a2ead30-7ca4-4b50-9c89-c1f408c9679f/sist-en-12770-2000>

EUROPEAN STANDARD

EN 12770

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 1999

ICS 61.060

English version

## Footwear - Test methods for outsoles - Abrasion resistance

Chaussures - Méthodes d'essai applicables aux semelles  
d'usure - Résistance à l'abrasion

Schuhe - Prüfverfahren für Laufsohlen - Abriebwiderstand

This European Standard was approved by CEN on 23 October 1999.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

ITeH STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN 12770:2000

<https://standards.iteh.ai/catalog/standards/sist/3a2ead30-7ca4-4b50-9c89-c1f408c9679f/sist-en-12770-2000>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

**Contents**

	<b>Page</b>
Foreword .....	3
1 Scope .....	4
2 Normative references .....	4
3 Terms and definitions .....	4
4 Apparatus and materials .....	5
5 Sampling and conditioning .....	6
6 Test method .....	7
7 Expression of results .....	8
8 Test Report .....	9

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 12770:2000

<https://standards.iteh.ai/catalog/standards/sist/3a2ead30-7ca4-4b50-9c89-c1f408c9679f/sist-en-12770-2000>

## Foreword

This European Standard has been prepared by Technical Committee CEN/TC 309 "Footwear", the secretariat of which is held by AENOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2000, and conflicting national standards shall be withdrawn at the latest by June 2000.

This standard is based on ISO 4649:1985 and it contains slight adaptations for the practice of footwear testing.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

## **iTeh STANDARD PREVIEW** **(standards.iteh.ai)**

SIST EN 12770:2000

<https://standards.iteh.ai/catalog/standards/sist/3a2ead30-7ca4-4b50-9c89-c1f408c9679f/sist-en-12770-2000>

Page 4  
EN 12770:1999

## 1 Scope

This European standard specifies a method for the determination of the abrasion resistance for outsoles, irrespective of the material.

## 2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 12222 Footwear - Standard atmospheres for conditioning and testing of footwear and components for footwear.

prEN 13400:1998 Footwear - Sampling location of components for footwear.

ISO 2420 Leather - Determination of apparent density.

ISO 2781 Rubber vulcanized - Determination of density.

ISO 4649:1985 Rubber - Determination of abrasion resistance using a rotating cylindrical drum device.

## 3 Terms and definitions

For the purposes of this standard the following definitions apply:

### 3.1

#### **abrasion resistance**

the resistance to wear by mechanical action upon a surface

### 3.2

#### **relative mass loss**

the mass loss, in milligrams, of the outsole after being subjected to abrasion by an abrasive cloth will cause the appropriate standard rubber to lose a mass of 200 mg under the preferred conditions, namely a distance of 40 m, a load of 10 N and using a non-rotating test piece

### 3.3 relative volume loss

the volume loss, in cubic millimetres, of the test rubber after being subjected to abrasion by an abrasive cloth will cause the appropriate standard rubber (see clause B.1 of ISO 4649:1985) to lose a mass of 200 mg under the preferred conditions, namely a distance of 40 m, a load of 10 N and using a non-rotating test piece

## 4 Apparatus and materials

The following apparatus and material shall be used:

### 4.1 Abrasion machine

The test apparatus (see figure 1) consists of a laterally movable test piece holder and a rotatable cylindrical drum to which the abrasive cloth (4.2) is fixed.

The drum shall have a diameter of  $150 \text{ mm} \pm 0,2 \text{ mm}$  and a length of about 500 mm and shall be rotated at a frequency of  $40 \text{ min}^{-1} \pm 1 \text{ min}^{-1}$ , the directions of rotation being as indicated in figure 1.

The test piece holder shall consist of a cylindrical opening, the diameter of which can be adjusted from 15,5 mm to 16,3 mm, and a device for adjusting the length of the test piece protruding from the opening to  $2 \text{ mm} \pm 0,2 \text{ mm}$ . The holder shall be mounted on a swivel arm which in turn is attached to a sledge which can be moved laterally on a spindle. The lateral displacement of the holder shall be  $4,20 \text{ mm} \pm 0,04 \text{ mm}$  per revolution of the drum.

The centre axis of the holder shall have an inclination of  $3^\circ$  to the perpendicular in the direction of rotation (see figure 1), and shall be placed directly above the longitudinal axis of the drum to within  $\pm 1 \text{ mm}$ .

The swivel arm and test piece holder shall be free from vibration during operation, and disposed such that the test piece is pressed against the drum with a vertical force of  $10 \text{ N} \pm 0,2 \text{ N}$  obtained by adding weights to the top of the test piece holder.

The abrasive cloth shall be attached to the drum using three evenly spaced strips of double-sided adhesive tape extending along the complete length of the cylinder. Care shall be taken to ensure that the abrasive cloth is firmly held so as to present a uniform abrasive surface over the whole area of the cylinder. One of the strips shall be placed where the ends of the abrasive cloth meet. Ideally the ends should meet exactly, but any gap left between them shall not exceed 2 mm. The adhesive tape shall be about 50 mm wide and not more 0,2 mm thick.

Placement of the test piece on to the cloth at the beginning of a test run, and its removal after an abrasion run of 40 m (equivalent to 84 revolutions), shall be automatic. In special cases of very high volume loss of the test piece, an abrasion distance of only 20 m (equivalent to 42 revolutions) may be used. If using an abrasion distance of 20 m, a revolution counter or automatic stopping device should be connected to the drum.

To protect the abrasive cloth from damage by the test piece holder, a device for switching

Page 6  
EN 12770:1999

off the apparatus just before the lower edge of the test piece holder touches the cloth is recommended.

#### 4.2 Abrasive cloth

Abrasive cloth made with aluminium oxide of grain size 60, at least 400 mm wide, 473 mm long and 1 mm average thickness, shall be used as the abrasive medium.

This abrasive surface shall cause a mass loss between 180 mg and 220 mg for an abrasion distance of 40 m.

When each new sheet of cloth is first used, the direction of motion shall be indicated on the sheet, as it is important that the same direction be used for all subsequent test runs.

NOTE Suitable paper abrasive cloth is listed in annex A of ISO 4649:1985.

#### 4.3 Hollow Drill

The specification for the hollow drill is given in detail in figure 2.

The frequency of rotation of the drill needs to be at least  $1\,000\text{ min}^{-1}$  for most outsoles materials.

(standards.iteh.ai)

#### 4.4 Balance

The balance shall be of sufficient accuracy to enable the mass loss of a test piece to be determined to  $\pm 1\text{ mg}$ .

SIST EN 12770:2000

Document identifier: SIST EN 12770:2000  
c1f408c9679f/sist-en-12770-2000

#### 4.5 Standard rubbers

Specifications for standard rubbers are given in detail in annex B (see clause B.1) of ISO 4649:1985.

### 5 Sampling and conditioning

The test pieces shall be cylindrical in shape, of diameter  $16\text{ mm} \pm 0,2\text{ mm}$ , with a minimum height of 6 mm. If test pieces of the required thickness are not available, the necessary thickness may be obtained by bonding a piece of the outsole to a base element of hardness not less than 80 IRHD. The thickness of this outsole should be not less than 2 mm.

Minimum three test pieces are necessary.

The test pieces to be tested shall be taken in accordance with prEN 13400:1998.

All test pieces shall be conditioned in accordance with EN 12222 before testing for a minimum of 24 h.



## 6 Test method

### 6.1 Procedure

Before each test, any rubber debris left on the abrasive cloth from a previous abrasion test shall be removed with a brush. A strong brush of about 55 mm diameter and about 70 mm length is recommended for this purpose. In some cases, a blank test with a standard rubber will effectively clean the abrasive cloth.

Weigh the test piece to the nearest 1 mg. Fix the test piece in the test piece holder in such a way that a length of  $2,0 \text{ mm} \pm 0,2 \text{ mm}$  protrudes from the opening. This length shall be controlled by means of a gauge.

The test piece shall be pressed against the drum with a vertical force of  $10 \text{ N} \pm 0,2 \text{ N}$ .

Move the test piece holder and sledge to the starting point, place the test piece on the abrasive cloth and set the cylinder in motion. Check for vibration in the test piece holder. This test method does not yield meaningful results if there is abnormal vibration in the test piece holder. The test run is stopped automatically after an abrasion distance of 40 m. For relatively large mass losses the test run may be stopped and the length of exposed test piece reset to  $2,0 \text{ mm} \pm 0,2 \text{ mm}$  so that the test can be restarted and completed.

The sample shall not be completely abraded at the end of the test (test sample carrier shall not be, or any part of it, in contact with the abradant paper). If it is, repeat the test using a reduced distance, for example, 20 m or less if it is necessary and then extrapolate the results to 40 m (This shall be stated in the test report).

### 6.2 Determination of density

Determine the density of the test material in accordance with ISO 2781 or ISO 2420 as appropriate.