



Designation: B 868 – 96 (Reapproved 2002)^{e1}

Standard Practice for Contact Performance Classification of Electrical Connection Systems¹

This standard is issued under the fixed designation B 868; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{e1} NOTE—Paragraph 1.5 was corrected editorially in June 2002.

1. Scope

1.1 This practice provides a uniform method of specifying performance requirements for (or reporting test results of) electrical contact and connection systems. Both conductor and connector system performance may be specified by this practice, separately or in combination.

1.2 This practice may be used for separable or permanent contacts employing metallic conductors and contacts.

1.3 This practice provides methods for both signal and power applications.

1.4 This practice does not specify the sample preparation or test sequences required for determining contact performance. It is the responsibility of the user of this practice to determine the applied test sequence(s) appropriate for the application.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

B 539 Test Methods for Measuring Resistance of Electrical Connections (Static Contacts)²

B 542 Terminology Relating to Electrical Contacts and Their Use²

B 812 Test Method for Resistance to Environmental Degradation of Electrical Pressure Connections Involving Aluminum and Intended for Residential Applications²

¹ This practice is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.11 on Electrical Contact Test Methods.

Current edition approved March 10, 1996. Published May 1996.

² *Annual Book of ASTM Standards*, Vol 02.04.

2.2 UL Standard:

UL 486B Wire Connectors for Use with Aluminum Conductors, Third Edition, 1991³

2.3 EEI-NEMA Standard:

EEI-NEMA Standard TDJ-162 (ANSI C119.4), “Connectors for Use Between Aluminum-to-Aluminum or Aluminum-to-Copper Bare Overhead Conductors”⁴

3. Terminology

3.1 Terms used in this practice are defined in Terminology B 542 except as noted in 3.2.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *conductor, n*—electrically conductive member carrying current to a contact interface. Examples are wire and cable, busbar, and conductive paths on an etched printed circuit board.

3.2.2 *contact performance, n*—contact interface behavior as indicated by initial electrical resistance and resistance change under the applied test conditions.

4. Summary of Practice

4.1 The prescribed performance specification (or reporting) statement consists of three sections, as follows:

4.1.1 *Performance Classification*, in accordance with this practice (Section 6).


4.1.2 *Variability Index*, determined by sample size and distribution of resistance values measured at end of test, in accordance with this practice (Section 7).

4.1.3 Statement of test method employed to determine performance classification.

4.2 The format for the performance specification (or reporting) statement is as follows:

³ Available from Underwriters Laboratories, 333 Pfingsten Rd., Northbrook, IL 60062–2096.

⁴ Available from American National Standards Institute, 25 W. 43rd St., 4th Floor, New York, NY 10036.



5. Significance and Use

5.1 This practice is based on the use of electrical resistance as an indicator of contact performance.

5.2 Existing standards, such as those referenced in Section 2 as representative examples, provide the basis for applied test conditions. Modifications in procedure or sample size, or both, of existing standards may have to be made to provide for resistance measurement and to meet variability index requirements that a user may specify.

5.3 This practice accommodates the use of multiple test methods, as may be required to assure satisfactory performance in a given application.

6. Performance Classification

6.1 The performance classification statement consists of three letters in sequence indicating, respectively, category of contact (signal or power), average initial contact resistance, and change of average contact resistance as a consequence of the applied test conditions.

6.2 For this standard classification method, the performance of a connection system for power applications is expressed as the ratio of the contact resistance to the equivalent resistance of the attached conductor. The equivalent resistance of the conductor is the resistance of a length of solid circular conductor exactly one diameter in length. The conductor size used for the evaluation shall be that which is normally specified or utilized with the particular connection system being evaluated.

6.2.1 For connection systems involving solid circular conductors, the equivalent resistance R_d is calculated according to the formula:

$$R_d = R \times D$$

where:

R_d = equivalent resistance,

R = resistance per unit length, Ω , and

D = diameter of conductor (in same length unit).

6.2.1.1 Appendix X1 provides representative nominal data for some common sizes of copper and aluminum conductors of circular cross section for the purpose of establishing instrumentation requirements.

6.2.2 For conductors with other than solid circular cross section, equivalent diameter based on actual conductive cross-section area shall be used. For example: a conductor of rectangular cross section 0.5 by 6 mm has a cross-section area equal to that of a solid circular conductor 1.95 mm in diameter, and therefore D in the equation in 6.2.1 is 1.95 mm.

6.2.3 For contacts incorporating or connecting conductors of different materials or cross section, or both, the R_d value used for contact performance determination shall be based on the conductor of minimum resistance per unit length.

6.2.4 For contacts involving a connector, the conductor material and cross section used for determination of the R_d value to be used shall be the wire, busbar, circuit board conductive strip, or other, as appropriate for the rating or representative application of the connector. The conductor size may be determined according to the connector manufacturer's specification, current rating, or conventional application practice.

6.2.5 Conductor resistance per unit length is preferably determined by measurements incorporating the same instrumentation used for contact resistance measurements, at the same ambient temperature and current as for the contact performance test being applied.

6.2.6 When conductor resistance is determined at the same time as contact performance in accordance with 6.2.5, and the conductor is solid with circular cross section, potential drop measurements may be used without conversion for the purpose of determining contact performance. (See example, Appendix X2.)

6.3 Contact resistance shall be measured in accordance with Test Methods B 539.

6.3.1 For power connections, resolution of resistance determination shall be $0.1 R_d$ or better. For most applications, this requires potential drop resolution of $10 \mu\text{V}$ at a measurement current density approximately equal to conductor ratings. (See Appendix X1.) Use Test Method B of Test Methods B 539 adjusting the current to meet the stated current requirements.

6.3.2 For signal connections, resolution of resistance determination shall be at 10 % of the average initial contact resistance or better, using Test Method C of Test Methods B 539.

6.3.3 For contact configurations in which bulk conductor or connector resistance is included in the measured contact resistance, a single value of measured bulk resistance (see Test Methods B 539) shall be subtracted from the measured contact resistance values. Resolution of the bulk resistance measurement shall be $0.1 R_d$ or finer, and the bulk resistance measurement error tolerance shall be no greater than $\pm 0.2 R_d$.

6.4 The first letter of the performance classification, indicating contact category, shall be "P" for power contacts and connections and "S" for signal contacts and connections. The letter is assigned according to the intended application for each of the applied test conditions.

6.4.1 A given connector type may be intended for multiple applications, both signal and power (example: circuit board connector). The category used for performance classification for each test sequence applied shall be that for which the test sequence is intended.

6.5 The letter indicating performance with respect to average (arithmetic mean) initial resistance of all samples tested shall be in accordance with Table 1.

6.6 The letter indicating performance with respect to resistance change of the worst-case sample tested shall be in accordance with Table 2.