

NOTICE: This standard has either been superseded and replaced by a new version or discontinued.
Contact ASTM International (www.astm.org) for the latest information.



Designation: A 213/A 213M – 99

An American National Standard
Used in USDOE-NE standards

AMERICAN SOCIETY FOR TESTING AND MATERIALS
100 Barr Harbor Dr., West Conshohocken, PA 19428
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Specification for Seamless Ferritic and Austenitic Alloy-Steel Boiler, Superheater, and Heat-Exchanger Tubes¹

This standard is issued under the fixed designation A 213/A 213M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification² covers minimum-wall-thickness, seamless ferritic and austenitic steel, boiler and superheater tubes and austenitic steel heat-exchanger tubes, designated Grades T5, TP304, etc. These steels are listed in Tables 1-3.

1.2 Grades TP304H, TP309H, TP309HCb, TP310H, TP310HCb, TP310HCbN, TP316H, TP321H, TP347H, TP347HFG (fine grained) and TP348H are modifications of Grades TP304, TP309S, TP309Cb, TP310S, TP310Cb, TP316, TP321, TP347, and TP348, and are intended for high-temperature service, such as for superheaters and reheaters.

1.3 The tubing sizes and thicknesses usually furnished to this specification are 1/8 in. [3.2 mm] in inside diameter to 5 in. [127 mm] in outside diameter and 0.015 to 0.500 in. [0.4 to 12.7 mm], inclusive, in minimum wall thickness. Tubing having other dimensions may be furnished, provided such tubes comply with all other requirements of this specification.

1.4 Mechanical property requirements do not apply to tubing smaller than 1/8 in. [3.2 mm] in inside diameter or 0.015 in. [0.4 mm] in thickness.

1.5 Optional supplementary requirements are provided and, when desired, shall be so stated in the order.

1.6 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification. The inch-pound units shall apply unless the "M" designation of this specification is specified in the order.

2. Referenced Documents

2.1 ASTM Standards:

A 262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels³

¹ This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.10 on Stainless and Alloy Steel Tubular Products.

Current edition approved Jan. 10, 1999. Published April 1999. Originally published as A 213 – 39 T. Last previous edition A 213/A 213M – 98.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-213 in Section II of that Code.

³ Annual Book of ASTM Standards, Vol 01.03.

A 450/A450M Specification for General Requirements for Carbon, Ferritic Alloy, and Austenitic Alloy Steel Tubes⁴
E 112 Test Methods for Determining the Average Grain Size⁵

E 527 Practice for Numbering Metals and Alloys (UNS)⁴

2.2 Other Standard:

SAE J1086 Practice for Numbering Metals and Alloys (UNS)⁶

3. Ordering Information

3.1 Orders for material under this specification should include the following, as required, to describe the desired material adequately:

3.1.1 Quantity (feet, metres, or number of lengths),

3.1.2 Name of material (seamless tubes),

3.1.3 Grade (Tables 1-3),

3.1.4 Manufacture (hot finished or cold finished),

3.1.5 Controlled structural characteristics (see 6.2),

3.1.6 Size (outside diameter and minimum wall thickness),

3.1.7 Length (specific or random),

3.1.8 Hydrostatic Test or Nondestructive Electric Test (see 12.1),

3.1.9 Specification designation, and

3.1.10 Special requirements and any supplementary requirements selected.

4. General Requirements

4.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A 450/A 450M, unless otherwise provided herein.

5. Materials and Manufacture

5.1 Tubes shall be made by the seamless process and shall be either hot finished or cold finished, as specified. Grade TP347HFG shall be cold finished.

5.2 Grain Size:

5.2.1 The grain size of Grades 304H, 316H, 321, 347H, 348H, and 310HCbN, as determined in accordance with Test

⁴ Annual Book of ASTM Standards, Vol 01.01.

⁵ Annual Book of ASTM Standards, Vol 03.01.

⁶ Available from Society of Automotive Engineers, 400 Commonwealth Drive, Warrendale, PA 15096.


 A 213/A 213M

TABLE 1 Chemical Requirements for Ferritic Steel

Grade	Composition, %						Chromium	Molybdenum	Titanium	Vanadium, min	Other Elements
	Carbon	Manganese	Phosphorus, max	Sulfur, max	Silicon						
T2 ^A	0.10–0.20	0.30–0.61	0.025	0.025	0.10–0.30	0.50–0.81	0.44–0.65		
T5	0.15 max	0.30–0.60	0.025	0.025	0.50 max	4.00–6.00	0.45–0.65		
T5b	0.15 max	0.30–0.60	0.025	0.025	1.00–2.00	4.00–6.00	0.45–0.65		
T5c	0.12 max	0.30–0.60	0.025	0.025	0.50 max	4.00–6.00	0.45–0.65	^B	...		
T9	0.15 max	0.30–0.60	0.025	0.025	0.25–1.00	8.00–10.00	0.90–1.10		
T11	0.05 min–0.15 max	0.30–0.60	0.025	0.025	0.50–1.00	1.00–1.50	0.44–0.65		
T12 ^A	0.05 min–0.15 max	0.30–0.61	0.025	0.025	0.50 max	0.80–1.25	0.44–0.65		
T17	0.15–0.25	0.30–0.61	0.025	0.025	0.15–0.35	0.80–1.25	0.15		
T21	0.05 min–0.15 max	0.30–0.60	0.025	0.025	0.50 max	2.65–3.35	0.80–1.06		
T22	0.05 min–0.15 max	0.30–0.60	0.025	0.025	0.50 max	1.90–2.60	0.87–1.13		
T91	0.08–0.12	0.30–0.60	0.020	0.010	0.20–0.50	8.00–9.50	0.85–1.05	0.18–0.25	Cb 0.06–0.1 N 0.030–0.070 Ni 0.40 max Al 0.04 max W 1.5–2.00 Cb 0.04–0.09 B 0.001–0.006 N 0.03–0.07 Ni 0.40 max Al 0.04 max N max 0.035 Ni + Cu max 1.00
T92	0.07–0.13	0.30–0.60	0.020	0.010	0.50 max	8.50–9.50	0.30–0.60	0.15–0.25	
18Cr-2Mo	0.025 max	1.00 max	0.040	0.030	1.00 max	17.5–19.5	1.75–2.50	^C	

^A It is permissible to order T2 and T12 with 0.045 max Sulfur.

^B Grade T5c shall have a titanium content of not less than four times the carbon content and not more than 0.70 %.

^C Grade 18Cr-2Mo shall have Ti + Cb = 0.20 + 4 (C + N) min, 0.80 max.

Methods E 112, shall be No. 7 or coarser.

5.2.2 The grain size of cold-worked Grade TP321H, as determined in accordance with Test Methods E 112, shall be No. 7 or coarser.

5.2.3 The grain size of TP309H, TP309HCb, TP310H and TP310HCb, as determined in accordance with Test Methods E 112, shall be No. 6 or coarser.

5.2.4 The grain size of cold-worked Grade TP347HFG as determined in accordance with Test Methods E 112 shall be between No. 7 and No. 10.

6. Heat Treatment

6.1 All tubes of grades shown in Table 1, except T5c, T91, and T92, and in accordance with 6.1.1 shall be reheated and furnished in the full-annealed, isothermal annealed, or normalized and tempered condition. If furnished in the normalized and tempered condition, the minimum tempering temperature for Grades T5, T5b, T9, T21, and T22 shall be 1250°F [675°C], and the minimum tempering temperature for Grades T11, and T17, shall be 1200°F [650°C].

6.1.1 Tubing of Grades T2 and T12 either hot-finished or cold-drawn, may be given a final heat treatment at 1200 to 1350°F [650 to 730°C] instead of heat treatments specified in 6.1 at the option of the manufacturer.

6.1.2 All tubing of Grade T5c shall be given a final heat treatment of approximately 1350°F [730°C] for a proper time, followed by air or furnace cooling.

6.1.3 Grade T91 shall be normalized at 1900°F [1040°C] minimum and tempered at 1350°F [730°C] minimum as a final heat treatment.

6.1.4 Grade T92 shall be normalized at 1900°F [1040°C] minimum and tempered at 1350°F [730°C] minimum as a final heat treatment.

NOTE 1—Isothermal annealing as applied to tubular products, may involve austenitizing a ferrous alloy and then cooling to and holding within the range of temperature at which austenite transforms to a relatively soft ferrite-carbide aggregate.

6.2 If any controlled structural characteristics are required these shall be so specified as to be a guide as to the most suitable heat treatment.

6.3 All austenitic tubes shall be furnished in the heat-treated condition. The heat-treatment procedure, except for the H grades and S30815, shall consist of heating the material to a minimum temperature of 1900°F [1040°C] and quenching in water or rapidly cooling by other means. Alternatively, immediately following hot forming, while the temperature of the tubes is not less than the specified minimum solution treatment temperature, tubes may be individually quenched in water or rapidly cooled by other means.

6.4 All H, S30815, S33228, and S31272 grades shall be furnished in the solution-treated condition. If cold working is involved in processing, the minimum solution treating temperature for Grades TP321H, TP347H and TP348H shall be 2000°F [1100°C] and for Grades TP304H, and TP316H, 1900°F [1040°C]. If the H grade is hot-rolled, the minimum solution treatment for Grades TP321H, TP347H, and TP348H shall be 1925°F [1050°C], and for Grades TP304H, and TP316H, 1900°F [1040°C]. The minimum solution treating temperature for S30815 and S31272 shall be 1920°F [1050°C]. The minimum solution treating temperature for S33228 shall be 2050°F [1120°C]. The minimum solution treating temperature for TP309H, TP309HCb, TP310H, and TP310HCb shall be 1900°F [1037°C]. The minimum solution treating temperature for TP310HCbN shall be 2000°F (1100°C) and sufficient to produce a grain size of No. 7 or coarser.


 A 213/A 213M

TABLE 2 Chemical Requirements of Austenitic Steel

Grade	TP201	TP202	TP304	TP304H	TP304N	TP304LN	TP304L	TP309Cb	TP309H	TP309Hcb	TP309S	TP310Cb	TP310H	TP310Hcb	TP31042	TP310S	TP316	TP316H		
UNS Designation ^a	S20100	S20200	S30400	S30409	S30451	S30453	S30403	S30940	S30909	S30941	S30908	S31040	S31009	S31041	S31042	S31008	S31600	S31609		
Carbon	0.15 max 5.50-7.50	0.15 max 7.50-10.0	0.08 max 2.00	0.04-0.10 2.00	0.08 max 2.00	0.035 max ^b 2.00	0.08 max 2.00	0.04-0.10 2.00	0.04-0.10 2.00	0.04-0.10 2.00	0.08 max 2.00	0.08 max 2.00	0.04-0.10 2.00	0.04-0.10 2.00	0.04-0.10 2.00	0.08 max 2.00	0.08 max 2.00	0.04-0.10 2.00	0.04-0.10 2.00	
Manganese, max	7.50	10.0	
Phosphorus, max	0.060	0.060	0.040	0.040	0.040	0.040	0.045	0.045	0.045	0.045	0.045	0.045	0.040	0.045	0.030	0.045	0.040	0.040	0.040	
Sulfur, max	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	
Silicon	1.00 max 3.50-5.50	1.00 max 4.00-6.00	0.75 max 8.00-11.0	0.75 max 8.00-11.0	0.75 max 8.00-11.0	0.75 max 8.00-11.0	0.75 max 8.00-11.0	0.75 max 8.00-11.0	0.75 max 8.00-11.0	0.75 max 8.00-11.0	0.75 max 8.00-11.0	0.75 max 8.00-11.0	0.75 max 8.00-11.0	0.75 max 8.00-11.0	0.75 max 8.00-11.0	0.75 max 8.00-11.0	0.75 max 8.00-11.0	0.75 max 8.00-11.0	0.75 max 8.00-11.0	
Nickel	3.50-5.50	4.00-6.00	8.00-11.0	8.00-11.0	8.00-11.0	8.00-11.0	12.00-16.00	12.00-16.00	12.00-16.00	12.00-16.00	12.00-16.00	19.00-22.00	19.00-22.00	19.00-22.00	17.00-23.00	19.00-22.00	11.0-14.0	11.0-14.0	11.0-14.0	
Chromium	16.0-18.0	17.0-19.0	18.0-20.0	18.0-20.0	18.0-20.0	18.0-20.0	22.00-24.00	22.00-24.00	22.00-24.00	22.00-24.00	22.00-24.00	24.00-26.00	24.00-26.00	24.00-26.00	24.00-26.00	24.00-26.00	16.0-18.0	16.0-18.0	16.0-18.0	
Molybdenum	0.75 max	0.75 max	0.75 max	0.75 max	0.75 max	0.75 max	...	0.75 max	...	0.75 max	2.00-3.00	2.00-3.00	2.00-3.00	
Titanium
Columbium + tantalum	10 × C min, 1.10 max	10 × C min, 1.10 max	10 × C min, 1.10 max	10 × C min, 1.10 max	10 × C min, 1.10 max	10 × C min, 1.10 max	...	10 × C min, 1.10 max	0.20-0.60	
Tantalum, max	
Nitrogen ^c	0.25 max	0.25 max	0.10-0.16	0.10-0.16	0.15-0.35	
Centium	
Others	


 A 213/A 213M

TABLE 3 Chemical Requirements of Austenitic Steel (Continued)

Grade	TP316L	TP316N	TP316LN	TP317	TP317L	TP321	TP321H	TP347	TP347H	TP347LN	TP347HFG	TP348	TP348H	XM-15	XM-19	...
UNS Designation ^a	S31603	S31651	S31653	S31700	S31703	S32100	S32109	S34700	S34709	S34751	S34800	S34809	S38100	S30615	S30815	S33228
Carbon	0.035 max ^b	0.08 max	0.035 max ^b	0.08 max	0.035 max	0.08 max	0.04 max	0.08 max	0.04 max	0.005 max	0.06 max	0.08 max	0.08 max	0.016 max	0.05 max	0.04 max
Manganese, max	2.00	2.00	2.00	2.00	2.00	2.00	2.00	2.00	2.00	2.00	2.00	2.00	2.00	2.00	2.00	1.0
Phosphorus, max	0.040	0.040	0.040	0.040	0.040	0.040	0.040	0.040	0.040	0.040	0.040	0.040	0.030	0.030	0.040	0.020
Sulfur, max	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.015
Silicon	0.75 max ^c	0.75 max	0.75 max	0.75 max	0.75 max	0.75 max	0.75 max	0.75 max	0.75 max	0.75 max	0.75 max	0.75 max	0.75 max	0.75 max	0.75 max	0.30
Nickel	10.0-15.0	11.0-14.0	11.0-14.0	11.0-14.0	11.0-14.0	9.00-13.0	9.00-13.0	9.00-13.0	9.00-13.0	9.00-13.0	9.00-13.0	9.00-13.0	13.5-17.5	13.5-17.5	13.5-17.5	31.0-39.0
Chromium	16.0-18.0	16.0-18.0	16.0-18.0	16.0-18.0	16.0-18.0	17.0-20.0	17.0-20.0	17.0-20.0	17.0-20.0	17.0-20.0	17.0-20.0	17.0-20.0	17.0-20.0	17.0-20.0	17.0-20.0	26.0-28.0
Molybdenum	2.00-3.00	2.00-3.00	2.00-3.00	3.00-4.00	3.00-4.00	0.3-1.5
Titanium
Columbium + tantalum
Tantalum, max
Nitrogen ^f , max
Nitrogen ^g	0.10-0.16	0.10-0.16	0.10-0.16	0.06-0.10	0.20-0.40
Cerium
Others

^a New designation established in accordance with Practice E 527 and SAE J1086.
^b For small diameter or thin walls, or both, where many drawing passes are required, a carbon maximum of 0.040 % is necessary in grades TP304L and TP316L. Small outside diameter tubes are defined as those less than 0.500 in. [12.7 mm] in outside diameter and light wall tubes are those less than 0.049 in. [1.2 mm] in average wall thickness (0.044 in. [1.1 mm] in minimum wall thickness).
^c For seamless TP316L tubes, the silicon maximum shall be 1.00 %.
^d Grade TP321 shall have a titanium content of not less than five times the carbon content and not more than 0.60 %.
^e Grade TP321H shall have a titanium content of not less than four times the carbon content and not more than 0.60 %.
^f Grades TP347 and TP348 shall have a columbium plus tantalum content of not less than ten times the carbon content and not more than 1.00 %.
^g Grades TP347H and TP348H shall have a columbium plus tantalum content of not less than eight times the carbon content and not more than 1.0 %.
^h Grade TP347LN shall have a columbium (niobium) plus tantalum content of not less than 15 times the carbon content.
ⁱ The method of analysis for nitrogen shall be a matter of agreement between the purchaser and manufacturer.