



Standard Specification for Seamless and Welded Carbon Steel Water-Well Pipe¹

This standard is issued under the fixed designation A 589; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers four specific types of plain end or threaded and coupled carbon steel pipe for use in water wells.

1.2 Each type of water well pipe shall conform to the following methods of manufacture and grade as specified on the purchase order:

1.2.1 *Type I, Drive Pipe*—Seamless or electric-resistance-welded, Grades A and B.

1.2.2 *Type II, Water-Well Reamed and Drifted Pipe*—Seamless or electric-resistance-welded, Grades A and B, or furnace-butt welded.

1.2.3 *Type III, Driven Well Pipe*—Seamless or electric-resistance-welded, Grades A and B, or furnace-butt welded.

1.2.4 *Type IV, Water-Well Casing Pipe*—Seamless or electric-resistance-welded, Grades A and B, or furnace-butt welded.

1.3 The values stated in inch-pound units are to be regarded as the standard.

NOTE 1—The dimensionless designator NPS (nominal pipe size) has been substituted in this standard for such traditional terms as “nominal diameter,” “size,” and “nominal size.”

2. Referenced Documents

2.1 ASTM Standards:

A 53 Specification for Pipe, Steel, Black and Hot-Dipped, Zinc-Coated Welded and Seamless²

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products³

A 751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products³

A 865 Specification for Threaded Couplings, Steel, Black or Zinc Coated (Galvanized), Welded or Seamless, for Use in Steel Pipe Joints²

2.2 API Standard:

5L Specification for Line Pipe⁴

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *defect*—an imperfection of sufficient size or magnitude to be cause for rejection.

3.1.2 *imperfection*—any discontinuity or irregularity found in the pipe.

4. Ordering Information

4.1 Orders for material to this specification should include the following, as required to describe the desired material adequately:

4.1.1 Quantity (feet or number of lengths),

4.1.2 Name of material or type number (see 1.2),

4.1.3 Method of manufacture (furnace-butt welded, seamless, or electric-resistance-welded),

4.1.4 Grade (A or B for seamless or electric-resistance welded),

4.1.5 Finish (black or galvanized),

4.1.6 Dimensions (NPS or outside diameter and wall thickness, or both, for Types I, II, and III. Outside diameter and wall thickness for Type IV),

4.1.7 End finish (plain end or threaded and coupled),

4.1.8 Coupling class for Type III (standard pipe, line pipe, or reamed and drifted pipe coupling),

4.1.9 Coupling make-up (hand tight or power tight),

4.1.10 Length (required random range length or special lengths),

4.1.11 Specification designation, and

4.1.12 Special requirements.

5. Materials and Manufacture

5.1 The steel for both seamless and welded pipe shall be made by one of the following processes: open-hearth, electric-furnace, or basic-oxygen.

5.2 Steel may be cast in ingots or may be strand cast. When steels of different grades are sequentially strand cast, identification of the resultant transition material is required. The producer shall remove the transition material by any established procedure that positively separates the grades.

6. Chemical Composition

6.1 The steel shall conform to the following requirements as to chemical composition:

Phosphorus, max, %	0.050
Sulfur, max, %	0.060

¹ This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.09 on Carbon Steel Tubular Products.

Current edition approved Oct. 10, 1996. Published October 1997. Originally published as A 589 – 68. Last previous edition A 589 – 95a.

² *Annual Book of ASTM Standards*, Vol 01.01.

³ *Annual Book of ASTM Standards*, Vol 01.03.

⁴ Available from American Petroleum Institute, Division of Production, 300 Corrigan Tower Building, Dallas, TX 75201.

7. Heat Analysis

7.1 An analysis of each heat of steel shall be made by the manufacturer to determine the percentage of the elements specified in 6.1. When requested by the purchaser, the chemical composition thus determined shall be reported to the purchaser, and shall conform to the requirements specified in 6.1.

8. Product Analysis

8.1 An analysis may be made by the purchaser on two lengths of pipe from each lot of 500 lengths, or fraction thereof. Samples for chemical analysis and the methods of analysis shall conform to the requirements of Test Methods, Practices, and Terminology A 751. The chemical composition thus determined shall conform to the requirements specified in 6.1.

8.2 If the analysis of either pipe does not conform to the requirements of 6.1, analysis shall be made on additional lengths of pipe of double the original number from the same lot, each of which shall conform to the requirements specified.

9. Tensile Requirements

9.1 The material shall conform to the requirements as to tensile properties specified in Table 1. See Table 2 for minimum elongation values.

TABLE 1 Tensile Requirements

	Butt Welded	Grade A	Grade B
Tensile strength, min, psi (MPa)	48 000 (330)	48 000 (330)	60 000 (415)
Yield strength, min, psi (MPa)	30 000 (205)	30 000 (205)	35 000 (240)
Elongation in 2 in.	A,B	A,B	A,B

^A The minimum elongation in 2 in. (50.8 mm) shall be that determined by the following equation:

$$e = 625\ 000\ A^{0.2} / U^{0.9}$$

where:

e = minimum elongation in 2 in. (50.8 mm) in percent rounded to the nearest 0.5 %.

A = cross-sectional area of the tension test specimen in square inches, based on specified outside diameter or nominal specimen width and specified wall thickness rounded to the nearest 0.01 in.2 If the area thus calculated is greater than 0.75 in.2, then the value 0.75 shall be used.

U = specified tensile strength, psi.

^B See Table 2 for minimum elongation values for various size tension specimens and grades.

9.2 The test specimen taken across the weld shall show a tensile strength not less than the minimum tensile strength specified for the grade of pipe ordered. This test is not required for pipe under 8 in. in outside diameter.

TABLE 2 Elongation Values^A

Area, A in. ^B	Tension Test Specimen			Elongation in 2 in. min %		
	Specified Wall Thickness, in. ^C			Specified Tensile Strength, psi		
	¼ -in. Specimen	1-in. Specimen	1 ½ -in. Specimen	45 000	48 000	60 000
0.75 and greater	0.944 and greater	0.746 and greater	0.497 and greater	38.5	36.0	29.5
0.74	0.980-0.993	0.735-0.745	0.490-0.496	38.0	36.0	29.5
0.73	0.967-0.979	0.726-0.734	0.484-0.489	38.0	36.0	29.5
0.72	0.954-0.966	0.715-0.725	0.477-0.483	38.0	36.0	29.5
0.71	0.941-0.953	0.706-0.714	0.471-0.476	38.0	35.5	29.0
0.70	0.927-0.940	0.695-0.705	0.464-0.470	38.0	35.5	29.0
0.69	0.914-0.926	0.686-0.694	0.457-0.463	37.5	35.5	29.0
0.68	0.900-0.913	0.675-0.685	0.450-0.456	37.5	35.5	29.0
0.67	0.887-0.899	0.666-0.674	0.444-0.449	37.5	35.5	29.0
0.66	0.874-0.886	0.655-0.665	0.437-0.443	37.5	35.0	29.0
0.65	0.861-0.873	0.646-0.654	0.431-0.436	37.0	35.0	28.5
0.64	0.847-0.860	0.635-0.645	0.424-0.430	37.0	35.0	28.5
0.63	0.834-0.846	0.626-0.634	0.417-0.423	37.0	35.0	28.5
0.62	0.820-0.833	0.615-0.625	0.410-0.416	37.0	35.0	28.5
0.61	0.807-0.819	0.606-0.614	0.404-0.409	36.5	34.5	28.5
0.60	0.794-0.806	0.595-0.605	0.397-0.403	36.5	34.5	28.5
0.59	0.781-0.793	0.586-0.594	0.391-0.396	36.5	34.5	28.0
0.58	0.767-0.780	0.575-0.585	0.384-0.390	36.5	34.5	28.0
0.57	0.754-0.766	0.566-0.574	0.377-0.383	36.0	34.0	28.0
0.56	0.740-0.753	0.555-0.565	0.370-0.376	36.0	34.0	28.0
0.55	0.727-0.739	0.546-0.554	0.364-0.369	36.0	34.0	28.0
0.54	0.714-0.726	0.535-0.545	0.357-0.363	36.0	34.0	27.5
0.53	0.701-0.713	0.526-0.534	0.351-0.356	35.5	33.5	27.5
0.52	0.687-0.700	0.515-0.525	0.344-0.350	35.5	33.5	27.5
0.51	0.674-0.686	0.506-0.514	0.337-0.343	35.5	33.5	27.5
0.50	0.660-0.673	0.495-0.505	0.330-0.336	35.5	33.5	27.0
0.49	0.647-0.659	0.486-0.494	0.324-0.329	35.0	33.0	27.0
0.48	0.634-0.646	0.475-0.485	0.317-0.323	35.0	33.0	27.0
0.47	0.621-0.633	0.466-0.474	0.311-0.316	35.0	33.0	27.0
0.46	0.607-0.620	0.455-0.465	0.304-0.310	34.5	33.0	27.0
0.45	0.594-0.606	0.446-0.454	0.297-0.303	34.5	32.5	26.5
0.44	0.580-0.593	0.435-0.445	0.290-0.296	34.5	32.5	26.5
0.43	0.567-0.579	0.426-0.434	0.284-0.289	34.5	32.5	26.5
0.42	0.554-0.566	0.415-0.425	0.277-0.283	34.0	32.0	26.5
0.41	0.541-0.553	0.406-0.414	0.271-0.276	34.0	32.0	26.0
0.40	0.527-0.540	0.395-0.405	0.264-0.270	34.0	32.0	26.0
0.39	0.514-0.526	0.386-0.394	0.257-0.263	33.5	31.5	26.0

TABLE 2 Continued

Area, A in. ^B	Tension Test Specimen			Elongation in 2 in. min %		
	Specified Wall Thickness, in. ^C			Specified Tensile Strength, psi		
	¾ -in. Specimen	1-in. Specimen	1 ½ -in. Specimen	45 000	48 000	60 000
0.38	0.500–0.513	0.375–0.385	0.250–0.256	33.5	31.5	26.0
0.37	0.487–0.499	0.366–0.374	0.244–0.249	33.0	31.5	25.5
0.36	0.474–0.486	0.355–0.365	0.237–0.243	33.0	31.0	25.5
0.35	0.461–0.473	0.346–0.354	0.231–0.236	33.0	31.0	25.5
0.34	0.477–0.460	0.335–0.345	0.224–0.230	32.5	31.0	25.0
0.33	0.434–0.446	0.326–0.334	0.217–0.233	32.5	30.5	25.0
0.32	0.420–0.433	0.315–0.325	0.210–0.216	32.5	30.5	25.0
0.31	0.407–0.419	0.306–0.314	0.204–0.209	32.0	30.5	25.0
0.30	0.394–0.406	0.295–0.305	0.197–0.203	32.0	30.0	24.5
0.29	0.381–0.393	0.286–0.294	0.191–0.196	31.5	30.0	24.5
0.28	0.367–0.380	0.275–0.285	0.184–0.190	31.5	29.5	24.5
0.27	0.354–0.366	0.266–0.274	0.177–0.183	31.0	29.5	24.0
0.26	0.340–0.353	0.255–0.265	0.170–0.176	31.0	29.0	24.0
0.25	0.327–0.339	0.246–0.254	0.164–0.169	30.5	29.0	23.5
0.24	0.314–0.326	0.235–0.245	0.157–0.163	30.5	29.0	23.5
0.23	0.301–0.313	0.226–0.234	0.151–0.156	30.0	28.5	23.5
0.22	0.287–0.300	0.251–0.225	0.144–0.150	30.0	28.5	23.0
0.21	0.274–0.286	0.206–0.214	0.137–0.143	29.5	28.0	23.0
0.20	0.260–0.273	0.195–0.205	0.130–0.136	29.5	27.5	22.5
0.19	0.247–0.269	0.186–0.194	0.124–0.129	29.0	27.5	22.5
0.18	0.234–0.246	0.175–0.185	0.117–0.123	29.0	27.0	22.0
0.17	0.221–0.233	0.166–0.174	0.111–0.116	28.5	27.0	22.0
0.16	0.207–0.220	0.155–0.165	0.104–0.110	28.0	26.5	21.5
0.15	0.194–0.206	0.146–0.154	0.097–0.103	27.5	26.0	21.5
0.14	0.180–0.193	0.135–0.145	0.091–0.096	27.5	26.0	21.0
0.13	0.167–0.179	0.126–0.134	0.084–0.090	27.0	25.5	21.0
0.12	0.154–0.166	0.115–0.125	0.077–0.083	26.5	25.0	20.5
0.11	0.141–0.153	0.106–0.114	0.071–0.076	26.0	24.5	20.0
0.10	0.127–0.140	0.095–0.105	0.064–0.070	25.5	24.0	19.5
0.09	0.114–0.126	0.086–0.094	0.057–0.063	25.0	23.5	19.5
0.08	0.100–0.113	0.075–0.085	0.050–0.056	24.5	23.0	19.0
0.07	0.087–0.099	0.066–0.074	0.044–0.049	24.0	22.5	18.5
0.06	0.074–0.086	0.055–0.065	0.037–0.043	23.0	22.0	18.0
0.05	0.061–0.073	0.046–0.054	0.031–0.036	22.5	21.0	17.0
0.04	0.047–0.060	0.035–0.045	0.024–0.030	21.5	20.0	16.5
0.03	0.034–0.046	0.026–0.034	0.017–0.023	20.0	19.0	15.5
0.02	0.020–0.033	0.015–0.025	0.010–0.016	18.5	17.5	14.5
0.01 and less	0.019 and less	0.014 and less	0.009 and less	16.0	15.0	12.5

^A Tabulated in this table are the minimum elongation values calculated by the equation given in Table 1.

^B 1 in.² = 645.16 mm².

^C 1 in. = 25.4 mm.

10. Dimensions, Weights, and Permissible Variations

10.1 The dimensions and weights of all types of pipe included in this specification are listed in Tables 3-10:

Type	Tables
I, Drive Pipe	3, 4
II, Reamed and Drifted Pipe	5, 6
III, Driven Well Pipe	7, 8
IV, Water-Well Casing Pipe	9, 10

10.2 Permissible Variations in Weight and Dimensions:

10.2.1 *Weight*—The weight of all types of pipe included in this specification shall vary not more than ±5 % from that prescribed. The weight tolerance for pipe NPS 4 and under may be determined from the weight of the customary lifts of pipe as produced for shipment, divided by the number of feet of pipe in the lift. For pipe over NPS 4, where individual lengths may be weighed, the weight is applicable to the individual length.

10.2.2 *Outside Diameter*—For pipe NPS 1½ and under, the outside diameters shall vary not more than ¼ in. (0.4 mm) from the outside diameter specified. For pipe NPS 2 and over

the outside diameter shall vary not more than ±1 % from the size specified.

10.2.3 *Inside Diameter*—For Type II pipe, the inside diameter at any point, shall permit passage of a drift pin having a length and diameter as indicated in Table 5 and Table 11.

10.2.4 *Thickness*—The minimum wall thickness shall be not more than 12.5 % under the nominal wall thickness specified.

10.3 Lengths:

10.3.1 Unless otherwise specified on the purchase order, pipe lengths shall be in accordance with the following regular practice:

10.3.1.1 Types I, II, and IV pipe may be furnished in single random lengths of 16 to 22 ft (4.9 to 6.7 m).

10.3.1.2 Type III pipe may be furnished in a random range from 3 to 6 ft (0.9 to 1.8 m) or 6 to 10 ft (1.8 to 3.0 m) as specified.

10.3.2 Random lengths other than indicated in 10.3.1 and cut lengths, shall be subject to negotiation and shall be indicated on the purchase order.

TABLE 3 Dimensions, Weights, and Test Pressures for Drive Pipe

NPS Designator	Weight per Foot, lb/ft ^A		Wall Thickness, in. ^B	Diameters, in. ^B		No. of Threads per Inch	Couplings			Test Pressures, psi ^C	
	Nominal Threads and Couplings	Calculated Plain Ends		Outside	Inside		Length, in. ^B	Outside Diameter, in. ^B	Calculated Weight, lb ^D	Grade A	Grade B
6	19.45	18.97	0.280	6.625	6.065	8	5 1/8	7.290	13.35	1200	1300
8	25.55	24.70	0.277	8.625	8.071	8	6 1/8	9.625	26.89	1200	1300
8	29.35	28.55	0.322	8.625	7.981	8	6 1/8	9.625	26.89	1300	1600
8	32.40	31.27	0.354	8.625	7.917	8	6 1/8	9.625	26.89	1300	1600
10	32.75	31.20	0.279	10.750	10.192	8	6 5/8	11.750	36.05	940	1100
10	35.75	34.24	0.307	10.750	10.136	8	6 5/8	11.750	36.05	1000	1200
10	41.85	40.48	0.365	10.750	10.020	8	6 5/8	11.750	36.05	1200	1400
12	45.45	43.77	0.330	12.750	12.090	8	6 5/8	14.000	52.72	950	1100
12	51.15	49.56	0.375	12.750	12.000	8	6 5/8	14.000	52.72	1100	1200
14 D	57.00	54.57	0.375	14.000	13.250	8	7 1/8	15.000	50.22	950	1100
16 D	65.30	62.58	0.375	16.000	15.250	8	7 1/8	17.000	57.17	850	1000

^A 1 lb/ft = 1.488 kg/m.
^B 1 in. = 25.4 mm.
^C 1 psi = 6.895 MPa.
^D 1 lb = 0.454 kg.

TABLE 4 Basic Threading Data for Drive Pipe

NOTE—All dimensions are in inches (1 in. = 25.4 mm).

NOTE—All dimensions are in inches (1 in. = 25.4 mm).													
Pipe		Threads ^A					Coupling						
NPS Designator	Outside Diameter	Number per Inch	Length, End of Pipe to Hand-tight Plane	Effective Length	Total Length, End of Pipe to Vanish Point	Pitch Diameter at Hand-tight Plane	Outside Diameter	Length	Diameter of Recess	Depth of Recess	Length, Face of Coupling to Hand-tight Plane	Width of Bearing Face	Hand-tight Standoff, Threads
	D ^B		L ₁ ^B	L ₂ ^B	L ₄ ^B	E ₁ ^B	W ^B	N _L ^B	Q ^B	q ^B	M ^B	b ^B	A ^B
6	6.625	8	1.093	1.973	2.438	6.51375	7.390	5 1/8	6.719	3/8	0.595	1/4	6
8	8.625	8	1.593	2.473	2.938	8.51375	9.625	6 1/8	8.719	3/8	0.595	1/4	6
10	10.750	8	1.843	2.723	3.188	10.63875	11.750	6 5/8	10.844	3/8	0.595	3/8	6
12	12.750	8	1.843	2.723	3.188	12.63875	14.000	6 5/8	12.844	3/8	0.595	3/8	6
14 D	14.000	8	2.093	2.973	3.438	13.88875	15.000	7 1/8	14.094	3/8	0.595	3/8	6
16 D	16.000	8	2.093	2.973	3.438	15.88875	17.000	7 1/8	16.094	3/8	0.595	3/8	6

^A Taper of threads is 3/16 in./ft on diameter for all sizes.
^B See Fig. 1.

11. Ends

11.1 When ordered with plain ends, the pipe shall be furnished to the following practice unless otherwise specified.

11.1.1 *NPS 1 1/2 and smaller*—Unless otherwise specified on the purchase order, end finish shall be at the option of the manufacturer.

11.1.2 *NPS 2 and larger*—Unless otherwise specified on the purchase order, end finish shall be plain end beveled to an angle of 30° + 5° and -0°, as measured from a line drawn perpendicular to the axis of the pipe, with a root face of 1/16 in. ± 1/32 in.

11.2 When ordered threaded and coupled, each length of water well pipe shall be furnished with threaded ends and provided with a suitable coupling applied handling-tight. If couplings are required to be made up power tight, this shall be indicated on the purchase order.

11.3 The basic thread dimensions for each type of water

well pipe are shown in Table 4, Table 6, Table 8, and Table 10. An illustration of the joint of each type of water well pipe is shown in Figs. 1-4.

11.4 For Type III pipe, the threads on the pipe ends are interchangeable with either the standard pipe coupling, the reamed and drifted pipe coupling, or the API line pipe coupling. Orders for this class material shall indicate the coupling class desired.

11.4.1 Standard pipe couplings shall be manufactured in accordance with Specification A 865.

11.4.2 Line pipe couplings shall be manufactured in accordance with API 5L Specification for Line Pipe.

11.5 The threads on the pipe ends not protected by a coupling shall be suitably protected against damage in normal handling and transit conditions.

11.6 The length of the pipe shall be measured to the outer face of the coupling.

TABLE 5 Dimensions, Weights, and Test Pressures for Water-Well Reamed and Drifted Pipe

NPS Designator	Weight per Foot, lb/ft ^A		Wall Thickness, in. ^B	Diameters, in. ^B		No. of Threads per Inch	Couplings			Test Pressures, psi ^C		
	Nominal Threads and Couplings	Calculated Plain Ends		Out-side	In-side ^D		Length, in. ^B	Outside Diameter, in. ^B	Calculated Weight, lb ^E	Butt Welded	Grade A	Grade B
1	1.70	1.68	0.133	1.315	1.049	11 1/2	2 3/4	1.576	0.52	700	700	700
1 1/4	2.30	2.27	0.140	1.660	1.380	11 1/2	2 3/4	1.900	0.60	1000	1000	1100
1 1/2	2.75	2.72	0.145	1.900	1.610	11 1/2	2 3/4	2.200	0.84	1000	1000	1100
2	3.75	3.65	0.154	2.375	2.067	11 1/2	3 3/8	2.750	1.58	1000	2300	2500
2	4.00	3.94	0.167	2.375	2.041	11 1/2	3 3/8	2.750	1.58	1000	2500	2500
2 1/2	5.90	5.79	0.203	2.875	2.469	8	3 15/16	3.250	2.32	1000	2500	2500
3	7.70	7.58	0.216	3.500	3.068	8	4 1/16	4.000	3.80	1000	2200	2500
3 1/2	9.25	9.11	0.226	4.000	3.548	8	4 3/16	4.625	5.53	1200	2000	2400
4	11.00	10.79	0.237	4.500	4.026	8	4 5/16	5.200	7.14	1200	1900	2200
5	15.00	14.62	0.258	5.563	5.047	8	4 1/2	6.296	9.57	1200	1700	1900
6	19.45	18.97	0.280	6.625	6.065	8	4 11/16	7.390	12.32	...	1500	1800
8	29.35	28.55	0.322	8.625	7.981	8	5 1/16	9.625	22.35	...	1300	1600
10	41.85	40.48	0.365	10.750	10.020	8	5 9/16	11.750	30.61	...	1200	1400
12	51.15	49.56	0.375	12.750	12.000	8	5 15/16	14.000	47.96	...	1100	1200

^A 1 lb/ft = 1.488 kg/m.
^B 1 in. = 25.4 mm.
^C 1 psi = 6.895 MPa.
^D Drift pin dimensions (see Table 11)
^E 1 lb = 0.454 kg.

TABLE 6 Basic Threading Data for Water-Well Reamed and Drifted Pipe

NOTE—All dimensions are in inches (1 in. = 25.4 mm).

NPS Designator	Pipe		Threads ^A				Coupling						
	Outside Diameter	Number per Inch	Length, End of Pipe to Hand-tight Plane	Effective Length	Total Length, End of Pipe to Vanish Point	Pitch Diameter at Hand-tight Plane	Outside Diameter	Length	Diameter of Recess	Depth of Recess	Length, Face of Coupling to Hand-tight Plane	Width of Bearing Face	Hand-tight Standoff, Threads
	D ^B		L ₁ ^B	L ₂ ^B	L ₄ ^B	E ₁ ^B	W ^B	NL ^B	Q ^B	q ^B	M ^B	b ^B	A ^B
1	1.315	11 1/2	0.4811	0.6828	0.9845	1.24369	1.576	2 3/4	1.378	0.1875	0.5034	1/16	0
1 1/4	1.660	11 1/2	0.5051	0.7068	1.0085	1.58869	1.900	2 3/4	1.723	0.1875	0.5034	1/16	0
1 1/2	1.900	11 1/2	0.5218	0.7235	1.0252	1.82869	2.200	2 3/4	1.963	0.1875	0.5034	3/32	0
2	2.375	11 1/2	0.7012	0.9884	1.2901	2.29835	2.750	3 3/8	2.469	0.1875	0.5889	3/32	0
2 1/2	2.875	8	0.9342	1.1375	1.5712	2.77792	3.250	3 15/16	2.969	0.1875	0.6370	3/32	0
3	3.500	8	0.9967	1.2000	1.6337	3.40292	4.000	4 1/16	3.594	0.1875	0.6370	1/8	0
3 1/2	4.000	8	1.0467	1.2500	1.6837	3.90292	4.625	4 3/16	4.094	0.1875	0.6370	3/16	0
4	4.500	8	1.0967	1.3000	1.7337	4.40292	5.200	4 5/16	4.594	0.1875	0.6370	1/4	0
5	5.563	8	1.2030	1.4063	1.8400	5.46592	6.296	4 1/2	5.657	0.1875	0.6370	1/4	0
6	6.625	8	1.3092	1.5125	1.9462	6.52792	7.390	4 11/16	6.719	0.1875	0.6370	1/4	0
8	8.625	8	1.5092	1.7125	2.1462	8.52792	9.625	4 11/16	8.719	0.1875	0.6370	1/4	0
10	10.750	8	1.7217	1.9250	2.3587	10.65292	11.750	5 9/16	10.844	0.1875	0.6370	3/8	0
12	12.750	8	1.9217	2.1250	2.5587	12.65292	14.000	5 15/16	12.844	0.1875	0.6370	3/8	0

^A Taper of threads is 3/4 in./ft on diameter for all sizes.
^B See Fig. 2

12. Finish

12.1 The finished pipe shall be reasonably straight and free of defects. Any imperfection that exceeds 12 1/2 % of the nominal wall thickness, or violates minimum wall shall be considered a defect.

12.2 The pipe ends shall be free of burrs. The zinc coating on galvanized pipe shall be free of voids or excessive roughness.

13. Galvanized Pipe

13.1 For the types of water well pipe required with galvanized coating, such coating shall comply with the requirements of the latest revision of Specification A 53.

14. Number of Tests

14.1 One longitudinal or transverse tension test of seamless and welded pipe, and in addition, one transverse weld test for

TABLE 7 Dimensions,^A Weights,^A and Test Pressures for Driven Well Pipe

NPS Designator	Weight per Foot, lb/ft ^B		Wall Thickness, in. ^C	Diameters, in. ^C		No. of Threads per Inch	Test Pressures, psi ^D		Grade A	Grade B
	Nominal Threads and Couplings	Calculated Plain Ends		Outside	Inside ^A		Calculated Weight, lb ^E	Butt Welded		
1	1.68	1.68	0.133	1.315	1.049	11 ½	0.40	700	700	700
1 ¼	2.28	2.27	0.140	1.660	1.380	11 ½	0.48	1000	1000	1100
1 ½	2.73	2.72	0.145	1.900	1.610	11 ½	0.67	1000	1000	1100
2	3.68	3.65	0.154	2.375	2.067	11 ½	1.05	1000	2300	2500

^A Nominal T & C weights shown are based on the standard pipe coupling. For pipe weights with reamed and drifted coupling applied, see Table 5 of this specification. For weights with the line pipe coupling applied refer to API Standard 5L.

^B 1 lb/ft = 1.488 kg/m.

^C 1 in. = 25.4 mm.

^D 1 psi = 6.895 MPa.

^E 1 lb = 0.454 kg.

TABLE 8 Basic Threading Data^A for Driven Well Pipe

NOTE—All dimensions are inches (1 in. = 25.4 mm).

Pipe		Threads					Joint Make-up		
NPS Designator	Outside Diameter	Number per Inch	Length, End of Pipe to Hand-tight Plane	Effective Length	Total Length, End of Pipe to Vanish Point	Pitch Diameter at Handtight Plane	Length, Face of Coupling to Handtight Plane	Width of Bearing Face	Handtight Standoff, Threads
	D ^B		L ₁ ^B	L ₂ ^B	L ₄ ^B	E ₁ ^B	M ^B	b ^B	A ^B
1	1.315	11 ½	0.400	0.6828	0.9845	1.23863	0.1304	approximately ⅓	5.22
1 ¼	1.660	11 ½	0.420	0.7068	1.0085	1.58338	0.1304	thickness of	5.27
1 ½	1.900	11 ½	0.420	0.7235	1.0252	1.82234	0.1304	coupling	5.46
2	2.375	11 ½	0.436	0.7565	1.0582	2.29627	0.1304		5.66

^A Based on standard-weight pipe with standard coupling. For basic threading data of reamed and drifted coupling see Table 6 of this specification. For line pipe coupling refer to API Standard 5L.

^B See Fig. 3.

TABLE 9 Dimensions, Weights, and Test Pressures for Water-Well Casing

Size, Outside Diameter, in. ^A	Weight per Foot, lb/ft ^B		Wall Thickness, in. ^A	Diameters, in. ^A		No. of Threads per Inch	Couplings		Test Pressures, psi ^C	
	Threads and Couplings	Plain Ends		Length, in. ^A	Outside Diameter, in. ^A		Calculated Weight, lb ^D			
3.500	4.60	4.51	0.125	3.500	3.250	14	3 ⅛	4.000	2.86	1100
4.000	5.65	5.53	0.134	4.000	3.732	14	3 ⅛	4.500	3.24	1000
4.500	6.75	6.61	0.142	4.500	4.216	14	3 ⅝	5.000	4.26	950
5.500	9.00	8.79	0.154	5.500	5.192	14	4 ⅛	6.050	6.38	850
6.000	10.50	10.22	0.164	6.000	5.672	14	4 ⅛	6.625	7.84	850
6.625	13.00	12.72	0.185	6.625	6.255	11 ½	4 ⅝	7.390	11.88	850
8.625	17.80	16.90	0.188	8.625	8.249	11 ½	5 ¼	9.625	22.92	650

^A 1 in. = 25.4 mm.

^B 1 lb/ft = 1.488 kg/m.

^C 1 psi = 6.895 MPa.

^D 1 lb = 0.454 kg.

electric-welded pipe NPS 8 and larger, shall be made on one length of pipe from each lot of 500 lengths, or fraction thereof, of each size. A length is defined as the length as ordered, except that in the case of orders for lengths shorter than single random, the term lot shall apply to the lengths as rolled, prior to cutting to the required short lengths.

14.2 Each length of pipe shall be subjected to the hydrostatic test as indicated for the type, size, and grade as shown in Tables 4-9. The hydrostatic pressure shall be maintained for not less than 5 s for all sizes of seamless and electric-resistance-welded pipe.

15. Retests

15.1 If the results of the tension tests of any lot do not conform to the requirements of Table 1, the lot shall be rejected, or retests shall be made on additional pipe of double the original number from the same lot, each of which shall conform to the requirements specified.

16. Test Methods

16.1 The tension tests required shall conform to those described in the latest issue of Test Methods and Definitions A 370.