

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Photovoltaic devices –
Part 3: Measurement principles for terrestrial photovoltaic (PV) solar devices
with reference spectral irradiance data

Dispositifs photovoltaïques –
Partie 3: Principes de mesure des dispositifs solaires photovoltaïques (PV) à
usage terrestre incluant les données de l'éclairement spectral de référence

<https://standards.iteh.ai/catalog/standards/iec/8651173a-a4c5-4b75-99ba-38e4e246cb7c/iec-60904-3-2008>



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2008 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch

Tel.: +41 22 919 02 11

Fax: +41 22 919 03 00

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

- Catalogue des publications de la CEI: www.iec.ch/searchpub/cur_fut-f.htm

Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,...). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.

- Just Published CEI: www.iec.ch/online_news/justpub

Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.

- Electropedia: www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International en ligne.

- Service Clients: www.iec.ch/webstore/custserv/custserv_entry-f.htm

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:

Email: csc@iec.ch

Tél.: +41 22 919 02 11

Fax: +41 22 919 03 00

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Photovoltaic devices –

**Part 3: Measurement principles for terrestrial photovoltaic (PV) solar devices
with reference spectral irradiance data**

Dispositifs photovoltaïques –

**Partie 3: Principes de mesure des dispositifs solaires photovoltaïques (PV) à
usage terrestre incluant les données de l'éclairement spectral de référence**

<https://standards.iteh.ai/catalog/standards/iec/6051173a-a4c5-4b75-99ba-38e4e246cb7c/iec-60904-3-2008>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX



CONTENTS

FOREWORD.....	3
1 Scope and object.....	5
2 Normative references	5
3 Measurement principles.....	6
4 Reference solar spectral irradiance distribution	6
Annex A (normative) Use of SMARTS	31
Figure 1 – Reference solar spectral irradiance distribution listed in Table 1.....	30
Table 1 – Reference solar spectral irradiance distribution	8

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

IEC 60904-3:2008

<https://standards.iteh.ai/catalog/standards/iec/6651173a-a4c5-4b75-99ba-38e4e246cb7c/iec-60904-3-2008>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

PHOTOVOLTAIC DEVICES –

**Part 3: Measurement principles for terrestrial photovoltaic (PV)
solar devices with reference spectral irradiance data**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60904-3 has been prepared by IEC technical committee 82: Solar photovoltaic energy systems.

This second edition cancels and replaces the first edition published in 1989. This edition constitutes a technical revision.

The main changes with respect to the previous edition are as follows:

- wavelength range extended deeper into the ultraviolet (280 nm instead of 305 nm);
- sunfacing surface considered;
- uniform wavelength intervals used (0,5 nm up to 400 nm, 1 nm up to 1 700 nm, 5 nm up to 4 000 nm); better resolution than in the first edition of 60904-3;
- more representative atmospheric conditions are considered;
- the model used to generate the spectrum has changed from BRITE to SMARTS (version 2.9), which is publicly available.

In addition, the terminology annex has been removed in the new version because this part is included in another technical committee 82 document (second edition of IEC TS 61836). The titles of some clauses have been changed (others have been added) to accord with the usual structure of IEC standards.

The text of this standard is based on the following documents:

FDIS	Report on voting
82/511/FDIS	82/519/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 60904 series, published under the general title *Photovoltaic devices*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

PHOTOVOLTAIC DEVICES –

Part 3: Measurement principles for terrestrial photovoltaic (PV) solar devices with reference spectral irradiance data

1 Scope and object

This part of IEC 60904 applies to the following photovoltaic devices for terrestrial applications:

- solar cells with or without a protective cover;
- sub-assemblies of solar cells;
- modules;
- systems.

NOTE The term “test specimen” is used to denote any of these devices.

The principles contained in this standard cover testing in both natural and simulated sunlight.

This standard is not applicable to solar cells designed for operation in concentrated sunlight or to modules embodying concentrators.

Photovoltaic conversion is spectrally selective due to the nature of the semiconductor materials used in PV solar cells and modules. To compare the relative performance of different PV devices and materials a reference standard solar spectral distribution is necessary. This standard includes such a reference solar spectral irradiance distribution.

This standard also describes basic measurement principles for determining the electrical output of PV devices. The principles given in this standard are designed to relate the performance rating of PV devices to a common reference terrestrial solar spectral irradiance distribution.

The reference terrestrial solar spectral irradiance distribution given in this standard is required in order to classify solar simulators according to the spectral performance requirements contained in IEC 60904-9.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60891:1987, *Procedures for temperature and irradiance corrections to measured I-V characteristics of crystalline silicon photovoltaic devices*
Amendment 1 (1992)

IEC 60904-1, *Photovoltaic devices – Part 1: Measurements of photovoltaic current-voltage characteristics*

IEC 60904-2, *Photovoltaic devices – Part 2: Requirements for reference solar devices*

IEC 60904-7, *Photovoltaic devices – Part 7: Computation of spectral mismatch error introduced in the testing of a photovoltaic device*

IEC 60904-9, *Photovoltaic devices – Part 9: Solar simulator performance requirements***3 Measurement principles**

In current practice the photovoltaic performance of a solar cell or module is determined by exposing it at a known temperature to stable sunlight, natural or simulated, and measuring its current-voltage (I-V) characteristic curve while measuring the magnitude of both the incident irradiance and the PV device temperature. Detailed I-V curve measurement procedures are included in IEC 60904-1. The measured performances can then be corrected to Standard Test Conditions (STC) or other desired conditions of irradiance and temperature according to IEC 60891. The corrected power output at the rated voltage and STC is commonly referred to as the rated power.

Incident irradiance can be measured by means of a PV reference device (whose spectral response must be known) or, if measuring under natural sunlight, by means of a thermopile-type irradiance detector (pyranometer). If a PV reference device is used, it shall satisfy the requirements specified in IEC 60904-2. Temperature determination of the PV device under test shall be made according to IEC 60904-1.

Since a solar cell has a wavelength-dependent response, its performance is significantly affected by the spectral distribution of the incident radiation, which in natural sunlight varies with several factors such as location, weather, time of year, time of day, orientation of the receiving surface, etc., and with a simulator varies with its type and conditions of use. If the irradiance is measured either with a thermopile-type radiometer (that is not spectrally selective) or with a reference solar cell, the spectral irradiance distribution of the incoming light must be known in order to make the necessary corrections to obtain the performance of the PV device under the reference solar spectral distribution defined in this standard as specified in IEC 60904-7. It is also possible for a user or array designer, using the spectral response of the cells, to compute within a reasonable tolerance the performance of a PV device when exposed to light of any other known spectral irradiance distribution. The methodology for this calculation can be found in IEC 60904-7.

4 Reference solar spectral irradiance distribution

The reference solar spectral distribution AM1.5 is given in Table 1 and Figure 1. This is a total distribution (direct + diffuse) of sunlight, corresponding to an integrated irradiance of 1 000 W·m⁻² incident on a sun-facing plane surface tilted at 37° to the horizontal considering the wavelength-dependent albedo of a light bare soil, under the following atmospheric conditions:

- U.S. Standard Atmosphere with CO₂ concentration increased to current level (370 ppm), a rural aerosol model, and no pollution;
- precipitable water: 1,4164 cm;
- ozone content: 0,3438 atm-cm (or 343,8 DU);
- turbidity (aerosol optical depth): 0,084 at 500 nm;
- pressure: 1013,25 hPa (i.e., sea level).

Data contained in Table 1 have been generated using the solar spectral model SMARTS, Version 2.9.2. A general description of this model and its suitability to reproduce actual solar spectral irradiance distributions can be found in “Proposed Reference Irradiance Spectra for Solar Energy Systems Testing” by C. A. Gueymard, C. Myers and K. Emery¹⁾, and in the references therein. Table 1 can be obtained using the data contained in Annex A as an input to the model SMARTS Version 2.9.2. The resulting output spectral irradiance values have to

¹⁾ C. A. Gueymard, C. Myers and K. Emery. “Proposed Reference Irradiance Spectra for Solar Energy Systems Testing”. *Energie solaire*, Vol 73, No. 6, pp. 443-467, 2002.

be multiplied by a normalization factor (0,9971) in order to get an integrated irradiance of $1000 \text{ W} \cdot \text{m}^{-2}$ in the wavelength range 0 to infinity.

At the time of publication of this standard the SMARTS Version 2.9.2 spectral model code is available, free of charge, subject to the author's license agreement, at <http://www.nrel.gov/rredc/smarts>. A copy of the model, not for distribution purposes, is kept under IEC TC 82 WG 2 control.

Withdrawing

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

IEC 60904-3:2008
<https://standards.iteh.ai/catalog/standards/iec/8651173a-a4c5-4b75-99ba-38e4e246cb7c/iec-60904-3-2008>

Table 1 – Reference solar spectral irradiance distribution

Wave-length (nm)	Spectral irradiance ($\text{W} \cdot \text{m}^{-2} \cdot \text{nm}^{-1}$)	Spectral photon irradiance ($\text{m}^{-2} \cdot \text{s}^{-1} \cdot \text{nm}^{-1}$)	Cumulative integrated irradiance ($\text{W} \cdot \text{m}^{-2}$)
280,0	4,72E-23	6,649E-05	0,00E+00
280,5	1,23E-21	1,733E-03	3,19E-22
281,0	5,67E-21	8,025E-03	2,04E-21
281,5	1,56E-19	2,213E-01	4,25E-20
282,0	1,19E-18	1,691E+00	3,79E-19
282,5	4,53E-18	6,443E+00	1,81E-18
283,0	1,84E-17	2,621E+01	7,54E-18
283,5	3,53E-17	5,032E+01	2,10E-17
284,0	7,25E-16	1,036E+03	2,11E-16
284,5	2,48E-15	3,550E+03	1,01E-15
285,0	7,99E-15	1,146E+04	3,63E-15
285,5	4,25E-14	6,107E+04	1,62E-14
286,0	1,36E-13	1,964E+05	6,10E-14
286,5	8,36E-13	1,205E+06	3,04E-13
287,0	2,73E-12	3,942E+06	1,20E-12
287,5	1,09E-11	1,573E+07	4,60E-12
288,0	6,22E-11	9,011E+07	2,29E-11
288,5	1,71E-10	2,485E+08	8,12E-11
289,0	5,61E-10	8,162E+08	2,64E-10
289,5	2,07E-09	3,015E+09	9,22E-10
290,0	6,00E-09	8,758E+09	2,94E-09
290,5	1,37E-08	2,010E+10	7,87E-09
291,0	3,50E-08	5,120E+10	2,00E-08
291,5	1,09E-07	1,597E+11	5,60E-08
292,0	2,68E-07	3,932E+11	1,50E-07
292,5	4,26E-07	6,267E+11	3,23E-07
293,0	8,62E-07	1,272E+12	6,45E-07
293,5	2,26E-06	3,345E+12	1,43E-06
294,0	4,16E-06	6,160E+12	3,03E-06
294,5	6,57E-06	9,743E+12	5,72E-06
295,0	1,23E-05	1,820E+13	1,04E-05
295,5	2,77E-05	4,127E+13	2,04E-05
296,0	4,78E-05	7,117E+13	3,93E-05
296,5	7,11E-05	1,062E+14	6,90E-05
297,0	9,65E-05	1,443E+14	1,11E-04
297,5	1,86E-04	2,779E+14	1,81E-04
298,0	2,89E-04	4,336E+14	3,00E-04
298,5	3,57E-04	5,362E+14	4,62E-04
299,0	4,91E-04	7,386E+14	6,73E-04
299,5	8,58E-04	1,294E+15	1,01E-03
300,0	0,0010	1,537E+15	0,00
300,5	0,0012	1,878E+15	0,00
301,0	0,0019	2,916E+15	0,00
301,5	0,0027	4,073E+15	0,00

Wave-length (nm)	Spectral irradiance ($\text{W} \cdot \text{m}^{-2} \cdot \text{nm}^{-1}$)	Spectral photon irradiance ($\text{m}^{-2} \cdot \text{s}^{-1} \cdot \text{nm}^{-1}$)	Cumulative integrated irradiance ($\text{W} \cdot \text{m}^{-2}$)
302,0	0,0029	4,428E+15	0,01
302,5	0,0043	6,505E+15	0,01
303,0	0,0071	1,079E+16	0,01
303,5	0,0090	1,368E+16	0,01
304,0	0,0094	1,445E+16	0,02
304,5	0,0119	1,827E+16	0,02
305,0	0,0164	2,520E+16	0,03
305,5	0,0187	2,870E+16	0,04
306,0	0,0185	2,853E+16	0,05
306,5	0,0210	3,247E+16	0,06
307,0	0,0278	4,291E+16	0,07
307,5	0,0355	5,500E+16	0,09
308,0	0,0377	5,850E+16	0,11
308,5	0,0413	6,415E+16	0,13
309,0	0,0404	6,287E+16	0,15
309,5	0,0432	6,728E+16	0,17
310,0	0,0508	7,926E+16	0,19
310,5	0,0653	1,021E+17	0,22
311,0	0,0827	1,294E+17	0,26
311,5	0,0838	1,315E+17	0,30
312,0	0,0931	1,462E+17	0,34
312,5	0,0987	1,553E+17	0,39
313,0	0,1070	1,686E+17	0,44
313,5	0,1073	1,693E+17	0,49
314,0	0,1193	1,886E+17	0,55
314,5	0,1302	2,062E+17	0,61
315,0	0,1359	2,154E+17	0,68
315,5	0,1180	1,875E+17	0,74
316,0	0,1231	1,959E+17	0,80
316,5	0,1499	2,389E+17	0,87
317,0	0,1711	2,730E+17	0,95
317,5	0,1819	2,908E+17	1,04
318,0	0,1754	2,808E+17	1,13
318,5	0,1854	2,972E+17	1,22
319,0	0,2041	3,278E+17	1,32
319,5	0,1953	3,142E+17	1,42
320,0	0,2047	3,297E+17	1,52
320,5	0,2445	3,945E+17	1,63
321,0	0,2495	4,032E+17	1,75
321,5	0,2377	3,848E+17	1,88
322,0	0,2214	3,589E+17	1,99
322,5	0,2165	3,514E+17	2,10
323,0	0,2116	3,441E+17	2,21
323,5	0,2479	4,037E+17	2,32

Wave-length (nm)	Spectral irradiance ($\text{W} \cdot \text{m}^{-2} \cdot \text{nm}^{-1}$)	Spectral photon irradiance ($\text{m}^{-2} \cdot \text{s}^{-1} \cdot \text{nm}^{-1}$)	Cumulative integrated irradiance ($\text{W} \cdot \text{m}^{-2}$)
324,0	0,2746	4,478E+17	2,45
324,5	0,2824	4,613E+17	2,59
325,0	0,2781	4,550E+17	2,73
325,5	0,3234	5,299E+17	2,88
326,0	0,3801	6,238E+17	3,06
326,5	0,4060	6,674E+17	3,25
327,0	0,3969	6,534E+17	3,45
327,5	0,3835	6,323E+17	3,65
328,0	0,3501	5,781E+17	3,83
328,5	0,3706	6,128E+17	4,01
329,0	0,4211	6,975E+17	4,21
329,5	0,4674	7,753E+17	4,43
330,0	0,4700	7,808E+17	4,67
330,5	0,4268	7,100E+17	4,89
331,0	0,4015	6,689E+17	5,10
331,5	0,4168	6,956E+17	5,30
332,0	0,4350	7,270E+17	5,52
332,5	0,4379	7,330E+17	5,74
333,0	0,4282	7,178E+17	5,95
333,5	0,4061	6,817E+17	6,16
334,0	0,4138	6,957E+17	6,37
334,5	0,4438	7,473E+17	6,58
335,0	0,4625	7,800E+17	6,81
335,5	0,4518	7,631E+17	7,03
336,0	0,4140	7,002E+17	7,25
336,5	0,3810	6,455E+17	7,45
337,0	0,3727	6,323E+17	7,64
337,5	0,3993	6,785E+17	7,83
338,0	0,4329	7,365E+17	8,04
338,5	0,4539	7,735E+17	8,26
339,0	0,4622	7,888E+17	8,49
339,5	0,4731	8,085E+17	8,72
340,0	0,5003	8,564E+17	8,97
340,5	0,4993	8,558E+17	9,22
341,0	0,4700	8,068E+17	9,46
341,5	0,4680	8,045E+17	9,69
342,0	0,4879	8,400E+17	9,93
342,5	0,5062	8,728E+17	10,18
343,0	0,5134	8,865E+17	10,44
343,5	0,4847	8,381E+17	10,69
344,0	0,4172	7,225E+17	10,91
344,5	0,4019	6,970E+17	11,12
345,0	0,4576	7,948E+17	11,33
345,5	0,4879	8,486E+17	11,57
346,0	0,4764	8,298E+17	11,81
346,5	0,4852	8,463E+17	12,05
347,0	0,4926	8,605E+17	12,29

Wave-length (nm)	Spectral irradiance ($\text{W} \cdot \text{m}^{-2} \cdot \text{nm}^{-1}$)	Spectral photon irradiance ($\text{m}^{-2} \cdot \text{s}^{-1} \cdot \text{nm}^{-1}$)	Cumulative integrated irradiance ($\text{W} \cdot \text{m}^{-2}$)
347,5	0,4754	8,316E+17	12,54
348,0	0,4737	8,299E+17	12,77
348,5	0,4820	8,455E+17	13,01
349,0	0,4643	8,157E+17	13,25
349,5	0,4767	8,386E+17	13,48
350,0	0,5264	9,276E+17	13,73
350,5	0,5658	9,983E+17	14,01
351,0	0,5501	9,720E+17	14,29
351,5	0,5287	9,355E+17	14,56
352,0	0,5164	9,151E+17	14,82
352,5	0,4882	8,663E+17	15,07
353,0	0,5189	9,221E+17	15,32
353,5	0,5706	1,015E+18	15,59
354,0	0,6032	1,075E+18	15,89
354,5	0,6098	1,088E+18	16,19
355,0	0,6096	1,089E+18	16,49
355,5	0,5886	1,053E+18	16,79
356,0	0,5523	9,897E+17	17,08
356,5	0,5179	9,295E+17	17,35
357,0	0,4554	8,184E+17	17,59
357,5	0,4608	8,293E+17	17,82
358,0	0,4288	7,728E+17	18,04
358,5	0,3981	7,185E+17	18,25
359,0	0,4682	8,461E+17	18,46
359,5	0,5639	1,020E+18	18,72
360,0	0,5964	1,081E+18	19,01
360,5	0,5637	1,023E+18	19,30
361,0	0,5187	9,427E+17	19,57
361,5	0,5081	9,246E+17	19,83
362,0	0,5327	9,707E+17	20,09
362,5	0,5834	1,065E+18	20,37
363,0	0,6002	1,097E+18	20,66
363,5	0,5837	1,068E+18	20,96
364,0	0,6045	1,108E+18	21,26
364,5	0,5988	1,099E+18	21,56
365,0	0,6218	1,142E+18	21,86
365,5	0,6843	1,259E+18	22,19
366,0	0,7332	1,351E+18	22,54
366,5	0,7344	1,355E+18	22,91
367,0	0,7208	1,332E+18	23,28
367,5	0,7071	1,308E+18	23,63
368,0	0,6657	1,233E+18	23,98
368,5	0,6612	1,227E+18	24,31
369,0	0,6911	1,284E+18	24,65
369,5	0,7425	1,381E+18	25,00
370,0	0,7529	1,402E+18	25,38
370,5	0,6806	1,269E+18	25,74

Wave-length (nm)	Spectral irradiance ($\text{W}\cdot\text{m}^{-2}\cdot\text{nm}^{-1}$)	Spectral photon irradiance ($\text{m}^{-2}\cdot\text{s}^{-1}\cdot\text{nm}^{-1}$)	Cumulative integrated irradiance ($\text{W}\cdot\text{m}^{-2}$)
371,0	0,6914	1,291E+18	26,08
371,5	0,7184	1,344E+18	26,43
372,0	0,6725	1,259E+18	26,78
372,5	0,6407	1,201E+18	27,11
373,0	0,6171	1,159E+18	27,42
373,5	0,5562	1,046E+18	27,72
374,0	0,5548	1,045E+18	27,99
374,5	0,5507	1,038E+18	28,27
375,0	0,5876	1,109E+18	28,55
375,5	0,6497	1,228E+18	28,86
376,0	0,6728	1,274E+18	29,19
376,5	0,6620	1,255E+18	29,53
377,0	0,7102	1,348E+18	29,87
377,5	0,7922	1,506E+18	30,25
378,0	0,8535	1,624E+18	30,66
378,5	0,8318	1,585E+18	31,08
379,0	0,7417	1,415E+18	31,47
379,5	0,6649	1,270E+18	31,82
380,0	0,6987	1,337E+18	32,17
380,5	0,7486	1,434E+18	32,53
381,0	0,7616	1,461E+18	32,90
381,5	0,6864	1,318E+18	33,27
382,0	0,5851	1,125E+18	33,58
382,5	0,5061	9,746E+17	33,86
383,0	0,4537	8,747E+17	34,10
383,5	0,4392	8,479E+17	34,32
384,0	0,5082	9,824E+17	34,56
384,5	0,6118	1,184E+18	34,84
385,0	0,6716	1,302E+18	35,16
385,5	0,6418	1,245E+18	35,49
386,0	0,6192	1,203E+18	35,80
386,5	0,6438	1,253E+18	36,12
387,0	0,6496	1,265E+18	36,44
387,5	0,6402	1,249E+18	36,76
388,0	0,6340	1,238E+18	37,08
388,5	0,6295	1,231E+18	37,40
389,0	0,6834	1,338E+18	37,73
389,5	0,7575	1,485E+18	38,09
390,0	0,7947	1,560E+18	38,47
390,5	0,8014	1,575E+18	38,87
391,0	0,8489	1,671E+18	39,29
391,5	0,8609	1,697E+18	39,71
392,0	0,7926	1,564E+18	40,13
392,5	0,6606	1,305E+18	40,49
393,0	0,4784	9,464E+17	40,77
393,5	0,3804	7,536E+17	40,99
394,0	0,4942	9,803E+17	41,21

Wave-length (nm)	Spectral irradiance ($\text{W}\cdot\text{m}^{-2}\cdot\text{nm}^{-1}$)	Spectral photon irradiance ($\text{m}^{-2}\cdot\text{s}^{-1}\cdot\text{nm}^{-1}$)	Cumulative integrated irradiance ($\text{W}\cdot\text{m}^{-2}$)
394,5	0,6819	1,354E+18	41,50
395,0	0,8054	1,601E+18	41,87
395,5	0,8579	1,708E+18	42,29
396,0	0,7544	1,504E+18	42,69
396,5	0,5486	1,095E+18	43,02
397,0	0,4250	8,493E+17	43,26
397,5	0,6276	1,256E+18	43,52
398,0	0,8500	1,703E+18	43,89
398,5	1,0040	2,014E+18	44,36
399,0	1,0662	2,142E+18	44,88
399,5	1,0989	2,210E+18	45,42
400,0	1,1109	2,237E+18	45,97
401,0	1,1569	2,335E+18	47,10
402,0	1,2026	2,434E+18	48,28
403,0	1,1579	2,349E+18	49,46
404,0	1,1767	2,393E+18	50,63
405,0	1,1478	2,340E+18	51,79
406,0	1,1194	2,288E+18	52,93
407,0	1,0994	2,253E+18	54,04
408,0	1,1481	2,358E+18	55,16
409,0	1,2263	2,525E+18	56,35
410,0	1,0455	2,158E+18	57,48
411,0	1,1704	2,422E+18	58,59
412,0	1,2442	2,580E+18	59,80
413,0	1,1936	2,482E+18	61,02
414,0	1,1808	2,461E+18	62,20
415,0	1,2222	2,553E+18	63,41
416,0	1,2587	2,636E+18	64,65
417,0	1,2276	2,577E+18	65,89
418,0	1,1743	2,471E+18	67,09
419,0	1,2222	2,578E+18	68,29
420,0	1,1199	2,368E+18	69,46
421,0	1,2720	2,696E+18	70,66
422,0	1,2547	2,665E+18	71,92
423,0	1,2149	2,587E+18	73,15
424,0	1,2082	2,579E+18	74,36
425,0	1,2452	2,664E+18	75,59
426,0	1,2100	2,595E+18	76,82
427,0	1,1690	2,513E+18	78,01
428,0	1,1805	2,543E+18	79,18
429,0	1,0931	2,361E+18	80,32
430,0	0,8721	1,888E+18	81,30
431,0	0,7916	1,718E+18	82,13
432,0	1,3169	2,864E+18	83,19
433,0	1,2252	2,671E+18	84,46
434,0	1,1319	2,473E+18	85,64
435,0	1,2416	2,719E+18	86,83

Wave-length (nm)	Spectral irradiance ($\text{W}\cdot\text{m}^{-2}\cdot\text{nm}^{-1}$)	Spectral photon irradiance ($\text{m}^{-2}\cdot\text{s}^{-1}\cdot\text{nm}^{-1}$)	Cumulative integrated irradiance ($\text{W}\cdot\text{m}^{-2}$)
436,0	1,3619	2,989E+18	88,13
437,0	1,3903	3,058E+18	89,50
438,0	1,2203	2,691E+18	90,81
439,0	1,1741	2,595E+18	92,01
440,0	1,3460	2,981E+18	93,27
441,0	1,3274	2,947E+18	94,60
442,0	1,4209	3,161E+18	95,98
443,0	1,4411	3,214E+18	97,41
444,0	1,4043	3,139E+18	98,83
445,0	1,4577	3,265E+18	100,26
446,0	1,3070	2,934E+18	101,64
447,0	1,4860	3,344E+18	103,04
448,0	1,5037	3,391E+18	104,53
449,0	1,5001	3,391E+18	106,04
450,0	1,5550	3,523E+18	107,56
451,0	1,6126	3,661E+18	109,15
452,0	1,5437	3,513E+18	110,73
453,0	1,4256	3,251E+18	112,21
454,0	1,5291	3,495E+18	113,69
455,0	1,5180	3,477E+18	115,21
456,0	1,5678	3,599E+18	116,75
457,0	1,5808	3,637E+18	118,33
458,0	1,5469	3,567E+18	119,89
459,0	1,5346	3,546E+18	121,43
460,0	1,5247	3,531E+18	122,96
461,0	1,5781	3,662E+18	124,51
462,0	1,5929	3,705E+18	126,10
463,0	1,5985	3,726E+18	127,70
464,0	1,5499	3,620E+18	129,27
465,0	1,5305	3,583E+18	130,81
466,0	1,5628	3,666E+18	132,36
467,0	1,4930	3,510E+18	133,88
468,0	1,5574	3,669E+18	135,41
469,0	1,5637	3,692E+18	136,97
470,0	1,5033	3,557E+18	138,50
471,0	1,5287	3,624E+18	140,02
472,0	1,6079	3,821E+18	141,59
473,0	1,5454	3,680E+18	143,16
474,0	1,5626	3,728E+18	144,72
475,0	1,6138	3,859E+18	146,31
476,0	1,5586	3,735E+18	147,89
477,0	1,5678	3,765E+18	149,46
478,0	1,6183	3,894E+18	151,05
479,0	1,5870	3,827E+18	152,65
480,0	1,6134	3,899E+18	154,25
481,0	1,6130	3,906E+18	155,87
482,0	1,6189	3,928E+18	157,48

Wave-length (nm)	Spectral irradiance ($\text{W}\cdot\text{m}^{-2}\cdot\text{nm}^{-1}$)	Spectral photon irradiance ($\text{m}^{-2}\cdot\text{s}^{-1}\cdot\text{nm}^{-1}$)	Cumulative integrated irradiance ($\text{W}\cdot\text{m}^{-2}$)
483,0	1,5991	3,888E+18	159,09
484,0	1,5688	3,822E+18	160,67
485,0	1,5638	3,818E+18	162,24
486,0	1,2679	3,102E+18	163,66
487,0	1,4200	3,481E+18	165,00
488,0	1,5368	3,775E+18	166,48
489,0	1,4477	3,564E+18	167,97
490,0	1,6177	3,990E+18	169,50
491,0	1,5550	3,843E+18	171,09
492,0	1,4826	3,672E+18	172,61
493,0	1,5857	3,935E+18	174,14
494,0	1,5480	3,850E+18	175,71
495,0	1,6437	4,096E+18	177,31
496,0	1,5631	3,903E+18	178,91
497,0	1,5898	3,977E+18	180,49
498,0	1,5464	3,877E+18	182,05
499,0	1,5462	3,884E+18	183,60
500,0	1,5406	3,878E+18	185,14
501,0	1,4935	3,767E+18	186,66
502,0	1,4923	3,771E+18	188,15
503,0	1,5608	3,952E+18	189,68
504,0	1,4545	3,690E+18	191,19
505,0	1,5590	3,963E+18	192,69
506,0	1,6217	4,131E+18	194,28
507,0	1,5515	3,960E+18	195,87
508,0	1,5121	3,867E+18	197,40
509,0	1,5847	4,060E+18	198,95
510,0	1,5436	3,963E+18	200,52
511,0	1,5723	4,045E+18	202,07
512,0	1,6139	4,160E+18	203,67
513,0	1,5162	3,916E+18	205,23
514,0	1,4842	3,840E+18	206,73
515,0	1,5270	3,959E+18	208,24
516,0	1,5410	4,003E+18	209,77
517,0	1,2557	3,268E+18	211,17
518,0	1,4361	3,745E+18	212,52
519,0	1,3917	3,636E+18	213,93
520,0	1,5192	3,977E+18	215,38
521,0	1,5301	4,013E+18	216,91
522,0	1,5644	4,111E+18	218,46
523,0	1,4746	3,882E+18	219,98
524,0	1,5859	4,183E+18	221,51
525,0	1,5735	4,159E+18	223,09
526,0	1,5297	4,050E+18	224,64
527,0	1,3378	3,549E+18	226,07
528,0	1,5312	4,070E+18	227,51
529,0	1,6024	4,267E+18	229,07

Wave-length (nm)	Spectral irradiance ($\text{W} \cdot \text{m}^{-2} \cdot \text{nm}^{-1}$)	Spectral photon irradiance ($\text{m}^{-2} \cdot \text{s}^{-1} \cdot \text{nm}^{-1}$)	Cumulative integrated irradiance ($\text{W} \cdot \text{m}^{-2}$)
530,0	1,5401	4,109E+18	230,64
531,0	1,6245	4,342E+18	232,23
532,0	1,5952	4,272E+18	233,84
533,0	1,4245	3,822E+18	235,35
534,0	1,5258	4,102E+18	236,82
535,0	1,5490	4,172E+18	238,36
536,0	1,6152	4,358E+18	239,94
537,0	1,4946	4,040E+18	241,50
538,0	1,5692	4,250E+18	243,03
539,0	1,5307	4,153E+18	244,58
540,0	1,4782	4,018E+18	246,08
541,0	1,4210	3,870E+18	247,53
542,0	1,5466	4,220E+18	249,02
543,0	1,5212	4,158E+18	250,55
544,0	1,5746	4,312E+18	252,10
545,0	1,5390	4,222E+18	253,65
546,0	1,5247	4,191E+18	255,19
547,0	1,5445	4,253E+18	256,72
548,0	1,5005	4,139E+18	258,24
549,0	1,5475	4,277E+18	259,77
550,0	1,5354	4,251E+18	261,31
551,0	1,5337	4,254E+18	262,84
552,0	1,5651	4,349E+18	264,39
553,0	1,5206	4,233E+18	265,94
554,0	1,5504	4,324E+18	267,47
555,0	1,5589	4,355E+18	269,03
556,0	1,5321	4,288E+18	270,57
557,0	1,4945	4,190E+18	272,08
558,0	1,5266	4,288E+18	273,59
559,0	1,4441	4,064E+18	275,08
560,0	1,4697	4,143E+18	276,54
561,0	1,5550	4,391E+18	278,05
562,0	1,4804	4,188E+18	279,57
563,0	1,5363	4,354E+18	281,08
564,0	1,5062	4,276E+18	282,60
565,0	1,5157	4,311E+18	284,11
566,0	1,4332	4,084E+18	285,58
567,0	1,5276	4,360E+18	287,06
568,0	1,5136	4,328E+18	288,58
569,0	1,4764	4,229E+18	290,08
570,0	1,4773	4,239E+18	291,55
571,0	1,4289	4,107E+18	293,01
572,0	1,5090	4,345E+18	294,48
573,0	1,5154	4,371E+18	295,99
574,0	1,5075	4,356E+18	297,50
575,0	1,4734	4,265E+18	298,99
576,0	1,4612	4,237E+18	300,46

Wave-length (nm)	Spectral irradiance ($\text{W} \cdot \text{m}^{-2} \cdot \text{nm}^{-1}$)	Spectral photon irradiance ($\text{m}^{-2} \cdot \text{s}^{-1} \cdot \text{nm}^{-1}$)	Cumulative integrated irradiance ($\text{W} \cdot \text{m}^{-2}$)
577,0	1,4979	4,351E+18	301,94
578,0	1,4518	4,224E+18	303,41
579,0	1,4727	4,293E+18	304,87
580,0	1,4976	4,373E+18	306,36
581,0	1,5045	4,400E+18	307,86
582,0	1,5276	4,475E+18	309,38
583,0	1,5434	4,530E+18	310,91
584,0	1,5403	4,528E+18	312,45
585,0	1,5280	4,500E+18	313,99
586,0	1,4910	4,398E+18	315,50
587,0	1,5237	4,502E+18	317,01
588,0	1,4891	4,408E+18	318,51
589,0	1,2857	3,812E+18	319,90
590,0	1,3669	4,060E+18	321,23
591,0	1,4619	4,349E+18	322,64
592,0	1,4312	4,265E+18	324,09
593,0	1,4519	4,334E+18	325,53
594,0	1,4449	4,321E+18	326,98
595,0	1,4267	4,273E+18	328,41
596,0	1,4702	4,411E+18	329,86
597,0	1,4745	4,431E+18	331,33
598,0	1,4565	4,384E+18	332,80
599,0	1,4564	4,392E+18	334,25
600,0	1,4710	4,443E+18	335,72
601,0	1,4537	4,398E+18	337,18
602,0	1,4318	4,339E+18	338,62
603,0	1,4621	4,438E+18	340,07
604,0	1,4878	4,524E+18	341,55
605,0	1,4852	4,523E+18	343,03
606,0	1,4779	4,509E+18	344,51
607,0	1,4868	4,543E+18	346,00
608,0	1,4819	4,536E+18	347,48
609,0	1,4706	4,509E+18	348,96
610,0	1,4643	4,497E+18	350,42
611,0	1,4569	4,481E+18	351,88
612,0	1,4788	4,556E+18	353,35
613,0	1,4579	4,499E+18	354,82
614,0	1,4135	4,369E+18	356,26
615,0	1,4654	4,537E+18	357,70
616,0	1,4269	4,425E+18	359,14
617,0	1,4087	4,375E+18	360,56
618,0	1,4621	4,549E+18	362,00
619,0	1,4690	4,578E+18	363,46
620,0	1,4696	4,587E+18	364,93
621,0	1,4759	4,614E+18	366,40
622,0	1,4228	4,455E+18	367,85
623,0	1,4124	4,430E+18	369,27