



Designation: B 92/B92M – 89 (Reapproved 1994)^{ε1}

Standard Specification for Magnesium Ingot and Stick For Remelting¹

This standard is issued under the fixed designation B 92/B92M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

^{ε1} NOTE—Keywords were added editorially in December 1994.

1. Scope *

1.1 This specification covers magnesium in the form of ingot and stick for remelting: 9980A is available in ingot and stick form, and 9980B, 9990A, 9995A, and 9998A are generally available only in ingot form.

1.2 The values stated in SI units are to be regarded as a separate standard. The values stated in each system are not exact equivalents, therefore each system must be used independently of the other.

2. Referenced Documents

2.1 ASTM Standards:

E 35 Test Methods for Chemical Analysis of Magnesium and Magnesium Alloys²

E 88 Practice for Sampling Nonferrous Metals and Alloys in Cast Form for Determination of Chemical Composition²

3. Terminology

3.1 Definitions:

3.1.1 *ingot*—a cast form suitable for remelting.

3.1.2 *stick*—an extruded form substantially uniform in cross section cut to desired length or weight.

4. Ordering Information

4.1 Orders for ingot and stick under this specification shall include the following information:

4.1.1 Grade (Section 6 and Table 1),

4.1.2 Quantity, in pieces or pounds [kilograms], and

4.1.3 Form; by agreement between the purchaser and the manufacturer the approximate form and weight of each piece or ingot may be specified.

4.1.4 For inch-pound orders specify B92, for metric orders specify B92M. Do not mix units.

5. Materials and Manufacture

5.1 No scrap shall be used in the production of magnesium ingot and stick, except such as shall accumulate at the manufacturer's plants from material of similar composition and of his own manufacture.

6. Chemical Composition

6.1 *Limits*—The material shall conform to the requirements as to chemical composition prescribed in Table 1.

6.2 Sampling:

6.2.1 Sufficient samples shall be taken by the manufacturer to assure conformance to the chemical composition requirements of the alloy. Samples may be taken from the molten metal when the ingot is poured or from the ingot. Samples shall be representative of the material.

6.2.2 In case of dispute, the sampling for chemical analysis shall be according to the requirements of Practice E 88. If the ingots are shipped in carload lots of the same alloy, not less than four ingots shall be taken at random from the carload for sampling. If the shipment is in less than carload lots, one ingot shall be taken for sampling for each 10 000 lb [4500 kg] or fraction thereof.

6.3 *Methods of Analysis*—Any suitable method of chemical analysis may be used. In case of dispute, the analysis shall be made by methods given in Test Methods E 35, or any other standard methods of analysis approved by ASTM unless some other method is agreed upon by the purchaser and vendor.

7. General Quality

7.1 Magnesium ingot and stick shall have a clean surface and shall be commercially free from dirt, slag, or other foreign material.

8. Rejection

8.1 Material that does not conform to the requirements of this specification may be rejected, and if rejected the conditions of replacement shall be as agreed upon between the purchaser and the seller. The seller's responsibility shall be limited to a period of six months from shipping date unless other agreement is made by the purchaser and seller.

¹ This specification is under the jurisdiction of the ASTM Committee B-7 on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.04 on Magnesium Alloy, Cast and Wrought Products.

Current edition approved May 26, 1989. Published July 1989. Originally published as B 92–33 T. Last previous edition B 92–80 (1985) and B 92M–83 (1988)^{ε1}.

² *Annual Book of ASTM Standards*, Vol 03.05.

*A Summary of Changes section appears at the end of this standard.