

INTERNATIONAL STANDARD

ISO
8263

First edition
1992-04-15

Corrected and reprinted
1993-05-15

Iron ore fines — Method for presentation of the results of sintering tests

*Particules de minerais de fer — Méthode de présentation des résultats
d'essais de frittage*
(standards.iteh.ai)

ISO 8263:1992

<https://standards.iteh.ai/catalog/standards/sist/30bb24a1-b4c9-4125-b955-35c81aa1cb8f/iso-8263-1992>



Reference number
ISO 8263:1992(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 8263 was prepared by Technical Committee ISO/TC 102, *Iron ores*, Sub-Committee SC 3, *Physical testing*.

Annex A forms an integral part of this International Standard.

Introduction

Sintering tests can be conducted for several different purposes, for example, the assessment of the sintering behaviour of a particular iron ore fines, for production and quality control purposes at a sinter plant, or for research purposes concerned with the sintering process or sintering technology.

From the results of these sintering tests, the sintering behaviour of an iron ore, or iron ore mix, is determined in terms of production rate, fuel consumption rate and sinter quality. The purpose of this International Standard is to establish the terminology and method for presentation of these results, for use when sintering test data is required to be exchanged between separate parties, such as will be the case where a particular iron ore fines has been assessed for commercial reasons, or where research or production results are to be published.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 8263:1992

<https://standards.iteh.ai/catalog/standards/sist/30bb24a1-b4c9-4125-b955-35c81aa1cb8f/iso-8263-1992>

iTeh STANDARD PREVIEW **(standards.itech.ai)**

This page intentionally left blank

ISO 8263:1992

<https://standards.itech.ai/catalog/standards/sist/30bb24a1-b4c9-4125-b955-35c81aa1cb8f/iso-8263-1992>

Iron ore fines — Method for presentation of the results of sintering tests

1 Scope

This International Standard specifies a method for presentation of the results of sintering tests. It is applicable to all iron ore fines that are agglomerated by the sintering process.

2 Definitions

For the purposes of this International Standard, the following definitions apply.

2.1 ore mix: The blend of iron ores, and other iron bearing raw materials, such as mill scale, basic oxygen steel making slag, dust, etc., used in the tests. It does not include return sintered fines, fluxes, coke or other solid fuel.

2.2 sinter mix: The mix of materials charged to the sintering test apparatus, which includes the ore mix, fluxes, coke or other fuel, and return sintered fines.

2.3 mixing times: The time, in minutes, taken for blending and granulating the various constituents of the sinter mix.

2.4 moisture content of sinter mix: The moisture content, as a percentage by mass, determined by drying the granulated sinter mix, as charged to the sintering test apparatus, at $105\text{ }^{\circ}\text{C} \pm 5\text{ }^{\circ}\text{C}$.

2.5 moisture content for maximum permeability: The moisture content of the granulated sinter mix at which maximum permeability is obtained.

2.6 bulk density of sinter mix: The mass per unit volume of the wet sinter mix as charged.

2.7 hearth layer: A layer of previously made and sized sinter, or other iron ore material, which is placed on the grate before the sinter mix is charged.

2.8 grate area: The area of the grate of the sintering test apparatus.

2.9 net bed height: The height of the bed of sinter mix above the hearth layer, prior to the application of suction and ignition.

2.10 suction: The air suction measured at the wind box or at the entrance of the main blower of the sintering test apparatus.

2.11 ignition intensity: The heat supplied per unit of grate area per unit time of ignition.

2.12 ignition temperature: The maximum temperature attained at or immediately above the surface of the sinter bed during the ignition process.

2.13 sintering time: The time from the start of ignition until the exhaust gas temperature reaches a maximum.

2.14 sinter cake: The total mass of sinter produced, including the hearth layer and the material collected from the bottom of the wind box.

2.15 sinter handling treatment: The tumbling and/or shatter treatment given to the sinter cake, obtained in a sinter pot to simulate the effects of handling and transportation in a sinter plant.

2.16 return sintered fines: The undersize fines separated from the sinter cake by sieving after the handling treatment.

2.17 sinter product: The sinter acceptable size for charging to the blast furnace.

2.18 productivity: The mass of sinter product, produced per unit grate area per unit of time (see 3.1.1).

2.19 fuel consumption: The dry mass(es) of solid fuel(s) consumed per unit mass of sinter product after deducting the hearth layer (see 3.1.2).

2.20 yield: The proportion (percentage) of sinter product in relation to the sinter cake, excluding the hearth layer (see 3.1.3).

2.21 return sintered fines balance: The ratio of the mass of return sintered fines charged to the mass of undersize sintered fines produced (see 3.1.4).

3 Sintering tests

For reference, an example of sintering test equipment is illustrated in figure 1, while figure 2 gives a flow-sheet of a typical sinter test procedure.

The International Standards covering test methods for determining the chemical analyses, sieving analyses, and sinter quality indices are listed in annex A. If any of these International Standards are not available, the respective national or regional standard should be used.

3.1 Calculation of results

3.1.1 Productivity

The productivity *P*, in tonnes of sinter per square metre per hour, is calculated from the equation

$$P = \frac{m_1 - m_2}{1\,000} \times \frac{1}{A} \times \frac{60}{t}$$

where

- m*₁ is the total mass, in kilograms, of sinter of acceptable size produced (including the hearth layer);
- m*₂ is the mass, in kilograms, of the hearth layer;
- A* is the area of grate, in square metres;
- t* is the sintering time, in minutes.

NOTE 1 Productivity may also be reported in terms of tonnes of iron contained in sinter of acceptable size per square metre per hour, to reflect changes in the grade of the sinter product.

The productivity *P*_{Fe}, in tonnes of iron in sinter per square metre per hour, is calculated from the equation

$$P_{Fe} = \frac{P \times w_{Fe}}{100}$$

where *w*_{Fe} is the percentage iron content in the sinter.

3.1.2 Fuel consumption

The fuel consumption *C* is calculated from the equation

$$C = \frac{m_3}{m_1 - m_2} \times 1\,000$$

where

- m*₁ is the total mass, in kilograms, of sinter of acceptable size produced (including the hearth layer);
- m*₂ is the mass, in kilograms, of the hearth layer;
- m*₃ is the dry mass of solid fuel in the sinter mix consumed.

3.1.3 Yield

The yield *Y*, as a percentage by mass, is calculated from the equation

$$Y = \frac{m_1 - m_2}{m_4 - m_2} \times 100$$

where

- m*₁ is the total mass, in kilograms, of sinter of acceptable size produced;
- m*₂ is the mass, in kilograms, of the hearth layer;
- m*₄ is the total mass, in kilograms, of sinter cake.

3.1.4 Return sintered fines balance

The return sintered fines balance *B* is calculated from the equation

$$B = \frac{m_5}{m_6}$$

where

- m*₅ is the mass of return sintered fines charged (input);
- m*₆ is the mass of undersize sintered fines produced (output).

NOTE 2 In a sinter pot test, this is normally maintained within limits of 1 ± 0,05, for results to be representative of actual practice.

The percentage of return sintered fines *F* may also be recorded, and is calculated from the equation

$$F = \frac{m_4 - m_1}{m_4 - m_2} \times 100$$

4 Method for reporting results

The results of sintering tests shall be reported according to schedules 1 to 6 as follows.

Schedule 1: Chemical analyses (dry basis) and size distribution of the various ores included in the ore mix.

Table 1 lists the chemical analysis and size distribution of each iron ore contained in the ore mix used in the tests.

A separate column is used for each ore, or iron bearing material, included in the ore mix. It is not necessary to actually name each ore source which can be referred to as ore A, B, C, etc.

Schedule 2: Composition of the ore mix.

Table 2 shows the percentage of each iron ore, or iron bearing material, contained in the ore mix for each test. These percentages are calculated on a dry basis.

Schedule 3: Chemical analyses (dry basis) and size distributions of fluxes, fuels and return sintered fines.

Table 3 is similar to table 1, but lists the chemical analyses and size distributions of all the other materials included in the sinter mix, such as the coke or alternative fuels used, each of the fluxes used, and the return sintered fines. The coke or fuel

analyses give the percentage of ash as well as fixed carbon and volatile matter.

If a hearth layer other than sized sinter is utilized, then the type and composition of the material used should be listed in table 3.

Schedule 4: Composition of the sinter mix.

Table 4 shows the percentage of each constituent of the sinter mix, including the ore mix, fluxes, coke or other fuel, and the return sintered fines.

NOTE 3 From tables 1 and 2, the overall weighted composition of the ore mix can be calculated and used as the basis for calculation of flux quantities.

Schedule 5: Sintering test results.

Table 5 gives the conditions under which the sintering tests were done and the results of the tests.

Schedule 6: Sinter product quality data.

In table 6 the results of chemical and physical tests undertaken on the sinter product are recorded.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 8263:1992

<https://standards.iteh.ai/catalog/standards/sist/30bb24a1-b4c9-4125-b955-35c81aa1cb8f/iso-8263-1992>

Table 1 — Chemical analyses (dry basis), moisture content and size distributions of the various ores included in the ore mix

| | Ore A | Ore B | Ore C | Ore D | Mill scale and/or other surface coatings | Test ore |
|--|---|----------|----------|----------|--|----------|
| | % | % | % | % | % | % |
| Chemical analysis Fe (total) FeO SiO ₂ Al ₂ O ₃ CaO MgO MnO S P Na ₂ O K ₂ O C TiO ₂ Loss on ignition Combined water | | | | | | |
| Moisture content | https://standards.iteh.ai/catalog/standards/sist/30bb24a1-b4c9-4125-b955-35c81aa1cb8f/iso-8263-1992 | | | | | |
| Size distribution + 8,0 mm – 8,0 mm + 5,6 mm – 5,6 mm + 4,0 mm – 4,0 mm + 2,0 mm – 2,0 mm + 1,0 mm – 1,0 mm + 500 µm – 500 µm + 250 µm – 250 µm + 125 µm – 125 µm + 63 µm – 63 µm | | | | | | |
| Method of size analysis: wet/dry sieving | | | | | | |

Table 2 — Composition of the ore mixValues in percentage by mass [% (*m/m*)] (dry basis)

| Constituents of ore mix | Test No. 1 | Test No. 2 | Test No. 3 | Test No. 4 | Test No. 5 | Test No. 6 |
|--|---------------|---------------|---------------|---------------|---------------|---------------|
| Ore A | | | | | | |
| Ore B | | | | | | |
| Ore C | | | | | | |
| Ore D | | | | | | |
| Mill scale and/or other surface coatings | | | | | | |
| Test ore | | | | | | |

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 8263:1992

<https://standards.iteh.ai/catalog/standards/sist/30bb24a1-b4c9-4125-b955-35c81aa1cb8f/iso-8263-1992>

Table 3 — Chemical analyses (dry basis), moisture content and size distributions of fluxes, fuels and return sintered fines

| | Coke or other fuel | Limestone | Flux | | | Return sintered fines |
|---------------------------------|-----------------------|-----------|----------|-----------|-------|-----------------------------|
| | | | Dolomite | Siliceous | Other | |
| | % | % | % | % | % | % |
| Chemical analysis | | | | | | |
| Fe (total) | | | | | | |
| FeO | | | | | | |
| SiO ₂ | | | | | | |
| Al ₂ O ₃ | | | | | | |
| CaO | | | | | | |
| MgO | | | | | | |
| MnO | | | | | | |
| S | | | | | | |
| P | | | | | | |
| Na ₂ O | | | | | | |
| K ₂ O | | | | | | |
| C | | | | | | |
| TiO ₂ | | | | | | |
| C (fixed) | | | | | | |
| Ash | | | | | | |
| Volatile Matter (VM) | | | | | | |
| Combined water | | | | | | |
| Moisture content | | | | | | |
| Size distribution | | | | | | |
| + 8,0 mm | | | | | | |
| – 8,0 mm + 5,6 mm | | | | | | |
| – 5,6 mm + 4,0 mm | | | | | | |
| – 4,0 mm + 2,0 mm | | | | | | |
| – 2,0 mm + 1,0 mm | | | | | | |
| – 1,0 mm + 500 µm | | | | | | |
| – 500 µm + 250 µm | | | | | | |
| – 250 µm + 125 µm | | | | | | |
| – 125 µm + 63 µm | | | | | | |
| – 63 µm | | | | | | |
| Method of size analysis: | | | | | | |
| wet/dry sieving | | | | | | |

Table 4 — Composition of the sinter mix

Values in percentage by mass [% (m/m)] (dry basis)

| Constituents of sinter feed | Test No. 1 | Test No. 2 | Test No. 3 | Test No. 4 | Test No. 5 |
|-----------------------------|---------------|---------------|---------------|---------------|---------------|
| Ore mix | | | | | |
| Return sintered fines | | | | | |
| Siliceous material | | | | | |
| Limestone | | | | | |
| Dolomite | | | | | |
| Other fluxes (if any) | | | | | |
| Coke | | | | | |
| Other fuel (if any) | | | | | |

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 8263:1992](https://standards.iteh.ai/catalog/standards/sist/30bb24a1-b4c9-4125-b955-35c81aa1cb8f/iso-8263-1992)

<https://standards.iteh.ai/catalog/standards/sist/30bb24a1-b4c9-4125-b955-35c81aa1cb8f/iso-8263-1992>