



Standard Specification for Ferrotungsten¹

This standard is issued under the fixed designation A 144; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Editorial changes were made throughout in February 1990.

1. Scope

1.1 This specification covers four grades of ferrotungsten.

2. Referenced Documents

2.1 *ASTM Standards:*

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications²

E 31 Methods for Chemical Analysis of Ferroalloys³

E 32 Practices for Sampling Ferroalloys and Steel Additives for Determination of Chemical Composition³

3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

3.1.1 Quantity,

3.1.2 Name of material,

3.1.3 ASTM designation and year of issue,

3.1.4 Grade,

3.1.5 Sizing, and

3.1.6 Requirements for packaging, analysis reports, etc., as appropriate.

3.2 Although ferrotungsten is ordered by total net weight, the customary basis of payment is per pound of contained tungsten.

4. Chemical Composition

4.1 The various grades shall conform to the requirements as to chemical composition specified in Table 1 and Table 2.

4.2 The manufacturer shall furnish an analysis of each shipment showing the elements specified in Table 1.

4.3 The values shown in Table 2 are expected maximums. Upon the request of the purchaser, the manufacturer shall furnish an analysis for any of these elements on a cumulative basis over a period mutually agreed upon between the manufacturer and the purchaser.

5. Chemical Analysis

5.1 The chemical analysis of the material shall be made in accordance with the procedure for ferrotungsten as described in Methods E 31 or alternative methods which will yield equivalent results.

5.2 If alternative methods of analysis are used, in case of discrepancy, Methods E 31 shall be used for referee.

5.3 Where no method is given in Methods E 31 for the analysis for a particular element, the analysis shall be made in accordance with a procedure agreed upon between the manufacturer and the purchaser.

6. Size

6.1 The various grades are available in the sizes listed in Table 3.

6.2 The ferrotungsten is available in various sizes such as ¼ by down (5 % maximum over ¼ in., 20 % maximum under 70 mesh), or ⅜ by down (5 % maximum over ⅜ in., 20 % maximum under 70 mesh). The size shall be specified on the order.

7. Sampling

7.1 The material shall be sampled in accordance with Practices E 32.

7.2 Other methods of sampling mutually agreed upon by the manufacturer and the purchaser may be used; however, in case of discrepancy, Practices E 32 shall be used for referee.

8. Inspection

8.1 The manufacturer shall afford the inspector representing the purchaser all reasonable facilities, without charge, to satisfy him that the material is being furnished in accordance with this specification.

9. Rejection

9.1 Any claims or rejections shall be made to the manufacturer within 45 days from receipt of material by the purchaser.

10. Product Marking

10.1 When the shipment is made in bulk it shall be accompanied by appropriate identification showing the material, the grade designation, the ASTM designation, the size, the

¹ This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.30 On Ferroalloys and Alloying Additives.

Current edition approved Aug. 27, 1973. Published October 1973. Originally published as A 144 – 32 T. Last previous edition A 144 – 66.

² *Annual Book of ASTM Standards*, Vol 14.02.

³ *Annual Book of ASTM Standards*, Vol 03.05.