



**SLOVENSKI STANDARD**  
**SIST EN 13938-4:2004**  
**01-februar-2004**

---

**Eksplozivi za civilno uporabo - Smodniki in raketna goriva – 4. del: Ugotavljanje hitrosti gorenja v normalnih razmerah**

Explosives for civil uses - Propellants and rocket propellants - Part 4: Determination of burning rate under ambient conditions

Explosivstoffe für zivile Zwecke - Treibladungspulver und Raketentreibstoffe - Teil 4: Bestimmung der Brenngeschwindigkeit bei Umgebungsbedingungen

Explosifs a usage civil - Poudres propulsives et propergols pour fusées - Partie 4: Détermination de la vitesse de combustion dans les conditions ambiantes

[SIST EN 13938-4:2004](https://standards.iteh.ai/catalog/standards/sist/e7948d4f-ffc-4820-8218-85907592f1da/sist-en-13938-4-2004)

**Ta slovenski standard je istoveten z: EN 13938-4:2003**

---

**ICS:**

71.100.30

**SIST EN 13938-4:2004**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 13938-4:2004

<https://standards.iteh.ai/catalog/standards/sist/e7948d4f-fffc-4820-8218-d55c7552f1da/sist-en-13938-4-2004>

ICS 71.100.30

English version

## Explosives for civil uses - Propellants and rocket propellants - Part 4: Determination of burning rate under ambient conditions

Explosifs à usage civil - Poudres propulsives et propergols  
pour fusées - Partie 4: Détermination de la vitesse de  
combustion dans les conditions ambiantes

Explosivstoffe für zivile Zwecke - Treibladungspulver und  
Raketentreibstoffe - Teil 4: Bestimmung der  
Brenngeschwindigkeit bei Umgebungsbedingungen

This European Standard was approved by CEN on 1 October 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 13938-4:2004](https://standards.iteh.ai/catalog/standards/sist/e7948d4f-fffc-4820-8218-d55c7552fd1da/sist-en-13938-4-2004)

<https://standards.iteh.ai/catalog/standards/sist/e7948d4f-fffc-4820-8218-d55c7552fd1da/sist-en-13938-4-2004>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

## Contents

page

Foreword.....	3
1 Scope .....	3
2 Normative references .....	3
3 Terms and definitions.....	4
4 Principle .....	4
5 Apparatus .....	4
6 Preparation of test sample.....	5
7 Procedure .....	5
8 Expression of results .....	6
9 Test report .....	6
Annex A (informative) Range of applicability of the test method.....	7
Annex ZA (informative) Clauses of this European Standard addressing essential requirements or other provisions of EU Directives .....	8

ITh STANDARD PREVIEW

(standards.iteh.ai)

[SIST EN 13938-4:2004](https://standards.iteh.ai/catalog/standards/sist/e7948d4f-fffc-4820-8218-d55c7552f1da/sist-en-13938-4-2004)

<https://standards.iteh.ai/catalog/standards/sist/e7948d4f-fffc-4820-8218-d55c7552f1da/sist-en-13938-4-2004>

## Foreword

This document EN 13938-4:2003 has been prepared by Technical Committee CEN /TC 321, "Explosives for civil uses", the secretariat of which is held by AENOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2004, and conflicting national standards shall be withdrawn at the latest by June 2004.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative annex ZA, which is an integral part of this document.

This European Standard is one of a series of standards with the generic title "*Explosives for civil uses – Propellants and rocket propellants*". The other parts of this series are listed below:

- |              |   |
|--------------|---|
| prEN 13938-1 | Part 1: Requirements.   |
| prEN 13938-2 | Part 2: Determination of resistance to electrostatic energy.                                      |
| EN 13938-3   | Part 3: Determination of deflagration to detonation transition.                                   |
| prEN 13938-5 | Part 5: Solid rocket propellants. Determination of voids and fissures.                            |
| prEN 13938-6 | Part 6: Solid rocket propellants. Guide for the determination of integrity of inhibitor coatings. |
| prEN 13938-7 | Part 7: Determination of the properties of black powder.  |

Annex A is informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard : Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

## 1 Scope

This European Standard specifies a method for the determination of burning rate under ambient conditions for propellants and black powder.

It is applicable to propellants and black powder in their original form up to a grain size of 8 mm.

## 2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN ISO/IEC 17025; *General requirements for the competence of testing and calibration laboratories (ISO/IEC 17025:1999)*.

EN 13857-1; *Explosives for civil uses - Part 1: Terminology*.

### 3 Terms and definitions

For the purposes of this European Standard, the terms and definitions given in EN 13857-1 and the following apply.

#### 3.1

##### **burning rate**

velocity at which the flame propagates through the sample along the trough

### 4 Principle

The test sample is loaded into a trough and the sample is ignited at one end by means of a hot wire. The time of flame propagation through the sample along the trough is measured and the burning rate is calculated.

### 5 Apparatus

**5.1 Trough**, (see Figure 1), consisting of a half cylinder ( $2\,000 \pm 1$ ) mm long with a diameter of ( $20,0 \pm 0,8$ ) mm, hollowed out from a stainless steel block. The block is marked at 2 positions, A and B, at distances of ( $400 \pm 1$ ) mm and ( $1\,900 \pm 1$ ) mm from the end where the ignition is to take place, respectively. A 2 mm thick stainless steel plate is welded to each end of the trough to close off the ends.


<https://standards.iteh.ai/catalog/standards/sist/e7948d4f-ffc-4820-8218-13938-4-2004>  
<https://standards.iteh.ai/catalog/standards/sist-en-13938-4-2004>

The trough shall be horizontal when set on its support.

**5.2 Hot wire**, as ignition device, consisting of a Ni/Cr wire, diameter ( $0,40 \pm 0,05$ ) mm, length ( $15 \pm 1$ ) mm, heated by a current of 4 A.

**5.3 Timing device**, consisting of a manual stopwatch with a scale division of 0,1 s or a recording chronograph activated by suitable detectors located at marks A and B. Black powder shall be tested using a recording chronograph.

Dimensions in millimetres

**Key**

1 Hot wire

2 Engraved marks

A First mark

B Second mark

Tolerance for all dimensions is  $\pm 1$  mm, except  $\pm 0,8$  mm for the diameter of the trough.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 13938-4:2004

**Figure 1 – Stainless steel trough****6 Preparation of test sample**

Condition the test sample by storing at  $(20 \pm 5)$  °C and  $(60 \pm 10)$  % relative humidity for at least 24 h immediately prior the test.

**7 Procedure**

Carry out two determinations, using separate test portions taken from the test sample.

Conduct the test under ambient conditions of temperature and humidity.

Ensure that the trough is dry and clean and condition it at  $(20 \pm 10)$  °C.

Pour the test sample into the trough so as to fill it flush with the top edge, without packing down the test sample.

Level the surface by moving a blade across it and record the mass of the test portion.

The time between filling the trough and ignition shall not exceed 15 min.

Connect the hot wire to the electrical circuit.

Maintain the current until the sample ignites (maximum time 60 s).

Record the following:

- $t_b$  time of flame propagation from mark A (400 mm) to mark B (1900 mm);
- $t_f$  time from mark A to extinction, in case of partial propagation of the sample;
- $d_f$  distance travelled by the flame in case of partial propagation of the sample.

NOTE This distance should be determined after disconnection of the hot wire and the cooling of the trough.

## 8 Expression of results

The burning rate of the sample under test shall be determined by means of the following equation:

$$V = \frac{1\ 500}{t_b}$$

Where

- $V$  is the burning rate, expressed in millimetres per second (mm/s);  
 $1\ 500$  is the distance between the marks expressed millimetres (mm); and  
 $t_b$  is the time of propagation between the marks, expressed in seconds(s)

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

## 9 Test report

The test report shall conform to EN ISO/IEC 17025. In addition the following information shall be given:

- SIST EN 13938-4:2004  
<https://standards.iteh.ai/catalog/standards/sist/e7948d41-ffc-4820-8218-d55c7552f1da/sist-en-13938-4-2004>
- a) a reference to this standard;
  - b) the complete identification of the sample, including its mass and grain size distribution;
  - c) the results of all tests in form of:
    - time,  $t_b$  (s) and burning rate,  $V$  (mm/s)or, in case of partial propagation:
    - time,  $t_f$  (s) and distance,  $d_f$  (mm)
  - d) the mean value of the burning rate obtained from the two tests (mm/s)



**Annex A**  
(informative)

**Range of applicability of the test method**

Range of applicability of the test method: - 30 °C to + 80 °C.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 13938-4:2004](https://standards.iteh.ai/catalog/standards/sist/e7948d4f-fffc-4820-8218-d55c7552f1da/sist-en-13938-4-2004)

<https://standards.iteh.ai/catalog/standards/sist/e7948d4f-fffc-4820-8218-d55c7552f1da/sist-en-13938-4-2004>