



Designation: A 101 – 93 (Reapproved 2000)

Standard Specification for Ferrochromium¹

This standard is issued under the fixed designation A 101; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers two types of ferrochromium designated as high carbon and low carbon, the latter including nitrogen-bearing and vacuum grades.

1.2 The values stated in inch-pound units are to be regarded as the standard. The SI units given in parentheses are for information only.

2. Referenced Documents

2.1 *ASTM Standards*:

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications²

E 31 Methods for Chemical Analysis of Ferroalloys³

E 32 Practices for Sampling Ferroalloys and Steel Additives for Determination of Chemical Composition³

E 363 Test Methods for Chemical Analysis of Chromium and Ferrochromium⁴

3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

3.1.1 Quantity,

3.1.2 Name of material,

3.1.3 ASTM designation and year of issue,

3.1.4 Grade,

3.1.5 Size, and

3.1.6 Requirements for packaging analysis reports, etc., as appropriate.

3.2 Although ferrochromium is purchased by total net weight the customary basis of payment is per pound of contained chromium.

4. Chemical Composition

4.1 The various grades shall conform to the requirements as to chemical composition specified in Table 1 and Table 2.

4.2 The manufacturer shall furnish an analysis of each shipment showing the elements specified in Table 1.

4.3 The values shown in Table 2 are expected maximums. Upon request of the purchaser, the manufacturer shall furnish an analysis for any of these elements on a cumulative basis over a period mutually agreed upon by the manufacturer and the purchaser.

5. Size

5.1 The various grades are available in sizes as listed in Table 3.

5.2 The sizes listed in Table 3 are typical, as shipped from the manufacturer's plant. These alloys exhibit varying degrees of friability; therefore, some attrition may be expected in transit, storage, and handling. A quantitative test is not available for rating relative friability of ferroalloys. A code system has been developed, therefore, for this purpose, and a number rating for each product type is shown in the last column of Table 3. Definitions applicable to these code numbers are given in the Appendix.

6. Sampling

6.1 The material shall be sampled in accordance with Practices E 32.

6.2 Other methods of sampling mutually agreed upon by the manufacturer and the purchaser may be used; however, in case of discrepancy, Practices E 32 shall be used for referee.

7. Chemical Analysis

7.1 The chemical analysis of the material shall be made in accordance with the procedure for the ferroalloys as described in Method E 31 and Test Methods E 363 or alternative methods that will yield equivalent results.

7.2 If alternative methods of analysis are used, in case of discrepancy, Method E 31 and Test Methods E 363 shall be used for referee.

¹ This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved Dec. 15, 1993. Published April 1994. Originally published as A 101 – 25 T. Last previous edition A 101 – 80 (1985) ϵ ¹.

² *Annual Book of ASTM Standards*, Vol 14.02.

³ *Annual Book of ASTM Standards*, Vol 03.05.

⁴ *Annual Book of ASTM Standards*, Vol 03.06.