
Eksplozivi za civilno uporabo - Smodniki in raketna goriva - 6. del: Trdna raketna goriva – Vodilo za ugotavljanje ustreznosti inhibitorских prevlek

Explosives for civil uses - Propellants and rocket propellants - Part 6: Solid rocket propellants - Guide for the determination of integrity of inhibitor coatings

Explosivstoffe für zivile Zwecke - Treibladungspulver und Raketentreibstoffe - Teil 6: Feste Raketentreibstoffe - Leitfaden zur Bestimmung der Integrität von Inhibitorbeschichtungen

Explosifs a usage civil - Propergol et blocs de propergol pour fusée - Partie 6: Bloc de propergol pour fusée - Guide de détermination de l'intégrité des revêtements inhibiteurs

Ta slovenski standard je istoveten z: EN 13938-6:2004

ICS:

71.100.30 Eksplozivi. Pirotehnika Explosives. Pyrotechnics

SIST EN 13938-6:2004**en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13938-6:2004

<https://standards.iteh.ai/catalog/standards/sist/6c14ba81-603b-4bc3-b303-510ea212b638/sist-en-13938-6-2004>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 13938-6

May 2004

ICS 71.100.30

English version

**Explosives for civil uses - Propellants and rocket propellants -
Part 6: Solid rocket propellants - Guide for the determination of
integrity of inhibitor coatings**

Explosifs à usage civil - Propergol et blocs de propergol
pour fusée - Partie 6: Bloc de propergol pour fusée - Guide
de détermination de l'intégrité des revêtements inhibiteurs

Explosivstoffe für zivile Zwecke - Treibladungspulver und
Raketentreibstoffe - Teil 6: Feste Raketentreibstoffe -
Leitfaden zur Bestimmung der Integrität von
Inhibitorbeschichtungen

This European Standard was approved by CEN on 6 February 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions.....	5
4 NDT methods.....	6
5 Test report	6

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 13938-6:2004](https://standards.iteh.ai/catalog/standards/sist/6c14ba81-603b-4bc3-b303-510ea212b638/sist-en-13938-6-2004)

<https://standards.iteh.ai/catalog/standards/sist/6c14ba81-603b-4bc3-b303-510ea212b638/sist-en-13938-6-2004>

Foreword

This document (EN 13938-6:2004) has been prepared by CEN /TC 321, "Explosives for civil uses", the secretariat of which is held by AENOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2004, and conflicting national standards shall be withdrawn at the latest by November 2004.

This European Standard is one of a series of standards with the generic title *Explosives for civil uses – Propellants and rocket propellants*. The other parts of this series are listed below:

prEN 13938-1 Part 1: Requirements.

prEN 13938-2 Part 2: Determination of resistance to electrostatic energy.

EN 13938-3 Part 3: Determination of deflagration to detonation transition.

EN 13938-4 Part 4: Determination of burning rate under ambient conditions.

prEN 13938-5 Part 5: Solid rocket propellants. Determination of voids and fissures.

prEN 13938-7 Part 7: Determination of properties of black powder.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Introduction

Incomplete adhesion of, or flaws in, the inhibitor coating to solid rocket propellant grains and the casing can result in dangerously high pressures in rocket motors and adversely affect their safety and performance. The category "Solid rocket propellants" encompasses charges over a wide range of composition and dimensions. It is not possible to define an acceptable level of defects (lack, crack or blister) in the inhibitor coating which is applicable to the whole range of products. It is necessary for this to be agreed between the producer and the customer. Consequently a Harmonised Standard cannot be defined with criteria for acceptance levels of integrity of inhibitor coating. However it is important that interested parties are aware of the methods which can be used to assess the extent of integrity of inhibitor coating in any particular product. This standard describes a number of methods which have been used. A method can be selected which is most appropriate to the charge under examination.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 13938-6:2004

<https://standards.iteh.ai/catalog/standards/sist/6c14ba81-603b-4bc3-b303-510ea212b638/sist-en-13938-6-2004>

1 Scope

This European Standard provides a guide to non-destructive testing (NDT) methods for detecting the integrity of inhibitor coatings in solid rocket propellants.

2 Normative references

This European Standard incorporates, by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 13857-1:2003, *Explosives for civil uses - Part 1: Terminology*

EN ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories (ISO/IEC 17025:1999)*

3 Terms and definitions

For the purposes of this European Standard, the terms and definitions given in EN 13857-1:2003 and the following apply.

3.1

NDT method

discipline applying a physical principle in non-destructive testing

NOTE: An example of an NDT method is ultrasonic testing.

3.2

NDT technique

specific way of utilising an NDT method

NOTE: An example of an NDT technique is immersion ultrasonic testing.

3.3

NDT procedure

orderly sequence of rules, which describes step by step how and in which sequence an NDT technique should be applied to a specific field

3.4

lack of coating

absence of inhibitor coating in a limited area on the surface of the propellant, which normally should be coated, or evident reduction of coating thickness on such a surface

3.5

crack in coating

discontinuity in coating which does not expose the propellant

3.6

blister in coating

Inclusion of gas under the external surface of inhibitor coating that can cause a hump

EN 13938-6:2004 (E)**3.7****integrity of inhibitor coating**

presence or absence of specified defects in the inhibitor coating

3.8**solid rocket propellant**

propellant consisting of one or more blocks, usually with a central hole, with an external inhibitor in order to burn in a controlled manner

3.9**debonding**

lack of adhesion causing separation of coating and propellant

4 NDT methods

The integrity of an inhibitor coating of a solid rocket propellant can be assessed by various NDT methods normally used for the testing of metal and welds. The NDT method and technique selected depend on many factors. Among them it may be useful to distinguish:

- minimum area of uncoated propellant or minimum size of crack or blister in the coating to be detected;
- type of propellant to be inspected;
- type of inspection (continuous production line inspection or the individual inspection of samples);
- number of units to be inspected.

The main NDT methods used are shown in Table 1.

<https://standards.iteh.ai/catalog/standards/sist/6c14ba81-603b-4bc3-b303-510ea212b638/sist-en-13938-6-2004>

5 Test report

The test report shall conform to EN ISO/IEC 17025. In addition, the following information shall be given:

- a) reference to this standard;
- b) identification of the product tested;
- c) reference to the agreed acceptance criteria for the product tested;
- d) reference to the NDT procedure used;
- e) identification of the NDT record(s);
- f) results of the NDT tests.