



Designation: A 480/A 480M – 99b

## Standard Specification for General Requirements for Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip<sup>1</sup>

This standard is issued under the fixed designation A 480/A 480M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification<sup>2</sup> covers a group of general requirements that, unless otherwise specified in the purchase order or in an individual specification, shall apply to rolled steel plate, sheet, and strip, under each of the following specifications issued by ASTM: Specifications A 167, A 176, A 240/A 240M, A 263, A 264, A 265, A 666, A 693, A 793, and A 895.

1.2 In case of any conflicting requirements, the requirements of the purchase order, the individual material specification, and this general specification shall prevail in the sequence named.

1.3 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

1.4 This specification and the applicable material specifications are expressed in both inch-pound and SI units. However, unless the order specifies the applicable “M” specification designation (SI units), the material shall be furnished in inch-pound units.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

A 167 Specification for Stainless and Heat-Resisting Chromium-Nickel Steel Plate, Sheet, and Strip<sup>3</sup>

A 176 Specification for Stainless and Heat-Resisting Chromium Steel Plate, Sheet, and Strip<sup>3</sup>

A 240/A240M Specification for Heat-Resisting Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels<sup>3</sup>

A 262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels<sup>3</sup>

A 263 Specification for Corrosion-Resisting Chromium Steel-Clad Plate, Sheet, and Strip<sup>3</sup>

A 264 Specification for Stainless Chromium-Nickel Steel-Clad Plate, Sheet, and Strip<sup>3</sup>

A 265 Specification for Nickel and Nickel-Base Alloy-Clad Steel Plate<sup>3</sup>

A 342 Test Methods for Permeability of Feebly Magnetic Materials<sup>4</sup>

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products<sup>3</sup>

A 666 Specification for Austenitic Stainless Steel Sheet, Strip, Plate, and Flat Bar<sup>3</sup>

A 693 Specification for Precipitation-Hardening Stainless and Heat-Resisting Steel Plate, Sheet, and Strip<sup>3</sup>

A 700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Domestic Shipment<sup>5</sup>

A 751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products<sup>3</sup>

A 763 Practices for Detecting Susceptibility to Intergranular Attack in Ferritic Stainless Steels<sup>3</sup>

A 793 Specification for Rolled Floor Plate, Stainless Steel<sup>3</sup>

A 895 Specification for Free-Machining Stainless Steel Plate, Sheet, and Strip<sup>3</sup>

A 923 Test Methods for Detecting Detrimental Intermetallic Phases in Wrought Duplex Austenitic/Ferritic Stainless Steels<sup>3</sup>

E 112 Test Methods for Determining the Average Grain Size<sup>6</sup>

E 140 Hardness Conversion Tables for Metals (Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Rockwell Superficial Hardness, Knoop Hardness, and Scleroscope Hardness)<sup>6</sup>

#### 2.2 Federal Standard:

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)<sup>7</sup>

#### 2.3 Military Standards:

MIL-STD-129 Marking for Shipment and Storage<sup>7</sup>

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage<sup>7</sup>

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel and Related Alloys, and is the direct responsibility of Subcommittee A01.17 on Flat-Rolled and Wrought Stainless Steel Products.

Current edition approved Dec. 10, 1999. Published February 2000. Originally published as A 480 – 62 T. Last previous edition A 480/A 480M – 99a.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications see related Specification SA – 480 in Section II of that Code.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 01.03.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 03.04.

<sup>5</sup> *Annual Book of ASTM Standards*, Vol 01.05.

<sup>6</sup> *Annual Book of ASTM Standards*, Vol 03.01.

<sup>7</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

#### 2.4 AIAG Standard:

B-5 Primary Metals Identification Tag Application Standard<sup>8</sup>

#### 2.5 ANSI Standard:

Accredited Standards Committee X 12, (ANSI ASC X12)<sup>9</sup>

### 3. Terminology

#### 3.1 Definitions:

3.1.1 Plate, sheet, strip, and cold work as used in this specification apply to the following:

3.1.2 *plate*—material  $\frac{3}{16}$  in. [5.00 mm] and over in thickness and over 10 in. [250 mm] in width. Finishes for *plate* are actually shown in Section 13.

3.1.3 *sheet*—material under  $\frac{3}{16}$  in. [5.00 mm] in thickness and 24 in. [600 mm] and over in width. Finishes for *sheet* are actually shown in Section 11.

3.1.4 *strip*—cold-rolled material under  $\frac{3}{16}$  in. [5.00 mm] in thickness and under 24 in. [600 mm] in width. Finishes are detailed in Section 12 for *strip*, and strip edges in Section 14 for Cold-Rolled Strip.

3.1.5 *cold work*—the changing of mechanical properties by work hardening.

### 4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Such requirements may include, but are not limited to, the following:

4.1.1 Quantity (weight and number of pieces),

4.1.2 Name of material (stainless steel),

4.1.3 Condition (hot-rolled, cold-rolled, annealed, heat-treated),

4.1.4 Finish (see Section 11 for Sheet, Section 12 for Strip, and Section 13 for Plates). In the case of polished finishes, specify whether one or both sides are to be polished,

4.1.5 Temper (if the applicable material specification requires this detail),

4.1.6 Form (plate, sheet, or strip),

4.1.7 Dimensions (thickness, width, length),

4.1.7.1 Thickness shall be ordered to decimal or fractional thickness. The use of the gage number is discouraged as being an archaic term of limited usefulness not having general agreement on meaning. The gage number shall not be a basis for rejection.

4.1.7.2 Thickness, width, and length, when applicable, should be ordered in the same units, for example, 0.060 in. by 48 in. by 120 in. (1.52 mm by 1219 mm by 3048 mm).

4.1.8 Edge, strip only (see Section 14 for Cold-Rolled Strip),

4.1.9 Type or UNS designation, refer to the applicable material specification,

4.1.10 Specification designation and date of issue,

4.1.11 Additions to specification or special requirements,

4.1.12 Restrictions (if desired) on methods for determining yield strength (see appropriate footnote to mechanical properties table of the basic material specification),

4.1.13 Marking requirements (see Section 25),

4.1.14 Preparation for delivery (see Section 25), and

4.1.15 Magnetic permeability test (when required). Refer to Section 19.

NOTE 1—A typical ordering description is as follows: 200 pieces, stainless steel sheets, 0.060 in. by 48 in. by 120 in., Type 410 No. 2B finish, ASTM A 176-XX.

### 5. Process

5.1 The steel shall be manufactured/produced by the following or as specified in the applicable material specification.

5.1.1 The steel shall be made by one of the following processes: electric-arc, electric-induction, or other suitable processes.

5.1.2 If a specific type of melting is required by the purchaser, it shall be so specified on the purchase order.

### 6. Heat Analysis

6.1 An analysis of each heat shall be made by the steel producer to determine the percentages of the elements specified in the applicable material specification. This analysis shall be made from a test sample taken during the pouring of the melt, or from the in-process product later in the manufacturing flow. The chemical composition thus determined shall conform to the applicable material specification.

6.2 Methods and practices relating to chemical analysis shall be in accordance with Test Methods, Practices, and Terminology A 751.

6.3 The steel shall not contain an unspecified element for the ordered grade to the extent that the steel conforms to the requirements of another grade for which that element is a specified element having a required minimum content. For this requirement, a grade is defined as an alloy described individually and identified by its own UNS designation in a table of chemical requirements within this specification or any specification listed within the scope as being covered by the specification.

### 7. Product Analysis

7.1 Product analysis (formerly check analysis) may be made by the purchaser to verify the identity of the finished material representing each heat or lot. Such analysis may be made by any of the commonly accepted methods that will positively identify the material.

7.2 The chemical composition determined in accordance with 7.1 shall conform to the limits of the material specification within the tolerances of Table A1.1, unless otherwise specified in the applicable material specification or the purchase order. The allowable variation of a particular element in a single sample for product analysis may be either above or below the specified range. However, percentages must exhibit the same tendencies in all samples; that is, the several determinations of any individual element in a heat may not vary both above and below the specified range.

### 8. Material Test Report and Certification

8.1 A report of the results of all tests required by the product

<sup>8</sup> Available from the Automotive Industry Action Group, 26200 Lahser, Suite 200, Southfield, MI 48034.

<sup>9</sup> Available from American National Standards Institute (ANSI), 655 15th Street, Washington, DC 20005.

specification shall be supplied to the purchaser. This material test report shall reference the product specification designation and year date indicating that the material was manufactured, sampled, tested, and inspected in accordance with requirements of the product specification and has been found to meet those requirements. The material test report shall report the melting process when the purchase order requires either a specific type of melting or requires that the melting process used is to be reported.

8.1.1 The report shall indicate the type of steel. If certifying that the material conforms to the requirements for more than one type of steel, the manufacturer may indicate each type of steel on the report, or may issue a separate report for each type of steel.

8.2 A signature is not required on the report. However, the document shall clearly identify the organization submitting the report.

8.3 A material test report, certificate of inspection, or similar document printed from or used in electronic form from an electronic data interchange (EDI) transmission shall be regarded as having the same validity as a counterpart printed in the certifiers' facility. The content of the EDI transmitted document must meet the requirements of the invoked ASTM standard(s) and conform to any existing EDI agreement between the purchaser and the supplier. Notwithstanding the absence of a signature, the organization submitting the EDI transmission is responsible for the content of the report.

8.4 When finished material is supplied to a purchase order specifying the product specification, the organization supplying that material shall provide the purchaser with a copy of the original manufacturer's test report.

NOTE 2—Notwithstanding the absence of a signature, the organization submitting the report is responsible for the content of the report.

NOTE 3—The industry definition as invoked here is: EDI is the computer-to-computer exchange of business information in a standard format such as ANSI ASC X 12.

## 9. Permitted Variations in Dimensions and Weight

9.1 Sheet, strip, and plate shall conform to the permitted variations in thickness, width, length and flatness, and other properties when specified, as listed in Annex A2 [Annex A3], for the ordered product form, or as agreed upon by seller and user and specified in the purchase order.

## 10. Workmanship

10.1 The material shall be of uniform quality consistent with good manufacturing and inspection practices. The steel shall have no imperfections of a nature or degree, for the type and quality ordered, that will adversely affect the stamping, forming, machining, or fabrication of finished parts.

10.2 *Sheet, Strip, and Plate*—Sheet, and strip with No. 1 finish and plate with hot-roll anneal or hot-roll anneal and pickle finish may be ground to remove surface imperfections, provided such grinding does not reduce the thickness or width at any point beyond the permissible variations in dimensions. An iron free abrasive wheel shall be used for such grinding and shall be operated at a speed ample to ensure that defective areas are cleanly cut out.

## 11. Finish for Sheet

11.1 The types of finish available on sheet products are:

11.1.1 *No. 1 Finish*—Hot-rolled, annealed, and descaled.

11.1.2 *No. 2D Finish*—Cold-rolled, dull finish.

11.1.3 *No. 2B Finish*—Cold-rolled, bright finish.

11.1.3.1 *Bright Annealed Finish*—A bright cold-rolled finish retained by final annealing in a controlled atmosphere furnace.

11.1.4 *No. 3 Finish*—Intermediate polished finish, one or both sides.

11.1.5 *No. 4 Finish*—General purpose polished finish, one or both sides.

11.1.6 *No. 6 Finish*—Dull satin finish, Tampico brushed, one or both sides.

11.1.7 *No. 7 Finish*—High luster finish.

11.1.8 *No. 8 Finish*—Mirror finish.

11.1.9 *TR Finish*—Cold-worked to obtain specified properties.

NOTE 4—*Explanation of Sheet Finishes:*

*No. 1*—This finish is produced by hot rolling to specified thickness followed by annealing and descaling. It is generally used in industrial applications, such as for heat and corrosion resistance, where smoothness of finish is not of particular importance.

*No. 2D*—Produced on either hand sheet mills or continuous mills by cold rolling to the specified thickness, annealing, and descaling. The dull finish may result from the descaling or pickling operation or may be developed by a final light cold-rolled pass on dull rolls. The dull finish is favorable for retention of lubricants on the surface in deep drawing operations. This finish is generally used in forming deep-drawn articles which may be polished after fabrication.

*No. 2B*—Commonly produced the same as 2D, except that the annealed and descaled sheet receives a final light cold-rolled pass on polished rolls. This is a general purpose cold-rolled finish. It is commonly used for all but exceptionally difficult deep drawing applications. This finish is more readily polished than No. 1 or No. 2D Finish.

*Bright Annealed Finish* is a bright cold-rolled highly reflective finish retained by final annealing in a controlled atmosphere furnace. The purpose of the atmosphere is to prevent scaling or oxidation during annealing. The atmosphere is usually comprised of either dry hydrogen or a mixture of dry hydrogen and dry nitrogen (sometimes known as dissociated ammonia).

*No. 3*—For use as a finish-polished surface or as a semifinished-polished surface when it is required to receive subsequent finishing operations following fabrication. Where sheet or articles made from it will not be subjected to additional finishing or polishing operations, No. 4 finish is recommended.

*No. 4*—Widely used for restaurant equipment, kitchen equipment, store fronts, dairy equipment, etc. Following initial grinding with coarser abrasives, sheets are generally finished last with abrasives approximately 120 to 150 grit.

*No. 6*—Has a lower reflectivity than No. 4 finish. It is produced by Tampico brushing No. 4 finish sheets in a medium of abrasive and oil. It is used for architectural applications and ornamentation where high luster is undesirable; it is also used effectively to contrast with brighter finishes.

*No. 7*—Has a high degree of reflectivity. It is produced by buffing a finely ground surface, but the grit lines are not removed. It is chiefly used for architectural or ornamental purposes.

*No. 8*—The most reflective finish that is commonly produced. It is obtained by polishing with successively finer abrasives and buffing extensively with very fine buffing rouges. The surface is essentially free of grit lines from preliminary grinding operations. This finish is most widely used for press plate, as well as for small mirrors and reflectors.

*TR Finish*—The finish of products resulting from cold-working an annealed and descaled or bright-annealed product sufficiently to obtain



mechanical properties higher than that normally obtained. Appearance will vary depending upon the amount of cold work required and the alloy ordered.

11.1.10 Sheets can be produced with one or two sides polished. When polished on one side only, the other side may be rough ground in order to obtain the necessary flatness.

## 12. Finish for Strip

12.1 The various types of finish procurable on cold-rolled strip products are:

12.1.1 *No. 1 Finish*—Cold-rolled to specified thickness, annealed, and descaled.

12.1.2 *No. 2 Finish*—Same as No. 1 Finish, followed by a final light cold-roll pass, generally on highly polished rolls.

12.1.3 *Bright Annealed Finish*—A bright cold-rolled finish retained by final annealing in a controlled atmosphere furnace.

12.1.4 *TR Finish*—Cold-worked to obtain specified properties.

12.1.5 *Polished Finish*—Stainless steel strip is also available in polished finishes such as No. 3 and No. 4, which are explained in Note 4.

NOTE 5—*Explanation of Strip Finishes:*

*No. 1*—Appearance of this finish varies from dull gray matte finish to a fairly reflective surface, depending largely upon composition. This finish is used for severely drawn or formed parts, as well as for applications where the brighter No. 2 Finish is not required, such as parts for heat resistance.

*No. 2*—This finish has a smoother and more reflective surface, the appearance of which varies with composition. This is a general purpose finish, widely used for household and automotive trim, tableware, utensils, trays, etc.

*Bright Annealed Finish*—See Note 4.

*TR Finish*—See Note 4.

## 13. Finish for Plates

13.1 The types of finish available on plates are:

13.1.1 *Hot-Rolled or Cold-Rolled, and Annealed or Heat Treated*—Scale not removed, an intermediate finish. Use of plates in this condition is generally confined to heat-resisting applications. Scale impairs corrosion resistance.

13.1.2 *Hot-Rolled or Cold-Rolled, and Annealed or Heat Treated, and Blast Cleaned or Pickled*—Condition and finish commonly preferred for corrosion-resisting and most heat-resisting applications, essentially a No. 1 Finish.

13.1.3 *Hot-Rolled or Cold-Rolled, and Annealed or Heat Treated, and Surface Cleaned and Polished*—Polish finish is generally No. 4 Finish.

13.1.4 *Hot-Rolled or Cold-Rolled, and Annealed or Heat Treated, and Descaled, and Temper Passed*—Smoother finish for specialized applications.

13.1.5 *Hot-Rolled or Cold-Rolled, and Annealed or Heat Treated, and Descaled; and Cold-Rolled, and Annealed or Heat Treated, and Descaled, and Optionally Temper Passed*—Smooth finish with greater freedom from surface imperfections than in 13.1.4.

## 14. Edges for Cold-Rolled Strip

14.1 The types of edges available on strip products are:

14.1.1 *No. 1 Edge*—A rolled edge, either round or square as specified.

14.1.2 *No. 3 Edge*—An edge produced by slitting.

14.1.3 *No. 5 Edge*—An approximately square edge produced by rolling or filing after slitting.

## 15. Heat Treatment

15.1 The heat treatments shown in this section are to be followed unless otherwise specified in the applicable material specification. Heat treatment thermal cycles shall be separate from other thermal processing cycles; for example, in-process thermal cycles are not permitted as a substitute for the separate annealing cycle.

15.2 *Austenitic Types:*

15.2.1 The material shall be solution annealed to meet the mechanical property requirements of the applicable material specification unless otherwise stated in the material specification.

15.2.2 Except as indicated in Table A1.2, Series 300, XM-15, N08800, S30415, S30815, S31725, S31726, and S32615 austenitic chromium-nickel steels, when specified on the purchase order, shall be capable of meeting the test for resistance to intergranular corrosion specified in 18.2.

15.2.3 For grades stabilized with titanium or columbium, refer to Note 6.

NOTE 6—Solution-annealing temperatures above 1950°F [1066°C] may impair the resistance to intergranular corrosion after subsequent exposure to sensitizing conditions in the stabilized grades, Types 309Cb, 309Hcb, 310Cb, 310Hcb, 316Ti, 316Cb, 321, 321H, 347, 347H, 348, 348H, and S35135. When intergranular corrosion is of concern, the purchaser should specify the corrosion test of 18.2 (to be conducted on sensitized specimens). The manufacturer may, if necessary, use a lower temperature resolution anneal or a stabilization anneal after a high temperature solution anneal in order to meet corrosion test requirements. Consideration should be given to the corrosive media before using a stabilization anneal at less than 1800°F [982°C], as such treatment may not be equally effective for all media.

15.2.4 For the stabilized H types, it is noted that the heat treatment requirements shown in Table A1.2 differ as a function of whether the material was cold worked or hot finished.

15.2.5 The chromium-manganese-nickel types (201, 202, S20103, S20400, S20153, S21800, XM-17, XM-18, XM-19, XM-29, and XM-31) shall be solution annealed to meet the mechanical property requirements of the applicable material specification and, to exhibit adequate resistance to intergranular corrosion (see 18.2). For S20161, the heat treatment is specified in Table A1.2.

15.2.5.1 Note that some of these types may contain high carbon content that can adversely affect resistance to intergranular corrosion.

15.3 *Duplex Types*—The duplex types shall be solution annealed in accordance with Table A1.2.

15.4 *Martensitic and Ferritic Types:*

15.4.1 The chromium steels (S32803, 400 Series, S40945, S41045, S41050, S41500, S43932, S44400, S44635, S44660, S44700, S44735, S44800, XM-27, and XM-33) shall be heat treated in such a manner as to satisfy all the requirements for mechanical and bending properties specified in the applicable material specification and (except for 400 Series, S41050, and S41500) to provide for adequate resistance to intergranular attack.

15.4.2 For S41500, heat to 1750°F [955°C] minimum, air cool to 200°F [93°C] or lower prior to any optional intermediate temper and prior to final temper. The final temper shall be between 1050°F [566°C] and 1150°F [621°C].

**16. Number of Tests**

16.1 Unless otherwise specified by the applicable material specification or by agreement between the seller and the purchaser the following number of tests are to be performed.

16.1.1 In the case of plate, sheet, and strip produced in coil form, two or more hardness tests (one from each end of the coil); one bend test, when required; one permeability test, when required; and one or more tension tests shall be made on specimens taken from each coil. If the hardness difference between the two ends of the coil exceeds 5 HRB, or equivalent, or if the material is temper rolled, tensile properties must be determined on both coil ends.

16.1.2 In the case of plate, sheet, or strip produced in cut lengths, one tension test; two tension tests if the material is temper rolled (one tension test for single piece lots); one bend test when required, and one or more hardness tests shall be made on each 100 or less pieces of the same heat and nominal thickness rolled separately or continuously and heat treated within the same operating period, either as a lot or continuously.

NOTE 7—The term continuously, as applied to heat treatment, is meant to describe a heat-treating operation in which one cut length follows another through the furnace. Interspersion of different melts is permissible if they are of approximately the same nominal thickness and are heat treated in the same operating period and under the same conditions (time and temperature).

16.1.3 One intergranular corrosion test, when required, shall be selected from each heat and thickness subjected to the same heat treatment practice. Such specimens may be obtained from specimens selected for mechanical testing.

**17. Test Specimens**

17.1 *Tension Test:*

17.1.1 Tension test specimens shall be taken from finished material and shall be selected in either or both longitudinal and transverse direction. The tension test specimen shall conform to the appropriate sections of Test Methods and Definitions A 370, unless otherwise specified in the applicable material specification or agreed upon by the seller and the purchaser.

17.1.2 The testing speed between the yield strength and the fracture of the specimen, shall be conducted at a constant strain rate between 1/8 in. [3.18 mm] and 1/2 in. [12.70 mm] inclusive, per inch [25.40 mm] of gage length per minute, or at a crosshead speed that will give a strain rate within this range. For the purposes of this specification, the rate of strain may be determined by a strain-rate pacer, indicator, or controller, or by dividing the unit elongation by the elapsed time from yield strength to fracture.

17.2 *Hardness Test*—Hardness tests may be made on the grip ends of the tension specimens before they are subjected to the tension test.

17.3 *Bend Test:*

17.3.1 Bend test specimens (when required) shall be taken from finished material and shall be selected in the transverse

direction or as indicated in the applicable material specification or as agreed upon by the seller and the purchaser. In the case of transverse bend test specimens, the axis of bend shall be parallel to the direction of rolling.

17.3.2 Bend test specimens from sheet and strip product shall be the full thickness of the material and approximately 1 in [25.4 mm] in width. The edges of the test specimen may be rounded to a radius equal to one half the specimen thickness.

17.3.3 The width of strip for which bend tests can be made is subject to practical limitations on the length of the bend test specimen. For narrow strip, the following widths can be tested:

Strip thickness, in. [mm]	Minimum Strip Width and Minimum Specimen Length for Bend Tests, in. [mm]
0.100 [2.5] and under	1/2 [12.7]
Over 0.100 [2.5] to 0.140 [3.5], excl.	1 [25.4]
0.140 [3.5] and over	1 1/2 [38.1]

Bend test specimens may be of any suitable length over the specified minimum length.

17.3.4 Bend test specimens taken from plates shall be in full thickness of the material up to and including 1/2 in. [12.7 mm] in thickness, of suitable length, and between 1 and 2 in [25.4 and 50.8 mm] in width. The sheared edges may be removed to a depth of at least 1/8 in. [3.2 mm] and the sides may be smoothed with a file. The corners of the cross section of the specimen may be broken with a file, but no appreciable rounding of the corners may be permitted.

17.3.5 In the case of plates over 1/2 in. [12.7 mm] in thickness, bend test specimens, machined to 1 in. [25.4 mm] nominal width by 1/2 in. [12.7 mm] nominal thickness and at least 6 in. [152.4 mm] in length, may be used. One surface, to be the outside surface in bending, shall be the original surface of the plate; however, surface preparation by light grinding is permitted. The edges may be rounded to a 1/16 in. [1.6 mm] radius. When permitted by agreement between the seller and the purchaser, the cross section may be modified to 1/2 in. [12.7 mm] nominal square.

17.3.6 In the case of plates over 1 in. [25.4 mm] in thickness, bend tests must be agreed upon between the seller and the purchaser.

17.3.7 The bend test specimen shall withstand cold bending through the angle specified in the applicable material specification without cracking on the outside of the bent portion.

17.4 The bend may be made over a diameter equal to the number of thicknesses of flat stock shown in the applicable material specification or over a single piece of flat stock equal to the number of thicknesses shown in the applicable material specification; or as shown as follows:

17.4.1 Material up to and including 3/8 in. [9.5 mm] in thickness shall be bent over a piece (or pieces) of flat stock that has the same nominal thickness of the material being tested (1T), allowing the test material to form its natural curvature.

17.4.2 Material over 3/8 in. [9.5 mm] and up to and including 1 in [25.4 mm] in thickness shall be bent over a piece (or pieces) of flat stock equalling two times the thickness of the material being tested (2T), allowing the test material to form its natural curvature.

## 18. Special Tests

18.1 If other tests that are thought to be pertinent to the intended application of the material covered by the purchase specification are required, the methods and limits shall be agreed upon between the seller and the purchaser and specified on the purchase order.

### 18.2 *Resistance to Intergranular Corrosion:*

18.2.1 The intergranular corrosion test, Practice E of Practices A 262, is not required unless it is specified on the purchase order. All austenitic chromium-nickel types except the H types are expected to be capable of passing this test. However, it is not necessary to actually run the test unless it is specified on the purchase order. Note that Practices A 262 requires the test to be performed on sensitized specimens in the low-carbon and stabilized types and on specimens representative of the as-shipped condition for other types. In the case of low-carbon types containing 3 % or more molybdenum in their specified composition, the applicability of the sensitizing treatment prior to testing shall be a matter for negotiation between the seller and the purchaser. When specified, all flat rolled products of the chromium-nickel series (300 series) in thickness up to and including 2 in. [50.8 mm] nominal size shall be capable of passing the intergranular corrosion test in the as shipped condition. In the case of heavier plates of types other than 304L, 304LN, 309Cb, 310Cb, 316Cb, 316L, 316LN, 316Ti, 317L, 321, 347, 348, S31725, and S31726, the applicability of this test shall be a matter for negotiation between the seller and the purchaser.

18.2.2 The H types are not normally subject to intergranular corrosion tests. However, Practice E of Practices A 262 may be specified for Type 321H when intergranular corrosion is of concern. In this case, the purchaser shall inform the seller and agree upon the requirements and these requirements shall be so stated on the purchase order.

18.2.3 Austenitic chromium-manganese-nickel types (201, 202, XM-17, XM-18, XM-19, XM-29, XM-31, S20400, and S21800) are to be heat treated for intergranular corrosion resistance. When intergranular corrosion tests are required, they shall be as agreed upon between the seller and the purchaser.

18.2.4 N08800 shall be heat treated for intergranular corrosion resistance. When intergranular corrosion tests are required, they shall be as agreed upon between the seller and purchaser.

18.2.5 Corrosion tests are not normally required for the 400 series types. Lower-carbon corrosion-resistant types (S44400, S44635, S44660, S44700, S44800, S44735, XM-27, and XM-33) are heat treated for resistance to corrosion. For S44400, S44635, S44660, S44700, S44800, S44735, XM-27, and XM-33, intergranular corrosion testing of Practices A 763, Practice X, Y, or Z may be specified as agreed upon between the seller and the purchaser.

18.3 *Detrimental Intermetallic Phases in Duplex Stainless Steels*—The tests for detrimental intermetallic phases in wrought duplex stainless steels, Methods A, B, or C of Test Methods A 923, are not required unless it is specified on the purchase order. All duplex (austenitic-ferritic) types that are listed in Test Methods A 923 are expected to be capable of

passing these tests. However, it is not necessary to actually run the tests unless specified on the purchase order. The applicability of these tests to duplex stainless steels not listed in Test Methods A 923 shall be a matter for negotiation between the seller and the purchaser.

## 19. Test Methods

19.1 The properties enumerated in applicable specifications shall be determined in accordance with the following ASTM standards.

19.1.1 *Tension Tests*—Test Methods and Definitions A 370.

19.1.2 *Brinell Tests*—Test Methods and Definitions A 370.

19.1.3 *Rockwell Hardness*—Test Methods and Definitions A 370.

19.1.4 *Hardness Equivalents*—Tables E 140.

19.1.5 *Intergranular Corrosion (when specified)*—Practices A 262, Practices A 763.

19.1.6 *Permeability Test (when required)*—Test Methods A 342.

19.1.7 *Charpy Impact Testing (when required)*—Test Methods and Definitions A 370.

## 20. Retests and Retreatment

20.1 Retests may be made in accordance with the provisions of Test Methods and Definitions A 370.

20.2 If any test specimen shows defective machining or develops flaws, it may be discarded and another specimen substituted.

20.2.1 If the percentage of elongation of any tension specimen is less than that specified and any part of the fracture is more than  $\frac{3}{4}$  in. [19.1 mm] from the center of the gage length of the 2 in. [50.8 mm] specimen or is outside the middle half of the gage length of an 8-in. [203.2-mm] specimen, as indicated by scribe marks placed on the specimen before testing, a retest shall be allowed.

20.3 If a bend test specimen fails, due to conditions of bending more severe than required by the specification, a retest shall be permitted, either on a duplicate specimen or on a remaining portion of the failed specimen.

20.4 If the results of any test lot are not in conformance with the requirements of the applicable material specification, such lots may be retreated at the option of the producer. The material shall be accepted if the results of retests on retreated material are within the specified requirements.

20.5 If any specimens selected to represent any heat fail to meet any of the test requirements as specified in the applicable material specification, the material represented by such specimens may be reheat-treated and resubmitted for test.

20.6 If the product analysis fails to conform to the specified limits, analysis shall be made on a new sample. The results of this retest shall be within the specified requirements.

## 21. Repair of Plate by Welding

21.1 Repair of surface defects of plate, by welding, is permitted unless prohibited by other specifications or purchase order requirements.

21.2 Defect depth shall not exceed 1/3 of the nominal thickness, and the total area shall not exceed 1 % of the plate surface area, unless prior approval from the purchaser is obtained.



21.3 Unacceptable imperfections shall be suitably prepared for welding by grinding or machining. Open clean defects, such as pits or impressions, may not require preparation.

21.4 The welding procedure and the welders or welding operators shall be qualified in accordance with Section IX of the ASME Code.<sup>2</sup>

21.5 The welding consumables shall be suitable with the plate.

21.6 After repair welding, the welded area shall be ground smooth and blended uniformly to the surrounding surface.

## 22. Inspection

22.1 Inspection of the material by the purchaser's representative at the producing plant shall be made as agreed upon between the purchaser and the seller as part of the purchase order.

22.2 Unless otherwise specified in the contract or purchase order: (1) the seller is responsible for the performance of all the inspection and test requirements in this specification, (2) the seller may use his own or other suitable facilities for the performance of the inspection and testing, and (3) the purchaser shall have the right to perform any of the inspection and tests set forth in this specification. The manufacturer shall afford the purchaser's inspector all reasonable facilities necessary to satisfy him that the material is being furnished in accordance with the specification. Inspection by the purchaser shall not interfere unnecessarily with the manufacturer.

## 23. Rejection

23.1 Unless otherwise specified, any rejection based on tests made in accordance with this specification shall be reported to the seller within 60 working days from the receipt of the material by the purchaser.

23.2 Material that shows injurious imperfections as described in Section 10 subsequent to its acceptance at the purchaser's works will be rejected and the seller shall be notified.

## 24. Rehearing

24.1 Samples tested in accordance with this specification that represent rejected material shall be retained for 3 weeks from the date of the notification to the seller of the rejection. In case of dissatisfaction with the results of the test, the seller may make claim for a rehearing within that time.

## 25. Packaging, Marking, and Loading

### 25.1 For Commercial Procurement:

25.1.1 *Marking*—Unless otherwise specified in the applicable material specification or the purchase order, marking shall be conducted as follows:

25.1.1.1 Sheet, strip, and plate shall be marked on one face, in the location indicated below with the specification designation number, type of steel (type or UNS designation), material identification number, and the name or mark of the manufacturer. For sheet, strip, and plate whose length and width dimensions are both less than 24 in., each piece shall be

marked with the type of steel and material identification number. The specification and designation number, and name or mark of the manufacturer shall be marked on the piece(s) or attached to the item or bundle. The characters shall be of such size as to be clearly legible. The marking shall be sufficiently stable to withstand normal handling. Unless otherwise specified by the purchaser, the marking, at the producer's option, may be done with (a) marking fluid (if a specific maximum impurity limit of designated elements in the marking fluid is required by the purchaser, it shall be so stated on the purchase order), (b) low-stress blunt-nosed continuous or low-stress blunt-nosed-interrupted-dot die stamp, (c) a vibratory tool with a minimum tip radius of 0.005 in. [0.1 mm], or (d) electrochemical etching.

25.1.1.2 Flat sheet, strip in cut lengths, and plate shall be marked in two places near the ends or may be continuously line marked along one edge. For flat sheet, strip in cut lengths, and plate whose length and width dimensions are both less than 48 in., may be marked in only one place.

25.1.1.3 Sheet, strip, and plate in coil form shall be marked near the outside end of the coil. The inside of the coil shall also be marked or shall have a tag or label attached and marked with the information of 25.1.1.1.

25.1.1.4 Material less than ¼ in. [6.4 mm] in thickness shall not be marked with die stamps.

25.1.1.5 The manufacturer's test identification number shall be legibly stamped on each test specimen, if to be shipped to the customer.

25.1.1.6 Material that conforms completely with the requirements of two types of steel within the ordering specification may be marked as both types of steel provided that the manufacturer is certifying the material as meeting the requirements of each of the types of steel. Such marking, if used, may be part of the same marking as used for a single type of steel, or may be a separate but similar marking immediately adjacent to the marking used for a single type of steel.

25.1.1.7 The AIAG primary metals identification tag (AIAG B-5) may be used as an auxiliary method of identification in cases where a bar-coded identification tag is desired. Use of this method shall be by agreement between purchaser and supplier.

25.1.2 *Packaging and Loading*—Unless otherwise specified in the applicable material specification or the purchase order, packaging and loading shall be in accordance with the procedures recommended by Practices A 700.

### 25.2 For U.S. Government Procurement:

25.2.1 When specified in the contract or order, and for direct procurement by or direct shipment to the government, marking for shipment shall be in accordance with Fed. Std. No. 123 for civil agencies and MIL-STD-129 for military agencies.

25.2.2 When specified in the contract or order, material shall be preserved, packaged, and packed in accordance with the requirements of MIL-STD-163. The applicable levels shall be as specified in the contract or order.

**ANNEXES**

**(Mandatory Information)**

**A1. PRODUCT ANALYSIS TOLERANCES AND HEAT TREATMENT REQUIREMENTS**

A1.1 Listed in Annex A1 are tables showing the permitted variations of composition for product analysis relative to specified chemical requirements (Table A1.1) and the heat treatment requirements for types of stainless steel covered by product specifications that reference Specification A 480/A 480M (Table A1.2).

**TABLE A1.1 Chemical Requirements (Product Analysis Tolerances)<sup>A</sup>**

Elements	Limit or Maximum of Specified Range, %	Tolerance Over the Maximum Limit or Under the Minimum Limit	Elements	Limit or Maximum of Specified Range, %	Tolerance Over the Maximum Limit or Under the Minimum Limit		
Carbon	to 0.010, incl	0.002	Titanium	to 1.00, incl	0.05		
	over 0.010 to 0.030, incl	0.005		over 1.00 to 3.00, incl	0.07		
	over 0.030 to 0.20, incl	0.01	Cobalt	over 0.05 to 0.50, incl	0.01 <sup>B</sup>		
	over 0.20 to 0.60, incl	0.02		over 0.50 to 2.00, incl	0.02		
Manganese	over 0.60 to 1.20, incl	0.03	over 2.00 to 5.00, incl	0.05			
	to 1.00, incl	0.03	Columbium plus tantalum	to 1.50, incl	0.05		
	over 1.00 to 3.00, incl	0.04		Tantalum	to 0.10, incl	0.02	
	over 3.00 to 6.00, incl	0.05			Copper	to 0.50, incl	0.03
	over 6.00 to 10.00, incl	0.06				over 0.50 to 1.00, incl	0.05
over 10.00 to 15.00, incl	0.10	over 1.00 to 3.00, incl	0.10				
over 15.00 to 20.00, incl	0.15	over 3.00 to 5.00, incl	0.15				
Phosphorus	to 0.040, incl	0.005	over 5.00 to 10.00, incl	0.20			
	over 0.040 to 0.20, incl	0.010	Aluminum	to 0.15, incl	-0.005, +0.01		
Sulfur	to 0.040, incl	0.005		over 0.15 to 0.50, incl	0.05		
	over 0.040 to 0.20, incl	0.010		over 0.50 to 2.00, incl	0.10		
	over 0.20 to 0.50, incl	0.020	Nitrogen	to 0.02, incl	0.005		
Silicon	to 1.00, incl	0.05		over 0.02 to 0.19, incl	0.01		
	over 1.00 to 3.00, incl	0.10		over 0.19 to 0.25, incl	0.02		
	over 3.00 to 6.00, incl	0.15		over 0.25 to 0.35, incl	0.03		
Chromium	over 4.00 to 10.00, incl	0.10		over 0.35 to 0.45, incl	0.04		
	over 10.00 to 15.00, incl	0.15	over 0.45 to 0.55, incl	0.05			
	over 15.00 to 20.00, incl	0.20	Tungsten	to 1.00, incl	0.03		
	over 20.00 to 30.00, incl	0.25		over 1.00 to 2.00, incl	0.05		
Nickel	to 1.00, incl	0.03	Vanadium	to 0.50, incl	0.03		
	over 1.00 to 5.00, incl	0.07		over 0.50 to 1.50, incl	0.05		
	over 5.00 to 10.00, incl	0.10	Selenium	all	0.03		
	over 10.00 to 20.00, incl	0.15					
	over 20.00 to 30.00, incl	0.20					
Molybdenum	over 0.20 to 0.60, incl	0.03					
	over 0.60 to 2.00, incl	0.05					
	over 2.00 to 8.00, incl	0.10					

<sup>A</sup> This table does not apply to heat analysis.

<sup>B</sup> Product analysis limits for cobalt under 0.05 % have not been established, and the manufacturer should be consulted for those limits.



**TABLE A1.2 Heat Treatment Requirements**

Designation/Type	Temperature	Cooling/Testing Requirements
Austenitic (Chromium-Nickel) (Chromium-Nickel-Manganese)		
All Cr-Ni steels except as listed below	1900°F [1040°C] minimum	A
302, S30215, S30452, S30615, 308, 309, 309Cb, 310, 310Cb, S32615, S33228, S38100	1900°F [1040°C] minimum	B
304H, 309H, 310H, 316H	1900°F [1040°C] minimum	B
309HCb, 310Hcb, 321H, 347H, 348H		
Cold Worked	2000°F [1095°C] minimum	B
Hot Finished	1925°F [1050°C] minimum	B
N08811	2100°F [1150°C] minimum	B
N08020	1700° to 1850°F [925° to 1010°C]	B
N08367	2025°F [1105°C] minimum	B
N08810	2050°F [1120°C] minimum	B
N08904	2000°F [1095°C] minimum	B
N08926	2010°F [1100°C] minimum	B
S20161	1900° to 2000°F [1040° to 1095°C]	B
S30600, S30601	2010° to 2140°F [1100° to 1170°C]	B
S31254, S31266, S32050, S32654	2100°F [1150°C] minimum	B
S33228	2050 to 2160°F [1120 to 1180°C]	B
S34565	2050° to 2140°F [1120° to 1170°C]	B
S35315	2010°F [1100°C] minimum	B
Duplex (Austenitic-Ferritic)		
S31200, S31803, S32001, S32550	1900°F [1040°C] minimum	B
S31260	1870° to 2010°F [1020° to 1100°C]	B
S32205	1900°F [1040°C] minimum	C
S32304	1800°F [980°C] minimum	B
S32520	1975 to 2050°F [1080 to 1120°C]	B
S32750	1880° to 2060°F [1025° to 1125°C]	B
S32760	2010°F [1100°C] minimum	B
S32900	1750° ± 25°F [955° ± 15°C]	B
S32950	1850° ± 25°F [1010° ± 15°C]	B

<sup>A</sup> Quenched in water or rapidly cooled by other means at a rate sufficient to prevent reprecipitation of carbides, as demonstrable by the capability of passing the test for resistance to intergranular corrosion specified in 18.2.

<sup>B</sup> Quenched in water or rapidly cooled by other means.

<sup>C</sup> Quenched in water, except that coiled product heat treated in a continuous annealing line shall be water quenched or rapidly cooled by other means.

ASTM A480/A480M-99b

<https://standards.iteh.ai/catalog/standards/sist/70465b1e-d6d8-411e-ae19-ae6da324b970/astm-a480-a480m-99b>

## A2. PERMITTED VARIATIONS IN DIMENSIONS, ETC.—INCH-POUND UNITS

A2.1 Listed in Annex A2 are tables showing the permissible variations in dimensions expressed in inch-pound units of measurement.

A2.1.1 The dimensional tolerances are grouped by production method (hot rolling or cold rolling, with or without coiling), product width (narrow (< 24 in. [610 mm]) or wide (≥ 24 in. [610 mm])), and by product dimension addressed.

A2.2 *Cold-Rolled Narrow (<24 in. [610 mm] width) Coil-Processed Product*—For thickness, width, length, and flatness tolerance tables, refer to Tables A2.1-A2.4.

A2.3 *Cold-Rolled Wide (≥24 in. [610 mm] width) Coil-Processed Product*—For thickness, width, length, and flatness tolerance tables, refer to Tables A2.5-A2.8.

A2.4 *Hot-Rolled Narrow (<24 in. [610 mm] width) Coil-*

*Processed Product*—For thickness, width, length, and flatness tolerance tables, refer to Tables A2.9-A2.12.

A2.5 *Hot-Rolled Wide (≥24 in. [610 mm] width) Coil-Processed Product*—For thickness, width, length, and flatness tolerance tables, refer to Tables A2.13-A2.16.

A2.6 *Hot-Rolled Product Processed Without Coiling*—For thickness, width, length, and flatness tolerance tables, refer to Tables A2.17-A2.20.

A2.7 *Cold-Rolled Product Processed Without Coiling*—For thickness, width, length, and flatness tolerance tables, refer to Table A2.21.

A2.8 *Tolerances for other dimensional characteristics*—For other tolerance tables, refer to Tables A2.22-A2.30.

**TABLE A2.1 Permitted Variations in Thickness for Cold-Rolled, Narrow, Coil-Processed Product as Coils and Cut Lengths**

NOTE 1—Thickness measurements are taken at least 3/8 in. [9.52 mm] in from the edge of the product, except on widths less than 1 in. [25.4 mm] the measurements should be taken at least 1/8 in. [3.18 mm] from the product edge.

NOTE 2—The tolerances in this table include crown tolerances.

Specified Thickness, in. [mm]	Thickness Tolerances, for the Thickness and Widths Given, Over and Under, in. [mm]		
	Width, in. [mm]		
	3/16 [4.76] to 6 [152], incl	Over 6 [152] to 12 [305], incl	Over 12 [305] to 24 [610], excl
	Thickness Tolerances <sup>A</sup>		
0.005 [0.13] to 0.010 [0.25], incl	10 %	10 %	10 %
Over 0.010 [0.25] to 0.011 [0.28], incl	0.0015 [0.04]	0.0015 [0.04]	0.0015 [0.04]
Over 0.011 [0.28] to 0.013 [0.33], incl	0.0015 [0.04]	0.0015 [0.04]	0.002 [0.05]
Over 0.013 [0.33] to 0.017 [0.43], incl	0.0015 [0.04]	0.002 [0.05]	0.002 [0.05]
Over 0.017 [0.43] to 0.020 [0.51], incl	0.0015 [0.04]	0.002 [0.05]	0.0025 [0.06]
Over 0.020 [0.51] to 0.029 [0.74], incl	0.002 [0.05]	0.0025 [0.06]	0.0025 [0.06]
Over 0.029 [0.74] to 0.035 [0.89], incl	0.002 [0.05]	0.003 [0.08]	0.003 [0.08]
Over 0.035 [0.89] to 0.050 [1.27], incl	0.0025 [0.06]	0.0035 [0.09]	0.0035 [0.09]
Over 0.050 [1.27] to 0.069 [1.75], incl	0.003 [0.08]	0.0035 [0.09]	0.0035 [0.09]
Over 0.069 [1.75] to 0.100 [2.54], incl	0.003 [0.08]	0.004 [0.10]	0.005 [0.13]
Over 0.100 [2.54] to 0.125 [2.98], incl	0.004 [0.10]	0.0045 [0.11]	0.005 [0.13]
Over 0.125 [2.98] to 0.161 [4.09], incl	0.0045 [0.11]	0.0045 [0.11]	0.005 [0.13]
Over 0.161 [4.09] to under 3/16 [4.76]	0.005 [0.13]	0.005 [0.13]	0.006 [0.15]

<sup>A</sup> Thickness tolerances given in in. [mm] unless otherwise indicated.

**TABLE A2.2 Permitted Variations in Width for Cold-Rolled, Narrow, Coil-Processed Product as Coils and Cut Lengths for Edge No. 3<sup>A</sup>**

Specified Thickness, in. [mm]	Width Tolerance, Over and Under, for Thickness and Width Given, in. [mm]					
	Under 1/2 [12.70] to 3/16 [4.76], incl	1/2 [12.70] to 6 [152.40], incl	Over 6 [152.40] to 9 [228.60], incl	Over 9 [228.60] to 12 [304.80], incl	Over 12 [304.80] to 20 [508.00], incl	Over 20 [508.00] to 24 [609.60], incl
0.068 [1.73] and under	0.005 [0.13]	0.005 [0.13]	0.005 [0.13]	0.010 [0.25]	0.016 [0.41]	0.020 [0.51]
Over 0.068 [1.73] to 0.099 [2.51], incl	0.008 [0.20]	0.008 [0.20]	0.010 [0.25]	0.010 [0.25]	0.016 [0.41]	0.020 [0.51]
0.100 [2.54] to 0.160 [4.06], incl	0.010 [0.25]	0.010 [0.25]	0.016 [0.41]	0.016 [0.41]	0.020 [0.51]	0.020 [0.51]
Over 0.160 [4.06] to 3/16 [4.76], excl	...	0.016 [0.41]	0.020 [0.51]	0.020 [0.51]	0.031 [0.79]	0.031 [0.79]

<sup>A</sup> For tolerances applicable to narrow product with Edge No. 1 or No. 5, see Table A2.21.

**TABLE A2.3 Permitted Variations in Length for Cold-Rolled, Narrow, Coil-Processed Product as Cut Lengths**

Specified Length, ft [mm]	Tolerance Over Specified Length (No Tolerance Under), in. [mm]
To 5 [1524], incl	3/8 [9.52]
Over 5 [1524] to 10 [3048], incl	1/2 [12.70]
Over 10 [3048] to 20 [6096], incl	5/8 [15.88]

**TABLE A2.4 Permitted Variations in Flatness of Cold-Rolled, Narrow, Coil-Processed Product as Cut Lengths**

Tolerances for variations of flatness cold-rolled products, narrow, coil-processed product as cut lengths shall be identical to the tolerances for cold-rolled, wide, coil-processed product as listed in A2.8 unless otherwise agreed upon by seller and purchaser and specified in the purchase order.

**TABLE A2.5 Permitted Variations in Thickness of Cold-Rolled, Wide, Coil-Processed Product as Coil and Cut Lengths**

Specified Thickness <sup>A</sup> , in. [mm]	Permitted Variations Over and Under <sup>B</sup>	
	in.	mm
Up to 0.005 [0.13]	0.001	0.03
Over 0.005 [0.13] to 0.007 [0.18], incl	0.0015	0.04
Over 0.007 [0.18] to 0.016 [0.41], incl	0.002	0.05
Over 0.016 [0.41] to 0.026 [0.66], incl	0.003	0.08
Over 0.026 [0.66] to 0.040 [1.02], incl	0.004	0.10
Over 0.040 [1.02] to 0.058 [1.47], incl	0.005	0.13
Over 0.058 [1.47] to 0.072 [1.83], incl	0.006	0.15
Over 0.072 [1.83] to 0.083 [2.11], incl	0.007	0.18
Over 0.083 [2.11] to 0.098 [2.49], incl	0.008	0.20
Over 0.098 [2.49] to 0.114 [2.90], incl	0.009	0.23
Over 0.114 [2.90] to 0.130 [3.30], incl	0.010	0.25
Over 0.130 [3.30] to 0.145 [3.68], incl	0.012	0.30
Over 0.145 [3.68] to < 0.1875 [4.76]	0.014	0.36

<sup>A</sup> Thickness measurements are taken at least 3/8 in. [9.52 mm] from the edge of the sheet.

<sup>B</sup> Cold-rolled sheets in cut lengths and coils are produced in some type numbers and some widths and thickness to tolerances less than those shown.