AMERICAN SOCIETY FOR TESTING AND MATERIALS 100 Barr Harbor Dr., West Conshohocken, PA 19428 Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Specification for Rolled Floor Plate, Stainless Steel¹

This standard is issued under the fixed designation A 793; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense. Consult the DoD Index of Specifications and Standards for the specific year of issue which has been adopted by the Department of Defense.

1. Scope


- 1.1 This specification covers stainless steel floor plates ½ in. and under for use in galley spaces, washrooms, engine rooms, and machinery spaces, and for ladder treads, gun platforms, and deck treads. For these uses, Patterns A, B, and C are considered interchangeable (see Figs. 1-3).
- 1.2 The values stated in inch-pound units are to be regarded as the standard.

2. Referenced Documents

- 2.1 ASTM Standards:
- A 340 Terminology of Symbols and Definitions Relating to Magnetic Testing²
- A 370 Test Methods and Definitions for Mechanical Testing of Steel Products³
- A 480/A480M Specification for General Requirements for Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip³
- A 700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Domestic Shipment⁴
- 2.2 *Military Standards:*
- MIL-I-17214 Indicator, Permeability; Low Mu (Go-No-Go)⁵
- MIL-STD-163 Preservation of Steel Products for Domestic Shipment (Storage and Overseas Shipment)⁵

3. Ordering Information

- 3.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Such requirements may include, but are not limited to, the following:
 - 3.1.1 Quantity—number of pieces,
- 3.1.2 Dimensions (thickness, width, and length, see Table 1),



Current edition approved Sept. 10, 1996. Published November 1996. Originally published as A 793 – 81. Last previous edition A 793 – $90e^{1}$.




FIG. 1 Pattern A (percent of reduction, 61 %)

- 3.1.3 Name of material (stainless steel floor plate),
- 3.1.4 Grade (see Table 2),
- 3.1.5 Flat back or hollow back (See Table 1),
- 3.1.6 Surface finish (see Specification A 480/A 480M),




FIG. 2 Pattern B (original of raised figures approximately 1¼ in., /percent of reduction 61 %)

² Annual Book of ASTM Standards, Vol 03.04.

³ Annual Book of ASTM Standards, Vol 01.03.

⁴ Annual Book of ASTM Standards, Vol 01.05.

⁵ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.




FIG. 3 Pattern C

TABLE 1 Dimensions, Weights, and Special Characteristics of Patterns A, B, and C

Thickness of Plate at	Thickness of Plate at	Hollov	v Back	Flat Back		
Base of Raised Figure (Nominal), in. (mm)	Base of Raised Figure, min, in. (mm)	Weight (Approximate), Ib/ft²(kg/m²) ^A	Height of Raised Figures, min, in. (mm)	Weight (Approximate),	Height of Raised Figures, min, in. (mm)	
0.025 (0.64)	0.015 (0.38)	1.10 (5.37)	0.025 (0.64)			
0.03125 (0.79)	0.02125 (0.54)	1.40 (6.84)	0.025 (0.64)			
0.0375 (0.95)	0.027 (0.69)	1.65 (5.69)	0.025 (0.64)			
0.05 (1.27)	0.039 (0.99)	2.30 (11.23)	0.035 (0.89)			
0.0625 (1.59)	0.051 (1.30)	2.90 (14.16)	0.035 (0.89)			
0.078 (1.98)	0.063 (1.60)	3.50 (17.09)	0.035 (0.89)			
0.09375 (2.38)	0.079 (2.01)	3.938 (19.23)	0.035 (0.89)	4.875 (23.80)	0.035 (0.89)	
0.109 (2.77)	0.096 (2.44)	4.59 (22.41)	0.030 (0.76)	5.50 (26.85)	0.045 (1.14)	
0.125 (3.18)	0.110 (2.79)	5.25 (25.64)	0.030 (0.76)	6.125 (23.90)	0.055 (1.40)	
0.140 (3.56)	0.126 (3.20)			6.75 (32.96)	0.055 (1.40)	
0.156 (3.96)	0.141 (3.58)			7.375 (36.01)	0.055 (1.40)	
0.172 (4.37)	0.157 (3.99)			8.000 (39.06)	0.055 (1.40)	
0.1875 (4.76)	0.173 (4.39)			8.625 (42.11)	0.060 (1.52)	
0.203 (5.16)	0.189 (4.80)			9.25 (45.16)	0.060 (1.52)	
0.218 (5.54)	0.204 (5.18)			9.875 (48.21)	0.060 (1.52)	
0.234 (5.94)	0.219 (5.56)			10.50 (51.27)	0.060 (1.52)	
0.250 (6.35)	0.235 (5.97)			11.125 (54.32)	0.060 (1.52)	

^A Approximate weights are shown for estimating convenience.

TABLE 2 Heat Chemical Composition, %

Туре	UNS Des- ignation	C, max	Mn, max	P, max	S, max	Si, max	N, max	Ni	Cr	Мо
304	S30400	0.08	2.00	0.045	0.030	0.75	0.10	8.00-10.50	18.00-20.00	
304L	S30403	0.030	2.00	0.045	0.030	0.75	0.10	8.00-12.00	18.00-20.00	
316	S31600	0.08	2.00	0.045	0.030	0.75	0.10	10.00-14.00	16.00-18.00	2.00-3.00
316L	S31603	0.030	2.00	0.045	0.030	0.75	0.10	10.00-14.00	16.00-18.00	2.00-3.00

- 3.1.7 Special requirements, such as magnetic permeability test (see 6.3),
 - 3.1.8 ASTM designation and date of issue,
- 3.1.9 Preparation for delivery, if different from Specification A 480/A 480M, and

 $3.1.10\,$ Marking requirements, if different from Specification A 480/A 480M.

Note 1-A typical ordering description is as follows: 100 pieces,