



SLOVENSKI STANDARD

SIST EN 2002-005:2009

01-september-2009

Aeronavtika - Preskusne metode za kovinske materiale - 005. del: Preskusi lezenja in loma pod stalno natezno obremenitvijo

Aerospace series - Test methods for metallic materials - Part 005: Uninterrupted creep and stress-rupture testing

Luft- und Raumfahrt - Prüfverfahren für metallische Werkstoffe - Teil 005: Kriech- und Zeitstandversuch unter konstanter Zugbeanspruchung

Série aérospatiale - Méthodes d'essais applicables aux matériaux métalliques - Partie 005 : Essai non interrompu de fluage et essai de rupture par fluage

<https://standards.iteh.ai/catalog/standards/sist/f5489dc6-09af-4948-b611-c4f7aa6bfc63/sist-en-2002-005-2009>

Ta slovenski standard je istoveten z: **EN 2002-005:2007**

ICS:

49.025.05	Železove zlitine na splošno	Ferrous alloys in general
49.025.15	Neželezove zlitine na splošno	Non-ferrous alloys in general

SIST EN 2002-005:2009

en,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 2002-005:2009

<https://standards.iteh.ai/catalog/standards/sist/f5489dc6-09af-4948-b611-c4f7aa6bfc63/sist-en-2002-005-2009>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 2002-005

November 2007

ICS 49.025.10

English Version

Aerospace series - Test methods for metallic materials - Part 005: Uninterrupted creep and stress-rupture testing

Série aérospatiale - Méthodes d'essais applicables aux
matériaux métalliques - Partie 005 : Essai non interrompu
de fluage et essai de rupture par fluage

Luft- und Raumfahrt - Prüfverfahren für metallische
Werkstoffe - Teil 005: Kriech- und Zeitstandversuch unter
konstanter Zugbeanspruchung

This European Standard was approved by CEN on 23 June 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 2002-005:2009](https://standards.iteh.ai/catalog/standards/sist/5489dc6-09af-4948-b611-c4f7aa6bfc63/sist-en-2002-005-2009)

<https://standards.iteh.ai/catalog/standards/sist/5489dc6-09af-4948-b611-c4f7aa6bfc63/sist-en-2002-005-2009>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Principle	4
4 Terms and definitions	4
5 Symbols and abbreviations	7
6 Specification of test requirements	9
7 Testing equipment	9
8 Proportional test pieces	11
9 Non-proportional test pieces	13
10 Preparation of test piece from sample	13
11 Measurement of cross-sectional area	14
12 Marking the original gauge length	14
13 Heating of test piece	14
14 Temperature control and observations	14
15 Loading of the test piece	14
16 Stress rupture test	15
17 Creep strain test – Determination of total plastic strain	15
18 Test report	16

STANDARD PREVIEW
(standards.itech.ai)

SIST EN 2002-005:2009

[https://standards.itech.ai/catalog/standards/sist/f5489dc6-09af-4948-b611-](https://standards.itech.ai/catalog/standards/sist/f5489dc6-09af-4948-b611-c47aa6bfc63/sist-en-2002-005-2009)

[c47aa6bfc63/sist-en-2002-005-2009](https://standards.itech.ai/catalog/standards/sist/f5489dc6-09af-4948-b611-c47aa6bfc63/sist-en-2002-005-2009)

Foreword

This document (EN 2002-005:2007) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2008, and conflicting national standards shall be withdrawn at the latest by May 2008.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 2002-005:2009

<https://standards.iteh.ai/catalog/standards/sist/f5489dc6-09af-4948-b611-c4f7aa6bfc63/sist-en-2002-005-2009>

EN 2002-005:2007 (E)**1 Scope**

This standard applies to uninterrupted constant-load tensile creep strain and stress-rupture testing of metallic materials governed by aerospace standards. It defines the properties that may need to be determined and the terms used in describing tests and test pieces. It specifies the dimensions of test pieces and the method of testing. The duration of the creep strain and stress-rupture tests complying with this standard shall be less than 10 000 h and at temperatures not exceeding 1 100 °C.

This standard may also apply to metallic materials for test durations exceeding 10 000 h and/or for test temperatures exceeding 1 100 °C providing that previous agreement has been reached between the manufacturer and the purchaser.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system (ISO 7500-1:2004)*

EN ISO 9513, *Metallic materials — Calibration of extensometers used in uniaxial testing (ISO 9513:1999)*

ASTM E 1012-91, *Practice for verification of specimen alignment under tensile loading.*¹⁾

3 Principle

The test consists in maintaining a test piece at a uniform temperature and subjecting it to a constant tensile force at that temperature in order to determine specified properties.

4 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

4.1**test piece**

portion of the test sample on which the creep strain or stress-rupture test is carried out (see Figures 1 to 5)

4.2**proportional test piece**

these test pieces have an original basis gauge length ($L_o = L_{e0}$, or L_s) which bears a specified relationship to the cross-sectional area

This ensures that comparable values for percentage elongation after rupture (A) are obtained from test pieces of different size but having the same relationship. The relationship $L_o = 5,65 \sqrt{S_o}$ which for test pieces of circular cross section gives a value of $L_o = 5 d_o$ has been accepted by international agreement and is preferred in the use of this standard. The relationship is indicated in the symbol for percentage elongation after rupture (A) as a subscript, e.g. A_5 representing the ratio L_o/d .

1) Published by American Society for Testing and Materials (ASTM), 1916 Race Street, Philadelphia, PA 19103.

4.3**non-proportional test piece**

in cases where the original basis gauge length has not the defined relationship to the cross-sectional area, a subscript shall be used with the symbol for elongation A to indicate the gauge length, i.e. $A_{40\text{ mm}}$

4.4**gauge length**

a length of the test piece on which elongation is measured at any moment during the test

4.5**measurement gauge length (L_m)**

the measurement gauge length shall be defined as either the extensometer gauge length L_{eo} for test pieces measured with extensometers gripping the parallel portion of the specimen or small annular ridges, when these are used, or the shoulder gauge length L_s for test pieces where extension is measured between points including the transition radii and/or gripping portions of the test piece

The measurement gauge length (L_m) is to be used only for the numerator in elongation calculations; that is, the change in length of that part of the test piece defined as L_m , whereas the basis gauge length, i.e. L_{eo} or L_s , is to be used for the denominator.

4.6**extensometer gauge length (L_{eo})**

where an extensometer is attached directly to the parallel portion of the unloaded test piece, the extensometer gauge length (L_{eo}) is equal to the distance between the points of contact of the extensometer measured at room temperature, and shall also be used as the corresponding basis gauge length

Alternatively, the extensometer may be attached to annular ridges on the parallel portion. In these cases, the basis gauge length to be used as the denominator in the elongation calculations shall be the equivalent gauge length, calculated as shown (see 4.7).

4.7**basis gauge length for elongation calculations (L_{eo} or L_s)**

the equivalent gauge length, i.e. the parallel length which would give the same extension, including all loaded portions of the test piece between the measuring points, except the gripped ends

It shall be used as the denominator in all elongation calculations. For stress-rupture test pieces, it is recommended that L_{eo} or L_s be calculated from the following equation:

$$L_{eo} \text{ or } L_s = L_c + 2 \sum_{i=1}^k [(d_o/d_i)^{2n} \times L_i] = 5,65 \sqrt{S_o}$$

where:

L_c is the parallel length between the annular ridges or test piece ends, with a diameter d_o , k is the number of sections of length L_i with increasing diameter of d_i at the two transition radii. The correct L_c shall be selected, so that the effective gauge length equals $5,65 \sqrt{S_o}$. It is recommended to use $n = 6$ as a basis for comparison, although the actual n for many aerospace materials is > 6 . This is based on the "power law" creep relationship:

$$\dot{\epsilon}_p = \left(\frac{\sigma}{K} \right)^n$$

4.8**shoulder gauge length (L_s)**

where the extension is measured at the test piece ends, or between reference marks on the enlarged ends of the test piece, the shoulder gauge length (L_s) shall be denoted

The basis gauge length shall be calculated as in 4.7 and based on room temperature measurements, including all loaded portions of the test piece between the measuring points, except the gripped ends.

EN 2002-005:2007 (E)

4.9

parallel length (L_c)

the length of the parallel portion of the test piece

For some test pieces, L_c will be less than L_m , the applicable original gauge length.

4.10

extension (ΔL_e)

the increase of the extensometer gauge length from the initial length, L_{eo} or $L_{eo'}$, indicated at the test temperature before loading, to a value L_e at a given moment during the test.

4.11

final measurement length after rupture (L_u)

the measure of the applicable gauge length (L_{eu} or L_{su}) after the test piece has ruptured, measured at room temperature

This may include the unstressed test piece ends, if the total length is used as the gauge length.

4.12

percentage elongation after rupture (A)

the permanent increase in length ($L_u - L_m$) of the applicable measurement gauge length, expressed as a percentage of the original applicable basis gauge length ($L_{eo'}$ or L_s), for example:

$$A = \frac{L_u - L_{eo'}}{L_{eo'}} \times 100, \text{ all measurements being made at room temperature}$$

iTeh STANDARD PREVIEW
(standards.iteh.ai)

4.13

percentage extension during testing (A_f)

the increase of the applicable gauge length, at a given time under full load, expressed as a percentage of the original applicable gauge length

The initial plastic strain during loading shall not be included in A_f , just the elongation after attainment of full load (see Figure 6).

4.14

percentage total plastic strain (A_p)

the total plastic extension of the original applicable measurement gauge length (L_{eo} or L_s) inclusive of any plastic extensions during loading (i.e. the total extension excluding elastic extensions), expressed as a percentage of the original applicable basis gauge length (see Figures 6 and 7)

4.15

original section (S_o)

the cross-sectional area of the gauge length of the test piece, determined before testing

4.16

final section (S_u)

the minimum cross-sectional area of the test piece, after rupture

4.17

percentage reduction of area after rupture (Z)

the maximum decrease of the cross-sectional area ($S_o - S_u$) expressed as a percentage of the original cross-sectional area (S_o), i.e. $Z = \frac{S_o - S_u}{S_o} \times 100$

4.18**stress (σ)**

the force on the test piece divided by the original cross-sectional area of the parallel portion

It should be noted that the thermal expansion of the test piece during heating increases the effective cross-sectional area. The effective stress is therefore slightly less than σ , which is based on room temperature.

4.19**rupture**

complete fracture of the test piece within the original gauge length under constant force and at constant temperature

4.20**time to rupture (t_r)**

the total time, at the test temperature and the test force, to the rupture of the test piece (see Figure 7)

4.21**time to specified total plastic strain (t_p)**

the total time, at the test temperature and including the portion of the loading time after the loading curve deviates from an extension of the linear-elastic modulus line, until the specified total plastic strain (A_p) is reached (see Figure 6)

4.22**theoretical stress concentration factor (K_t)**

the ratio of the greatest in the region of a notch as determined by the theory of elasticity to the corresponding nominal stress

$$K_t = \frac{\sigma_{\text{peak}}}{\sigma_{\text{nom.}}}$$

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 2002-005:2009](https://standards.iteh.ai/catalog/standards/sist/f5489dc6-09af-4948-b611-c4f7aa6bfc63/sist-en-2002-005-2009)

where

<https://standards.iteh.ai/catalog/standards/sist/f5489dc6-09af-4948-b611-c4f7aa6bfc63/sist-en-2002-005-2009>

K_t is the theoretical stress concentration factor;

σ_{peak} is the peak stress by notch;

$\sigma_{\text{nom.}}$ is the nominal stress.

5 Symbols and abbreviations

See Table 1 and Figures 1 to 5.

Table 1

Symbol	Unit	Designation
a	mm	Thickness of test section of test piece of rectangular cross-section
A	%	Percentage elongation after rupture
A_f	%	Percentage strain during testing
A_p	%	Percentage total plastic strain
α	°	Notch angle
b	mm	Width of test section of test piece of rectangular cross-section
d	mm	Diameter of test section of test piece of circular cross-section
d_n	mm	Diameter of test piece at root of notch
D_n	mm	Diameter of the parallel portion of a notched test piece of circular cross-section
K_t	–	Theoretical stress concentration factor of a notched test piece
L_c	mm	Parallel length
L_e	mm	Extensometer gauge length (L_{eo} = initial ; L_{eu} = final)
L_o, L_{eo} , or L_s	mm	Basis gauge length for elongation calculations
ΔL_e	mm	Extension of extensometer gauge length
L_m	mm	Measurement gauge length
L_n	mm	Parallel length of the test piece containing the notch
L_s	mm	Shoulder gauge length for test without extensometer on the parallel length (L_{so} = initial; L_{su} = final)
L_t	mm	Total length of the test piece
L_u	mm	Final measurement length after rupture
r	mm	Transition radius
r_n	mm	Notch root radius
δ	MPa	Stress, based on room temperature cross-sectional area
S_o	mm ²	Original room temperature cross-sectional area of test section
S_u	mm ²	Minimum cross-sectional area of test section after rupture
t	h	Time of the test under specified conditions for temperature and stress
t_p	h	Time to specified total plastic strain
t_r	h	Time to rupture
θ_T	°C	Test temperature
Z	%	Percentage reduction of area after rupture

6 Specification of test requirements

The material standard shall state the following:

- type of test piece (see Clauses 8 and 9);
- specified test temperature (θ_T);
- specified test stress (σ);
- time the test piece shall be simultaneously under the specified conditions of temperature and stress (t);
- maximum soaking time where applicable (see Clause 13);
- criterion of acceptance which may be one of the following:
 - a) a statement of the percentage total plastic strain (A_p) or percentage total strain (A_f) that shall not be exceeded;
 - b) a requirement that the test piece shall not rupture before the end of the test time specified above;
 - c) any other requirement specified, such as minimum percent elongation at fracture.

7 Testing equipment

7.1 Load calibration

The testing machine shall be calibrated at intervals not exceeding one year in accordance with EN ISO 7500-1 and shall be at grade 1,0 or better. The machine should be equipped with a device which minimizes shock when the test piece ruptures (only with more than 1 test device).

7.2 Strain calibration

The instruments used for the measurements of creep strain shall have an accuracy within 0,006 % of the gauge length or 1 % of the total creep strain to be measured, whichever is the greater. They shall be calibrated at intervals not exceeding one year in accordance with EN ISO 9513, class 0.5. Calibration should be checked at more frequent. More frequent spot checks are recommended.

7.3 Calibration for long-term tests

Where long-term tests are carried out in excess of one year the testing machine and extensometer shall be calibrated immediately before and on the completion of such tests.

7.4 Extensometer requirements

If an extensometer is used, it shall be capable of measuring the extension on opposite sides of the test piece, and the readings shall be averaged. An extensometer that measures the extension on each side and gives only the average reading, or measures only one length may be used by agreement between the manufacturer and the purchaser of the material being tested. Any parts of the extensometer projecting beyond the furnace shall be so designed or protected that short period changes of temperature or draughts do not affect readings. It is advisable to maintain reasonable stability of the temperature of the air surrounding the testing machine. A temperature-compensated extensometer is recommended.

7.5 Machine alignment

Test pieces shall be held by a positive means, in such a way that the load can be applied as axially as possible. If bending is not measured as in 17a), then the machine grips shall be checked on at least an annual basis with a strain-gauged test piece at room temperature. The difference between strains on any two opposing sides of the test piece shall not be more than 10 % of the mean strain, at the lowest force used on the machine during tests. The ASTM E 1012 may be referred to for a verification method.