

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Optical fibres – **STANDARD PREVIEW**
Part 2-60: Product specifications – Sectional specification for category C single-
mode intraconnection fibres (standards.iteh.ai)

Fibres optiques – [IEC 60793-2-60:2008](https://standards.iteh.ai/catalog/standards/sist/245ec743-0c3c-4f80-85d3-466770d9ce-06)
Partie 2-60: Spécifications de produits – Spécification intermédiaire pour fibres
unimodales d'intraconnexion de catégorie C



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2008 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

Useful links:

IEC publications search - www.iec.ch/searchpub

The advanced search enables you to find IEC publications by a variety of criteria (reference number, text, technical committee,...).

It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available on-line and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary (IEV) on-line.

Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Liens utiles:

Recherche de publications CEI - www.iec.ch/searchpub

La recherche avancée vous permet de trouver des publications CEI en utilisant différents critères (numéro de référence, texte, comité d'études,...).

Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

Just Published CEI - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications de la CEI. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 30 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (VEI) en ligne.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: csc@iec.ch.



IEC 60793-2-60

Edition 1.0 2008-02

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Optical fibres – **iTeh STANDARD PREVIEW**
Part 2-60: Product specifications – Sectional specification for category C single-
mode intraconnection fibres (standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/245ec743-0c3c-4f80-85d3-4668708231ec-60793-2-60>
Fibres optiques – IEC 60793-2-60:2008
Partie 2-60: Spécifications de produits – Spécification intermédiaire pour fibres
unimodales d'intraconnexion de catégorie C

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

T

ICS 33.180.10

ISBN 978-2-83220-353-8

Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

CONTENTS

FOREWORD.....	4
1 Scope.....	6
2 Normative references	7
3 Terms, definitions, symbols and abbreviations.....	8
3.1 Terms and definitions	8
3.2 Symbols and abbreviations.....	8
4 Specifications.....	8
4.1 Dimensional requirements	8
4.2 Mechanical requirements.....	9
4.3 Transmission requirements	9
4.4 Environmental requirements.....	10
4.4.1 Transmission requirements.....	11
4.4.2 Mechanical requirements.....	11
Annex A (normative) Family specification for C1 single-mode fibre	13
Annex B (normative) Family specification for C2 single-mode fibre	16
Annex C (normative) Family specification for C3 single-mode fibre	19
Annex D (normative) Family specification for C4 single-mode fibre	21
Bibliography.....	23
Table 1 – List of families and main differences.....	6
Table 2 – Dimensional attributes and measurement methods.....	8
Table 3 – Requirements common to class C fibres.....	9
Table 4 – Mechanical attributes and measurement methods	9
Table 5 – Mechanical requirements common to class C fibres	9
Table 6 – Transmission attributes and measurement methods	10
Table 7 – Transmission requirements common to class C fibres	10
Table 8 – Transmission attributes required in family specifications	10
Table 9 – Environmental attributes and test methods	10
Table 10 – Environment dependant mechanical or transmission attributes and test methods.....	11
Table 11 – Tensile strength requirements common to class C fibres	11
Table 12 – Stress corrosion susceptibility requirements common to class C fibres	12
Table A.1 – Dimensional requirements for C1 fibres.....	13
Table A.2 – Mechanical requirements for C1 fibres	13
Table A.3 – Transmission requirements for C1 fibres	14
Table A.4 – Environment dependant transmission requirements for C1 fibres	14
Table A.5 – Environment dependant mechanical requirements for C1 fibres	15
Table B.1 – Dimensional requirements for C2 fibres.....	16
Table B.2 – Mechanical requirements for C2 fibres	16
Table B.3 – Transmission requirements for C2 fibres	17

Table B.4 – Environment dependant transmission requirements for C2 fibres	17
Table B.5 – Environment dependant mechanical requirements for C2 fibres	18
Table C.1 – Dimensional requirements for C3 fibres	19
Table C.2 – Mechanical requirements for C3 fibres	19
Table C.3 – Transmission requirements for C3 fibres	20
Table C.4 – Environment dependant transmission requirements for C3 fibres	20
Table C.5 – Environment dependant mechanical requirements for C3 fibres	20
Table D.1 – Dimensional requirements for C4 fibres	21
Table D.2 – Mechanical requirements for C4 fibres	21
Table D.3 – Transmission requirements for C4 fibres	22
Table D.4 – Environment dependant transmission requirements for C4 fibres	22

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[IEC 60793-2-60:2008](https://standards.iteh.ai/catalog/standards/sist/245ec743-0c3c-4f80-85d3-4e5688598034/iec-60793-2-60-2008)

<https://standards.iteh.ai/catalog/standards/sist/245ec743-0c3c-4f80-85d3-4e5688598034/iec-60793-2-60-2008>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRES –

**Part 2-60: Product specifications –
Sectional specification for category C
single-mode intraconnection fibres**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60793-2-60 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This bilingual version (2012-09) corresponds to the monolingual English version, published in 2008-02. The text of this standard is based on the following documents:

CDV	Report on voting
86A/1160A/CDV	86A/1201/RVC

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

The French version of this standard has not been voted upon.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 60793 series can be found, under the general title *Optical Fibres*, on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition; or
- amended.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[IEC 60793-2-60:2008](#)

<https://standards.iteh.ai/catalog/standards/sist/245ec743-0c3c-4f80-85d3-4e5688598034/iec-60793-2-60-2008>

OPTICAL FIBRES –

Part 2-60: Product specifications – Sectional specification for category C single-mode intraconnection fibres

1 Scope

This part of IEC 60793 is applicable to optical fibre types C1, C2, C3, C4, as described in Table 1. These fibres are used for the intraconnections within or between components or photonic systems or subsystems. While the fibres are sold in lengths on the scale of kilometres, they are normally cut into short lengths for use in these intraconnections. While the fibres could be overcoated or buffered for the purpose of making protected pigtails, they may be used without overcoating. They may, however, be colour-coded.

The general requirements defined in IEC 60793-2 apply to these fibres. Specific requirements that are common to these fibres are found in the body of this text. Particular requirements for individual fibre types or applications are defined in Annexes A, B, C and D, which refer to normative family specifications. These family specifications are distinguished based on optimum transmission wavelengths and nominal Mode Field Diameter (MFD), which affects splice loss.

For each family specification, there are two sub-categories that are distinguished on the basis of the cladding diameter and other related attributes. The conventional nominal cladding diameter of 125 μm is augmented with the reduced cladding type product with a nominal diameter of 80 μm . These are distinguished with the suffixes: "125" or "80". For example C1 fibre can be selected as either C1_125 or C1_80. The transmission characteristics of the two cladding diameter choices should be the same.

For each family specification except C1, there are two sub-categories that are distinguished on the basis of transmission characteristics that relate to MFD. To denote these sub-categories, a "_a" or "_b" suffix is added, for lower or higher MFD. In general, the fibres can be optimised for either splice loss or macro-bend loss using MFD as a main variable. A C2 fibre with 80 μm cladding diameter and lower MFD is designated as C2_80_a.

Fibres for the C1_125 family specification can be selected from category B1.1 or B1.3 single-mode fibres and are suitable for use with any category B single-mode fibre at wavelengths from 1 280 nm to 1 625 nm. Fibres for the C2 and C3 family specifications are optimized at nominal wavelengths of 1 310 nm and 1 550 nm respectively for connection to any category B single-mode fibre. Fibres for the C4 family specification are optimized for transporting optical amplifier pump light at 980 nm or higher.

Table 1 – List of families and main differences

Families	Nominal transmission wavelengths nm	Nominal MFDs
C1	1 260, 1 550 and 1 625	8,6 – 9,5 μm at 1 310 nm
C2	1 310	5,0 – 7,0 μm at 1 310 nm
C3	1 550 and 1 625	5,5 – 7,5 μm at 1 550 nm
C4	980	4,0 – 7,0 μm at 980 nm

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60793-1-20, *Optical fibres – Part 1-20: Measurement methods and test procedures – Fibre geometry*

IEC 60793-1-21, *Optical fibres – Part 1-21: Measurement methods and test procedures – Coating geometry*

IEC 60793-1-22, *Optical fibres – Part 1-22: Measurement methods and test procedures – Length measurement*

IEC 60793-1-30, *Optical fibres – Part 1-30: Measurement methods and test procedures – Fibre proof test*

IEC 60793-1-31, *Optical fibres – Part 1-31: Measurement methods and test procedures – Tensile strength*

IEC 60793-1-32, *Optical fibres – Part 1-32: Measurement methods and test procedures – Coating strippability*

IEC 60793-1-33, *Optical fibres – Part 1-33: Measurement methods and test procedures – Stress corrosion susceptibility*

IEC 60793-1-40, *Optical fibres – Part 1-40: Measurement methods and test procedures – Attenuation*

IEC 60793-1-44, *Optical fibres – Part 1-44: Measurement methods and test procedures – Cut-off wavelength*

IEC 60793-1-45, *Optical fibres – Part 1-45: Measurement methods and test procedures – Mode field diameter*

IEC 60793-1-46, *Optical fibres – Part 1-46: Measurement methods and test procedures – Monitoring of changes in optical transmittance*

IEC 60793-1-47, *Optical fibres – Part 1-47: Measurement methods and test procedures – Macrobending loss*

IEC 60793-1-50, *Optical fibres – Part 1-50: Measurement methods and test procedures – Damp heat (steady state)*

IEC 60793-1-51, *Optical fibres – Part 1-51: Measurement methods and test procedures – Dry heat*

IEC 60793-1-52, *Optical fibres – Part 1-52: Measurement methods and test procedures – Change of temperature*

IEC 60793-2, *Optical fibres – Part 2: Product specifications – General*

IEC/TR 61931, *Fibre optic – Terminology*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

IEC 60793-2-60:2008
<https://standards.iteh.ai/catalog/standards/sist/245ec743-0c3c-4f80-85d3-4e5688598034/iec-60793-2-60-2008>

3 Terms, definitions, symbols and abbreviations

3.1 Terms and definitions

For the purposes of this document, the terms and definitions related to testing given in IEC 61931, as well as the terms and definitions related to fibres given in IEC 60793-2, apply. Moreover, the definitions of the specified attributes are contained in the test methods.

3.2 Symbols and abbreviations

The following symbols and abbreviations are used in this document:

F_{avg}	average strip force
F_{peak}	peak strip force
MFD	Mode Field Diameter
n_d	stress corrosion parameter – dynamic

4 Specifications

The fibre shall consist of a glass core, glass cladding, and coating in accordance with 5.1 of IEC 60793-2.

4.1 Dimensional requirements

Dimensional attributes and measurement methods that may be specified are given in Table 2. Minimum requirements, common to all fibres in this category, are given in Table 3. Some family specification requirements may be more strict.

Table 2 – Dimensional attributes and measurement methods

Attributes	Tests
Cladding diameter	IEC 60793-1-20
Cladding non-circularity	IEC 60793-1-20
Core concentricity error	IEC 60793-1-20
Coating diameter	IEC 60793-1-21
Coating non-circularity	IEC 60793-1-21
Cladding-coating concentricity error	IEC 60793-1-21
Fibre length	IEC 60793-1-22

Table 3 – Requirements common to class C fibres

Attributes	Units	_125 Limits	_80 Limits
Cladding diameter ^a	µm	125 ± 1,0	80 ± 1,0
Cladding non-circularity	%	≤ 1,0	≤ 1,0
Core concentricity error	µm	≤ 0,5	≤ 0,5
Coating diameter – uncoloured ^a	µm	235 to 255	155 to 175
Fibre length	km	^b	^b
^a Tolerance applies to the entire length of fibre.			
^b Length requirements vary and should be agreed between customer and supplier.			

4.2 Mechanical requirements

Mechanical attributes and measurement methods that may be specified are given in Table 4. Minimum mechanical requirements, common to all fibres in class C, are given in Table 5. Some family specification values may be more strict.

Table 4 – Mechanical attributes and measurement methods

Attributes	Tests
Proof test	IEC 60793-1-30
Tensile strength	IEC 60793-1-31
Coating strippability	IEC 60793-1-32
Stress corrosion susceptibility	IEC 60793-1-33

<https://standards.itec.ai/catalog/standards/sist/245ec743-0c3e-4f80-85d3-4e5688598034/iec-60793-2-60-2008>

Table 5 – Mechanical requirements common to class C fibres

Attributes	Units	Limits
Proof stress level	GPa	≥ 0,69
Coating strip force		The coating shall be mechanically strippable. Heat stripping may be most appropriate for some coatings
Tensile strength (median) for 0,5 m specimen length	GPa	≥ 3,8

4.3 Transmission requirements

Transmission attributes and measurement methods that may be specified are given in Table 6. Some family specifications may have additional attributes or test methods. Minimum requirements, common to all class C fibres, are given in Table 7. Some family specifications may be more stringent. Requirements that shall be specified in the family specifications are listed in Table 8.

Table 6 – Transmission attributes and measurement methods

Attributes	Tests
Attenuation coefficient	IEC 60793-1-40 ^a
Fibre cut-off wavelength	IEC 60793-1-44
Mode field diameter	IEC 60793-1-45
Macro-bending loss	IEC 60793-1-47
^a The attenuation coefficient at various wavelengths can be calculated using the measured values at a few wavelengths using a spectral model such as the one given in IEC 60793-1-40. For example, the attenuation at 1 480 nm can be calculated and used for design of systems that employ remote pumping of optical amplifiers.	

Table 7 – Transmission requirements common to class C fibres

Attributes	Units	Limits
This table is empty, but retained in case of some common minimum requirement		

Table 8 – Transmission attributes required in family specifications

Attributes required in family specifications
Maximum attenuation coefficient and wavelength
Nominal mode field diameter, tolerance, and wavelength
Macro-bending loss increase, wavelength, bend radius, and number of turns
Fibre cut-off wavelength
NOTE Fibre cut-off wavelength is the default, but alternative configurations may be agreed for some applications such as fibre being used on a bobbin. In these cases, the measured cut-off wavelength values can be generally mapped to the bend/length conditions for the alternative applications.

4.4 Environmental requirements

Environmental attributes tests and measurement methods are documented in two forms:

- various environmental exposure tests are given in Table 9;
- mechanical or transmission attributes that may change when subjected to environmental exposure are listed in Table 10.

Table 9 – Environmental attributes and test methods

Environmental exposures	Tests
Damp heat tests	IEC 60793-1-50
Dry heat tests	IEC 60793-1-51
Change of temperature tests	IEC 60793-1-52

Table 10 – Environment dependant mechanical or transmission attributes and test methods

Attributes	Test methods
Change in optical transmission	IEC 60793-1-46
Attenuation	IEC 60793-1-40
Coating strip force	IEC 60793-1-32
Tensile strength	IEC 60793-1-31
Stress corrosion sensitivity	IEC 60793-1-33

These tests are normally conducted periodically as type-tests for a fibre and coating design. Unless otherwise specified, the recovery period allowed between completing the environmental exposure and performing the attribute measurements shall be as stated in the particular environmental conditioning test standard.

4.4.1 Transmission requirements

Change in attenuation from the initial value shall be less than the values specified in the relevant family specification.

4.4.2 Mechanical requirements

These tests are, in practice, the most severe requirements amongst the environment exposures defined in Table 9.

4.4.2.1 Coating strip force (standards.iteh.ai)

In addition to the un-aged strip force requirements in 4.2, coating strip force after damp heat ageing shall be specified in the family specifications. The ageing options are also specified.

4.4.2.2 Tensile strength

The attributes given in Table 11 shall be verified following removal of the fibre from the environment.

Table 11 – Tensile strength requirements common to class C fibres

Environment	Median tensile strength (GPa), specimen length: 0,5 m	15 % of the tensile strength distribution (GPa), specimen length: 0,5 m
Damp heat	≥ 3,03	≥ 2,76
NOTE These requirements do not apply to hermetically coated fibre or to fibre that is intended for sole use within hermetically sealed enclosure.		

4.4.2.3 Stress corrosion susceptibility

The attributes given in Table 12 shall be verified following removal of the fibre from the environment.

**Table 12 – Stress corrosion susceptibility requirements
common to class C fibres**

Environment	Stress corrosion Susceptibility constant, n_d
Damp heat	≥ 18
NOTE This requirement does not apply to hermetically coated fibre or to fibre that is intended for sole use within hermetically sealed enclosures.	

iTeh STANDARD PREVIEW
(standards.iteh.ai)

IEC 60793-2-60:2008

<https://standards.iteh.ai/catalog/standards/sist/245ec743-0c3c-4f80-85d3-4e5688598034/iec-60793-2-60-2008>

Annex A (normative)

Family specification for C1 single-mode fibre

A.1 Introduction

The C1 single-mode fibre is a single-mode intraconnection fibre that is suitable for use with any category B single-mode fibre at wavelengths from 1 280 nm to 1 625 nm. It is optimised for precision glass geometry and improved macro-bending, and generally having lower fibre cut-off wavelength compared to that of B1.1 fibres.

The following clauses and tables contain the requirements for C1 fibres. Common requirements, copied for ease of reference from the sectional specification, are noted by an entry in the "Ref." column. Relevant notes from the sectional specification are not repeated, but indicated with a superscript^{SS}.

A.2 Dimensional requirements

Table A.1 contains dimensional requirements for C1 fibres.

Table A.1 – Dimensional requirements for C1 fibres

Attributes	Units	_125 Limits	_80 Limits	Ref.
Cladding diameter	µm	125,0 ± 0,7	80 ± 1,0	
Cladding non-circularity	%	≤ 0,7	≤ 1,0	
Core concentricity error	µm	≤ 0,5	≤ 0,5	
Coating diameter – uncoloured	µm	235 to 255	155 to 175	4.1
Fibre length	km	(See 4.1)	(See 4.1)	4.1

A.3 Mechanical requirements

Table A.2 contains mechanical requirements for C1 fibres.

Table A.2 – Mechanical requirements for C1 fibres

Attributes	Units	_125 Limits	_80 Limits	Ref.
Proof stress level	Gpa	≥ 0,69	≥ 0,69	4.2
Coating strip force (average)	N	$1,0 \leq F_{\text{avg}} \leq 5,0$	$1,0 \leq F_{\text{avg}} \leq 5,0$	
Coating strip force (peak)	N	$F_{\text{peak}} \leq 8,9$	$F_{\text{peak}} \leq 8,9$	
Tensile strength (median) for 0,5 m specimen length	GPa	≥ 3,8	≥ 3,8	4.2