



SLOVENSKI STANDARD
SIST EN 2003-009:2009

01-maj-2009

5 YfcbUj h_U!`DfYg_i gbY'a YrcXY!'H]HUb`]b`h]Hbcj Y'n`]hbY!`\$\$- "XY.`8 c`c Ub`Y`
_cbHLa]bUW`Y`dcj fy]b

Aerospace series - Test methods - Titanium and titanium alloys - Part 009: Determination of surface contamination

Luft- und Raumfahrt - Prüfverfahren - Titan und Titanlegierungen - Teil 009: Bestimmung der Oberflächenverunreinigung

Série aérospatiale - Méthodes d'essais - Titane et alliages de titane - Partie 009 : Détermination de la contamination de surface

ITIH STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/c9f4fd38-9edd-4b2f-bf8a-d1119cb8f55c/sist-en-2003-009-2009>

Ta slovenski standard je istoveten z: EN 2003-009:2007

ICS:

49.025.30 Titan Titanium

SIST EN 2003-009:2009 en,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 2003-009:2009

<https://standards.iteh.ai/catalog/standards/sist/c9f4fd38-9edd-4b2f-bf8a-d1119cb8f55c/sist-en-2003-009-2009>

EUROPEAN STANDARD

EN 2003-009

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2007

ICS 49.025.30

English Version

Aerospace series - Test methods - Titanium and titanium alloys - Part 009: Determination of surface contamination

Série aérospatiale - Méthodes d'essais - Titane et alliages
de titane - Partie 009 : Détermination de la contamination
de surface

Luft- und Raumfahrt - Prüfverfahren - Titan und
Titanlegierungen - Teil 009: Bestimmung der
Oberflächenverunreinigung

This European Standard was approved by CEN on 5 October 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 2003-009:2009](https://standards.iteh.ai/catalog/standards/sist/c9f4fd38-9edd-4b2f-bf8a-d1119cb8f55c/sist-en-2003-009-2009)

<https://standards.iteh.ai/catalog/standards/sist/c9f4fd38-9edd-4b2f-bf8a-d1119cb8f55c/sist-en-2003-009-2009>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

| Contents | | Page |
|---|---|------|
| Foreword..... | | 3 |
| Introduction | | 4 |
| 1 | Scope | 4 |
| 2 | Normative references | 4 |
| 3 | Terms and definitions | 4 |
| 4 | Principle | 4 |
| 5 | Micrographic examination (Method A) | 5 |
| 6 | Hardness testing (Method B)..... | 5 |
| 7 | Test report | 6 |
| Annex A (informative) Examples of contamination | | 7 |

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 2003-009:2009

<https://standards.iteh.ai/catalog/standards/sist/c9f4fd38-9edd-4b2f-bf8a-d1119cb8f55c/sist-en-2003-009-2009>

Foreword

This document (EN 2003-009:2007) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2007, and conflicting national standards shall be withdrawn at the latest by September 2007.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 2003-009:2009

<https://standards.iteh.ai/catalog/standards/sist/c9f4fd38-9edd-4b2f-bf8a-d1119cb8f55c/sist-en-2003-009-2009>

Introduction

Contamination caused by an α -stabilizer occurs in an environment containing oxygen, nitrogen or carbon when the product surface reaches a temperature which allows these elements to diffuse into the product surface. It leads to the formation of an α -stabilized surface which is hard and brittle, seldom exceeding 0,2 mm and is detrimental to the product.

1 Scope

This standard specifies two methods of determining surface contamination caused by an α -stabilizer on titanium and titanium alloys, for aerospace applications.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2002-7, *Aerospace series — Metallic materials — Test methods — Part 7: Hardness test.* ¹⁾

EN 3114-001, *Aerospace series — Test method — Microstructure of ($\alpha + \beta$) titanium alloy wrought products — Part 001: General requirements.*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 3114-001 apply.

4 Principle

Determination of surface contamination is carried out by:

- micrographic examination (Method A);
- or
- hardness testing (Method B).

1) Published as ASD Prestandard at the date of publication of this standard.

5 Micrographic examination (Method A)

5.1 Sampling

Unless otherwise specified the product shall be sampled in the delivery condition, such that the product surface can be examined at its transverse section.

The location of the sample shall be at the discretion of the manufacturer, unless otherwise specified.

The sampling procedure shall not result in any heating which may lead to a contamination of the test sample.

5.2 Procedure

5.2.1 Preparation of the micro-section

The micro-section selected from the test sample shall be prepared by mechanical polishing. The method of preparation shall not cause any damage to the microstructure. It shall lead to sharp edges.

The micro-section shall be etched, using an appropriate solution e.g.:

— 2 % to 5 % HF (hydrofluoric acid);

— 40 % to 50 % 2-Propanol (isopropylalcohol);

— water.

or

— 2 % to 5 % HF (hydrofluoric acid); [SIST EN 2003-009:2009](https://standards.iteh.ai/catalog/standards/sist/c9f4fd38-9edd-4b2f-bf8a-119cb8f55c/sist-en-2003-009-2009)

— 10 % to 20 % HNO₃ (nitric acid); <https://standards.iteh.ai/catalog/standards/sist/c9f4fd38-9edd-4b2f-bf8a-119cb8f55c/sist-en-2003-009-2009>

— water.

5.2.2 Micro-examination

Optical micro-examination shall be carried out with a magnification of 100 times to 500 times.

5.3 Expression of results

Report any appearance of a white layer or an area with a high density of light colour α -phase (see annex), indicating the presence of surface contamination.

6 Hardness testing (Method B)

6.1 Sampling

See 5.1.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

EN 2003-009:2007 (E)**6.2 Procedure****6.2.1 Preparation of the specimen**

The section to be inspected shall be prepared by mechanical polishing. This preparation shall not cause any alteration. It shall lead to sharp edges.

6.2.2 Tests

Unless otherwise specified, Vickers hardness measurements shall be carried out under a load of 0,200 kg according to EN 2002-7 at the following locations:

- at least, three points at a distance $\leq 0,1$ mm from the section surface;
- at least, three points at about mid-thickness of the section.

The average value of these measurements shall be calculated for each location.

6.3 Expression of results

Report the difference between the two average values. A difference between these values > 50 HV_{0,2}, indicates surface contamination.

7 Test report

iTeh STANDARD PREVIEW
(standards.iteh.ai)

The test report shall refer to this standard and shall include:

- complete identification of the tested product, including the manufacturer's name, designation and batch number;
SIST EN 2003-009:2009
<https://standards.iteh.ai/catalog/standards/sist/c9f4fd38-9edd-4b2f-bf8a-d1119cb8f55c/sist-en-2003-009-2009>
- method used : micrographic examination (Method A) or hardness testing (Method B);
- location of test sample;
- method of test sample preparation;
- all relevant test sample dimensions;
- date of test and traceability to individuals performing the test work;
- equipment used;
- for micrographic examination (Method A) the etchant used;
- for hardness test (Method B), recorded individual and average hardnesses for the two test locations and the difference between the two averages;
- test results;
- any factor which may have affected the results and any deviation from the test method.