
International Standard



8490

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Metallic materials — Sheet and strip — Modified Erichsen cupping test

Matériaux métalliques — Tôles et bandes — Essai d'emboutissage Erichsen modifié

First edition — 1986-10-01

iteh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 8490:1986](#)

<https://standards.iteh.ai/catalog/standards/sist/1a681fca-54f4-41c4-bc1a-4f606a10708e/iso-8490-1986>

UDC 669-41 : 620.176.5

Ref. No. ISO 8490-1986 (E)

Descriptors : metals, sheet metal, strips, tests, Erichsen cupping tests.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 8490 was prepared by Technical Committee ISO/TC 164, *Mechanical testing of metals*.

It cancels and replaces ISO Recommendation R 149-1960, of which it constitutes a technical revision.

Users should note that all International Standards undergo revision from time to time and that any reference made herein to any other International Standard implies its latest edition, unless otherwise stated.

Metallic materials — Sheet and strip — Modified Erichsen cupping test

iTeh STANDARD PREVIEW (standards.iteh.ai)

1 Scope and field of application

This International Standard specifies a method for determining the ability of metallic sheets and strips having a thickness from 0,2 up to 2 mm and a width of 90 mm or more to undergo plastic deformation in stretch drawing.

NOTE — The test is referred to as the modified Erichsen cupping test as, in the test as originally introduced, no blank holder pressure was used but, in the interests of obtaining greater consistency of results, this was changed.

2 Principle

Forming a cup shape by pressing a punch with a spherical end against a clamped test piece between a blank holder and a die until a through crack appears. The measured depth of the cup is the result of the test based on the movement of the punch.

3 Symbols, designation and units

Symbols, designations and units used in the Erichsen cupping test are given in table 1 and the figure.

Table 1 — Symbols, designations and units

| Symbol | Designation | Value (mm) |
|--------|--|-----------------|
| a | Thickness of the test piece | * |
| b | Width or diameter of the test piece | |
| d_1 | Diameter of the spherical end of the punch | $20 \pm 0,05$ |
| d_2 | Bore diameter of the die | $27 \pm 0,05$ |
| d_3 | Bore diameter of the blank holder | $33 \pm 0,1$ |
| d_4 | Outside diameter of the die | $55 \pm 0,1$ |
| d_5 | Outside diameter of the blank holder | $55 \pm 0,1$ |
| R_1 | Outside corner radius of the die, outside corner radius of the blank holder | $0,75 \pm 0,1$ |
| R_2 | Inside corner radius of the die | $0,75 \pm 0,05$ |
| h_1 | Height of the inside rounded part of the die | $3 \pm 0,1$ |
| h | Depth of the cup during the test | * |
| IE | Erichsen cupping index | * |

* See the figure.

5.3 Before testing, the test piece shall not be submitted to any hammering or hot or cold working.

6 Procedure

6.1 In general, the test shall be carried out at ambient temperature within the limits of 10 to 35 °C. The test carried out under controlled conditions shall be made at a temperature of 23 ± 5 °C.

6.2 Determine the thickness of the test piece to the nearest 0,01 mm.

6.3 Before operating the machine, lightly grease the two faces of the test piece and the punch with graphite grease. For the recommended composition of the graphite grease, see the annex.

By agreement, another type of lubricant may be used.

6.4 Clamp the test piece between the blank holder and the die. The blank holder force shall be approximately 10 kN.

6.5 Bring the punch without shock into contact with the test piece. Make the measurement of penetration from this point.

6.6 Proceed with forming the cup smoothly at a rate between 5 and 20 mm/min. Towards the end of the operation, reduce the speed to the vicinity of the lower limit in order to determine accurately the moment when a through crack appears.

6.7 Terminate the movement of the punch at the instant when a crack appears through the full thickness of the test piece.

6.8 Measure the depth of penetration to the nearest 0,1 mm. This depth expressed in millimetres is the value of the Erichsen cupping index IE.

7 Test report

The test report shall include at least the following information :

- a) reference to this International Standard ;
- b) identification of the test piece ;
- c) thickness of the test piece ;
- d) type of lubricant used ;
- e) value of the Erichsen cupping index.

ISO 8490:1986
<https://standards.iteh.ai/catalog/standards/sist/1a681fca-54f4-41c4-bc1a-4f606a10708e/iso-8490-1986>

Annex

Recommended composition of the graphite grease (see 6.3)

(This annex is given for information only.)

It is known that the results of tests depend on the type of grease used. One representative grease which is known to be suitable has the following characteristics, as determined by the relevant material specifications.

The grease consists of calcium soap, refined mineral oil and flake graphite.

It should be free from corrosive matter, grit resin, wax and fillers.

The grease and its components should conform to the requirements shown in table 2.

Table 2 — Recommended characteristics of the graphite grease

| | Characteristic | Requirement |
|----------------|---|--------------------------------------|
| Grease | Worked penetration of cone of 150 g at a temperature of 25 °C | 250 to 280 |
| | Free acidity | 0,2 % (m/m) max. oleic acid |
| | Free alkalinity | 0,3 % (m/m) max. Ca(OH) ₂ |
| | Water content | 0,5 to 1,2 % (m/m) |
| | Graphite content | 23 to 28 % (m/m) |
| Flake graphite | Average particle size | 0,3 mm |
| | Maximum particle size | 0,5 mm |
| | Ash | 4,5 % (m/m) max. |
| Mineral oil | Viscosity at 37,8 °C | 100 to 120 cS |
| | Closed flash point | 177 °C min. |
| | Ash | 0,01 % (m/m) max. |
| | Neutralization value | 0,1 mg of KOH/g max. |

iTeh STANDARD PREVIEW

(standards.iteh.ai)

This page intentionally left blank

ISO 8490:1986

<https://standards.iteh.ai/catalog/standards/sist/1a681fca-54f4-41c4-bc1a-4f606a10708e/iso-8490-1986>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

This page intentionally left blank

ISO 8490:1986

<https://standards.iteh.ai/catalog/standards/sist/1a681fca-54f4-41c4-bc1a-4f606a10708e/iso-8490-1986>