



# SLOVENSKI STANDARD

## SIST EN 2093:2001

01-januar-2001

---

**Aerospace series - Aluminium alloy AL-P7009-T74 - Hand forgings 20 mm < or = a < or = 150 mm**

Aerospace series - Aluminium alloy AL-P7009-T74 - Hand forgings 20 mm < or = a < or = 150 mm

Luft- und Raumfahrt - Aluminiumlegierung AL-P7009-T74 - Freiformschmiedestücke 20 mm < oder = a < oder = 150 mm

Série aérospatiale - Alliage d'aluminium AL-P7009-T74 - Pièces forgées 20 mm < ou = a < ou = 150 mm

[SIST EN 2093:2001  
https://standards.iteh.ai/catalog/standards/sist/a4b60f2d-a7b8-4479-900e-df521c71230b/sist-en-2093-2001](https://standards.iteh.ai/catalog/standards/sist/a4b60f2d-a7b8-4479-900e-df521c71230b/sist-en-2093-2001)

**Ta slovenski standard je istoveten z: EN 2093:1992**

---

**ICS:**

49.025.20      Aluminij                                      Aluminium

**SIST EN 2093:2001                                      en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 2093:2001

<https://standards.iteh.ai/catalog/standards/sist/a4b60f2d-a7b8-4479-900e-df521c71230b/sist-en-2093-2001>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN 2093**

September 1992

UDC : 669.715-4:621.73.042:629.7

Key words : Aircraft industry, forgings, aluminium alloys, specifications, chemical composition, dimensions, characteristics

English version

Aerospace series  
Aluminium alloy AL-P7009-  
T74  
Hand forgings  
20 mm ≤ a ≤ 150 mm

Série aéronautique  
Alliage d'aluminium AL-P7009-  
T74  
Pièces forgées  
20 mm ≤ a ≤ 150 mm

Luft- und Raumfahrt  
Aluminiumlegierung AL-P7009-  
T74  
Freiformschmiedestücke  
20 mm ≤ a ≤ 150 mm

SIST EN 2093:2001

This European Standard was accepted by CEN on 1992-03-09. CEN members are bound to comply with the requirements of CEN Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to CEN Central Secretariat has the same status as the official versions.

CEN members are the national standards organizations of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

**CEN**

European Committee for Standardization  
Comité Européen de Normalisation  
Europäisches Komitee für Normung

Central Secretariat : Rue de Stassart, 36, B-1050 Bruxelles

## Foreword

This European Standard has been prepared by the European Association of Aerospace Manufacturers (AECMA).

After inquiries and votes carried out in accordance with the rules of this Association, this Standard has successively received the approval of the National Associations and the Official Services of the member countries of AECMA, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 1993, and conflicting national standards shall be withdrawn at the latest by March 1993.

In accordance with the Common CEN/CENELEC Rules the following countries are bound to implement this European Standard : Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/a4b60fd-a7b8-4479-900e-df521c71230b/sist-en-2093-2001>

## 0 Introduction

For the use of this standard, see EN 2500-2.

## 1 Scope

This standard specifies the requirements relating to hand forgings in aluminium alloy AL-P7009-, for use in the T74 <sup>1)</sup> condition,  $20 \text{ mm} \leq a \leq 150 \text{ mm}$ , for aerospace applications.

## 2 References

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 2004-1 Aerospace series - Test methods for aluminium and aluminium alloys products - Part 1- Determination of electrical conductivity of wrought aluminium alloys <sup>2)</sup>

EN 2082-3 Aerospace series - Aluminium alloys forging stock and forgings - Technical specification - Part 3 - Pre-production and production forgings

EN 2500-2 Aerospace series - Instructions for the drafting and use of metallic material standards - Part 2 - Specific requirements for aluminium, aluminium alloys and magnesium alloys <sup>3)</sup>.

<https://standards.iteh.ai/catalog/standards/sist/a4b60fd-a7b8-4479-900e-df521c71230b/sist-en-2093-2001>

1) Formerly designated T736.

2) Published as AECMA standard at the date of publication of this standard.

3) Published as AECMA pre-standard at the date of publication of this standard.

1		Material designation		Aluminium alloy AL-P7009-												
2	Chemical composition %	Element	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ag	Ti	Others		Al		
			min.	-	-	0,6	-	2,1	0,10	5,5	0,25	-	-		-	
			max.	0,20	0,20	1,3	0,10	2,9	0,25	6,5	0,40	0,20	0,05		0,15	
3		Method of melting		-												
4		Form		Hand forgings												
		Method of production		-												
		Limit dimensions (mm)		$20 \leq a \leq 150$												
5		5.1 Technical specification		EN 2082-3												
		5.2 Dimensional standards		-												
6		6.1 Delivery condition and heat treatment		O1 $460^{\circ}\text{C} \leq \theta \leq 470^{\circ}\text{C} / \text{AC}$					T74 $460^{\circ}\text{C} \leq \theta \leq 470^{\circ}\text{C} / \text{WQ } \theta \leq 80^{\circ}\text{C}$ $+ 115^{\circ}\text{C} \leq \theta \leq 125^{\circ}\text{C} / 20 \text{ h} \leq t \leq 24 \text{ h}$ $+ 167^{\circ}\text{C} \leq \theta \leq 173^{\circ}\text{C} / 6 \text{ h} \leq t \leq 18 \text{ h}$							
		6.2 Delivery condition code		A					U							
7		Use condition and heat treatment		T74 Delivery condition $+ 460^{\circ}\text{C} \leq \theta \leq 470^{\circ}\text{C} / \text{WQ } \theta \leq 80^{\circ}\text{C}$ $+ 115^{\circ}\text{C} \leq \theta \leq 125^{\circ}\text{C} / 20 \text{ h} \leq t \leq 24 \text{ h}$ $+ 167^{\circ}\text{C} \leq \theta \leq 173^{\circ}\text{C} / 6 \text{ h} \leq t \leq 18 \text{ h}$					T74 Delivery condition							
8		Sample Test piece Heat treatment		Characteristics Cut from the forgings in accordance with the drawing and/or inspection schedule (location and direction) SIST EN 2093:2001 Use condition: T74												
9		Dimensions concerned		mm		$20 \leq a \leq 75$					$75 < a \leq 125$					
10		Thickness of cladding on each face		%		$125 < a \leq 150$										
11		Direction of test piece		L	LT	ST	L	LT	ST	L	LT	ST				
12		Temperature		$\theta$	$^{\circ}\text{C}$	Ambient temperature										
13		Proof stress		$R_{p0.2}$	MPa	$\geq 440$	$\geq 430$	$\geq 420$	$\geq 420$	$\geq 410$	$\geq 400$	$\geq 390$	$\geq 380$	$\geq 360$		
14		Strength		$R_m$	MPa	$\geq 500$	$\geq 500$	$\geq 480$	$\geq 480$	$\geq 470$	$\geq 460$	$\geq 470$	$\geq 460$	$\geq 440$		
15		Elongation		A	%	$\geq 8$	$\geq 5$	$\geq 4$	$\geq 7$	$\geq 5$	$\geq 4$	$\geq 6$	$\geq 5$	$\geq 4$		
16		Reduction of area		Z	%	-										
17		Hardness		-												
18		Shear strength		$R_c$	MPa	-										
19		Bending		k	-	-										
20		Impact strength		-												
21		Temperature		$\theta$	$^{\circ}\text{C}$	-										
22		Time			h	-										
23		Stress		$\sigma_{\alpha}$	MPa	-										
24		Elongation		a	%	-										
25		Rupture stress		$\sigma_P$	MPa	-										
26		Elongation at rupture		A	%	-										
27		Notes (see line 98)		1)												

32	Electrical conductivity	1	See EN 2004-1		
		6	Measurement on specimen for tensile test (flat machined surface if necessary)		
		7	$\gamma \geq 22,0 \text{ MS/m}$	Acceptable	
			$21,5 \text{ MS/m} \leq \gamma < 22,0 \text{ MS/m}$	Not acceptable unless a stress corrosion test gives satisfactory results	
		$\gamma < 21,5 \text{ MS/m}$	Not acceptable		
39	Stress corrosion	2	In case of dispute or if $21,5 \text{ MS/m} \leq \gamma < 22,0 \text{ MS/m}$		
		3	$a \geq 20 \text{ mm}$		
		6	$\sigma = 60\% R_{p0,2} \text{ min. } L / t = 20 \text{ d}$		
44	External defects	-	See EN 2082-3		
51	Macro-structure	7	Grain flow : see EN 2082-3		
61	Internal defects	-	See EN 2082-3		
82	Batch uniformity	1	See EN 2082-3		
		7	Electrical conductivity	See EN 2082-3	
			or		
		7	Hardness	145 HB (typical value)	
		$\delta \leq 20 \text{ HB per product}$	$\Delta \leq 30 \text{ HB per batch}$		
		<p><b>(standards.iteh.ai)</b></p> <p>SIST EN 2093:2001</p> <p><a href="https://standards.iteh.ai/catalog/standards/sist/a4b60f2d-a7b8-4479-900e-df521c71230b/sist-en-2093-2001">https://standards.iteh.ai/catalog/standards/sist/a4b60f2d-a7b8-4479-900e-df521c71230b/sist-en-2093-2001</a></p>			
97	Designation		See relevant drawing		
98	Notes		1) Also applicable to pre-machined wall thickness $\leq 75 \text{ mm}$		
99	Typical use				