



## Standard Specification for Concentric-Lay-Stranded Copper-Clad Steel Conductors<sup>1</sup>

This standard is issued under the fixed designation B 228; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification covers bare concentric-lay-stranded conductors made from bare round copper-clad steel wires for general use for electrical purposes.

1.2 For the purpose of this specification, conductors are classified as follows: Grade 40 HS, Grade 30 HS, and Grade 30 EHS.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are in SI units.

### 2. Referenced Documents

2.1 The following documents of the issue in effect on the date of material purchase form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards:*

B 227 Specification for Hard-Drawn Copper-Clad Steel Wire<sup>2</sup>

B 354 Terminology Relating to Uninsulated Metallic Electrical Conductors<sup>2</sup>

2.3 *ANSI Standards:*

C 42 Definitions of Electrical Terms<sup>3</sup>

2.4 *National Institute of Standards and Technology:*

NBS *Handbook 100—Copper Wire Tables*<sup>4</sup>

### 3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

3.1.1 Quantity of each size and grade,

3.1.2 Conductor size: approximate diameter in fractions of an inch, or number and AWG size of individual wires (Section 7 and Table 1),

3.1.3 Grade (see 1.2 and Table 1),

3.1.4 Direction of lay of outer layer, if other than left-hand (see 6.3),

3.1.5 When physical tests shall be made (see 8.2),

3.1.6 Package size (see 13.1),

3.1.7 Special package marking, if required (Section 12),

3.1.8 Lagging, if required (see 13.2), and

3.1.9 Place of inspection (Section 14).

3.2 In addition, Supplementary Requirements shall apply only when specified by the purchaser in the inquiry, contract, or purchase order for direct procurement by agencies of the U. S. Government (S1, S2, and S3).

### 4. Material for Wires

4.1 The purchaser shall specify the grade of wire to be used in the conductor.

4.2 Before stranding, the copper-clad steel wire shall meet all the requirements of Specification B 227.

4.3 All wires in the conductor shall be of the same grade and quality.

### 5. Joints

5.1 Joints or splices may be made in the finished individual copper-clad steel wires composing concentric-lay-stranded conductors, using more than three wires provided that such joints or splices have a protection equivalent to that of the wire itself and that they do not decrease the strength of the finished stranded conductor below the minimum breaking strength shown in Table 1. Such joints or splices shall be not closer than 50 ft (15 m) to any other joint in the same layer in the conductor (Note 1).

NOTE 1—Joints or splices in individual copper-clad steel wires in their finished size are made by electrical butt welding. Two types of joints are used and are described as follows:

(a) *Weld-Annealed Joints*—After butt welding, the wire is annealed for a distance of approximately 5 in. (127 mm) on each side of the weld. The weld is then protected from corrosion with a snug fitting seamless copper sleeve which extends at least  $\frac{3}{8}$  in. (9.5 mm) on each side of the weld and which is thoroughly sealed to the wire with solder. The wall thickness of the sleeve is at least 10 % of the radius of the wire.

This joint has a tensile strength of approximately 60 000 psi (415 MPa). This is less than the strength of the individual wires, but an allowance is made for this in the rated strength of the conductor as a whole. The completed conductor when containing such joints is required to have the full rated strength.

This type of joint is but slightly larger than the wire itself and is applicable for 7, 12, and 19-wire stranded conductors.

(b) *Compression-Weld Joints*—Compression-weld joints differ from weld-annealed joints in that the wire is not annealed after the butt-welding operation but is reinforced with a hard-drawn, seamless, silicon-tin bronze

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B-1 on Electrical Conductors and is the direct responsibility of Subcommittee B01.06 on Composite Conductors.

Current edition approved March 10, 1998. Published September 1998. Originally published as B 228 – 48 T. Last previous edition B 228 – 93.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 02.03.

<sup>3</sup> Available from American National Standards Institute, 11 W. 42nd St., 13th Floor, New York, NY 10036.

<sup>4</sup> Available from National Institute of Standards and Technology, (NIST), Gaithersburg, MD 20899.

**TABLE 1 Construction Requirements and Breaking Strength of Concentric-Lay-Stranded Copper-Clad Steel Conductors**

NOTE 1—*Metric Equivalents*—For diameter, 1 in. = 25.40 mm (round to 4 significant figures); for breaking strength, 1 lb = 0.45359 kg (round to 4 significant figures).

| Size Designation  |                  | Conductor Diameter, in. <sup>A</sup> | Rated Breaking Strength, min, lb <sup>B</sup> |             |              |
|-------------------|------------------|--------------------------------------|---|-------------|--------------|
| Inch <sup>C</sup> | AWG <sup>D</sup> |                                      | Grade 40 HS                                   | Grade 30 HS | Grade 30 EHS |
| 7/8               | 19 No. 5         | 0.910                                | 50 240  | 55 570      | 66 910       |
| 13/16             | 19 No. 6         | 0.810                                | 41 600  | 45 830      | 55 530       |
| 23/32             | 19 No. 7         | 0.721                                | 34 390  | 37 740      | 45 850       |
| 21/32             | 19 No. 8         | 0.642                                | 28 380  | 31 040      | 37 690       |
| 9/16              | 19 No. 9         | 0.572                                | 23 390  | 25 500      | 30 610       |
|                   | 7 No. 4          | 0.613                                | 22 310  | 24 780      | 29 430       |
| 9/16              | 7 No. 5          | 0.546                                | 18 510  | 20 470      | 24 650       |
| 1/2               | 7 No. 6          | 0.486                                | 15 330  | 16 890      | 20 460       |
| 7/16              | 7 No. 7          | 0.433                                | 12 670  | 13 910      | 16 890       |
| 3/8               | 7 No. 8          | 0.385                                | 10 460  | 11 440      | 13 890       |
| 11/32             | 7 No. 9          | 0.343                                | 8 616   | 9 393       | 11 280       |
| 5/16              | 7 No. 10         | 0.306                                | 7 121   | 7 758       | 9 196        |
| ...               | 3 No. 5          | 0.392                                | 8 373   | 9 262       | 11 860       |
| ...               | 3 No. 6          | 0.349                                | 6 934   | 7 639       | 9 754        |
| ...               | 3 No. 7          | 0.311                                | 5 732   | 6 291       | 7 922        |
| ...               | 3 No. 8          | 0.277                                | 4 730   | 5 174       | 6 282        |
| ...               | 3 No. 9          | 0.247                                | 3 898   | 4 250       | 5 129        |
| ...               | 3 No. 10         | 0.220                                | 3 221   | 3 509       | 4 160        |
| ...               | 3 No. 12         | 0.174                                | 2 236   | ...         | ...          |

<sup>A</sup> Diameter of circumscribing circle.

<sup>B</sup> Breaking loads of 7-wire and 19-wire conductors are taken as 90 % of the sum of the breaking loads of the individual wires; breaking load of 3-wire conductors is taken as 95 % of the sum of the breaking loads of the individual wires.

<sup>C</sup> The designation "Inch" is the approximate diameter in proper fraction of an inch.

<sup>D</sup> The designation of "AWG" is a combination of the number of wires each of the American Wire Gage size indicated by "No."

**TABLE 2 Density of Copper-Clad Steel**

| Units                        | Density at 20°C |
|------------------------------|-----------------|
| Grams per cubic centimetre   | 8.15            |
| Pounds per cubic inch        | 0.29444         |
| Pounds per circular mil-foot | 0.000027750     |

## 7. Construction

7.1 The numbers and diameters of the wires in the concentric-lay-stranded conductors shall conform to the requirements prescribed in Table 1 (Note 2).

NOTE 2—For definitions of terms relating to conductors, reference should be made to (1) ANSI C42.35-latest revision and (2) Terminology B 354.

## 8. Physical and Electrical Tests

8.1 Tests for physical and electrical properties of wires composing concentric-lay-stranded conductors made from copper-clad steel wire shall be made before stranding.

8.2 At the option of the purchaser, tension and elongation tests before stranding may be waived and the complete conductors may be tested as a unit. The breaking strength of the conductors so tested shall be not less than that required in Table 1.

8.3 Where breaking strength tests are required on the finished conductor, they shall be made on representative samples, not less than 4 ft (1.22 m) in length. For lots of 10 000 lb (4 540 kg) or less, two samples shall be taken from separate reels or coils in the lot except that but one sample shall be required where the total amount of conductor is 5 000 ft (1 525 m) or less. For quantities over 10 000 lb, one sample for each 10 000 lb or fraction thereof, shall be taken, but the minimum number of samples shall be three.

8.4 Specimens of the completed conductor shall be tested in a tensile testing machine equipped with jaws suitable for gripping of the conductor or equipped for holding properly

sleeve which is applied by means of a hydraulic compressor over the weld. This sleeve is covered with solder so as to completely seal the ends. These sleeves have a wall thickness of 25 to 50 % of the radius of the wire, depending on the wire size. Their use is usually limited to 3-wire conductors where the relatively large diameter is not objectionable. This joint develops the full strength of the wire.

## 6. Lay

6.1 For 3-wire conductors the preferred lay is 16½ times the outside diameter, but the lay shall not be less than 14 times nor more than 20 times this diameter.

6.2 For 7- and 19-wire conductors the preferred lay is 13½ times the diameter of that layer, but the lay shall not be less than 10 nor more than 16 times this diameter.

6.3 The direction of lay of the outer layer shall be left-hand unless the direction of lay is specified otherwise by the purchaser.

6.4 The direction of lay shall be reversed in consecutive layers.

6.5 All wires in the conductor shall lie naturally in their true positions in the completed conductor. They shall tend to remain in position when the conductor is cut at any point and shall permit restranding by hand after being forcibly unraveled at the end of the conductor.