INTERNATIONAL STANDARD

ISO 12737

First edition 1996-11-15

Metallic materials — Determination of plane-strain fracture toughness

iTeh STANDARD PREVIEW

Matériaux métalliques — Détermination du facteur d'intensité de contrainte critique **en al**

<u>ISO 12737:1996</u> https://standards.iteh.ai/catalog/standards/sist/98434d40-6695-4ffc-8d87-1e28fe0e9e1c/iso-12737-1996



Contents

Page

1	Scope	1			
2	Normative references	1			
3	Definitions	1			
4	Symbols and designations	2			
5	Principle	2			
6	Apparatus	4			
7	Test specimen size, configuration and preparation 5				
8	Procedure				
9	Test procedure				
10	Calculation and interpretation of results	8 d40-6695-4ffc-8d87			
11	Test report	⁵ 8			

Annexes

Α	Fatigue precracking of <i>K</i> _{Ic} fracture toughness specimens		
в	Bend test specimen	11	
С	Compact specimen	13	
D	Test fixtures	15	
Е	Bibliography	17	

© ISO 1996

```
Case Postale 56 • CH-1211 Genève 20 • Switzerland
```

Printed in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting

iTeh STANDARD PREVIEW

International Standard ISO 12737 was prepared by Technical Committee ISO/TC164, Mechanical testing of metals, Subcommittee SC 4, Toughness testing.

https://standards.innexces D and E are for information only.

iTeh This page Intentionally left blankEVIEW (standards.iteh.ai)

<u>ISO 12737:1996</u> https://standards.iteh.ai/catalog/standards/sist/98434d40-6695-4ffc-8d87-1e28fe0e9e1c/iso-12737-1996

Metallic materials — Determination of plane-strain fracture toughness

1 Scope

This International Standard specifies the method for determining the plane-strain fracture toughness of homogeneous metallic materials using a specimen that is notched and precracked by fatigue, and subjected to slowly increasing crack displacement force.

iTeh STANDARD PREVIEW

(standards.iteh.ai)

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this international Standard are encouraged to investigate the possibility of applying the most recent edition of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 7500-1:1986, Metallic materials — Verification of static uniaxial testing machines — Part 1: Tensile testing machines.

ISO 9513:1989, Metallic materials — Verification of extensometers used in uniaxial testing.

3 Definitions

For the purposes of this International Standard, the following definitions apply.

3.1 plane-strain stress intensity factor, K_1 : Magnitude of the elastic stress field at the tip of a crack subjected to opening mode displacement (mode I). It is a function of applied force and test specimen size, geometry, and crack length, and has the dimensions of force times length^{-3/2}.

3.2 plane-strain fracture toughness, K_{lc} : Measure, by the operational procedure of this method, of a material's resistance to crack extension when the state of stress near the crack tip is predominantly plane strain and plastic deformation is limited.

NOTE — It is the critical value of K_1 at which significant crack extension occurs on increasing load with high constraint to plastic deformation.

3.3 crack plane orientation: Method for relating the plane and direction of crack extension to the characteristic directions of the product.

NOTE — A hyphenated code is used wherein the letter(s) preceding the hyphen represent(s) the direction normal to the crack plane and the letter(s) following the hyphen represent(s) the anticipated direction of crack extension (see figure 1). For wrought metals, the letter X always denotes the principal direction of grain flow, Z the direction of principal working force, and Y the direction normal to the X-Z plane. If specimen directions do not coincide with the product's characteristic directions, then two letters are used to denote the normal to the crack plane and/or the expected direction of crack extension [see figure 1 b)]. If there is no grain flow direction (as in a casting), reference axes may be arbitrarily assigned but must be clearly identified.

3.4 notch opening displacement, V: Displacement measured at or near the notch mouth.

4 Symbols and designations

For the purposes	of this International	Standard the follow	wing symbols ap	ply (see also fi	gures 1, 2 and	4).

Symbol	Unit	Designation		
а	mm	Crack length		
В	mm	Specimen thickness		
Ε	MPa 📊	Young's modulus ARD PREVIEW		
F	kN	Applied force		
$F_{\rm Q}$	kN	Particular value of F (see figure 4).21		
F ₅	kN	Particular value of <i>F</i> (see figure 4)		
K _f	MPa·m ^{1/21)}	Maximum stress intensity factor during the final stage of fatigue cracking		
KQ	MPa·m ^{1/2^{nups://s}}	Provisional value of K Provisional value of K State of the state of th		
K	MPa∙m ^{1/2}	Opening mode stress intensity factor (mode I)		
K _{IC}	MPa⋅m ^{1/2}	Critical value of $K_{\rm I}$ (plane-strain fracture toughness)		
R	_	Ratio of minimum to maximum fatigue cracking force during any single cycle of fatigue operation		
$R_{\rm p0.2}$	MPa	0,2 % offset yield strength		
S	mm	Span between outer loading points		
V	mm	Notch opening displacement		
W	mm	Width for bend specimen or effective width for compact specimen		
ΔK_{\parallel}	MPa·m ^{1/2}	Difference between maximum and minimum values of K_1 during any single cycle of fatigue operation		
1) 0,031 6 MPa m ^{1/2} = 1 N mm ^{-3/2} = 0,031 6 MN m ^{-3/2}				

5 Principle

This method covers the determination of the plane strain fracture toughness (K_{lc}) of metallic materials by increasing-force tests of fatigue-precracked test specimens. Details of the test specimens and experimental procedures are given in annexes B and C. Force versus notch opening displacement is recorded autographically, or converted to digital form for accumulation in a computer information storage facility and subsequent processing. The force corresponding to 2 % apparent crack extension is established by a specified deviation from the linear portion of the test record. If certain validity requirements are satisfied, the value of K_{lc} is calculated from this force.



c) Radial grain flow, axial working direction

d) Axial grain flow, radial working direction

Figure 1 — Crack plane identification

The property K_{lc} characterizes the resistance of a material to fracture in the presence of a sharp crack under severe tensile constraint, such that

- a) the state of stress near the crack front approaches plane strain; and
- b) the crack-tip plastic zone is small compared to the crack size, specimen thickness, and ligament ahead of the crack.

 K_{lc} is believed to represent a lower limiting value of fracture toughness in the environment and at the temperature of test.

Cyclic or sustained loads can cause crack extension at K_1 values less than K_{1c} . Crack extension under cyclic or sustained loads can be influenced by temperature and environment. Therefore when K_{1c} is applied to the design of service components, differences between laboratory test and field conditions should be considered.

© ISO

With plane-strain fracture toughness testing, there can be no advance assurance that a valid K_{lc} will be determined in a particular test.

6 Apparatus

6.1 Testing machine and load measurement

The testing machine shall be calibrated in accordance with ISO 7500-1 and shall be of at least grade 1. The testing machine shall have provisions for autographic recording of the force applied to the specimen; alternatively, a computer data acquisition system may be used to record load and displacement for subsequent analysis. The combination of load-sensing device and recording system shall permit the force F_{Ω} (as defined in clause 10) to be determined from the test record to ± 1 %.

6.2 Fatigue cracking machine

When possible, the fatigue machine and load-indicating device shall be calibrated statically in accordance with ISO 7500-1 and shall have a grade of at least 2. If the machine cannot be calibrated statically, the applied force shall be known to \pm 2,5 %. Careful alignment of the specimen and fixturing is necessary to encourage straight fatigue cracks. The fixturing shall be such that the stress distribution is uniform across the specimen thickness and symmetrical about the plane of the prospective crack.

(standards.iteh.ai)

ISO 12737:1996

6.3 Displacement gaugehttps://standards.iteh.ai/catalog/standards/sist/98434d40-6695-4ffc-8d87-1e28fe0e9e1c/iso-12737-1996

The displacement gauge electrical output shall represent the relative displacement (*V*) of two precisely located gauge positions spanning the notch mouth. The design of the displacement gauge and knife edges shall allow free rotation of the points of contact between the gauge and the specimen.

The displacement gauge shall be calibrated in accordance with ISO 9513, as interpreted in relation to this method, and shall be of at least class 1; however, calibration shall be performed at least weekly during the time the gauge is in use. Periodic verification of greater frequency may be required depending on use and agreement between contractual parties.

Verification of the gauge shall be performed at the temperature of test to ± 5 °C. Response of the gauge shall correspond to the calibration apparatus to $\pm 0,003$ mm for displacements up to 0,3 mm and ± 1 % for higher values.

The determination of an absolute displacement value is not necessary since only changes in displacement are used in this method. Two proven designs of displacement gauge are given in [1] and [2] (see annex E) and similar gauges are commercially available.

6.4 Testing fixtures

The bend test shall be performed using a fixture designed to minimize friction effects by allowing the support rollers to rotate and translate slightly as the specimen is loaded, thus achieving rolling contact. A design suitable for testing bend specimens is shown in figure D.1.

A loading clevis suitable for testing compact specimens is shown in figure D.2.

7 Test specimen size, configuration and preparation

7.1 Specimen size

In order for a result to be considered valid according to this method, the specimen thickness (B), crack length (a), and ligament length (W-a) must all be not less than $2,5(K_{1c}/R_{p0,2})^2$, where $R_{p0,2}$ is the 0,2 % offset yield strength of the material in the environment and at the temperature of test. Meeting this requirement cannot be ensured in advance, thus specimen dimensions should be conservatively established for the first test in a series. If the form of the available material is such that it is not possible to obtain a test specimen with thickness, crack length and ligament length equal to or greater than 2,5($K_{lc}/R_{p0,2}$)², then it is not possible to make a valid K_{lc} measurement according to this method.

7.2 Recommended specimen proportions

7.2.1 Recommended specimens

The recommended specimens are shown in figures B.1 and C.1. Width (W) is nominally twice the thickness (B). Crack length (a) is between 0,45 and 0,55 times the width.

7.2.2 Alternative proportions

In certain cases it may be necessary or desirable to use specimens having W/B ratios other than 2, and alternative proportions are allowed (see annex B or C). Specimens having alternative proportions shall nevertheless have the same crack length-to-width (a/W) ratio as the recommended specimens.

7.2.3 Alternative specimen configurations (for information only)

By prior agreement, alternative specimen configurations and their associated methods of analysis may be used provided that they be accepted as national standards for K_{lc} testing by an ISO member body, including those standards which have the multiple purpose of measuring K_{lc} along with J and/or CTOD (crack tip opening displacement) properties.

7.2.4 Fatigue crack starter notch

Two fatigue crack starter notch configurations are shown in figures 2 a) and 2 b). The suggested root radius for the straight-through slot terminating in a V-notch is 0,10 mm or less. For the chevron form of notch, the suggested root radius is 0,25 mm or less. The method of notch preparation is discretionary. The starter notch (plus fatigue crack) must lie within the envelope shown in figure 2 c) (see annex A).

Two types of knife edges for attaching the displacement gauge are illustrated in figure 3.

7.3 Specimen preparation and fatigue precracking

7.3.1 Material condition

All specimens shall be tested in the finally heat-treated, mechanically-worked and environmentally-conditioned state. Normally, specimens shall also be machined in this final state. However, for material that cannot be machined in the final condition, the final treatment may be carried out after machining provided that the required dimensions and tolerances on specimen size, shape and overall surface finish are met (see figures B.1 and C.1), and that full account is taken of the effects of specimen size on metallurgical condition induced by certain heat treatments, e.g., water quenching of steels.



NOTES

1 Crack starter notch shall be perpendicular to specimen surfaces to $\pm 2^{\circ}$. Notch width shall not exceed 0,1*W* but need not be less than 1,6 mm.

2 For straight-through notch: suggested notch root radius 0,10 mm, maximum. Cutter tip angle 90° maximum. Fatigue crack extension on each surface of specimen shall be at least 0,025W or 1,3 mm, whichever is greater.

3 For chevron notch: suggested notch root radius 0,25 mm, maximum. Cutter tip angle 90° maximum A = C within ± 0,01W. Fatigue crack shall emerge on both surfaces of specimen DARD PREVIEW

Figure 2 — Crack starter notches and maximum permissible notch/crack envelope



NOTES

1 2y plus the diameter of screw thread shall not exceed W/2. If knife edges are glued or similarly attached to edge of specimen, dimension 2y shall correspond to the distance between extreme points of attachment.

2 Knife edges shall be square with specimen surfaces and parallel to $\pm 0,5^{\circ}$.

Figure 3 — Knife edge detail

7.3.2 Crack plane orientation

The fracture toughness of a material is usually dependent on the orientation and direction of propagation of the crack in relation to the principal directions of metal working, grain flow or otherwise-produced texture. Orientation of the crack plane shall be decided before machining (see 7.3.3), identified in accordance with the prescribed coordinate systems (see 3.3) and recorded (see clause 11).

7.3.3 Machining

Specimen sizes, shapes, dimensional tolerances and surface finishes shall be as given in figures B.1 and C.1.

7.3.4 Fatigue precracking

Fatigue precracking normally shall be done at room temperature with the specimen in the finally heat-treated, mechanically-worked or environmentally-conditioned state in which it is to be tested. Different fatigue precracking temperatures and intermediate thermal/mechanical/environmental treatments between fatigue precracking and testing shall be used only when such treatments are necessary to simulate the conditions for a specific structural application and required dimensions and tolerances on specimen size and shape can be maintained. Such fatigue precracking shall be performed according to the requirements of annex A.

iTeh STANDARD PREVIEW

(standards.iteh.ai)

8.1 Specimen measurement

8 Procedure

Measure specimen thickness (B) to the nearest 0.025 mm or to 0.14%, whichever is larger, at not less than three equally spaced positions along the anticipated crack extension path. Take the average of these measurements as the thickness.

Measure specimen width (W) to the nearest 0,025 mm or to 0,1 %, whichever is larger, at not less than three positions near the notch location. Take the average of these measurements as the width. For the compact specimen, measure the width from the plane of the centreline of the loading pin holes.

After fracture, measure specimen crack length (*a*) to the nearest 0,05 mm or to 0,5 %, whichever is the greater, at mid-thickness and at the two quarter-thickness points. Take the average of these measurements as the crack length. The difference between any two of the three central crack length measurements shall not exceed 10 % of the average.

Measure the crack length also at each surface. For the straight-through starter notch, no part of the crack front shall be closer to the starter notch than 1,3 mm or 0,025*W*, whichever is larger; furthermore, neither surface crack length measurement shall differ from the average crack length by more than 15 % and their difference shall not exceed 10 % of the average crack length. For the chevron notch starter, the fatigue crack shall emerge from the average crack length measurement shall differ from the average crack length measurement shall differ from the average crack length.

The fracture plane shall be parallel to the plane of the starter notch to $\pm 10^{\circ}$ and there shall be no evidence of multiple cracking (i.e., more than one crack).

8.2 Fixture measurements for bend specimen

Align the bend test fixture such that the line of action of the applied force passes midway between the support rollers to ± 1 % of the span (S) and is perpendicular to the roller axes to $\pm 2^{\circ}$. Measure the span (S) to ± 0.5 %.