



## Standard Terminology Relating to Non-ferrous Metals and Alloys<sup>1</sup>

This standard is issued under the fixed designation B 899; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 To promote precise understanding and interpretation of standard, reports, and other technical writings promulgated by Committee B02.

1.2 To standardize the terminology used in these documents.

1.3 To explain the meanings of technical terms used within these documents for those not conversant with them.

### 2. Significance and Use

2.1 The terms defined in this document are generic in respect to the standards under the jurisdiction of Committee B02 on Nonferrous Metals and Alloys. The same terms may have different definitions in other ASTM technical committees.

2.2 Some definitions may differ within the committee because of limitations on items such as weights or dimensions. In such cases the terms will be more precisely defined in the *Terminology* section of the standards in which these terms are used.

### 3. Index of Terms

#### 3.1 Alphabetical Listing of Terms

average diameter  
bar  
billet  
can  
cathodic protection  
coiled sheet  
compact  
contact resistance  
contact resistance probe  
die casting  
fill pin  
fineness  
flats  
flat sheet  
foundry casting  
galvanic anode  
graphite permanent mold casting  
heat  
ingot

liquidus  
lot  
lot number  
melt  
nominal wall  
part  
permanent mold casting  
pig  
pipe  
plate  
powder  
powder blend  
precious metals  
pressure die casting  
producer  
rod  
rough part  
saline electrolyte  
sand casting  
seamless pipe  
semi-permanent mold casting  
shapes  
sheet  
shot  
solidus  
sponge  
spring wire  
strip  
thin-wall tube  
tube  
weaving wire  
welded pipe  
wire

### 4. Terminology

#### 4.1 Terms and Their Definitions

**average diameter**, *n*—the average of the maximum and minimum outside diameters, as determined at any one section of the pipe or tube. **B 160, B 161, B 163, B 165, B 167, B 407, B 423, B 444, B 445, B 535, B 622, B 677, B 690, B 710, B 722, B 723, B 726, B 729, B 739, B 751, B 759, B 775**

**bar**, *n*—an elongated, forged or rolled metal product with uniform strength, length and section (such as rectangular, square, round, oval or hexagonal). **B 327, B 518**

<sup>1</sup> This terminology is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.91 on Editorial and Terminology.

Current edition approved May 10, 2001. Published July 2001. Originally published as B 899–99. Last previous edition B 899–99a.

NOTE 1—In the following standards the term “bar” has a similar definition, but with greater and more specific detail. **B 160, B 164, B 166, B 408, B 425, B 446, B 473, B 511, B 512, B 637, B 639, B 649, B 672, B 691, B 719, B 756, B 805**

**billet**, *n*—a formed shape that may be further worked, or a solid, semifinished, round, or rectangular product that has been hot-worked by forging, rolling, or extrusion.

**can**, *n*—the container used to encapsulate the powder during the pressure consolidation process; it is removed from the final part. **B 834**

**cathodic protection**, *n*—protection of a metal from corrosion by making it a cathode through the galvanic sacrifice of a less noble metal or through an impressed electric current. **B 418**

**coiled sheet**, *n*—sheet in coils with slit edges. **B 69**

**compact**, *n*—the consolidated powder from one can; it may be used to make one or more parts. **B 834**

**contact resistance**, *n*—the resistance to current flow between two touching bodies, consisting of constriction resistance and film resistance. **B 667**

**contact resistance probe**, *n*—an apparatus for determining electrical contact resistance characteristics of a metal surface.

DISCUSSION—probe, in this instance, should be distinguished from the classical tool whose function it is to touch or move an object. **B 667**

**die casting**, *n*—a casting process wherein molten metal is injected under high pressure into the cavity of a metal mold and solidified; also, a product of such a process. **B 86, B 102, B 240**

**fill pin**, *n*—the part of the compact in the spout used to fill the can; it is usually integral to the part produced. **B 834**

**fineness**, *n*—a measure of the purity of precious metals expressed in parts per thousand.

**flat sheet**, *n*—sheet with sheared, silt, or sawed edges that has been flattened or leveled. **B 69**

**foundry casting**, *n*—a casting process wherein a molten metal is poured by gravity into the cavity of a mold and solidified; also, a product of such a process. **B 86**

**galvanic anode**, *n*—a metal electrode that sacrificially corrodes when coupled to a more noble metal in a conducting medium, thereby supplying a protective electric current to the more noble electrode. **B 418**

**graphite permanent mold casting**, *n*—a metal object produced by introducing molten metal by gravity or low pressure into a graphite mold and allowing it to solidify. **B 86**

**heat**, *n*—refer to melt.

**ingot**, *n*—a casting of simple shape suitable for hot-working or remelting. **B 240, B 327**

**liquidus**, *n*—the lowest temperature at which an alloy under equilibrium conditions begins to freeze on cooling or is completely melted on heating.

**lot**, *n*—a quantity of metal made under conditions that, for sampling purposes, are considered uniform. **B 6, B 32, B 240, B 418, B 749**

**lot number**, *n*—a unique alphanumeric designation for a lot

that is traceable to manufacturing records. **B 32**

**melt**, *n*—all the metal that, while molten, was held at the same time in the same holding vessel.

**nominal wall**, *n*—specified wall thickness with a published plus and minus tolerance from the specified thickness at any point. **B 535, B 710, B 722, B 723, B 726, B 739, B 751, B 775**

**part**, *n*—a single item coming from a compact, either prior to or after machining. **B 834**

**permanent mold casting**, *n*—a metal object produced by introducing molten metal by gravity or low pressure into a mold constructed of durable material, usually iron or steel, and allowing it to solidify. See also graphite permanent mold casting. **B 86, B 792**

**pig**, *n*—an oblong or square mass of metal that has been cast while still molten into a mold that gives the metal its particular shape; most commonly used for lead and tin in weights that can be handled manually. **B 29, B 339**

**pipe**, *n*—a tubular metal product, cast or wrought, of dimensions that conform to those referred to commercially as standard pipe sizes. **B 161, B 165, B 167, B 407, B 423, B 444, B 445, B 535, B 622, B 677, B 690, B 710, B 722, B 723, B 729, B 759, B 775**

**plate**, *n*—a flat-rolled metal product of same minimum thickness and width arbitrarily dependent on the type of metal. **B 69, B 333, B 434, B 435, B 463, B 536, B 575, B 582, B 599, B 620, B 625, B 709, B 718, B 814, B 818**

**powder**, *n*—particles of a solid characterized by small size, nominally within the range of from 0.1 to 1000 u.m.

**powder blend**, *n*—a homogeneous mixture of powder from one or more heats; it is limited to the amount that can be mixed in the same blender at one time. **B 834**

**precious metals**, *n*—the eight noble metals: gold, silver, palladium, platinum, rhodium, iridium, rhenium, and ruthenium.

**pressure die-casting**, *n*—Same as die casting. **B 86, B 791**

**producer**, *n*—the primary manufacturer of the material. **B 32**

**rod**, *n*—wrought material of round, solid straight lengths. **B 408, B 518, B 691**

NOTE 2—In the following standards the term “rod” has a similar definition, but is worded differently. **B 160, B 164, B 166, B 425, B 446, B 637, B 639, B 756**

**rough part**, *n*—the part prior to final machining. **B 834**

**saline electrolyte**, *n*—a solution customarily consisting of the chlorides of the alkali metals. **B 418**

**sand casting**, *n*—a casting process wherein molten metal is poured by gravity into the cavity of a sand mold and solidified; also, a product of such a process. **B 791**

**seamless pipe**, *n*—a round, hollow product made with a continuous periphery in all stages of manufacture and produced to the particular dimensions commercially known as standard pipe sizes. **B 423, B 444, B 775**

**semi-permanent mold casting**, *n*—mold casting that is made with an expendable core such as sand. **B 791**

**shapes**, *n*—materials of solid section in such forms as angles, channels, tees, I-beams, and four-fluted bars. **B 511**

**sheet**, *n*—a flat-rolled metal product of some maximum